

# INTERNATIONAL STANDARD



**Superconductivity –  
Part 23: Residual resistance ratio measurement – Residual resistance ratio  
of cavity-grade Nb superconductors**

IEC 61788-23:2021

<https://standards.iteh.ai/catalog/standards/iec/01928a35-4580-4954-b79c-214d49400d4e/iec-61788-23-2021>



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2021 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

**About the IEC**

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

**About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

**IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)**

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

**IEC online collection - [oc.iec.ch](http://oc.iec.ch)**

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

**IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)**

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

**Electropedia - [www.electropedia.org](http://www.electropedia.org)**

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

**IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)**

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

IEC 61788-23:2021

<https://standards.iteh.ai/catalog/standards/iec/01928a35-4580-4954-b79c-214d49400d4c/iec-61788-23-2021>

# INTERNATIONAL STANDARD



**Superconductivity –  
Part 23: Residual resistance ratio measurement – Residual resistance ratio  
of cavity-grade Nb superconductors**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

ICS 17.220; 29.050

ISBN 978-2-8322-4958-1

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	2
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions .....	7
4 Principle.....	8
5 Measurement apparatus .....	9
5.1 Mandrel or base plate.....	9
5.2 Cryostat and support of mandrel or base plate .....	9
6 Specimen preparation.....	10
7 Data acquisition and analysis.....	11
7.1 Data acquisition hardware .....	11
7.2 Resistance ( $R_1$ ) at room temperature.....	11
7.3 Residual resistance ( $R_2$ ) just above the superconducting transition .....	11
7.4 Validation of the residual resistance measurement.....	13
7.5 Residual resistance ratio .....	13
8 Uncertainty of the test method .....	13
9 Test report.....	13
9.1 General.....	13
9.2 Test information.....	13
9.3 Specimen information.....	14
9.4 Test conditions.....	14
9.5 RRR value .....	14
Annex A (informative) Additional information relating to the measurement of RRR.....	15
A.1 Considerations for specimens and apparatus.....	15
A.2 Considerations for specimen mounting orientation .....	16
A.3 Alternative methods for increasing temperature of specimen above superconducting transition temperature .....	16
A.3.1 General .....	16
A.3.2 Heater method .....	16
A.3.3 Controlled methods.....	16
A.4 Other test methods.....	16
A.4.1 General .....	16
A.4.2 Measurement of resistance versus time .....	17
A.4.3 Comparison of ice point and room temperature.....	17
A.4.4 Extrapolation of the resistance to 4,2 K .....	17
A.4.5 Use of magnetic field to suppress superconductivity at 4,2 K.....	18
A.4.6 AC techniques .....	18
Annex B (informative) Uncertainty considerations .....	19
B.1 Overview.....	19
B.2 Definitions.....	19
B.3 Consideration of the uncertainty concept .....	20
B.4 Uncertainty evaluation example for IEC TC 90 standards .....	22
Annex C (informative) Uncertainty evaluation for resistance ratio measurement of Nb superconductors .....	24

C.1	Evaluation of uncertainty .....	24
C.1.1	Room temperature measurement uncertainty .....	24
C.1.2	Cryogenic measurement uncertainty .....	25
C.1.3	Estimation of uncertainty for typical experimental conditions .....	27
C.2	<b>Round robin test</b> Inter-laboratory comparison summary .....	28
	Bibliography .....	29

Figure 1	– Relationship between temperature and resistance near the superconducting transition .....	8
----------	---	---

Figure A.1	– Determination of the value of $R_2$ from a resistance versus time plot.....	17
------------	---	----

Figure C.1	– Graphical description of the uncertainty of regression related to the measurement of $R_2$ .....	27
------------	--	----

Table B.1	– Output signals from two nominally identical extensometers.....	20
-----------	--	----

Table B.2	– Mean values of two output signals .....	20
-----------	---	----

Table B.3	– Experimental standard deviations of two output signals.....	21
-----------	---	----

Table B.4	– Standard uncertainties of two output signals.....	21
-----------	---	----

Table B.5	– Coefficients of variation of two output signals.....	21
-----------	--	----

Table C.1	– Uncertainty of measured parameters .....	27
-----------	--	----

Table C.2	– RRR values obtained by <b>round robin test</b> inter-laboratory comparison using liquid helium .....	28
-----------	--	----

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## SUPERCONDUCTIVITY –

**Part 23: Residual resistance ratio measurement –  
Residual resistance ratio of **cavity-grade Nb superconductors****

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 61788-23:2018. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.**

IEC 61788-23 has been prepared by IEC technical committee 90: Superconductivity. It is an International Standard.

This second edition cancels and replaces the first edition published in 2018. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) The scope of this standard was modified to restrict the range of residual resistance ratio to that encountered by providers of material for superconducting radio-frequency cavities.
- b) The references to technical material were updated and corrected.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
90/478/FDIS	90/482/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at [www.iec.ch/members\\_experts/refdocs](http://www.iec.ch/members_experts/refdocs). The main document types developed by IEC are described in greater detail at [www.iec.ch/standardsdev/publications](http://www.iec.ch/standardsdev/publications).

A list of all parts in the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under [webstore.iec.ch](http://webstore.iec.ch) in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**IMPORTANT – The 'color inside' logo on the cover page of this publication indicates that it contains colors which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a color printer.**

## INTRODUCTION

High-purity niobium is the chief material used to make superconducting radio-frequency cavities. Similar grades of niobium may be used in the manufacture of superconducting wire. Procurement of raw materials and quality assurance of delivered products often use the residual resistance ratio (RRR) to specify or assess the purity of a metal. RRR is defined for non-superconducting metals as the ratio of electrical resistance measured at room temperature (293 K) to the resistance measured for the same specimen at low temperature (~4,2 K). The low-temperature value is often called the residual resistance. Higher purity is associated with higher values of RRR.

Niobium presents special problems due to its transformation to a superconducting state at ~9 K, so DC electrical resistance is effectively zero below this temperature. The definition above would then yield an infinite value for RRR. This document describes a test method to determine the residual resistance value by using a plot of the resistance to temperature as the test specimen is gradually warmed through the superconducting transition in the absence of an applied magnetic field. This results in a determination of the residual resistance at just above superconducting transition, ~10 K, from which RRR is subsequently determined.

International Standards also exist to determine the RRR of superconducting wires. In contrast to superconducting wires, which are usually a composite of a superconducting material and a non-superconducting material and the RRR value is representative of only the non-superconducting component, here the entire specimen is composed of superconducting niobium. Frequently, niobium is procured as a sheet, bar, tube, or rod, and not as a wire. For such forms, test specimens will likely be a few millimetres in the dimensions transverse to electric current flow. This difference is significant when making electrical resistance measurements, since niobium samples will likely be much longer than that for the same length-to-diameter ratio as a wire, and higher electrical current may be required to produce sufficient voltage signals. Guidance for sample dimensions and electrical connections is provided in Annex A. Test apparatus should also take into consideration aspects such as the orientation of a test specimen relative to the liquid helium surface, accessibility through ports on common liquid helium dewars, design of current contacts, and minimization of thermal gradients over long specimen lengths. These aspects distinguish this document from similar wire standards.

Other test methods have been used to determine RRR. Some methods use a measurement at a temperature other than 293 K for the high resistance value. Some methods use extrapolations at 4,2 K in the absence of an applied magnetic field for the low resistance value. Other methods use an applied magnetic field to suppress superconductivity at 4,2 K. A comparison between this document and some other test methods is presented in Annex A. ~~It should be noted~~ Note that systematic differences of up to 10 % are produced by these other methods, which is larger than the target uncertainty of this document. ~~Care should~~ It is therefore ~~be taken~~ important to apply this document or the appropriate corrections listed in Annex A according to the test method used.

Whenever possible, this test method should be transferred to vendors and collaborators who also perform RRR measurements. To promote consistency, the results of inter-laboratory comparisons are described in Clause C.2.



## SUPERCONDUCTIVITY –

### Part 23: Residual resistance ratio measurement – Residual resistance ratio of **cavity-grade Nb** superconductors

#### 1 Scope

This part of IEC 61788 addresses a test method for the determination of the residual resistance ratio (RRR),  $r_{RRR}$ , of cavity-grade niobium. This method is intended for high-purity niobium grades with ~~15~~  $150 < r_{RRR} < 600$ . The test method ~~should be~~ is valid for specimens with rectangular or round cross-section, cross-sectional area greater than  $1 \text{ mm}^2$  but less than  $20 \text{ mm}^2$ , and a length not less than 10 nor more than 25 times the width or diameter.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-815, *International Electrotechnical Vocabulary – Part 815: Superconductivity* (available at: [www.electropedia.org](http://www.electropedia.org))

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-815 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

##### 3.1 residual resistance ratio RRR

$r_{RRR}$


ratio of resistance at room temperature to the resistance just above the superconducting transition

$$r_{RRR} = R_1 / R_2 \quad (1)$$

where

$R_1$  is the resistance at 293 K;

$R_2$  is the resistance just above the superconducting transition, at ~10 K.



**Figure 1 – Relationship between temperature and resistance near the superconducting transition**

Note 1 to entry: In this document, the room temperature is defined as 20 °C = 293 K, and  $r_{RRR}$  is obtained as follows: Figure 1 shows schematically resistance versus temperature data and the graphical procedure used to determine the value of  $R_2$ . In Figure 1, the region of maximum slope is extrapolated upward in resistance, as shown by line (a), and the region of minimum slope at temperatures above the transition temperature is extrapolated downward in temperature, as shown by line (b). The intersection of these extrapolations at point A determines the value of  $R_2$  as well as a temperature value  $T_c^*$ .

Note 2 to entry: The value  $T_c^*$  is similar to the transition value defined in [1]<sup>1</sup>, and should not be confused with the value defined at the midpoint of the transition, called  $T_c^*$  in [2].

Note 3 to entry: Some standards or documented techniques, e.g. [3], [4], [5], [6], define  $r_{RRR}$  with the value of  $R_1$  determined at a temperature other than 293 K, or the value of  $R_2$  determined at a temperature below the superconducting transition. The user of this document should be alert for such differences in definition.

#### 4 Principle

The 4-point DC electrical resistance technique shall be performed both at room temperature and at cryogenic temperature. The test may be done either as a function of temperature or as a function of time with increasing temperature.

The relative combined standard uncertainty of this method is 3 % with coverage factor 2.

Measurements shall have the following attributes.

- a) Measuring current is sufficiently high to provide voltage signals of the order of 1 μV. For electrical safety, maximum current density should never exceed 1 A mm<sup>-2</sup>.

<sup>1</sup> Numbers in square brackets refer to the Bibliography.

- b) Contact resistance for current leads is sufficiently low to avoid excessive heating of the sample. Typical cryogenic measurement conditions require power dissipation at contacts to be less than 1 mW.
- c) Sample sizes ~~shall be~~ are sufficiently large to minimize effects from cutting and handling damage. Typical samples are 1 mm to 3 mm in cross-section dimension and  $> 5 \text{ mm}^2$  in cross-sectional area.
- d) Sample length ~~shall be~~ is at least 10 times and not more than 25 times the width or diameter.

Annex A discusses considerations for sample dimensions and measuring current.

## 5 Measurement apparatus

### 5.1 Mandrel or base plate

A straight mandrel or base plate shall be used to support the specimen. Possible materials of construction include pure copper, pure aluminium, pure silver, electrical grades of Cu-Zr, Cu-Cr-Zr, Cu-Be, and other copper alloys, electrical grades of Al-Mg, Al-Ag, and other aluminium alloys, and electrical grades of silver alloys. These provide high thermal conductivity and serve to remove thermal gradients during measurement. ~~Care should be taken to insulate~~ The specimen shall be insulated from the mandrel. Possible insulating materials include polyethylene terephthalate, polyester, and polytetrafluoroethylene, which may be applied as foils, tapes, or coatings. Glass-fibre reinforced epoxy or other composite materials with good thermal conductivity at cryogenic temperature may also be used.

The base plate should have a clean and smooth surface finish. There should be no burrs, ridges, seams, or other asperities that may affect the specimen. High-purity niobium specimens are soft and are susceptible to indentation by surface flaws, and such indentations may alter the sample and invalidate the resistance measurement.

The mandrel or base plate shall support the entire length and width of the specimen. Mandrel or base plate geometry should not impose a bending strain of more than 0,2 % on the sample.

A thermometer accurate to 0,1 K is helpful but not required. The mandrel or base plate may incorporate a mounting for a cryogenic thermometer directly against the body of the mandrel or base plate and near the centre of the test specimen.

Practical base plates are at least 30 mm in length to accommodate assembly of pieces and handling of samples by human hands. Multiple samples may be mounted against a single base plate.

### 5.2 Cryostat and support of mandrel or base plate

The apparatus shall make provisions for mechanical support of the mandrel or base plate. In addition, such support shall provide electrical leads to carry currents for samples and thermometers, and measure their voltages. For  $R_1$  and  $R_2$  measurements, the support shall permit current to flow through only the sample, so that the entire resulting voltage measured is only that generated by the sample.

The support structure shall permit measurement of both  $R_1$  and  $R_2$  without dismounting or remounting the test specimen. Measurement of  $R_2$  shall require the use of a cryostat, which shall, moreover, integrate with the support.

The cryostat shall include a liquid helium reservoir at the bottom of a substantial vertical column. A support structure shall accommodate the raising and lowering of the sample into or out of the helium bath. In addition, anchoring of the sample position, either when immersed in liquid helium or suspended above the surface of the liquid at an arbitrary height, shall be provided. Such suspension permits the equilibration of temperature during measurement and slow increase of temperature with height above the helium bath. Alternatively, immersion of the sample into the bath followed by reduction of the bath level via boil-off or pressurized transfer can also be used to vary temperature.

A heater may be employed to warm the mandrel or base plate. ~~Care should be taken to distribute~~ The heater ~~should be distributed~~ along the mandrel and ~~avoid~~ excessive power settings ~~should be avoided~~. For instance, a point source of 1 W heat input operating at the centre of a 1 cm<sup>2</sup> mandrel upon which a 5 cm sample is mounted could produce thermal gradients of 2,5 K along the sample if the thermal conductivity is 100 W m<sup>-1</sup> K<sup>-1</sup>.

Proper cryogenic techniques shall be followed for the construction of the cryostat and apparatus. This includes the use of low thermal conductivity materials such as thin-walled stainless steel tubes, composite materials, ceramics, and insulation, to prevent excessive boil-off due to heat conduction from the surroundings. A can or shield may surround the base plate or mandrel with mounted sample to improve thermal stability. Provisions for pressure relief and vacuum isolation of the liquid helium should be incorporated with the apparatus.

## 6 Specimen preparation

High-purity niobium is quite malleable, and even the slightest force can produce deformation of the material. Since dislocations are one source of electron scattering, specimen deformation ~~may~~ can inadvertently contribute to the residual resistivity and affect the test result. Therefore, special protocols shall be observed when preparing the specimen. Cutting techniques shall avoid heat and strain to the extent possible. Discharge machining, fluid-jet cutting, or low-speed conventional machining are acceptable and widely-used techniques for applications using high-purity niobium. Specimens cut from larger pieces ~~should~~ shall be protected and immobilized against a support piece during transport. Operations to de-burr samples ~~should be done with great care to~~ shall not bend, excessively heat or otherwise damage the sample. Light sanding with fine paper is one acceptable approach.

Specimens should be rectangular or circular bars with uniform cross-section. Long sides of the specimen shall be parallel. Any twisting or curvature shall be avoided to ensure that bending or torsion is not applied to the test specimen during mounting to the mandrel or base plate. Specimens that form an arc or a U shape are acceptable provided that the entire curvature can be supported on a plane, without applying torsion to the bent specimen.

The specimen shall be clean and have no trace of residues from cutting fluids or any other surface contaminants. Degreasing with solvents, followed by ultrasonic cleaning using a mild water-based detergent, followed by rinsing with distilled or ultra-pure water, then drying in air, is preferred for cleaning residues. Chemical etching to clean the surface poses a risk of introducing contaminants, especially hydrogen and oxygen, and should be avoided. Gentle mechanical polishing of the regions where voltage taps and current leads attach is usually sufficient to remove surface oxides. Coating these regions with indium foil or another metal, for example by evaporation or sputtering, is an acceptable method to protect polished contacts provided ~~care is taken to avoid~~ that coating the entire specimen is avoided.

The test specimen shall be a single piece and shall not include any joints or splices.

A mechanical method shall be used to affix the test specimen to the mandrel or base plate. ~~Special care shall be taken during the~~ Installation and instrumentation of the specimen ~~to ensure that there is no~~ shall not apply excessive force, bending strain, tensile strain, or torsion ~~applied~~ to the specimen.

The test specimen shall be instrumented with current contacts near each end of the specimen and a pair of voltage contacts over the central portion between the current contacts (i.e. a 4-point measurement technique). The voltage contacts shall be separated from the current contacts by a distance no smaller than the largest dimension (width, thickness, or diameter) perpendicular to the specimen length.

## 7 Data acquisition and analysis

### 7.1 Data acquisition hardware

Modern power supplies can be computer controlled and come with a variety of features that permit remote control of the current output. Use of such power supplies is not required but could greatly enable automation of the data acquisition. Pulsed modes permit application of current only when voltage signals are being acquired, thereby removing heat generated in the sample during the off cycle. If pulsed current application is used, the pulse duration shall include ample periods for voltage signals to settle and be filtered.

Some power supplies incorporate an internal shunt to regulate the output current. If such a power supply is used, the internal shunt shall be calibrated periodically with an external shunt and voltage measurement.

The test set-up may establish an arbitrary baseline voltage  $U_0$ , which might be detectable when the sample is in the superconducting state and the power supply is off. The value  $U_0$  can drift over time due to changes in the thermal environment and other effects. More complex hardware includes compensation for drift and automatic nulling such that the time average of  $U_0$  is 0. Digital voltage meters are not required but greatly enhance the data acquisition. Besides compensation for drift and voltage nulling, filtering and internal compensation for thermally-induced voltages can improve the accuracy of the voltage measurement. Filtering should average voltage signals for a time at least as long as the thermal time constant of the apparatus at low temperature, typically of the order of 0,1 s to 10 s. ~~Care should be taken~~ It is important to understand how voltages are corrected for drift and thermal effects. Sensitive voltage meters, especially nanovolt meters, require a pre-amplifier that needs to be at thermal equilibrium, which ~~may~~ can require several hours of operation in advance of the measurement.

Data acquisition via computer greatly facilitates the recording and reporting of data.

### 7.2 Resistance ( $R_1$ ) at room temperature

The ambient temperature  $T_1$  of the measurement laboratory shall be measured. A specimen current  $I_1$  shall be applied in accordance with the requirements in Clause 4. The resulting voltage  $U_1$  shall be recorded together with  $I_1$  and  $T_1$ . The resistance shall be determined by

$$R_1 = \frac{U_1}{I_1} [1 - 0,0037 (T_1 - 293)] \quad (2)$$

with  $T_1$  in units of kelvin. The coefficient 0,003 7 reflects the experimentally observed rate of change of resistance with temperature given in [7] over the interval 273 K to 300 K.

### 7.3 Residual resistance ( $R_2$ ) just above the superconducting transition

The measurement of  $R_2$  shall be made with the sample still mounted on the mandrel or base plate for the measurement of  $R_1$ .

The specimen shall be placed in a cryostat as specified in 5.2. The specimen shall be slowly lowered into a liquid helium bath and cooled to liquid helium temperature. While a vigorous boil-off of liquid helium will accompany the initial cool down, removal of heat from the mandrel, especially if it is shielded, can require a time period of more than 5 min. Current may be applied, and voltage may be monitored during this period, but no measurement shall be made until the vigorous boil-off of liquid helium has subsided.

After the boil-off rate is suitable for measurements, a voltage measurement  $U_0$  shall be recorded while the sample is immersed in liquid helium. The sample ~~should~~ is likely to be in the superconducting state under these conditions. Current  $I_2$  shall then be applied per requirements of Clause 4 and with considerations of Clause 5. Voltage readings  $U_0^+$  and  $U_0^-$  shall be acquired for forward and reverse current polarity, respectively. Any differences between  $U_0$ ,  $U_0^+$ , and  $U_0^-$  shall be recorded.

The specimen shall then be gradually warmed so that a transition from the superconducting state into the normal state occurs gradually. An apparatus that conforms to Clause 6 will permit gradual warming of the specimen by raising the level of the mandrel above the level of the liquid helium bath, for example. Two voltages  $U_2^+$  and  $U_2^-$  shall be measured almost simultaneously with the application of the same measuring current  $I_2$  with forward and reverse polarity, respectively. The current shall not be applied when measurements are not being recorded. The voltage  $U_2$  shall be determined by

$$U_2 = \frac{|U_2^+ - U_2^-|}{2} \tag{3}$$

where it should be noted that the sign of  $U_2^-$  is opposite that of  $U_2^+$ ; i.e. Formula (3) indicates an average of the two numbers approximately equal in magnitude. A resistance  $R$  shall be determined from the voltage by

$$R = \frac{U_2}{I_2} \tag{4}$$

As the sample is warmed, values  $R$  shall be recorded as a function of ~~either~~ the temperature  $T$  determined by the thermometer attached to the mandrel or base plate, ~~or the time  $t$~~ . Graphical aids and data analysis software are acceptable tools for plotting the resistance versus temperature curve ~~or resistance versus time curve~~ and performing extrapolations.

A resistance versus temperature curve shall thus be obtained as in Figure 1. The resistance versus temperature curve shall be continuously recorded until a temperature of at least 15 K is reached. The resistance versus temperature curve shall be analysed by drawing a line through the region of steepest slope near the midpoint of the resistance rise, line (a) on Figure 1, and extrapolating this line sufficiently above the value of  $R$  recorded at 15 K. A second line shall be drawn through the region of the resistance versus temperature curve above the transition, line (b) in Figure 1, and this line shall be extrapolated to sufficiently lower temperature such that it intersects with line (a). The intersection is labelled as point A in Figure 1. The value of resistance  $R_2$  corresponding to intersection point A shall be recorded, along with the value of temperature  $T_c^*$  corresponding to intersection point A.