



Edition 3.0 2022-04 COMMENTED VERSION

INTERNATIONAL STANDARD



Electrostatics – Part 5-3: Protection of electronic devices from electrostatic phenomena – Properties and requirements classification for packaging intended for electrostatic discharge sensitive devices

EC 61340-5-3:2022

https://standards.iteh.ai/catalog/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2022 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11 info@iec.ch www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.







Edition 3.0 2022-04 COMMENTED VERSION

INTERNATIONAL STANDARD



Electrostatics – Part 5-3: Protection of electronic devices from electrostatic phenomena – Properties and requirements classification for packaging intended for electrostatic discharge sensitive devices

IEC 61340-5-3:2022

https://standards.iteh.ai/catalog/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 17.220.99; 29.020

ISBN 978-2-8322-4962-8

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

F	OREWO	DRD	4
IN	ITRODI	JCTION	6
1	Sco	be	7
2	Norr	native references	7
3	Tern	ns, definitions and abbreviated terms	7
	3.1	Terms and definitions	7
	3.2	Abbreviated terms	9
4	Tailo	pring	9
5	Pacl	aging application requirement	9
	5.1	General	9
	5.2	Inside an EPA	9
	5.3	Outside an EPA	10
6	Clas	sification of ESD packaging material properties	10
	6.1	General	10
	6.2	Material resistance properties	10
	6.2.		
	6.2.2		
	6.2.	J	
	6.2.3		11
	6.2.4		
	6.3 6.3. ²	Material electrostatic shielding properties 1 Electrostatic discharge shielding	11 11
	6.3.2		
7		nnical requirements for ESD protective packaging	
tps://	standare	to tak silastala alatanda lisa (6296) far h2f 1327 952 Ohalfa 112612 lisa 612	10-5-3 ₁ 2022
	7.2	Packaging marking	
	7.2.		
	7.2.2	-	
	7.2.3	3 Traceability	14
Aı	nnex A	(informative) Guidance on ESD packaging material-guidance	15
	A.1	Environment and device sensitivity	15
	A.1.	1 General	15
	A.1.		15
	A.1.		
	A.2	Equipotential bonding	
	A.3	Dissipative material for intimate contact	
	A.4	Packaging from incoming material to the point of use	
	A.5	Periodic verification Examples of measurement procedures for qualification and verification of	18
	A.6	packaging	19
Aı	nnex B	(informative) Device damage	21
	B.1	Damage from ESD	21
	B.2	Discharge to a device	21
	B.2.		04
		device from external objects	
	B.2.	2 Retained charge on a packaging	ZI

IEC 61340-5-3:2022 CMV © IEC 2022 - 3 -

B.3 Disc	harge from a floating device (CDM)	21
B.3.1	Charged device model (CDM) Discharges from devices in an electric field	21
B.3.2	Tribo-electrification Discharges from tribo-electrified devices	21
Annex C (infor	mative) Guidance on electric field shielding	22
Annex D (infor	mative) Low charging material property	23
Bibliography		24
List of commer	nts	25

Figure 1 – Example of packaging label (*Primary function code)	13
Figure A.1 – Examples of EPA configurations	16
Figure A.2 – Application of ESD protective packaging	18

Table 1 – Test methods for electrostatic protective packaging	.12
Table 2 – Test methods and requirements for electrostatic discharge shielding packaging	.13
Table 3 – Primary function code and ESD classification symbol	.14
Table A.1 – Packaging characteristics for environmental consideration	.15
Table A.2 – Examples of qualification and verification of packaging	.19

iTeh Standards

(https://standards.iteh.ai Document Preview

IEC 61340-5-3:2022

https://standards.iteh.ai/catalog/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTROSTATICS -

Part 5-3: Protection of electronic devices from electrostatic phenomena – Properties and requirements classification for packaging intended for electrostatic discharge sensitive devices

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- ^{(IPS}6)³ All users should ensure that they have the latest edition of this publication. ⁹ balle412613/iec-61340-5-3-2022
 - 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
 - 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
 - 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This commented version (CMV) of the official standard IEC 61340-5-3:2022 edition 3.0 allows the user to identify the changes made to the previous IEC 61340-5-3:2015 edition 2.0. Futhermore, comments from IEC TC 101 experts are provided to explain the reasons of the most relevant changes.

A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text. Experts' comments are identified by a blue-background number. Mouse over a number to display a pop-up note with the comment.

This publication contains the CMV and the official standard. The full list of comments is available at the end of the CMV.

IEC 61340-5-3:2022 CMV © IEC 2022 - 5 -

IEC 61340-5-3 has been prepared by IEC technical committee 101: Electrostatics. It is an International Standard.

This third edition cancels and replaces the second edition published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) reference to IEC 61340-4-10¹ [1]² was removed;
- b) material resistance property "electrostatic field shielding" was removed;
- c) the requirement for electrostatic discharge shielding was changed from 50 nJ to 20 nJ;
- d) Table 1 footnote "b" was changed to mention the two-point probe in IEC 61340-2-3;
- e) "shall be marked" was changed to "should be marked" in 7.2.2 and 7.2.3;
- f) Table 3 the classification symbol and the primary function code F was removed;
- g) Table A.2 references to IEC TS 61340-5-4 [2] and IEC TR 61340-5-5 [3] were added;
- h) Annex C guidance regarding electric field shielding was added;
- i) Annex D low charging material property was added.

The text of this International Standard is based on the following documents:

Draft	Report on voting	
101/649/FDIS	101/660/RVD	

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 61340 series, published under the general title *Electrostatics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

¹ Withdrawn.

² Numbers in square brackets refer to the bibliography.

INTRODUCTION

Packaging is necessary to protect electrostatic discharge sensitive devices (ESDSs) from static electricity and electrostatic discharge (ESD) damage as well as **1** physical and environmental damage during manufacture, transportation and storage.

iTeh Standards (https://standards.iteh.ai) Document Preview

IEC 61340-5-3:2022

https://standards.iteh.ai/catalog/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022

ELECTROSTATICS –

Part 5-3: Protection of electronic devices from electrostatic phenomena – Properties and requirements classification for packaging intended for electrostatic discharge sensitive devices

1 Scope

This part of IEC 61340 defines the ESD protective packaging properties-needed required to protect-electrostatic discharge ESD sensitive devices (ESDSs) through all phases of production, rework/ and maintenance, transport and storage. Test methods are referenced to evaluate packaging and packaging materials for these product and material properties. Performance limits are provided.

This document does not address protection from electromagnetic interference (EMI), electromagnetic pulsing (EMP) or protection of volatile materials electrically initiated explosive materials or devices **2**.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61340-2-3, *Electrostatics – Part 2-3: Methods of test for determining the resistance and resistivity of solid planar materials used to avoid electrostatic charge accumulation*

IEC 61340-4-8, Electrostatics – Part 4-8: Standard test methods for specific applications – Electrostatic discharge shielding – Bags

IEC 61340-4-10, Electrostatics – Part 4-10: Standard test methods for specific applications – Two-point resistance measurement³ 3

IEC 60417, Graphical symbols for use on equipment (available at http://www.graphicalsymbols.info/equipment) 4

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

³ At the time of writing, it is proposed withdrawing IEC 61340-4-10: 2012 and incorporating the test method into the next edition of IEC 61340-2-3.

3.1.1 electrostatic discharge ESD

rapid transfer of charge between bodies at different electrostatic potentials

Note 1 to entry: This note applies to the French language only.

3.1.2 electrostatic discharge ESD sensitive device ESDS

sensitive device, integrated circuit or assembly that may can be damaged by electrostatic fields or electrostatic discharge

Note 1 to entry: This note applies to the French language only.

Note 1 to entry: See Clause B.2 and Clause B.3 in Annex B.

3.1.3 ESD protected area EPA

area in which an ESDS can be handled with acceptable risk of damage caused by electrostatic discharge or fields

SEE: Figure A.1 in Annex A.

3.1.4 iTeh Standards UPA area outside an EPA https://standards.iteh.ai)

Note 1 to entry: This note applies to the French language only.

SEE: Figure A.1 in Annex A.

3.1.5

EC 61340-5-3:2022

intimate packaging log/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022 material which makes contact with an ESDS

3.1.6

proximity packaging

material not making contact with an ESDS and which is used to enclose one or more devices

3.1.7

secondary packaging

material used primarily to give additional physical protection to the outside of proximity-package packaging

3.1.8

volume resistance

 R_V

ratio of a DC voltage (V) applied between two electrodes placed on two (opposite) surfaces of a specimen and the current (A) between the electrodes

Note 1 to entry: Volume resistance is expressed in $\boldsymbol{\Omega}.$

3.1.9

point-to-point resistance

 R_{p-p}

ratio of a DC voltage (V) applied between two electrodes on a surface of a specimen and the current (A) between the electrodes

Note 1 to entry: The electrode configuration for point-to-point resistance measurements is usually a pair of circular faced electrodes with a defined distance apart.

Note 2 to entry: Point-to-point resistance is expressed in Ω .

3.1.10

surface resistance

 R_{S}

ratio of a DC voltage (V) applied between two electrodes in a defined configuration on a surface of a specimen and the current (A) between the electrodes

Note 1 to entry: The electrode configuration for surface resistance measurement is usually a pair of parallel rectangular electrodes or a pair of circular concentric electrodes.

Note 2 to entry: Surface resistance is expressed in Ω .

3.2 Abbreviated terms

- CDM charged device model
- EMI electromagnetic interference
- EMP electromagnetic pulsing
- EPA ESD protected area
- ESD electrostatic discharge
- ESDS electrostatic discharge sensitive device
- HBM human body model
- MM Machine model 5
- UPA unprotected area

4 Tailoring

This document, or portions thereof, may does not necessarily apply to all applications. Tailoring is accomplished by evaluating the applicability of each requirement for the specific application. Upon completion of the evaluation, requirements may be added, modified or deleted.

Tailoring decisions, including rationale, shall be documented.

5 Packaging application requirement

5.1 General

Transportation and storage of ESDSs require packaging that provides protection from electrostatic hazards (for example from an electrostatic discharge). Within an EPA in which all ESD risks are well controlled, it is possible that ESD protective packaging may will not be necessary.

5.2 Inside an EPA

Packaging used within an EPA shall consist of dissipative or conductive materials for intimate contact.

Items sensitive to <100 V human body model (HBM) may need additional protection depending on application and program plan requirements.

Additional protection can be necessary for items sensitive to < 100 V for HBM, < 200 V for CDM and < 35 V for isolated conductors, depending on application and program plan requirements. 6

NOTE Dissipative materials are preferred for intimate packaging in situations where charged device model (CDM) damage is a concern.

5.3 Outside an EPA

Transportation and storage of sensitive products outside of an EPA shall-require be done in packaging that provides both

- a) dissipative or conductive materials for intimate contact,
- b) a structure that provides electrostatic discharge shielding.

If electrostatic field shielding materials are used to provide discharge shielding, a material that provides a barrier to current flow should be used in combination with the electrostatic field shielding material.

NOTE Dissipative materials are preferred for intimate packaging in situations where charged device model (CDM) damage is a concern.

6 Classification of ESD packaging material properties

6.1 General

Materials and <u>packages</u> packaging that are useful in preventing damage to ESD sensitive <u>electronic</u> devices exhibit certain properties. These properties include:

- a) resistance properties:
 - conductive;
 - dissipative;
- b) shielding properties:
 - electrostatic discharge
 - electrostatic field;
- c) low charging properties:

See Annex D. 7

EC 61340-5-3:2022

https://standards.iteh.ai/catalog/standards/iec/63862fec-b3f6-4ce7-8e52-9ba1fe412613/iec-61340-5-3-2022 6.2 Material resistance properties

6.2.1 General

Most standard packaging materials are electrically insulating and insulating materials retain charge. Making the <u>package</u> packaging less insulating provides a path for the charge to dissipate from the <u>package</u> packaging to a material at a lower potential.

Specific ranges of resistance are useful for different purposes. Packaging can be classified by these resistance ranges of the material used in its construction.

6.2.2 **Resistance of conductive materials**

Conductive materials may can be surface conductive, volume conductive or both.

a) Surface conductive materials

Surface conductive materials shall have a surface resistance of $< 1 \times 10^4 \Omega$.

b) Volume conductive materials

Volume conductive materials shall have a volume resistance of < 1 × $10^4 \Omega$.

NOTE The thickness of the material-might can have a significant influence on the measured value of volume resistance.

IEC 61340-5-3:2022 CMV © IEC 2022 - 11 -

6.2.3 Resistance of electrostatic field shielding materials 8

Within the conductive materials classification, electrostatic field shielding materials shall have a homogeneous layer with a surface resistance of $<1 \times 10^3 \Omega$ or a volume resistance of $<1 \times 10^3 \Omega$.

Other methods may also define the electrostatic field shielding classification.

NOTE These resistance values do not necessarily imply EMI/EMP shielding.

6.2.3 Resistance of dissipative materials

Dissipative materials-may can be surface dissipative, volume dissipative or both.

a) Surface dissipative materials

Surface dissipative materials shall have a surface resistance $\ge 1 \times 10^4$ and $< 1 \times 10^{11} \Omega$.

b) Volume dissipative materials

Volume dissipative materials shall have a volume resistance $\geq 1 \times 10^4$ and $< 1 \times 10^{11} \Omega$.

NOTE The thickness of the material-might can have a significant influence on the measured value of volume resistance.

6.2.4 Resistance of insulating materials

Electrostatic insulating materials may can be surface insulating, volume insulating or both.

a) Surface insulating materials

Electrostatic surface insulating materials have a surface resistance $\ge 1 \times 10^{11} \Omega$.

b) Volume insulating materials current Preview

Electrostatic volume insulating materials have a volume resistance $\ge 1 \times 10^{11} \Omega$.

6.3 Material electrostatic shielding properties 2022

NOTE Electrostatic shielding materials protect packaged sensitive electronic items ESDSs from the effects of electrostatic discharges and fields that are external to the package packaging.

6.3.1 Electrostatic discharge shielding

Electrostatic discharge shielding packaging is capable of attenuating an electrostatic discharge. The calculated energy allowed inside-<u>a static</u> an electrostatic discharge shielding bag shall be less than-<u>50</u> 20 nJ **9** when tested according to IEC 61340-4-8 or equivalent test method modified to accommodate the product.

6.3.2 Electrostatic field shielding

Electrostatic field shielding packaging is capable of attenuating an electrostatic field.

NOTE Classified field-shielding materials can allow current flow through their volume.

See Annex C.

7 Technical requirements for ESD protective packaging

7.1 Packaging and material properties

Table 1 and Table 2 provide test methods for determining material classifications for finished packages packaging and materials. When possible, testing shall be performed on the finished package packaging. When testing cannot be performed on a finished package packaging, the

material classification shall be defined by the bulk material used for the production of the final package packaging.

Other probes (electrodes) may be used providing the results correlate with the specified probes (electrodes). In case of dispute, the probe (electrode) assemblies specified in IEC 61340-2-3 shall be used. 10

Material classification	Test method ^a	Method description	Limits
Surface conductive	IEC 61340-2-3 ^e	R _S Surface resistance	< 1 × 10 ⁴ Ω
conductive	IEC 61340-2-3 ^{b,e}	<i>R</i> _{p-p} Point-to-point resistance	< 1 × 10 ⁴ Ω ^c
	IEC 61340-4-10^{-b} <mark>11</mark>	R _{p-p} _Point-to-point resistance	<1 × 10⁴ Ω [€]
Volume conductive	IEC 61340-2-3 ^e	<i>R</i> _V Volume resistance	$< 1 \times 10^4 \Omega^d$
Electrostatic	IEC 61340-2-3 ^e	R _S Surface resistance	<1 × 10³ Ω
^{field} shielding <mark>12</mark>	IEC 61340-2-3 °	<i>R</i> _V —Volume resistance	<1 × 10³ Ω^d
Surface	IEC 61340-2-3 ^e	R _S Surface resistance	$\geq 1 \times 10^4$ to < 1 × 10 ¹¹ Ω
dissipative	IEC 61340-2-3 ^{b,e}	<i>R</i> _{p-p} Point-to-point resistance	\geq 1 × 10 ⁴ to < 1 × 10 ¹¹ Ω ^c
	IEC 61340-4-10^{-b} IICN N	R _{p-p} Point-to-point resistance	≥1 × 10⁴⁻ to <1 × 10¹¹ Ω °
Volume dissipative	IEC 61340-2-3 e	R _V Volume resistance	\ge 1 × 10 ⁴ to < 1 × 10 ¹¹ Ω ^d
Surface	IEC 61340-2-3 ^e	R _S Surface resistance	$\geq 1 \times 10^{11} \Omega$
insulating	IEC 61340-4-10 ^{-b} IEC 61340-2-3 ^{b,e}	R _{p-p} Point-to-point resistance	≥ 1 × 10 ¹¹ Ω ^c
Volume insulating ards.it	IEC 61340-2-3 ° IEC 61340-2-3 ° In al/catalog/standards/iec/63862f	$R_{\rm V}$ Volume resistance	≥ 1 × 10 ¹¹ Ω ^d 2613/iec-b1340-5-3-20

Table 1 – Test methods for electrostatic protective packaging

For product qualification of packaging materials, the environmental conditions for preconditioning and testing shall be 23 °C ± 2 °C and 12 % ± 3 % relative humidity. The preconditioning before the measurement shall be \geq 48 h.

IEC 61340-2-3 describes point-to-point resistance measurements using two 2,5 kg electrodes. It also describes a two-point probe for point-to-point resistance measurements for non-planar materials and products with small structures. Either of these two test methods may be used. 13

- с The results of a measurement of R_{p-p} according to IEC 61340-2-3 or IEC 61340-4-10 can be different compared to the results of a measurement of $R_{\rm S}$ according to IEC 61340-2-3 due to the usage of different probes.
- d The thickness of the material might can have a significant influence on the values of a measured volume resistance. The requirement is the same despite the thickness of the material.
- IEC 61340-2-3 describes test methods for the determination of the electrical resistance and resistivity of solid materials in the range from $10^4 \Omega$ to $10^{12} \Omega$, and refers to other standards for measurements outside this range. However, it is possible that the other test methods referred to-may will not be appropriate for measuring packaging materials or products. Therefore, for the purposes stated in this table, any of the concentric ring probe electrodes specified in IEC 61340-2-3 shall be used. The instrumentation used shall be able to measure to below $10^3 \Omega$; it is acceptable for the open circuit voltage or voltage under load of the instrumentation used to be less than 10 V.

IEC 61340-4-10 describes the R_{p-p}-point to point resistanc h IEC 61340-2-3 describes all three test methods $R_{\rm g}$, $R_{\rm V}$ and $R_{\rm p,p}$.