

Designation: D3722 – 05 (Reapproved 2019)

Standard Specification for Natural Red and Brown Iron Oxide Pigments¹

This standard is issued under the fixed designation D3722; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers dry and wet ground naturally occurring iron oxide, dry and wet ground calcined naturally occurring iron oxide, and mixtures of these with synthetic iron oxides. These pigments are suitable for use in paints, coatings, and many other applications.

1.2 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese

D185 Test Methods for Coarse Particles in Pigments

D280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments

D1208 Test Methods for Common Properties of Certain Pigments

3. Composition and Properties

3.1 The pigments shall conform to the following requirements:

Total iron as Fe ₂ O ₃ , min, %	40.0
Moisture and other volatile matter, max, %	1.0
Organic coloring matter	none
Total sulfates expressed as SO ₃ , max, %	2.0
Matter soluble in water, max, %	2.0
Matter soluble in water, max, % (primer pigments)	1.0
Coarse particles (total residue retained on a No. 325	2.0
(45-µm) sieve) max, %	

3.2 The mass color and character of the tint and the tinting strength formed by a mixture with a white pigment shall be within mutually agreed upon limits of a standard acceptable to both the purchaser and the seller.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear samples shall be taken from different packages in the ratio of two samples for each 5 tons (inch-pound or SI), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately, or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods 2cd64d8849/astm-d3722-052019

5.1 Tests shall be conducted in accordance with the appropriate ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Total Iron Oxide, Sulfur, and Organic Coloring Matter*—Test Methods D50.

5.1.2 *Moisture and Other Volatile Matter*—Test Method D280, Method A.

5.1.3 Matter Soluble in Water-Test Method D1208.

5.1.4 *Coarse Particles in Dry Pigments*—Test Method D185.

6. Keywords

6.1 iron oxide; natural brown; pigments

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved May 1, 2019. Published May 2019. Originally approved in 1978. Last previous edition approved in 2011 as D3722 – 05 (2011). DOI: 10.1520/D3722-05R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.