



Designation: ~~D5933 – 96 (Reapproved 2013)~~ **D5933 – 19**

Standard Specification for 2⁵/₈-in. and 4-in. Diameter Metal Shear Plates for Use in Wood Constructions¹

This standard is issued under the fixed designation D5933; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers standardizing the dimensions and materials for the manufacture of 2⁵/₈ and 4-in. diameter steel or cast iron shear plates used in the fabrication of connections in wood constructions. The referencing of this specification in design, construction, and purchase order documents gives the using parties ~~assurance~~ insurance that the shear plates to be used in an assembly meet minimum materials quality standards and that dimensions for fabrication and finish can be relied on to ensure connection performance. This specification provides regulatory agencies with a set of standards by which to judge the acceptability of shear plates encountered in the field and in fabricators' shops.

1.2 The values stated in inch-pound units are to be regarded as standard. The values in parentheses are ~~for information only.~~ mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *Safety Hazards*—There are no known hazards with the use of this specification. ~~The~~ It is necessary that the products manufactured to this specification should not be brittle or difficult to install with proper tools.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[A47/A47M Specification for Ferritic Malleable Iron Castings](#)

[A153/A153M Specification for Zinc Coating \(Hot-Dip\) on Iron and Steel Hardware](#)

[A570/A570M Specification for Structural Steel, Sheet and Strip, Carbon, Hot-Rolled \(Withdrawn 2000\)](#)³

[A653/A653M Specification for Steel Sheet, Zinc-Coated \(Galvanized\) or Zinc-Iron Alloy-Coated \(Galvannealed\) by the Hot-Dip Process](#)

[A924/A924M Specification for General Requirements for Steel Sheet, Metallic-Coated by the Hot-Dip Process](#)

2.2 Other Document:

[AISI/SAE No. 1010 Carbon Steel, Steel Products Manual, Plates, Iron and Steel Society](#)

3. Terminology

3.1 Definitions:

3.1.1 *shear plate*—A round, cast, or stamped disk-like load-transfer device having a flat base and a perimeter bearing rim protruding in one direction normal to the base, with a hole passing through the center of the disk to accommodate an attachment bolt or lag screw.

3.1.1.1 Discussion—

The fastener hole at the center may have an additional bearing hub. If a bearing hub is present it projects in the same direction

¹ This specification is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.05 on Wood Assemblies. Current edition approved April 1, 2013 April 1, 2019. Published April 2013 May 2019. Originally approved in 1997. Last previous edition approved in 2007 2013 as D5933 – 96 (2007) (2013). DOI: 10.1520/D5933-96R13-10.1520/D5933-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

as the bearing rim. A shear plate is installed into one or more faces of a piece of wood to transfer shear forces between the member containing the shear plate or plates and adjacent members which may be of wood or steel. This shear transfer is accomplished through the bolt or lag screw.

4. Classification

4.1 This specification covers the two basic diameters of metal shear plates commonly used in North American timber construction—2⁵/₈ in. (66.7-mm) diameter stamped steel or malleable cast iron, and 4-in. (102.1-mm) diameter malleable cast iron. The use of these shear plates is covered in the National Design Specification for Wood Construction⁴ and other wood design documents.

5. Materials and Manufacture



5.1 *General:*

5.1.1 Cast iron shear plates shall be free from any casting defects such as voids, irregular holes or sharp burrs greater than 0.03 in. (0.8 mm), or any other casting defect that would hinder normal installation and performance. All residual metal at casting gate locations and any other protrusions that would prevent the proper installation and fit of the plates shall be ground smooth or otherwise removed.

5.1.2 Shear plates shall be permanently marked with the manufacturer’s name or a readily recognizable logo, or both; the number of this ASTM standard; the country of origin; and the model number, if applicable. ~~Such marking may~~ It is acceptable for such marking to be on any nonbearing surface and shall be recessed into the device so as not to interfere with installation or weaken the finished shear plate.

5.1.3 Shear plates shall have two diametrically opposed holes which can be used to nail-attach the plate in the piece of wood in which it is installed to facilitate shipping and handling without dislodging of the plate. See Fig. 1, Fig. 2, and Fig. 3.

5.1.4 Casting draft on the rim and on the hub, if present, of cast iron shear plates shall be minimal and as shown to facilitate removal from the mold without diminishing strength or creating a poor fit into cutterhead grooves (see Fig. 2 and Fig. 3).



SECTION A-A

NOTE 1—Make from Specification A570/A570M or AISI/SAE No. 1010 carbon steel. Tolerance on all dimensions except sheet steel thickness: ±0.020 in. Tolerance on sheet steel thickness per manufacturing specifications.

FIG. 1 2⁵/₈-in. Diameter Stamped Steel Shear Plate

⁴ Available from the American Forest and Paper Association, 1111 19th St., NW, Suite 800, Washington, DC 20036.