

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Ferrite cores – Guidelines on dimensions and the limits of surface irregularities –
Part 9: Planar-cores

IEC STANDARD PREVIEW
(standards.iteh.ai)

Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites des irrégularités de surface –
Partie 9: Noyaux planaires

IEC 63093-9:2020

<https://standards.iteh.ai/catalog/standards/63093-9-112-47/6-adda-33093-9-2020>





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

<https://standards.iteh.ai/catalog/standardlist/4035697-512-4776-a0aa>

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.



IEC 63093-9

Edition 1.0 2020-04

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Ferrite cores – Guidelines on dimensions and the limits of surface irregularities –
Part 9: Planar-cores

[ITEH STANDARD PREVIEW](#)
(standards.iteh.ai)

Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites des irrégularités de surface –
Partie 9: Noyaux planaires

[IEC 63093-9-2020](#)

[http://www.iec.ch/standards/63093-9-2020](#)

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.100.10

ISBN 978-2-8322-8080-5

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Primary dimensions	7
4.1 Planar shapes and dimensions	7
4.2 Dimensions and effective parameters of planar EL-core and mating PLT-core	8
4.3 Dimensions and effective parameters of low-profile E-core and mating PLT-core	10
4.4 Dimensions and effective parameters of low-profile ER-core and mating PLT-core	12
5 Limits of surface irregularities	15
5.1 General	15
5.2 Examples of surface irregularities	16
5.3 Chips and ragged edges	17
5.3.1 General	17
5.3.2 Chips and ragged edges on the mating surfaces	17
5.3.3 Chips and ragged edges on other surfaces	18
5.4 Cracks	20
5.5 Flash	20
5.6 Pull-outs	IEC 63093-9:2020
5.7 Crystallites	https://standards.iteh.ai/catalog/standards/iso/4d3b697-5f82-4776-adca-ec0309ba8dbb/iec-63093-9-2020
5.8 Pores	24
Annex A (normative) Low-profile core design	26
A.1 General design	26
A.2 EL-core design	26
A.3 ER-core design	27
Annex B (informative) Reference values of allowable areas of chips	29
Bibliography	31
 Figure 1 – Planar EL-core and mating PLT-core	8
Figure 2 – Low-profile E-core and mating PLT-core	10
Figure 3 – Low-profile ER-core and mating PLT-core	12
Figure 4 – Examples of surface irregularities for planar EL-core	16
Figure 5 – Examples of surface irregularities for low-profile E-core	16
Figure 6 – Examples of surface irregularities for low-profile ER-core	16
Figure 7 – Chip location for planar EL-core	17
Figure 8 – Chip location for low-profile E-core	17
Figure 9 – Chip location for low-profile ER-core	17
Figure 10 – Cracks and pull-out location for planar EL-core	20
Figure 11 – Cracks and pull-out location for low-profile E-core	21
Figure 12 – Cracks and pull-out location for low-profile ER-core	21
Figure 13 – Reference dimensions for EL-core	21

Figure 14 – Reference dimensions for E-core	22
Figure 15 – Reference dimensions for ER-core	23
Figure 16 – Example of the location of a crystallite on planar EL-core.....	24
Figure 17 – Example of the location of a crystallite on low-profile E-core	24
Figure 18 – Example of the location of a crystallite on low-profile ER-core.....	24
Figure 19 – Example of the location of a pore on planar EL-core	25
Figure 20 – Example of the location of a pore on low-profile E-core	25
Figure 21 – Example of the location of a pore on low-profile ER-core.....	25
Table 1 – Dimensions of planar EL-core EL and mating PLT-core	9
Table 2 – Effective parameter values and A_{\min} values.....	10
Table 3 – Dimensions of low-profile E-core and mating PLT-core.....	11
Table 4 – Effective parameter values and A_{\min} values.....	12
Table 5 – Dimensions of low-profile ER-core and mating PLT-core	13
Table 6 – Effective parameter values and A_{\min} values.....	14
Table 7 – Area and length reference for visual inspection	19
Table 8 – Limits of cracks for planar EL-core	22
Table 9 – Limits of cracks for low-profile E-core	23
Table 10 – Limits of cracks for low-profile ER-core	23
Table A.1 – Sizes and design ratios for ER-core	28
Table B.1 – Allowable areas of chips for planar EL-core	29
Table B.2 – Allowable areas of chips for low-profile E-core	29
Table B.3 – Allowable areas of chips for low-profile ER-core	30

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 9: Planar-cores

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
<https://standards.iec.ch/catalog/standards/iec/63093-9-2020/ec0309ba8dbb/iec-63093-9-2020>
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 63093-9 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This first edition cancels and replaces the first edition of IEC 60424-5 published in 2009 and first edition of IEC 62317-9 published in 2006 and its Amendment 1:2007. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous editions of IEC 60424-5 and IEC 62317-9:

- a) IEC 63093-9 integrates IEC 60424-5 and IEC 62317-9;
- b) Table 1, Table 2 and Table 3 in IEC 60424-5:2009 have been moved to Annex B;
- c) some numbers are corrected in Table 4;
- d) Table 6 is amended following IEC 60205.

The text of this International Standard is based on the following documents:

CDV	Report on voting
51/1308/CDV	51/1326/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 63093 series, published under the general title *Ferrite cores – Guidelines on dimensions and the limits of surface irregularities*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 63093-9:2020](#)

<https://standards.iteh.ai/catalog/standards/sist/4de3b697-5ff2-4776-adaa-ec0309ba8dbb/iec-63093-9-2020>

INTRODUCTION

Today, DC-to-DC converter power supplies increasingly employ transformers and chokes, the windings of which are made of multi-layer printed circuit boards or are constructed in the motherboard, rather than the transformers wound by conventional copper wires. This document specifies the optimum shapes and dimensions of cores for surface mounted devices (SMDs) and of cores for which the windings are constructed in the motherboard. The motherboard has slots cut out to accept the ferrite cores. This is called the total integration in a multi-layer motherboard. The core shape specified in this document satisfies the demand for lower profile as well as for smaller floor space.

The relations between the main dimensions of planar E-, ER- and EL-cores differ from those of standard cores. For example, the width of planar-cores is larger while the total height is much smaller. Also the thickness of the legs is in most cases smaller than compared to standard cores. Therefore the concept of fixed reference dimensions to determine the length of crack limits yields crack lengths which are not acceptable for this type of core. This document follows another concept which relates the crack length to dimensions of the surface on which the crack occurs.

Also the concept to determine the maximum area of chips based on the total mating surface fails in the case of planar-cores. The outer legs of planar-cores are much thinner than those of standard cores which makes overlapping and gluing much more difficult. A single chip of maximum size on the outer leg can affect the functionality of the core set. Therefore this document uses as a reference the mating surface on which the chip occurs.

iTeh STANDARD PREVIEW

Windings of planar-cores are often PCBs which are glued to the inner surfaces of the planar-core. For this reason the inner surfaces of the planar-cores should have a better quality than the inner surfaces of standard cores. This was taken into account by reducing the maximum allowable area of pull-outs in the inner surfaces.
IEC 63093-9:2020

<https://standards.iteh.ai/catalog/standards/sist/4de3b697-5ff2-4776-adaa-ec0309ba8dbb/iec-63093-9-2020>

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 9: Planar-cores

1 Scope

This part of IEC 63093 specifies the shapes and dimensions of ferrite cores for inductive components (transformers and chokes), whose the coil is typically made of multi-layer boards (or the coil is part of the motherboard), and the effective parameter values used in calculations. This document gives guidelines on allowable limits of surface irregularities applicable to planar-cores as well.

This document is considered as a sectional specification useful in the negotiation between ferrite core suppliers and users about surface irregularities.

The general consideration upon which the design of this range of cores is based is given in Annex A.

2 Normative references *ITech STANDARD PREVIEW* *(standards.iteh.ai)*

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/4de3b697-5f2-4776-adaa-ec0309ba8dbb/iec-63093-9-2020>

IEC 60205:2016, *Calculation of the effective parameters of magnetic piece parts*

IEC 60401-1, *Terms and nomenclature for cores made of magnetically soft ferrites – Part 1: Terms used for physical irregularities*

IEC 60424-1, *Ferrite cores – Guidelines on the limits of surface irregularities – Part 1: General specification*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in IEC 60401-1 and IEC 60424-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Primary dimensions

4.1 Planar shapes and dimensions

The main shapes and dimensions shall be as given in the following figures and tables.

The main shapes, dimensions, and parameters for EL-cores are given in:

- Figure 1 – Planar EL-core- and mating PLT-core;
- Table 1 – Dimensions of planar EL-core and mating PLT-core;
- Table 2 – Effective parameter values and A_{\min} values.

The main shape, dimensions, and parameters for low-profile E-cores are given in:

- Figure 2 – Low-profile E-core and mating PLT-core;
- Table 3 – Dimensions of low-profile E-core and mating PLT-core;
- Table 4 – Effective parameter values and A_{\min} values.

The main shape, dimensions, and parameters for ER-cores are given in:

- Figure 3 – Low-profile ER-core and mating PLT-core;
- Table 5 – Dimensions of low-profile ER-core and mating PLT-core;
- Table 6 – Effective parameter values and A_{\min} values.

A uniform dimensional nomenclature has been chosen in order to facilitate a comparison of major physical attributes among the different core shapes.

4.2 Dimensions and effective parameters of planar EL-core and mating PLT-core

For the definitions of effective parameters and their calculations, reference shall be made to IEC 60205.

iTeh STANDARD PREVIEW
(standards.iteh.ai)




Figure 1 – Planar EL-core and mating PLT-core

Table 1 – Dimensions of planar EL-core EL and mating PLT-core

Size	A	B₁	B₂	C	D	E	F₁	F₂	R₂	<i>Dimensions in millimetres</i>
EL11 × 2,0	min. max.	10,80 11,20	1,91 2,11		8,60 9,00	0,90 1,10	8,97 9,37	2,68 2,88	6,25 6,55	0,3
EL11 × 3,0	min. max.	10,80 11,20	2,91 3,11		8,60 9,00	1,90 2,10	8,97 9,37	2,68 2,88	6,25 6,55	0,3
PLT11 × 1,0	min. max.	10,80 11,20		0,96 1,06	8,60 9,00					
EL13 × 2,2	min. max.	12,75 13,25	2,09 2,29		10,20 10,60	0,90 1,10	10,63 11,03	3,19 3,39	7,41 7,71	0,3
EL13 × 3,2	min. max.	12,75 13,25	3,09 3,29		10,20 10,60	1,90 2,10	10,63 11,03	3,19 3,39	7,41 7,71	0,3
PLT13 × 1,2	min. max.	12,75 13,25		1,14 1,24	10,20 10,60					
EL15,5 × 2,9	min. max.	15,20 15,80	2,82 3,02		12,15 12,65	1,40 1,60	12,67 13,17	3,82 4,02	8,81 9,21	0,3
EL15,5 × 4,4	min. max.	15,20 15,80	4,32 4,52		12,15 12,65	2,90 3,10	12,67 13,17	3,82 4,02	8,81 9,21	0,3
PLT15,5 × 1,4	min. max.	15,20 15,80		1,32 1,52	12,15 12,65					
EL18 × 3,7	min. max.	17,70 18,30	3,55 3,75		14,15 14,65	1,90 2,10	14,70 15,30	4,45 4,65	10,27 10,67	0,3
EL18 × 5,7	min. max.	17,70 18,30	5,55 5,75		14,15 14,65	3,85 4,15	14,70 15,30	4,45 4,65	10,27 10,67	0,3
PLT18 × 1,7	min. max.	17,70 18,30		1,55 1,75	14,15 14,65					
EL20 × 3,8	min. max.	19,65 20,35	3,73 3,93		15,70 16,30	1,90 2,10	16,37 16,97	4,91 5,21	11,43 11,83	0,5
EL20 × 5,8	min. max.	19,65 20,35	5,68 5,98		15,70 16,30	3,85 4,15	16,37 16,97	4,91 5,21	11,43 11,83	0,5
PLT20 × 1,8	min. max.	19,65 20,35		1,73 1,93	15,70 16,30					
EL22 × 4,0	min. max.	21,60 22,40	3,92 4,12		17,30 17,90	1,90 2,10	17,98 18,68	5,41 5,71	12,54 13,04	0,5
EL22 × 6,0	min. max.	21,60 22,40	5,87 6,17		17,30 17,90	3,85 4,15	17,98 18,68	5,41 5,71	12,54 13,04	0,5
PLT22 × 2,0	min. max.	21,60 22,40		1,92 2,12	17,30 17,90					
EL25 × 4,3	min. max.	24,55 25,45	4,19 4,39		19,65 20,35	1,90 2,10	20,48 21,18	6,17 6,47	14,29 14,79	0,5
EL25 × 6,3	min. max.	24,55 25,45	6,14 6,44		19,65 20,35	3,85 4,15	20,48 21,18	6,17 6,47	14,29 14,79	0,5
PLT25 × 2,3	min. max.	24,55 25,45		2,19 2,39	19,65 20,35					

iTech STANDARD PREVIEW
(standards.itech.ai)

IEC 63093-9:2020
<https://standards.itech.ai/catalog/standards/sist/4de3b697-5ff2-4776-adaa-ec0309ba8dbb> iec-63093-9-2020

Table 2 – Effective parameter values and A_{\min} values

Size	C_1 mm $^{-1}$	C_2 mm $^{-3}$	l_e mm	A_e mm 2	V_e mm 3	A_{\min}^a mm 2	Remarks
EL-EL11 × 4,0	0,826 45	$49,923 \times 10^{-3}$	13,7	16,5	226	15,9	The combination EL-EL refers to two shorter height EL- cores for size- designation.
EL-EL13 × 4,4	0,666 66	$28,815 \times 10^{-3}$	15,4	23,1	357	22,4	
EL-EL15,5 × 5,8	0,596 74	$18,143 \times 10^{-3}$	19,6	32,9	646	31,9	
EL-EL18 × 7,3	0,538 30	$12,162 \times 10^{-3}$	23,8	44,3	1 050	43,0	
EL-EL20 × 7,7	0,468 64	$8,586 6 \times 10^{-3}$	25,6	54,6	1 400	52,9	
EL-EL22 × 8,0	0,412 80	$6,231 4 \times 10^{-3}$	27,3	66,2	1 810	64,2	The combination EL-PLT refers to one taller height EL core paired with one PLT- core for each size- designation.
EL-EL25 × 8,6	0,350 34	$4,094 2 \times 10^{-3}$	30,0	85,6	2 570	83,0	
EL-PLT11 × 4,0	0,826 45	$49,943 \times 10^{-3}$	13,7	16,5	226	15,9	
EL-PLT13 × 4,4	0,666 66	$28,815 \times 10^{-3}$	15,4	23,1	357	22,4	
EL-PLT15,5 × 5,8	0,569 74	$18,143 \times 10^{-3}$	19,6	32,9	646	31,9	
EL-PLT18 × 7,3	0,538 30	$12,162 \times 10^{-3}$	23,8	44,3	1 050	43,0	The combination EL-PLT refers to one taller height EL core paired with one PLT- core for each size- designation.
EL-PLT20 × 7,7	0,468 64	$8,586 6 \times 10^{-3}$	25,6	54,6	1 400	52,9	
EL-PLT22 × 8,0	0,412 80	$6,231 4 \times 10^{-3}$	27,3	66,2	1 810	64,2	
EL-PLT25 × 8,6	0,350 34	$4,094 2 \times 10^{-3}$	30,0	85,6	2 570	83,0	
EL-PLT11 × 3,0	0,701 76	$42,170 \times 10^{-3}$	11,7	16,6	194	15,9	
EL-PLT13 × 3,4	0,577 71	$24,857 \times 10^{-3}$	13,4	23,2	312	22,4	The combination EL-PLT refers to one taller height EL core paired with one PLT- core for each size- designation.
EL-PLT15,5 × 4,3	0,502 96	$15,212 \times 10^{-3}$	16,6	33,1	550	31,9	
EL-PLT18 × 5,3	0,445 54	$10,011 \times 10^{-3}$	19,8	44,5	882	43,0	
EL-PLT20 × 5,7	0,392 32	$7,167 9 \times 10^{-3}$	21,6	54,9	1 180	52,9	
EL-PLT22 × 6,0	0,350 61	$5,264 5 \times 10^{-3}$	23,4	66,6	1 560	64,2	
EL-PLT25 × 6,6	0,302 22	$3,515 6 \times 10^{-3}$	26,0	86,0	2 230	83,0	

^a See 4.2 of IEC 60205:2016 for the definition of A_{\min} .

4.3 Dimensions and effective parameters of low-profile E-core and mating PLT-core

For the definitions of effective parameters and their calculations, reference shall be made to IEC 60205.




Figure 2 – Low-profile E-core and mating PLT-core

Table 3 – Dimensions of low-profile E-core and mating PLT-core

Size							<i>Dimensions in millimetres</i>
	A	B₁	B₂	C	D	E	F
E14 × 3,5 × 5	min.	13,70	3,40		4,90	1,90	10,75
	max.	14,30	3,60		5,10	2,10	11,25
PLT14 × 1,5 × 5	min.	13,70		1,40	4,90		
	max.	14,30		1,60	5,10		
E18 × 4 × 10	min.	17,65	3,90		9,80	1,90	13,70
	max.	18,35	4,10		10,20	2,10	14,30
PLT18 × 2 × 10	min.	17,65		1,90	9,80		
	max.	18,35		2,10	10,20		
E22 × 6 × 16	min.	21,40	5,60		15,50	3,10	16,40
	max	22,20	5,80		16,10	3,30	17,20
PLT22 × 2,5 × 16	min.	21,40		2,40	15,50		
	max.	22,20		2,60	16,10		
E32 × 6 × 20	min.	31,10	6,20		19,90	2,95	24,90
	max.	32,40	6,50		20,75	3,40	26,10
PLT32 × 3 × 20	min.	31,10		3,00	19,90		
	max.	32,40		3,35	20,75		
E38 × 8 × 25	min.	37,30	8,10		24,85	4,30	30,20
	max.	38,90	8,40		25,95	4,60	31,40
PLT38 × 4 × 25	min.	37,30		3,65	24,85		
	max.	38,90		3,95	25,95	5ff2-4776-adaa-	
E43 × 10 × 28	min.	42,30	9,35		27,30	5,25	34,70
	max.	44,10	9,65		28,50	5,55	36,30
PLT43 × 4 × 28	min.	42,30		3,95	27,30		
	max.	44,10		4,25	28,50		
E58 × 11 × 38	min.	57,20	10,35		37,30	6,35	50,00
	max.	59,60	10,75		38,90	6,65	52,20
PLT58 × 4 × 38	min.	57,20		3,85	37,30		
	max.	59,60		4,25	38,90		
E64 × 10 × 50	min.	62,70	10,05		49,70	4,95	52,50
	max.	65,30	10,35		51,90	5,25	54,70
PLT64 × 5 × 50	min.	62,70		4,95	49,70		
	max.	65,30		5,25	51,90		
E102 × 20 × 38	min.	100,0	20,10		36,50	12,90	85,00
	max.	104,0	20,50		38,50	13,40	88,60
PLT102 × 7 × 38	min.	100,0		6,95	36,50		
	max	104,0		7,35	38,50		

Table 4 – Effective parameter values and A_{\min} values

Size	C_1 mm ⁻¹	C_2 mm ⁻³	l_e mm	A_e mm ²	V_e mm ³	A_{\min}^a mm ²	Remarks
E-E14	1,380 8	$92,055 \times 10^{-3}$	20,7	15,0	311	15,0	Combination E-E
E-E18	0,607 08	$15,177 \times 10^{-3}$	24,3	40,0	971	40,0	
E-E22	0,410 81	$5,200 1 \times 10^{-3}$	32,5	79,0	2 560	79,0	
E-E32	0,324 85	$2,525 5 \times 10^{-3}$	41,8	129	5 370	127	
E-E38	0,276 13	$1,443 9 \times 10^{-3}$	52,8	191	10 100	185	
E-E43	0,274 13	$1,219 7 \times 10^{-3}$	61,6	225	13 800	215	
E-E58	0,269 43	$0,893 10 \times 10^{-3}$	81,3	302	24 500	278	
E-E64	0,153 67	$0,295 56 \times 10^{-3}$	79,9	520	41 500	518	
E-E102	0,273 88	$0,506 86 \times 10^{-3}$	148	540	80 000	525	
E-PLT14	1,114 2	$74,277 \times 10^{-3}$	16,7	15,0	251	15,0	Combination E-PLT
E-PLT18	0,507 08	$12,677 \times 10^{-3}$	20,3	40,0	811	40,0	
E-PLT22	0,329 80	$4,174 6 \times 10^{-3}$	26,1	79,0	2 060	79,0	
E-PLT32	0,275 28	$2,138 6 \times 10^{-3}$	35,4	129	4 560	127	
E-PLT38	0,229 08	$1,195 0 \times 10^{-3}$	43,9	192	8 420	185	
E-PLT43	0,225 10	$0,996 95 \times 10^{-3}$	50,8	226	11 500	214	
E-PLT58	0,225 00	$0,740 83 \times 10^{-3}$	68,3	304	20 800	278	
E-PLT64	0,134 18	$0,258 30 \times 10^{-3}$	70,0	519	36 200	518	
E-PLT102	0,225 76	$0,418 68 \times 10^{-3}$	122	539	65 600	525	

NOTE Values ignore the effect of radii. These can have some influence on the outcome of the calculation. They can be incorporated in the formulae as shown in IEC 60205.

<https://standards.iteh.ai/catalog/standards/sist/4de3b697-5f24-4776-adaa-023914dbb/iec-63093-9-2020>

^a See 4.2 of IEC 60205:2016 for the definition of A_{\min} .

4.4 Dimensions and effective parameters of low-profile ER-core and mating PLT-core

For the definitions of effective parameters and their calculations, reference shall be made to IEC 60205.


**Figure 3 – Low-profile ER-core and mating PLT-core**

Table 5 – Dimensions of low-profile ER-core and mating PLT-core

Size	A	B₁	B₂	C	D	E	F	G
ER9,5 × 2,5 × 5	min. max.	9,15 9,55	2,375 2,525		4,80 5,00	1,60 1,75	7,50 7,75	3,25 3,55
PLT9,5 × 1 × 5	min. max.	9,15 9,55		0,70 0,85	4,80 5,00			
ER11 × 2,5 × 6	min. max.	10,65 11,00	2,375 2,525		5,80 6,00	1,50 1,65	8,70 9,00	4,00 4,25
PLT11 × 1 × 6	min. max.	10,65 11,00		0,80 0,95	5,80 6,00			
ER13 × 3 × 9	min. max.	12,5 13,1	2,775 2,925		8,45 8,95	1,625 1,875	10,9 11,5	4,85 5,15
PLT13 × 1 × 9	min. max.	12,5 13,1		1,00 1,20	8,45 8,95			
ER14,5 × 3 × 7	min. max.	14,30 14,70	2,90 3,00		6,60 6,80	1,55 1,75	11,6 12,0	4,60 4,80
PLT14,5 × 1 × 7	min. max.	14,30 14,70		1,20 1,40	6,60 6,80			
ER18 × 3 × 10	min. max.	17,65 18,35	3,05 3,25		9,5 9,9	1,50 1,70	15,3 15,9	6,05 6,35
PLT18 × 1,5 × 10	min. max.	17,65 18,35		1,45 1,65	9,5 9,9			
ER20 × 6 × 14	min. max.	19,65 20,35	6,20 6,40		13,7 14,3	3,95 4,25	17,65 18,35	8,65 8,95
PLT20 × 2 × 14	min. max.	19,65 20,35		2,25 2,35	13,7 14,3			
ER23 × 3,6 × 13	min. max.	22,75 23,65	3,50 3,70		12,25 12,75	1,50 1,70	19,8 20,6	7,8 8,2
ER23 × 5 × 13	min. max.	22,75 23,65	5,00 5,20		12,25 12,75	3,00 3,20	19,8 20,6	7,8 8,2
PLT23 × 2 × 13	min. max.	22,75 23,65		1,90 2,10	12,25 12,75			
ER25 × 8 × 18	min. max.	24,6 25,4	7,90 8,10		17,7 18,3	5,00 5,30	21,6 22,4	10,8 11,2
PLT25 × 3 × 18	min. max.	24,6 25,4		2,75 2,95	17,7 18,3			
ER25 × 6 × 15	min. max.	24,5 25,5	5,40 5,60		14,5 15,1	3,00 3,20	21,3 22,1	9,20 9,60
PLT25 × 2,4 × 15	min. max.	24,5 25,5		2,30 2,50	14,5 15,1			
ER25 × 6 × 18	min. max.	24,6 25,4	5,55 5,65		17,7 18,3	3,05 3,35	21,6 22,4	10,8 11,2
PLT25 × 2 × 18	min. max.	24,6 25,4		2,35 2,45	17,7 18,3			

Dimensions in millimetres