



Designation: **D6400—12 D6400 – 19**

Standard Specification for Labeling of Plastics Designed to be Aerobically Composted in Municipal or Industrial Facilities¹

This standard is issued under the fixed designation D6400; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers plastics and products made from plastics that are designed to be composted under aerobic conditions in municipal and industrial aerobic composting facilities, where thermophilic conditions are achieved.

1.2 This specification is intended to establish the requirements for labeling of materials and products, including packaging made from plastics, as “compostable in aerobic municipal and industrial composting facilities.”

1.3 The properties in this specification are those required to determine if end items (including packaging), which use plastics and polymers as coatings or binders will compost satisfactorily, in large scale aerobic municipal or industrial composting facilities. Maximum throughput is a high priority to composters and the intermediate stages of plastic disintegration and biodegradation not be visible to the end user for aesthetic reasons.

1.4 The following safety hazards caveat pertains to the test methods portion of this standard: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate health-safety, health, and safety environmental practices and to determine the applicability of regulatory limitations prior to use.*

NOTE 1—This test method is equivalent to ISO 17088.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D883 Terminology Relating to Plastics

D5338 Test Method for Determining Aerobic Biodegradation of Plastic Materials Under Controlled Composting Conditions, Incorporating Thermophilic Temperatures

2.2 Organization for Economic Development (OECD) Standard:³

OECD Guideline 208 Terrestrial Plant Test: Seedling Emergence and Seedling Growth Test

2.3 Comite Europeen de Normalisation (CEN):⁴

EN 13432: 2000, 2000 CEN/TC 261/SC 4 N 99 Packaging—Requirements for Packaging Recoverable through Composting and Biodegradation—Test Scheme and Evaluation Criteria for the Final Acceptance of Packaging (EN 13432)

2.4 ISO Standard:⁴

ISO 14855-1 Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions—Method by analysis of evolved carbon dioxide—Part 1: General method

ISO 14855-2 Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions—Method by analysis of evolved carbon dioxide—Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.96 on Environmentally Degradable Plastics and Biobased Products.

Current edition approved May 15, 2012; May 1, 2019. Published May 2012; May 2019. Originally approved in 1999. Last previous edition approved in 2004; 2012 as D6400-04; D6400-12. DOI: 10.1520/D6400-12.10.1520/D6400-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Organization for Economic Development, Director of Information, 2 rue Andre' Pascal, 75775 Paris Cedex 16, France.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard

ISO 16929 Plastics—Determination of the Degree of Disintegration of Plastic Materials under Defined Composting Conditions in a Pilot-Scale Test

ISO 17088 Specifications for Compostable Plastics

ISO 20200 Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test

2.5 U.S. Government Standard:⁵

40 CFR Part 503.13 Standards for the Use or Disposal of Sewage Sludge

2.6 Canadian Government Standard:⁶

Trade Memorandum T-4-93 Standards for Metals in Fertilizers and Supplements

3. Terminology

3.1 *Definitions*: Definitions appearing in this specification are found in Terminology D883, unless otherwise noted.

3.1.1 *biodegradable plastic*—a degradable plastic in which the degradation results from the action of naturally occurring microorganisms such as bacteria, fungi, and algae.

3.1.2 *compostable plastic*—a plastic that undergoes degradation by biological processes during composting to yield CO², water, inorganic compounds, and biomass at a rate consistent with other known compostable materials and leave no visible, distinguishable or toxic residue.

3.1.3 *composting*⁷—a managed process that controls the biological decomposition and transformation of biodegradable materials into a humus-like substance called compost: the aerobic mesophilic and thermophilic degradation of organic matter to make compost; the transformation of biologically decomposable material through a controlled process of biooxidation that proceed through mesophilic and thermophilic phases and results in the production of carbon dioxide, water, minerals, and stabilized organic matter (compost or humus).

3.1.4 *degradable plastic*—a plastic designed to undergo a significant change in its chemical structure under specific environmental conditions, resulting in a loss of some properties that may be properties as measured by standard test methods appropriate to the plastic and the application in a period of time that determines its classification.

3.1.5 *plastic*—a material that contains as an essential ingredient one or more organic polymeric substances of large molecular weight, is solid in its finished state, and, at some stage in its manufacture or processing into finished articles, can be shaped by flow.

3.1.6 *polymer*—a substance consisting of molecules characterized by the repetition (neglecting ends, branch junctions, other minor irregularities) of one or more types of monomeric units.

4. Classification

4.1 The purpose of this specification is to establish requirements for identifying items made from plastics or polymers so that they do not interfere with their satisfactorily composting in commercial and municipal aerobic composting facilities. Products meeting the requirements outlined below be labeled as “compostable in municipal or industrial aerobic facilities” in accordance with the guidelines issued by the Federal Trade Commission⁸ as long as proper qualifications as to the availability of such facilities are included on the label.

5. Basic Requirements

5.1 In order to compost satisfactorily, a product or material must demonstrate each of the characteristics found in 5.1.1 – 5.1.3, and which are quantified in Section 6.

5.1.1 *Disintegration During Composting*—A plastic product or material will disintegrate during composting such that any remaining plastic residuals are not readily distinguishable from the other organic materials in the finished product. Additionally, the material or product must not be found in significant quantities during screening prior to final distribution of the compost.

5.1.2 *Biodegradation*—A level of biodegradation for the plastic products shall be established by tests under controlled conditions.

5.1.3 *No Adverse Impacts on Ability of Compost to Support Plant Growth*—The tested materials shall not adversely impact on the ability of composts to support plant growth, when compared to composts derived from biowaste without any addition of tested products or reference materials. Additionally, the polymeric products or materials must not introduce unacceptable levels of regulated metals or hazardous substances into the environment, upon sample decomposition.

NOTE 2—For a better understanding of why these criteria are important, consult the *Compost Facility Operating Guide*,⁷ and CEN/TC 261/SC 4 N 99.

⁵ Code of Federal Regulations, available from U.S. Government Printing Office, Washington, DC 20402.

⁶ Available from the Canadian Food Inspections Agency, Fertilizer Section, Ottawa, Canada

⁷ *Compost Facility Operating Guide*, Composting Council, Alexandria, VA, 1995.

⁸ *Guidelines for the Use of Environmental Marketing Claims*, Federal Trade Commission, Washington, DC, 1992.