



Designation: ~~D280 – 01 (Reapproved 2012)~~ D280 – 01 (Reapproved 2019)

Standard Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments¹

This standard is issued under the fixed designation D280; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 These test methods cover procedures for determining hygroscopic moisture (and other matter volatile under the test conditions) in pigments.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and healthenvironmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

METHOD A—FOR PIGMENTS THAT DO NOT DECOMPOSE AT 110°C

2. Apparatus

2.1 *Weighing Bottle*, wide-mouth, cylindrical, glass (flat form, about 30 mm in height and about 70 mm in diameter), provided with a ground-in glass stopper. Or, an aluminum moisture dish (about 90 mm in diameter and about 50 mm in depth) with a tightly fitting cover.

2.2 *Oven* in which a temperature of from $110 \pm 2^\circ\text{C}$ is maintained.

2.3 *Analytical Balance*.

3. Procedure

3.1 Weigh accurately the glass weighing bottle and stopper or the aluminum moisture dish with cover. Place a specimen of from 3 to 5 g of the pigment in the clean, dry weighing bottle or in the clean, dry aluminum moisture dish. Insert the stopper (or cover) and weigh to 0.1 mg. Subtract the weight of the vessel from the total weight to obtain the weight of sample used in the test. Remove the stopper (or cover) and place it and the bottle (or dish) containing the specimen in an oven that has been previously heated to $110 \pm 2^\circ\text{C}$, heat for 2 h at a temperature of 105 to 110°C . Replace the stopper (or cover), cool in a desiccator, and weigh. Calculate the total loss in weight as percent of moisture and other volatile matter.

METHOD B—FOR PIGMENTS THAT DECOMPOSE AT 110°C

4. Apparatus

4.1 *Weighing Bottle*, glass, as described in 2.1.

4.2 *Open-Tube Manometer* made of glass tubing 6 mm in diameter, filled with mercury to approximately 860 mm, fitted with rubber pressure tubing attached to a T-joint leading to the desiccator and the pump. A suitable low-pressure gage may be used in place of the manometer.

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Nov. 1, 2012 June 1, 2019. Published November 2012 June 2019. Originally approved in 1928. Last previous edition approved in 2007 2012 as D280 – 01 (2007) (2012). DOI: 10.1520/D0280-01R12.10.1520/D0280-01R19.