

TECHNICAL REPORT



**Electrical insulating materials – Thermal endurance properties –
Part 7-2: Accelerated determination of relative thermal endurance using
analytical test methods (RTEA) – Results of the round robin tests to validate
procedures of IEC TS 60216-7-1 by non-isothermal kinetic analysis of
thermogravimetric data**

IEC TR 60216-7-2:2024

<https://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024>





THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

International
Standards
Document Preview
standards.iteh.ai

[IEC TR 60216-7-2:2024](http://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024)

<https://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024>

TECHNICAL REPORT



**Electrical insulating materials – Thermal endurance properties –
Part 7-2: Accelerated determination of relative thermal endurance using
analytical test methods (RTEA) – Results of the round robin tests to validate
procedures of IEC TS 60216-7-1 by non-isothermal kinetic analysis of
thermogravimetric data**

[IEC TR 60216-7-2:2024](https://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024)

<https://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 19.020; 29.020; 29.035.01

ISBN 978-2-8322-9692-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Test specimens	8
5 Test apparatus	9
5.1 Thermogravimetric analyser (TGA)	9
5.2 Purge gas supplied into the TGA furnace	9
6 Test procedures	10
6.1 General.....	10
6.2 Preconditioning of test samples	10
6.3 TGA tests with multiple heating rates	10
6.4 Calculation of the activation energy (E_a).....	10
6.5 Determination of thermal endurance using TGA	11
6.5.1 General	11
6.5.2 Determination of RTE_A by given degree of conversion from reference material (Method A)	11
6.5.3 Determination of TI_A by fixed degree of conversion at 0,05 (Method B)	12
7 Round robin test results.....	12
7.1 TGA test results.....	12
7.2 Degree of conversion correlated to the activation energy from conventional heat ageing data	12
7.3 HIC_A determined by Method A and Method B	13
7.4 RTE_A determined by Method A and TI_A by Method B.....	14
7.5 Difference between RTE_A and TI determined by the conventional heat ageing tests	16
8 Observations from the round robin test results.....	18
8.1 General.....	18
8.2 Sample weight variation	18
8.3 Humidity and hydrolysis of the sample	20
8.4 Considerations on repeatability of TGA curves.....	20
8.5 Baseline drift and responsiveness to heating rates of TGA.....	21
9 Conclusion	25
Annex A (informative) Additional round robin studies with polybutylene terephthalate	26
A.1 Objectives.....	26
A.2 Test specimens.....	26
A.3 Test apparatus.....	26
A.4 Test procedures.....	27
A.5 Test results	27
A.6 Observations	32
Bibliography.....	35

Figure 1 – Fitting curve of plots between degree of conversion and activation energy determined by ISO 11358-2 [3] (example).....	11
---	----

Figure 2 – Correlation between the initial sample mass of sample A and the difference of RTE_A (TI_A) from TI	19
Figure 3 – Correlation between the initial sample mass of sample B and the difference of RTE_A (TI_A) from TI	19
Figure 4 – Overlay charts of TGA curves in multiple heating rates in multiple laboratories (enlarged).....	22
Figure 5 – Logarithm plots for activation energy calculation	23
Figure 6 – Fitting curves of degree of conversion versus activation energy by TGA	24
Figure A.1 – Effect of sample amount on E_a (data provided by laboratory E)	33
Figure A.2 – Summary of factors affecting the TGA kinetic study for determination of RTE_A and TI_A	34
Table 1 – Heat ageing properties of the test specimens by the conventional procedure described in IEC 60216-5 [4].....	9
Table 2 – Degree of conversion identical to the activation energy of the conventional heat ageing.....	13
Table 3 – HIC_A determined by Method A and Method B for dielectric strength	13
Table 4 – HIC_A determined by Method A and Method B for tensile strength	14
Table 5 – HIC_A determined by Method A and Method B for impact strength	14
Table 6 – RTE_A determined by Method A and TI_A by Method B for dielectric strength	15
Table 7 – RTE_A determined by Method A and TI_A by Method B for tensile strength	15
Table 8 – RTE_A determined by Method A and TI_A by Method B for impact strength	16
Table 9 – Difference between RTE_A or TI_A , and TI for dielectric strength	16
Table 10 – Difference between RTE_A or TI_A , and TI for tensile strength	17
Table 11 – Difference between RTE_A or TI_A , and TI for impact strength	17
Table 12 – Comparison of degree of conversion with original or rerun data at 8 K/min	21
Table A.1 – Heat ageing properties of the PBT test specimens by the conventional procedure in accordance with IEC 60216-5 [4].....	26
Table A.2 – Degrees of conversion at the activation energy identical to that from conventional heat ageing	27
Table A.3 – HIC_A determined by Method A and Method B for dielectric strength.....	28
Table A.4 – HIC_A determined by Method A and Method B for tensile strength.....	28
Table A.5 – HIC_A determined by Method A and Method B for impact strength.....	29
Table A.6 – RTE_A determined by Method A and TI_A by Method B for dielectric strength.....	29
Table A.7 – RTE_A determined by Method A and TI_A by Method B for tensile strength.....	30
Table A.8 – RTE_A determined by Method A and TI_A by Method B for impact strength.....	30
Table A.9 – Difference between RTE_A or TI_A , and TI for dielectric strength.....	31
Table A.10 – Difference between RTE_A or TI_A , and TI for tensile strength.....	31
Table A.11 – Difference between RTE_A or TI_A , and TI for impact strength.....	32

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRICAL INSULATING MATERIALS –
THERMAL ENDURANCE PROPERTIES –****Part 7-2: Accelerated determination of relative thermal endurance using
analytical test methods (RTEA) – Results of the round robin tests to
validate procedures of IEC TS 60216-7-1 by non-isothermal kinetic
analysis of thermogravimetric data**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TR 60216-7-2 has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems. It is a Technical Report.

This second edition cancels and replaces the first edition published in 2016. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Annex A (informative) has been added to provide a round robin test with a different polymer type – polybutylene terephthalate (PBY) – as an additional use case of the method in accordance with IEC TS 60216-7-1;
- b) Tables 3 to 11 have been corrected by adding units, and texts have been refined for more technical clarifications of the procedures and observations.

The text of this Technical Report is based on the following documents:

Draft	Report on voting
112/651/DTR	112/658/RVDTR

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Report is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60216 series, published under the general title *Electrical insulating materials – Thermal endurance properties*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

IEC technical committee 112, (IEC TC 112) has been working on the development of IEC TS 60216-7-1 [1]¹ that considers the use of activation energy determined through thermal analytical tools plus abbreviated conventional heat ageing to determine a thermal index on a polymeric compound. At the same time, the Underwriters Laboratories Long-Term Thermal Aging Forum (UL LTТА Forum) has been discussing alternative methods that can speed up the determination of a thermal index. Members of the IEC TC 112 and of the UL LTТА Forum have made joint efforts to determine whether the Technical Specification developed by IEC TC 112 can be used to offer an alternative method of evaluating polymeric compounds for a thermal index.

Members of IEC TC 112 and the UL LTТА Forum decided to conduct a round robin test (RRT) using thermogravimetric analysis (TGA) according to ISO 11358-2 [3] on a known compound, with a known activation energy determined through conventional ageing with a view to validate the acceptability of IEC TS 60216-7-1, and to determine whether a similar thermal index can be calculated. The round robin testing was conducted with conventional TGA by multiple heating rates. However, running isothermal tests can be a follow-up of this RRT.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC TR 60216-7-2:2024](#)

<https://standards.iteh.ai/catalog/standards/iec/353b6edb-7cff-439d-a2df-c924bf2fa92b/iec-tr-60216-7-2-2024>

¹ Numbers in square brackets refer to the Bibliography.

ELECTRICAL INSULATING MATERIALS – THERMAL ENDURANCE PROPERTIES –

Part 7-2: Accelerated determination of relative thermal endurance using analytical test methods (RTEA) – Results of the round robin tests to validate procedures of IEC TS 60216-7-1 by non-isothermal kinetic analysis of thermogravimetric data

1 Scope

This part of IEC 60216 is intended to validate the procedures of IEC TS 60216-7-1 in providing a similar temperature index to conventional methods used in other parts of the IEC 60216 series.

The round robin test results do not provide statistical analysis for precision. The round robin test focuses on preliminary studies to understand the evaluation and calculation procedures, influence on apparatus, and data variance among laboratories before determination of precision.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

activation energy

Arrhenius activation energy

E_a

empirical parameter characterizing the exponential temperature dependence of the reaction rate constant

3.2

end-point

limit for a diagnostic property value based on which the thermal endurance is evaluated

3.3

time to end-point

failure time

time to reach the end-point or conventional failure

3.4 relative temperature endurance index

RTE

numerical value of the temperature in degrees Celsius at which the estimated time to end-point of the candidate material is the same as the estimated time to end-point of the reference material at a temperature equal to its assessed temperature index

Note 1 to entry: RTE_A is the relative temperature endurance index calculated through the analytical procedure.

3.5 temperature endurance index

TI

numerical value of the temperature in degrees Celsius derived from the thermal endurance relationship at a time of 20 000 h (or other specified time)

Note 1 to entry: TI_A is the temperature index calculated through the analytical procedure.

[SOURCE: IEC 60050-212:2010, 212-12-11 [2], modified – "characterizing the thermal capability of an insulating material or an insulation system" has been replaced with "derived from the thermal endurance relationship at a time of 20 000 h (or other specified time)" and the two notes to entry have been replaced by a new note to entry.]

3.6 halving interval

HIC

numerical value of the temperature interval in kelvin which expresses the halving of the time to end-point taken at the temperature equal to TI

Note 1 to entry: HIC_A is the halving interval calculated through the analytical procedure.

3.7 degree of conversion

α

quantity of products present at a particular time and temperature during a reaction compared with the final quantity of the products

[SOURCE: ISO 11358-2:2021, 3.3 [3], modified – The symbol "C" has been replaced with " α " and the notes to entry have been deleted.]

4 Test specimens

For the round robin test, one generic type of polymer, liquid crystal polyester (LCP), was pre-selected. Although it is known that materials can undergo more than one transition, the round robin test verified the assumption that one single thermal degradation reaction is predominant and directly correlated to the end-point of dielectric strength as a diagnostic property.

NOTE Since different materials can undergo more than one transition, the validity of results obtained from the evaluation of thermal endurance properties using TGA are assessed for the different materials.

LCP originally has very little entwining of molecules exhibiting crystalline properties as a liquid. Hence, there is less thermal transformation between solid and liquid, or between oven ageing conditions of conventional thermal endurance test and TGA conditions at higher temperature ranges. In addition, LCP molecular chains align themselves when moulded, and this generates a self-reinforcing effect, thereby resulting in high mechanical and electrical stress resistance.

In this round robin, two LCP materials (LCP sample A, LCP sample B) were chosen as test samples which already have the conventional heat oven ageing data of dielectric strength, tensile strength, and impact strength to validate the acceptability of whether or not RTE_A can be similar to RTE. Both sample A and sample B consist of 30 % glass fibres reinforced materials. Configurations of monomers are the only differences between the samples which influence the difference in thermal resistance, as shown in Table 1.

The samples were homogenized by freeze-pulverization from test plaques. 100 mg each of freeze-pulverized powders from the same batch were prepared and provided to eleven testing laboratories for evaluation, after pre-drying at 140 °C for 4 h.

Table 1 – Heat ageing properties of the test specimens by the conventional procedure described in IEC 60216-5 [4]

Temperature in ovens	Time to end-point at 50 % retention of initial dielectric strength		Time to end-point at 50 % retention of initial tensile strength		Time to end-point at 50 % retention of initial impact strength	
	h		h		h	
°C	LCP Sample A	LCP Sample B	LCP Sample A	LCP Sample B	LCP Sample A	LCP Sample B
290		1 141		1 215		1 860
285	2 896		1 789		2 870	
280		1 917		3 229		2 655
275	5 591		3 083		4 164	
270		4 300		4 597		3 920
265	8 255		6 706		8 412	
260		5 848		7 625		6 640
250						9 600
TI (°C)	250,0	241,5	249,1	246,2	249,1	234,7
E_a (kJ/mol)	130,6	142,3	165,2	145,9	134,5	102,9

5 Test apparatus

5.1 Thermogravimetric analyser (TGA)

A thermogravimetric analyser (TGA) in accordance with ISO 11358-1 [5] was used for the determination of RTE_A concerning the test samples. In fact, a number of commercial instruments suitable for the measurement are available and various models of TGAs were used for evaluation of the test samples by the participating laboratories. Before the RRT, weight and temperature calibrations were implemented based on ISO 11358-1 and TGA apparatus manufacturer's guidance.

5.2 Purge gas supplied into the TGA furnace

For purge gas into the TGA furnace, air was chosen to assume oxidative thermal degradation, as well as degradation of electrical and mechanical strengths with test specimens in oven ageing. Most of the laboratory participants selected dry air (water content less than 1 ppm²), but air supplied from the facility (compressed air with or without an air dryer) was used in a few laboratories.

² ppm = parts per million.

6 Test procedures

6.1 General

Thermal analysis with TGA of the test samples was evaluated with reference to ISO 11358-2 [3] and IEC TS 60216-7-1 in principle. A few modifications of test conditions and more detailed procedures were added as follows.

6.2 Preconditioning of test samples

5 mg \pm 0,5 mg of the test sample were initially measured in each laboratory and mounted on the empty pan in the furnace opened. Then the furnace was closed and pre-conditioned in equilibrium at 100 °C for 1 h before heating tests were started. The weight value just before the heating test (time at 0 s in the heating run, or 60 min at the end of the equilibrium) was used for calculation on the degree of conversion.

NOTE ISO 11358-2 [3] requires using test samples of identical mass \pm 1 % of the initial weight in multiple heating conditions which is much narrower than the above. Influence on the initial mass deviation is taken into consideration in 7.2.

6.3 TGA tests with multiple heating rates

Multiple heating rates testing at 1 K/min, 2 K/min, 4 K/min, 6 K/min and 8 K/min were selected for evaluation which resulted in the lowest and highest heating rates differing by a factor of 8, in accordance with ISO 11358-2 [3]. Evaluation temperature range was set between 100 °C and 700 °C. Each heating rate test was run one time each for sample A and sample B, but 8 K/min was evaluated twice as an approximate check and to consider repeatability.

6.4 Calculation of the activation energy (E_a)

After TGA data with multiple heating rates were obtained, the activation energies were calculated for given degrees of conversion in accordance with Equation (2) in ISO 11358-2:2021 [3]. Then, both values of degree of conversion and the activation energies were plotted between 1 % and 19 % with 2 % interval of degree of conversion and a cubic curve fitting approximately was performed as shown in Figure 1. Equation (2) in ISO 11358-2:2021 [3] was used for the selection of appropriate activation energy and degree of conversion to determine RTE_A .

For example, if the activation energy of a reference material was already determined as 150 kJ/mol by the conventional heat ageing (e.g. dielectric strength), the corresponding degree of conversion of the reference material can be read and obtained with the equation of the fitting curve graph (see Figure 1). Then the corresponding degree of conversion for this reference material can be used for reading the activation energy of a candidate material from another graph which was also evaluated with ISO 11358-2 [3] and had a similar degree of conversion versus the activation energy fitting curve for the candidate material.

All TGA raw data were submitted by eleven participating laboratories and analysis with ISO 11358-2 [3] was carried out by one of the laboratories with the analytical tool, to avoid any discrepancy among various software calculations.