



Designation: E3024/E3024M – 19

Standard Practice for Magnetic Particle Testing for General Industry¹

This standard is issued under the fixed designation E3024/E3024M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice establishes minimum requirements for magnetic particle testing used for the detection of surface or slightly subsurface discontinuities in ferromagnetic material. This standard is intended for industrial applications. Refer to Practice E1444/E1444M for aerospace applications. Guide E709 may be used in conjunction with this practice as a tutorial.

1.2 The magnetic particle testing method is used to detect cracks, laps, seams, inclusions, and other discontinuities on or near the surface of ferromagnetic materials. Magnetic particle testing may be applied to raw material, billets, finished and semi-finished materials, welds, and in-service parts. Magnetic particle testing is not applicable to non-ferromagnetic metals and alloys such as austenitic stainless steels. See Appendix X1 for additional information.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3.1 This standard is a combined standard, an ASTM standard in which rationalized SI units and inch-pound units are included in the same standard, with each system of units to be regarded separately as standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.03 on Liquid Penetrant and Magnetic Particle Methods.

Current edition approved June 1, 2019. Published July 2019. Originally approved in 2016. Last previous edition approved in 2016 as E3024/E3024M – 16. DOI: 10.1520/E3024_E3024M-19.

2. Referenced Documents

2.1 The following documents form a part of this standard practice to the extent specified herein.

2.2 ASTM Standards:²

E543 Specification for Agencies Performing Nondestructive Testing

E709 Guide for Magnetic Particle Testing

E1316 Terminology for Nondestructive Examinations

E1444/E1444M Practice for Magnetic Particle Testing

E2297 Guide for Use of UV-A and Visible Light Sources and Meters used in the Liquid Penetrant and Magnetic Particle Methods

E3022 Practice for Measurement of Emission Characteristics and Requirements for LED UV-A Lamps Used in Fluorescent Penetrant and Magnetic Particle Testing

2.3 ASNT Documents:³

SNT-TC-1A Recommended Practice for Personnel Qualification and Certification in Nondestructive Testing

ANSI/ASNT CP-189 Standard for Qualification and Certification of Nondestructive Testing Personnel

2.4 Society of Automotive Engineers (SAE)-AMS Documents:^{4,5}

AMS 2641 Magnetic Particle Inspection Vehicle

AMS 3040 Magnetic Particles, Nonfluorescent, Dry Method

AMS 3041 Magnetic Particles, Nonfluorescent, Wet Method, Oil Vehicle, Ready-To-Use

AMS 3042 Magnetic Particles, Nonfluorescent, Wet Method, Dry Powder

AMS 3043 Magnetic Particles, Nonfluorescent, Wet Method, Oil Vehicle, Aerosol Packaged

AMS 3044 Magnetic Particles, Fluorescent, Wet Method, Dry Powder

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society for Nondestructive Testing (ASNT), P.O. Box 28518, 1711 Arlingate Ln., Columbus, OH 43228-0518, <http://www.asnt.org>.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, <http://www.sae.org>.

⁵ Copies of standards, specifications, drawings, and publications required by manufacturers in connection with specification acquisition should be obtained from the contracting activity or as directed by the contracting officer.

AMS 3045 Magnetic Particles, Fluorescent, Wet Method, Oil Vehicle, Ready-To-Use

AMS 3046 Magnetic Particles, Fluorescent, Wet Method, Oil Vehicle, Aerosol Packaged

AMS 5062 Steel, Low Carbon Bars, Forgings, Tubing, Sheet, Strip, and Plate 0.25 Carbon, Maximum

AMS I-83387 Inspection Process, Magnetic Rubber

AS 4792 Water Conditioning Agents for Aqueous Magnetic Particle Inspection

AS 5371 Reference Standards Notched Shims for Magnetic Particle Inspection

2.5 *Federal Standards*:^{5,6}

FED-STD-313 Material Safety Data Sheets, Preparation and the Submission of

2.6 *Military Standards*:^{5,7}

A-A-59230 Fluid, Magnetic Particle Inspection, Suspension

2.7 *OSHA Document*:^{5,8}

29 CFR 1910.1200 Hazard Communication

2.8 *ISO Documents*:^{5,9}

ISO 7810 Identification Cards—Physical Characteristics

ISO 9712 Nondestructive Testing—Qualification and Certification of NDT Personnel

ISO 10012 Measurement Management Systems—Requirements for Measurement Processes and Measuring Equipment

ISO 17025 General Requirements for the Competence of Testing and Calibration Laboratories

2.9 *Order of Precedence*—In the event of conflict between the text of this practice and the referenced documents cited herein, the text of this practice takes precedence.

3. Terminology

3.1 *Definitions*—The definitions relating to magnetic particle testing, which appear in Terminology E1316, shall apply to the terms used in this practice.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *magnetometer, n*—mechanical instrument used to measure magnetic field strength, in air, adjacent to the part.

4. Significance and Use

4.1 *Description of Process*—Magnetic particle testing consists of magnetizing the area to be examined, applying suitably prepared magnetic particles while the area is magnetized, and subsequently interpreting and evaluating any resulting particle accumulations. Maximum detectability occurs when the discontinuity is positioned on the surface and perpendicular to the direction of magnetic flux in the part.

⁶ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

⁷ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁸ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

⁹ Available from International Organization for Standardization (ISO), ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.

4.2 This practice establishes the basic parameters for controlling the application of the magnetic particle testing method. This practice is written so that it can be specified on the engineering drawing, specification, or contract. It is not a detailed how-to procedure to be used by the examination personnel and, therefore, must be supplemented by a detailed written procedure that conforms to the requirements of this practice.

5. General Practice

5.1 *Personnel Qualification*—Personnel performing examinations in accordance with this practice shall be qualified and certified in accordance with ASNT Recommended Practice No. SNT-TC-1A, ANSI/ASNT Standard CP-189, ISO 9712, or as specified in the contract or purchase order.

5.2 *Agency Qualification*—If specified in the contractual agreement, NDT agencies shall be qualified and evaluated as described in Specification E543. The applicable edition of Specification E543 shall be specified in the contractual agreement.

5.3 *Written Procedure*—Magnetic particle testing shall be performed in accordance with a written procedure applicable to the part or group of parts under examination. The procedure shall be in accordance with the requirements of this practice. The process, when conducted in accordance with the written procedure, shall be capable of detecting discontinuities specified in the acceptance criteria. The written procedure may be general if it clearly applies to all of the specified parts being examined and meets the requirements of this practice. All written procedures, including technique sheets for specific parts, shall be approved by an individual qualified and certified at Level III for magnetic particle testing in accordance with the requirements of 5.1.

5.3.1 *Elements of the Written Procedure*—The written procedure shall include at least the following elements, either directly or by reference to the applicable documents:

5.3.1.1 Procedure identification number and the date it was written;

5.3.1.2 Identification of the part(s) to which the procedure applies; this shall include the material or alloy, or both;

5.3.1.3 For new components, sequence of magnetic particle testing as related to manufacturing process operation (for example, post-plating, after heat treat, etc.);

5.3.1.4 Identification of test parts used for system performance verification (see 7.1.1 and 7.1.2);

5.3.1.5 Process controls (see Table 1); including the definition of “use” in 7.3.2.2 and 7.4.4;

5.3.1.6 Areas of the part to be examined and where appropriate, identified by a photograph, sketch, or relationship to a drawing, etc., to show the area;

5.3.1.7 Part preparation required before examination;

5.3.1.8 Directions for positioning the item with respect to the magnetizing equipment;

5.3.1.9 The type of magnetizing current and the equipment to be used;

5.3.1.10 Method of establishing the magnetization (internal conductor, head, coil, prods, yoke, cable wrap, etc.);

TABLE 1 Required Verification Intervals

Item	Maximum Time Between Verification ^A	Paragraph
Lighting		
Visible light intensity	Weekly	7.3.1.1, 7.3.1.2
Ambient visible light intensity	Weekly	7.3.1.2
UV-A intensity	Daily	7.3.2, 7.4.5
Battery powered UV-A lamp intensity	Before and after each use	7.3.2.2
UV-A lamp integrity	Weekly	7.3.2
System Performance ^B	Daily	7.1.7.1.1, 7.1.2
Wet particle concentration	8 hours, or every shift change	7.2.1.1
Wet particle contamination ^B	1 week	7.2.1.2
Water break test	Daily	7.2.2
Equipment calibration check: ^B		
Timer control	6 months	7.4.1
Quick break	6 months	7.4.2
Yoke dead weight check	6 months	7.4.3
Yoke dead weight check (battery-powered)	6 months	7.4.4
UV-A radiometers and visible light meters	Before and after each use	7.4.4
Electronic Gaussmeter accuracy	12 months	7.4.7
Magnetometer accuracy	12 months	7.4.6
Magnetometer accuracy	6 months	7.4.6

^A When the test system is in operation.

^B The maximum time between verifications may be reduced or extended when substantiated by actual technical/reliability data.

5.3.1.11 Directions of magnetization to be used, the order in which they are applied, and any demagnetization procedures to be used between field applications;

5.3.1.12 The current level, or the number of ampere turns, to be used and the duration of its application or a procedure for establishing proper magnetization;

5.3.1.13 Type of magnetic particle material (dry or wet, visible or fluorescent, etc.) to be used and the method and equipment to be used for its application and, for the case of wet particles, the particle concentration limits;

5.3.1.14 Type of records and method of marking parts after examination;

5.3.1.15 Acceptance requirements, to be used for evaluating indications and disposition of parts after evaluation; and

5.3.1.16 Post-examination demagnetization and cleaning requirements.

5.4 *Examination Sequence*—Perform magnetic particle examination after all operations which might cause or reveal discontinuities. Such operations include, but are not limited to, forging, heat treating, electroplating, forming, welding, grinding, straightening, machining, and proof loading.

5.4.1 Unless otherwise specified in the contract or part drawing, magnetic particle examination shall be performed prior to shot peening and prior to applying protective finishes such as priming, painting, plating (see 5.4.3 through 5.4.3.2), or other coatings.

5.4.2 In-process examinations may not be substituted for final examination.

5.4.3 *Plating and Coatings*—The written procedure shall specify any limitations or other requirements associated with plating or coatings.

5.4.3.1 Use caution when examining parts with an electroplated nickel coating as indications may form from the resulting leakage fields within the nickel plating itself.

5.4.3.2 For in-service examination, plating or coatings do not require removal prior to examination unless they are damaged or they interfere with the examination process.

NOTE 1—Examination sensitivity decreases as plating/coating thickness increases.

5.5 *Materials:*

5.5.1 *Dry Particle Requirements*—Dry particles shall meet the requirements of AMS 3040.

5.5.2 *Wet Particle Requirements*—Wet particles shall meet the requirements of AMS 3041, 3042, 3043, 3044, 3045, or 3046, as applicable.

5.5.2.1 *Dual Response*—Dual response particles are detectable in visible light and also display fluorescence when viewed under UV-A or a combination of visible and UV-A light. Use in accordance with the manufacturer's recommendations.

5.5.2.2 *White Background and Black Oxide*—A thin white background is applied by aerosol to provide a thin (≤ 2 mil), smooth, high contrast background prior to magnetization and particle application. After background has dried, magnetization and particle application follow normal procedures. The high contrast between the white background and black particles provides high sensitivity in visible light conditions. Detailed application and use instructions of the manufacturer shall be followed for optimum results.

5.5.3 *Suspension Vehicles*—The suspension vehicle for the wet method shall be a light petroleum distillate conforming to AMS 2641 (Type I) or A-A-59230, or a suitably conditioned water that conforms to the requirements of 5.5.4. When approved by the Level III, AMS 2641 (Type II) may be used. When specified, the oil suspension vehicle shall meet the salient characteristics specified in A-A-59230.

5.5.4 *Conditioned Water Vehicle*—When water is used as a suspension vehicle for magnetic particles, the conditioning agents used shall comply with AS 4792. Proper wetting shall be determined by a water break test (see 7.2.2). Smoother surfaces generally require a greater percent of wetting agent than rough surfaces. Foaming of the bath must be minimized to the point that it does not interfere with the examination process.

5.5.4.1 *Water Vehicle Conditioning Agents*—Any agents added to the water vehicle for any purpose shall conform to the requirements of the particle manufacturer.

5.5.5 *Particle Concentration*—The concentration of particles in the suspension bath shall be as specified in the written procedure. Particle concentrations outside of the range of 0.1 to 0.4 mL in a 100 mL bath sample for fluorescent particles and 1.2 to 2.4 mL in a 100 mL sample for nonfluorescent particles shall not be used. Fluorescent particles and nonfluorescent particles shall not be used together.

5.5.5.1 The concentration of dual response particles in the wet-method bath suspension shall be adjusted to best perform in the desired lighting environment. Higher particle concentration is used for visible light areas and lower particle concentration is used for UV-A areas. Use in accordance with the particle manufacturer's recommendations.

5.6 *Safety*—The safe handling of magnetic particles (wet or dry), oil vehicles, water baths, and water conditioner concentrates are governed by the suppliers' Safety Data Sheets (SDS). SDS, conforming to 29 CFR 1910.1200, or equivalent, must be provided by the supplier to any user and shall be prepared in accordance with FED-STD-313.

5.6.1 *Flammability*—Flash point of oil vehicles shall be in accordance with AMS 2641, Type I carriers. The suppliers' SDS shall certify the flash point.

5.6.2 *Personnel Hazards*—Precautions against inhalation, skin contact, and eye exposure are detailed in the suppliers' SDS. These precautions shall be observed.

5.6.3 *Electrical Hazards*—Magnetizing equipment shall be maintained properly to prevent personnel hazards from electrical short circuits. Care must be taken to reduce arcing and the possible ignition of oil baths.

5.6.4 *Ultraviolet (UV-A) Lamp*—Replace cracked or broken ultraviolet filters immediately. Broken filters can allow harmful shortwave ultraviolet energy to be emitted and must be replaced immediately. Spectacles designed to absorb ultraviolet wavelength radiation are suggested for close, high-intensity UV-A lamp examination.

6. Specific Practice

6.1 *Preparation of Parts for Testing*

6.1.1 *Pre-examination Demagnetization*—The part shall be demagnetized before testing if prior operations have produced a residual magnetic field that may interfere with the examination.

6.1.2 *Surface Cleanliness and Finish*—The surface of the part to be examined shall be essentially smooth, clean, dry, and free of oil, scale, machining marks, or other contaminants or conditions that might interfere with the efficiency of the examination.

6.1.3 *Plugging and Masking*—Plugging and masking is required when specified.

6.1.4 All areas on the part where electrical contact is made shall be sufficiently clean to prevent electrical arcing.

6.2 *Magnetization Methods:*

6.2.1 *Types of Magnetizing Current*—The types of currents used for magnetic particle testing are full-wave rectified current (1 or 3 phase), half-wave rectified current, alternating

current, direct current, and capacitor discharge current. The equipment used shall fulfill the magnetizing and demagnetizing requirements adequately, as outlined herein, without damage to the part under examination, and they shall include the necessary features required for safe operation.

6.2.2 *Permanent Magnets*—Permanent magnets may be used when approved by the Level III and when a technique has been developed and approved.

6.2.3 *Yokes*—When using yokes (electromagnetic probes) for magnetic particle testing, they shall meet the requirements of 7.4.4.

6.2.3.1 When using yokes, the pole pieces shall be positioned in contact with the part surface as flat as possible.

6.2.3.2 Yoke leg positioning shall include overlapping shots with consideration for the banding effects at the leg/pole contact points.

6.2.3.3 When examining localized areas on parts with complicated geometries, leg spacing shall include consideration for both field direction and banding effects.

6.2.3.4 When using portable equipment that is not timer controlled, any examination that does not have the magnetizing power on during both particle application and excess particle removal is considered a residual examination.

6.2.3.5 For weld examinations, one yoke orientation shall be approximately perpendicular to the weld with the second orientation set parallel to the weld.

6.2.3.6 Battery powered DC yokes may be used when approved by the Level III and when a technique has been developed and approved.

(1) The technique must be validated for material thickness greater than $\frac{3}{8}$ in. (9.5 mm).

(2) Battery powered yokes may not show all surface indications for all thicknesses of material, even though the requirements in 7.4.4 have been met or the field strength has been indicated on a shim, or both.

NOTE 2—Use of dry magnetic particles for surface indications is not recommended when using battery powered DC yokes.

6.2.4 *Magnetizing Current Application*—Full-wave rectified current has the deepest penetration and should be used for examination of sub-surface discontinuities when using the wet magnetic particle method. Half-wave rectified current may also be used for examination of sub-surface discontinuities and due to the pulsating nature of the waveform, it has the advantage of increased particle mobility. Alternating current is to be only used for the detection of discontinuities open to the surface.

6.2.4.1 *Direct Current (DC)*—Direct Current is produced by banks of batteries, full-wave rectified AC, or a DC generator.

6.2.4.2 *Capacitor Discharge (CD) Current*—A bank of capacitors are used to store energy and when triggered the energy reaches high amperage with a very short duration (normally less than 25 milliseconds). Because of the short pulse duration, the current requirements are affected by the amount of material to be magnetized as well as the applied amperage. The capacitor discharge technique may be used to establish a residual magnetic field in tubing, casing, line pipe, and drill pipe. For specific requirements, see Appendix X5.

6.2.5 *Magnetic Field Directions*—Discontinuities are difficult to detect by the magnetic particle method when they make

an angle less than 45° to the direction of magnetization. To ensure the detection of discontinuities in any direction, each part must be magnetized in a minimum of two directions at approximately right angles to each other. Depending on part geometry, this may consist of circular magnetization in two or more directions, multiple circular and longitudinal magnetizations, or of longitudinal magnetization in two or more directions. The pie-field indicator as illustrated in Fig. X4.1, the flexible laminated strips as described in Annex A3, or a properly prepared master part using notched shims may only be used as a tool to demonstrate the direction of the external magnetic field. The pie-field indicator or flexible laminated strips shall not be used to determine adequate field strength.

6.2.6 Multidirectional Magnetization—Multidirectional magnetization may be used to fulfill the requirement for magnetization in two or more directions if it is demonstrated that the technique is effective in all areas requiring examination. Test parts in accordance with 6.3.1.1 or shims manufactured to the requirements of AS 5371 shall be used to verify field direction, strength, and balance in multidirectional magnetization. Balancing of the combined magnetic field is critical and an adequate balance must be visually demonstrated to be effective in all areas requiring examination. The particle application must be timed so that the magnetization levels reach full value in all directions while the particles are mobile on the surface under examination.

6.2.7 Direct Magnetization—Direct magnetization is accomplished by passing current directly through the part under examination. Electrical contact is made to the part using head and tail stock, prods, clamps, magnetic leeches, or by other means. Caution shall be taken to ensure that the electrical current is not flowing while contacts are being applied or removed and that excessive heating does not occur in any area of the part. Prods shall not be used for the examination of finished surfaces.

6.2.8 Indirect Magnetization—Indirect part magnetization uses pre-formed coils, cable wraps, yokes, field (flux) flow fixtures, or an internal conductor to induce a magnetic field in a part when no direct electrical contact is made.

6.2.9 Induced Current Magnetization—Induced current magnetization (toroidal or circumferential field) is accomplished by inductively coupling a part to an electrical coil in order to create a suitable current flow within the part as illustrated in Fig. X4.2. This method is often advantageous on ring-shaped parts with a central aperture and with an L/D ratio less than three, especially where the elimination of arcing or burning is of vital importance.

6.2.10 Parallel Current Induced Magnetization—This method of magnetization may occur when a ferromagnetic part is placed alongside and parallel to a current-carrying conductor. This type of magnetization shall only be used when approved by the Level III and when an approved technique has been developed for use on solid parts.

6.3 Magnetic Field Strength:

6.3.1 Magnetic Field Strength—The applied magnetic field shall have sufficient strength to produce satisfactory indications, but it must not be so strong that it causes the masking of relevant indications by nonrelevant accumulations

of magnetic particles. Adequate magnetic field strength may be determined by one or a combination of the following methods.

6.3.1.1 In unidirectional or multidirectional magnetizing applications, by examining parts having known or artificial discontinuities of the type, size, and location specified in the acceptance requirements or by using the notched shims as defined in Annex A1.

6.3.1.2 In unidirectional magnetizing applications only, by using an electronic gaussmeter capable of measuring the peak values of the tangential field as described in Annex A4. Tangential-field strengths shall have a minimum value of 30 Gauss (30×10^{-4} Tesla [T]) when measured at the part surface using an electronic gaussmeter as described in Annex A4. The maximum Gauss value derived is limited by the restrictions of 6.3.1.

6.3.1.3 For circular magnetization, the written procedure shall specify the amperage requirements for the specific part to be examined. If the requirements are unknown, the formulas in Appendix X3 may be used as a starting point in developing the required amperage for specific parts.

6.3.1.4 For longitudinal magnetization, the written procedure shall specify the amp-turns, particle mobility characteristics, or external field strength requirements, or a combination thereof, for the specific part to be examined. If the requirements are unknown, the formulas in Appendix X3 in Guide E709 may be used as a starting point in developing the required amperage for specific parts. The current levels and formulas in Guide E709 provide only a rough guide and shall only be used in conjunction with either 6.3.1.1, or 6.3.1.2. In some cases, these formulas may lead to over magnetization of the work piece and care should be exercised when using them.

6.3.2 Longitudinal Magnetization Using Coils—The actual effective distance must be demonstrated based on the particular part to be examined. For parts longer than these effective distances, the entire length shall be examined by repositioning the part within the coil, allowing for approximately 10 % effective magnetic field overlap. See 6.3.1 for field strength methods that can be used in coil magnetization.

6.4 Particle Application

6.4.1 Dry Magnetic Particle Application, Continuous Method—When using dry particles, the flow of magnetizing current shall be initiated prior to application of the magnetic particles to the surface under examination and terminated after particle application has been completed and any excess blown off. Precautions shall be taken to prevent any damage to the part due to overheating.

6.4.1.1 Apply dry powder so that a light, uniform, dust-like coating settles on the surface of the part under examination while the part is being magnetized. Specially designed powder blowers or shakers using compressed air or hand power shall be used. The applicators shall introduce the particles into the air in a manner such that they reach the part surface in a uniform cloud with a minimum of force.

6.4.1.2 After the powder is applied, and before the magnetizing force is removed, excess powder shall be removed, by means of a dry air current with sufficient force to remove the excess particles, if they interfere with interpretation and evaluation, but not strong enough to disturb particles held by a

leakage field that is indicative of discontinuities. In order to recognize the broad, fuzzy, lightly held powder patterns formed by near-surface discontinuities, the formation of indications must be observed carefully during both powder application and removal of the excess powder.

6.4.1.3 Dry magnetic particles shall not be reused, unless a process for reclamation has been established and approved by the Level III.

6.4.2 *Wet Magnetic Particle Application, Continuous Method*—Fluorescent or nonfluorescent particles suspended in a liquid vehicle at the required concentration shall be applied by gently spraying or flowing the suspension over the area to be examined.

6.4.2.1 Proper sequencing and timing of part magnetization and application of particle suspension are required to obtain the proper formation and retention of indications. This requires that the stream of suspension be diverted from the part simultaneously with, or slightly before, energizing the magnetic circuit.

6.4.2.2 The magnetizing current shall be applied for a duration of at least 0.5 second for each application, with a minimum of two shots being used. The second shot shall follow the first while the particles are still mobile on the surface of the part.

6.4.2.3 Under special circumstances, such as the use of automated equipment or for critical parts, the 0.5-second duration and the two-shot requirement may be waived provided it is demonstrated that the procedure can detect known discontinuities in reference parts.

6.4.2.4 Care shall be exercised to prevent any damage to the part due to overheating or other causes. Weakly held indications on highly finished parts are readily washed away, and care must be exercised to prevent high-velocity flow over critical surfaces.

6.4.2.5 Particle application by continuous immersion shall be used only when it has been documented that it can detect discontinuities or artificial discontinuities in parts under examination.

6.4.3 *Residual Magnetization Method*—In the residual magnetization method, the magnetic particles (dry or wet) are applied to the part under examination after the magnetizing force has been discontinued. The residual method is not as sensitive as the continuous method. It can be useful on materials with high retentivity. When inducing circular fields and longitudinal fields in long pieces, residual fields are normally sufficient to meet magnetizing requirements consistent with the requirements of 7.1.1 or 7.1.2. The residual method has found wide use examining pipe and tubular goods. For magnetization requirements of oilfield tubulars, refer to **Appendix X5**. It is also useful for the examination of parts or areas of parts, which because of geometric constraints, cannot be examined with the continuous method. The residual method shall be used only when it has been documented that it can detect discontinuities or artificial discontinuities in parts under examination and when approved by the Level III. The test parts shall have the same material and processing steps, and similar geometry, to the actual parts being examined.

6.4.4 *Magnetic Slurry/Paint Application*—Magnetic paints or slurries are applied to the part with a brush, squeeze bottle, or aerosol can before or during the magnetization operation. This method is for special applications, such as overhead or underwater examination.

6.4.5 *Magnetic Polymer Application*—Polymerizable material containing magnetic particles shall be held in contact with the part under examination during the period of its cure. Before curing takes place, and while the magnetic particles are still mobile, the part shall be magnetized to the specified level. This requires prolonged or repeated periods of magnetization. This method is for special applications, such as bolt holes which cannot be examined readily by the wet or dry method. AMS-I-83387 establishes the examination process for magnetic rubber.

6.5 *Evaluation*—Following magnetization and particle application, the parts shall be examined for indications. All indications will be identified as relevant or nonrelevant. Relevant indications will be compared to the proper accept/reject criteria and the parts accepted or rejected accordingly.

6.5.1 *Eye Glasses*—Personnel shall not wear eye glasses that are photochromic or that have permanently darkened lenses. This is not intended to prohibit the use of eyeglasses with lenses treated to absorb UV-A.

6.5.2 *Dark Adaptation*—Personnel must wait at least one minute after entering a darkened area for their eyes to adjust to the low-level lighting before performing fluorescent magnetic particle testing.

6.5.3 *Acceptance Requirements*—The acceptance requirements applicable to the part or group of parts shall be incorporated as part of the written procedure either specifically or by reference to other applicable documents containing the necessary information.

6.6 *Recording of Indications*—When required by the written procedure, the location of all rejectable indications shall be marked on the part, and permanent records of the location, direction, and frequency of indications may be made by one or more of the following methods:

6.6.1 *Written Description*—By recording the location, length, direction, and number of indications in sketch or tabular form;

6.6.2 *Transparent Tape*—For dry particle indications, by applying transparent adhesive-backed tape to which the indications will adhere and placing it on an approved form along with information giving its location on the part;

6.6.3 *Strippable Film*—By covering the indication with a spray-on strippable film that fixes the indications in place and placing the resultant reproduction on an approved form along with information giving its location on the part; and

6.6.4 *Photography*—By photographing or video recording the indications themselves, the tape, or the strippable film reproduction and placing the photograph in a tabular form along with information giving its location on the part.

6.7 *Post-Examination Demagnetization and Cleaning*—All parts shall be demagnetized and cleaned after final examination. Apply corrosion protection as required.

6.7.1 *Demagnetization:*