



Designation: D1387 – 89 (Reapproved 2019)

Standard Test Method for Saponification Number (Empirical) of Synthetic and Natural Waxes¹

This standard is issued under the fixed designation D1387; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the saponification number of synthetic waxes and natural waxes.

1.2 This test method is applicable to Fischer Tropsche, microcrystalline, polyethylene, and Montan Ester waxes.

1.3 Certain synthetic waxes, notably copolymers of ethylene, exhibit poor reproducibility when running saponification values. Reproducibility can be improved if cooking time in 7.2 is extended from 3 h to 18–20 h.

1.4 Some oxidized polyethylene and other waxes with a melt temperature above 100°C may give poor reproducibility.

1.5 Some dark-colored (Gardner Color 14) waxes may obscure the color change of the indicator, resulting in poor reproducibility.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

¹ This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.02 on Raw Materials.

Current edition approved July 1, 2019. Published July 2019. Originally approved in 1955. Last previous edition approved in 2012 as D1387 – 89(2012). DOI: 10.1520/D1387-89R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis

3. Terminology

3.1 *Definitions:*

3.1.1 *saponification number*—the number of milligrams of potassium hydroxide required to hydrolyze 1 g of the sample and is a measure of the amount of saponifiable matter present.

4. Significance and Use

4.1 This test method is used to determine the property of ester functionality. Ester functionality determines the utility of the wax as well as being a significant quality control test.

5. Apparatus

5.1 *Analytical Balance.*

5.2 *Boiling Chips*, chemically resistant glass.

5.3 *Burets*, two 50-mL capacity with 0.1-mL graduations.

5.4 *Erlenmeyer Flasks*, 250-mL, alkali-resistant.

5.5 *Hot Plate.*

5.6 *Reflux Condenser.*

6. Reagents and Materials

6.1 *Purity of Reagents*—Reagent-grade chemicals or equivalent as specified in Practice E200 shall be used in all tests.

6.2 *Hydrochloric Acid Standard (0.5 N).*

6.3 *Phenolphthalein Indicator Solution (10 g/litre)*—Dissolve 1 g of phenolphthalein in 100 mL of USSD3A denatured ethanol or 95 % ethanol.

6.4 *Potassium Hydroxide, Alcoholic Solution (6.6 g/litre)*—Dissolve 6.6 g of potassium hydroxide (KOH) in USSD3A denatured ethanol or 95 % ethanol. Dilute to 1 L with the ethanol.

6.5 *Xylene.*

7. Procedure

7.1 Transfer approximately 1 g of the sample, weighed to the nearest 0.001 g to a 250-mL Erlenmeyer flask.