

Designation: E1730 – 15 E1730 – 19

Standard Specification for Rigid Foam for Use in Structural Sandwich Panel Cores¹

This standard is issued under the fixed designation E1730; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

- 1.1 This specification covers rigid, closed cell, polyurethane and polyisocyanurate thermal insulation for sandwich panels used in shelter construction for exposure to ambient temperatures of -25° to 160° F (-32° 160 °F (-32° 160 °F (-32° 100 °F (-32° 160 °F (-32°
- 1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.3 The following precautionary caveat pertains only to the test method portion, Section 12, of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety safety, health, and health environmental practices and determine the applicability of regulatory limitations prior to use.
- 1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

C165 Test Method for Measuring Compressive Properties of Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C273/C273M Test Method for Shear Properties of Sandwich Core Materials

C366/C366M Test Methods for Measurement of Thickness of Sandwich Cores | 68-a0faec 76d | d0/astm-e | 730-19

C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C550 Test Method for Measuring Trueness and Squareness of Rigid Block and Board Thermal Insulation

D883 Terminology Relating to Plastics

D1621 Test Method for Compressive Properties of Rigid Cellular Plastics

D1622/D1622M Test Method for Apparent Density of Rigid Cellular Plastics

D1623 Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics

D2126 Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging

D2856 Test Method for Open-Cell Content of Rigid Cellular Plastics by the Air Pycnometer (Withdrawn 2006)³

E631 Terminology of Building Constructions

E1749 Terminology Relating to Rigid Wall Relocatable Shelters

2.2 Code of Federal Regulations Aeronautics and Space:⁴

14 CFR 25.853 CFR 25.853 (Federal Air Regulation 25.853) Compartment Interior (Amend. 25-72)

¹ This specification is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is under the direct responsibility of Subcommittee E06.53 on Materials and Processes for Durable Rigidwall Relocatable Structures.

Current edition approved May 1, 2015 July 1, 2019. Published August 2015 August 2019. Originally approved in 1995. Last previous edition approved in 2009 2015 as E1730 – 19. E1730 – 15. DOI: 10.1520/E1730 – 15. 10.1520/E1730 – 19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from U.S. Government Publishing Office, 732 N. Capitol St., NW, Washington, DC 20401-0001, http://www.gpo.gov.

2.3 Federal Standard:⁵

QQ-A-250/11 Aluminum Alloy 6061-T6 Plate and Sheet

2.4 Military Standard:⁵

MIL STD 105-MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

2.5 Other Documents:⁶

Aircraft Materials Fire Test Handbook DOT/FAA/AR-00/12

Federal Aviation Regulation (FAR) 25.853

3. Terminology

3.1 Definitions—The terms used in this specification are defined in Terminologies C168, D883, E631, and E1749.

4. Classification

- 4.1 The unfaced foam thermal insulation boards covered by this specification are classified as follows:
- 4.1.1 *Type 1*—Nominal density: 2.0 lb/ft³ (32 kg/m³).
- 4.1.2 *Type* 2—Nominal density: 3.0 lb/ft³ (48 kg/m³).
- 4.1.3 *Type 3*—Nominal density: 4.0 lb/ft³ (64 kg/m³).
- 4.1.4 Type 4—Nominal density: 12.0 lb/ft³ (192 kg/m³).

5. Ordering Information

- 5.1 Orders for materials purchased under this specification shall include the following:
- 5.1.1 Designation of this specification,
- 5.1.2 Product name and type, or both,
- 5.1.3 Dimensions and tolerances,
- 5.1.4 Impact resistance test specimen preparation,
- 5.1.5 Material marking requirements, and
- 5.1.6 Packaging requirements.

6. Foam

6.1 The morphology of the insulation shall consist of a multitude of individual cells of uniform size and dimension, essentially closed off from each other, homogeneous throughout, free of voids, accumulations of unexpanded material, foreign inclusions, or seams (see Table 1).

7. Dimensions and Tolerances

7.1 The dimensions, squareness, and tolerances shall be specified by the purchaser.

8. Qualification

- 8.1 When required by the purchaser, materials supplied under this specification must be tested for and meet the properties listed in Table 2. Having a qualified product does not obviate the supplier from continued, ongoing product compliance with all requirements to this specification.
- 8.2 In addition to meeting the requirements of the tests stipulated in Table 2 as manufactured, the compressive, tensile, and shear properties must also meet these requirements after having been preconditioned for 4 h at 230°F (110°C), 230 °F (110 °C), and allowed to equilibrate in accordance with 11.2.

TABLE 1 Classification of Characteristics

Characteristic	Major	Minor	Method of Inspection
Length, width, and thickness	Χ		9.4.3
Edge squareness	X		9.4.3
Holes through board exceeding 40 mm ² for each 0.0625 in. ² (92900 mm ²	Х		9.4.2
for each square foot) of area			
Crushed foam	X		9.4.2
Voids larger than 0.0625 in.2 (40 mm)	X		9.4.2
Unexpanded material		Χ	9.4.2
Foreign inclusions		X	9.4.2
Contaminants		Χ	9.4.2
Seams	X		9.4.5

⁵ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, http://quicksearch.dla.mil.

⁶ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, 20899, http://www.nist.gov.