

Designation: C507M - 19

Standard Specification for Reinforced Concrete Elliptical Culvert, Storm Drain, and Sewer Pipe (Metric)¹

This standard is issued under the fixed designation C507M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

- 1.1 This specification covers reinforced elliptically shaped concrete pipe to be used for the conveyance of sewage, industrial wastes, storm water, and for the construction of culverts.
- 1.2 Pipe designed for placement with the major axis horizontal shall be designated as "Horizontal Elliptical Pipe." Pipe designed for placement with the major axis vertical shall be designated as "Vertical Elliptical Pipe."
- 1.3 This specification is the SI companion to Specification C507; therefore, no inch-pound equivalents are presented in this specification. Reinforced concrete pipe that conforms to the requirements of C507 are acceptable under this Specification C507M unless prohibited by the owner.

Note 1—This specification is a manufacturing and purchase specification only, and does not include requirements for bedding, backfill, or the relationship between field load condition and the strength classification of pipe. However, experience has shown that the successful performance of this product depends upon the proper selection of the class of pipe, type of bedding and backfill, and care that the installation conforms to construction specifications. The owner of the reinforced concrete pipe specified herein is cautioned that he must correlate the field requirements with the class of pipe specified and provide inspection at the construction site.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

A36/A36M Specification for Carbon Structural Steel

A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete

C33/C33M Specification for Concrete Aggregates

C150/C150M Specification for Portland Cement

C260/C260M Specification for Air-Entraining Admixtures for Concrete

C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete

C443M Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets (Metric)

C494/C494M Specification for Chemical Admixtures for

C497M Test Methods for Concrete Pipe, Concrete Box Sections, Manhole Sections, or Tile (Metric)

C595/C595M Specification for Blended Hydraulic Cements C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C822 Terminology Relating to Concrete Pipe and Related Products

C989/C989M Specification for Slag Cement for Use in Concrete and Mortars

C990M Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants (Metric)

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.02 on Reinforced Sewer and Culvert Pipe.

Current edition approved July 1, 2019. Published July 2019. Originally approved in 1980. Last previous edition approved in 2018 as C507M - 18. DOI: 10.1520/C0507M-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



C1017/C1017M Specification for Chemical Admixtures for Use in Producing Flowing Concrete
C1116/C1116M Specification for Fiber-Reinforced Concrete
C1602/C1602M Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete

3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology C822.

4. Classification

4.1 Pipe manufactured according to this specification shall be of five classes each for horizontal elliptical and vertical elliptical pipe with identification as follows:

Horizontal Elliptical Pipe	Vertical Elliptical Pipe
Class HE-A	Class VE-II
Class HE-I	Class VE-III
Class HE-II	Class VE-IV
Class HE-III	Class VE-V
Class HE-IV	Class VE-VI

4.2 The strength requirements for horizontal elliptical pipe are prescribed in Table 1 and for vertical elliptical pipe are prescribed in Table 2.

5. Basis of Acceptance

5.1 Unless otherwise designated by the owner at the time of, or before, placing an order, there are two separate and alternative bases of acceptance. Independent of the method of

TABLE 1 Design Requirements for Horizontal Elliptical (HE) Pipe^A

Note 1—The test load in kilonewtons per linear metre equals D-load × inside span in millimetres.

Note 2—Single cage reinforcement, providing tension steel at the top, bottom, and springline, shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be 112 % of the tabulated inner cage area.

Note 3—An inner and outer cage plus quadrant mats shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be in accordance with Fig. 1.

Note 4—An inner and outer cage plus a middle cage shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be in accordance with Fig. 2.

Designated Di-			Reinforcement, cm²/linear m										
			Class HE-A Class HE-I Class HE-II					Class HE-III		Class HE-IV			
ameter, Equiva-	Designated Rise, mm x		D-Loads D-Loads										
lent Round Size, mm	Span, mm			= 30 = 45	0.3 = 40 Ult = 60		0.3 = 50 Ult = 75		0.3 = 65 Ult = 100		0.3 = 100 Ult = 150		
			In Cage	Out Cage	In Cage	Out Cage	In Cage	Out Cage	In Cage	Out Cage	In Cage	Out Cage	
450	365 × 575	69	1.7		2.3		3.0		4.0		5.7		
600	490×770	82	2.3		3.2		4.0		5.5		8.3		
675	550×865	88	3.0		3.8	N / 11/0	4.9		6.6		9.7		
750	610×960	94	2.1	2.1	2.8	2.8	3.6	3.6	4.9	4.9	7.2	7.2	
825	670 × 1055	94	2.5	2.5	3.6 7	3.6	4.4	4.4	5.9	5.9	5 8.7	8.7	
ttps:/900 andai	730 × 1150	113	2.3	2.3	3.2	3.2	4.0	4.0	5.5	5.5	8.3	8.3	
975	795×1250	119	2.8	2.8	3.6	3.6	4.4	4.4	6.1	6.1	9.3	9.3	
1050	855×1345	125	3.2	3.2	4.2	4.2	5.1	5.1	7.0	7.0	10.6	10.6	
1200	975×1535	138	3.6	3.6	4.9	4.9	5.9	5.9	8.3	8.3			
1350	1095×1730	150	4.2	4.2	5.7	5.7	7.2	7.2	9.5	9.5			
1500	1220×1920	163	5.1	5.1	6.8	6.8	8.5	8.5	11.2	11.2			
1650	1340×2110	175	5.7	5.7	7.6	7.6	9.5	9.5	12.9	12.9			
1800	1465×2305	188	6.6	6.6	8.7	8.7	11.0	11.0	14.8	14.8			
1950	1585×2495	200	7.2	7.2	9.5	9.5	11.9	11.9	16.5	16.5			
2100	1705×2690	213	8.0	8.0	10.6	10.6	13.3	13.3	18.6	18.6			
2250	1830×2880	225											
2400	1950×3070	238											
2550	2075×3265	244											
2700	2195×3455	250											
2850	2315×3648	263											
3000	2440×3840	275											
3300	2680×4225	300											
3600	2925×4610	325											
Concrete strength ^B , MPa		27.6 27.6		27	7.6	†450 to 1650 mm, 27.6 †1800 to 2100 mm, 34.5		27.6					

^A Concrete strength for designs with reinforcement tabulated. For modified or special designs, see 7.3.

^B For sizes and loads beyond those shown in this table, pipe designs are available that make use of one or a combination of the following: shear steel, multiple cages, or thicker walls in accordance with the provisions of 7.3.



TABLE 2 Design Requirements for Vertical Elliptical Pipe^A

Note 1—Test load in kilonewtons per linear metre equals D-load x inside span in millimetres.

Note 2—An inner and outer cage plus quadrant mats shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be in accordance with Fig. 3.

Note 3—Single cage reinforcement, providing tension steel at the top, bottom, and spring line shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be 112 % of the tabulated inner cage area.

Note 4—An inner and outer cage plus a middle cage shall be permitted instead of double cage reinforcement. The area of such reinforcement shall be in accordance with Fig. 4.

Designated Diameter, Equivalent Round Size, mm		– Minimum	Reinforcement, cm²/linear m										
			Class		Class		Class		Class		Class		
			VE-II		VE-III		VE-IV		VE-V		VE-VI		
	Wall					D-L	oads						
	/	Thickness, - mm -	0.3 = 50 Ult = 75		0.3 = 65 Ult = 100		0.3 = 100 Ult = 150		0.3 = 140 Ult = 175		0.3 = 190 Ult = 235		
													In
			Cage	Cage	Cage	Cage	Cage	Cage	Cage	Cage	Cage	Cage	
			900	1150 × 730	113	1.7	1.1	2.3	1.5	3.4	2.1	4.9	3.0
975	1250×795	119	1.9	1.1	2.5	1.5	3.8	2.3	5.5	3.4	7.4	4.4	
1050	1345×855	125	2.1	1.3	2.8	1.7	4.2	2.5	6.1	3.6	8.0	4.9	
1200	1535×975	138	2.3	1.5	3.2	1.9	4.7	2.8	7.0	4.2	9.3	5.5	
1350	1730×1095	150	2.8	1.7	3.8	2.3	5.7	3.4	8.5	5.1	11.2	5.8	
1500	1920×1220	163	3.4	2.1	4.4	2.8	6.6	4.0	9.9	5.9			
1650	2110×1340	175	3.8	2.3	5.3	3.2	7.6	4.7	11.6	7.0			
1800	2305×1465	188	4.4	2.8	5.9	3.6	8.7	5.3					
1950	2495×1585	200	4.9	3.0	6.6	4.0	9.9	5.9					
2100	2690×1705	213	5.5	3.4	7.4	4.4	11.2	6.8					
2250	2880×1830	225											
2400	3070×1950	238											
2550	3265×2075	244	1 (1)	hQ	ton	or	d a.						
2700	3455×2195	250	TITC		rani	ual	US.						
2850	3648×2315	263											
3000	3840 × 2440	275	a//	04-0 -	do		ital	0.1					
3300	4225 × 2680	300	5//	21311	IU.a.	IU.S.		1.4.1)					
3600	4610 × 2925	325						/					
Concrete strength ^B , MPa			27.6		27.6		27.6		34.5		41.4		

^A For sizes and loads beyond those shown in this table, pipe designs are available which make use of one or a combination of the following: shear steel, multiple cages, or thicker walls in accordance with the provisions of 7.3.

ASTM C507M-19

https://standards.iteh.ai/catalog/standards/sist/628461ad-7ed3-4941-84d3-d45632445b73/astm-c507m-19

acceptance, the pipe shall be designed to meet both the 0.01-in. crack and ultimate strength requirements specified in Table 1.

- 5.1.1 Acceptance on Basis of Plant Load-Bearing Tests, Material Tests, and Inspection of Manufactured Pipe for Visual Defects and Imperfections—Acceptability of the pipe in all diameters and classes produced in accordance with 7.1 or 7.2 shall be determined by the results of the three-edge-bearing tests as defined in 11.3.1; by such material tests as are required in 6.2, 6.3, 6.5 and 6.6; by an absorption test of the concrete from the wall of the pipe as required in 11.9; and by visual inspection of the finished pipe to determine its conformance with the accepted design prescribed and its freedom from defects.
- 5.1.2 Acceptance on the Basis of Material Test and Inspection of Manufactured Pipe for Defects and Imperfections—Acceptability of the pipe in all diameters and classes produced in accordance with 7.1 or 7.2 shall be determined by the results of such material tests as are required in 6.2, 6.3, 6.5 and 6.6; by crushing tests on concrete cores or cured concrete cylinders; by an absorption test of the concrete from the wall of the pipe for each mix design that is used on an order; and by inspection of the finished pipe, including amount and placement of

- reinforcement, to determine its conformance with the accepted design and its freedom from defects.
- 5.1.3 When agreed upon by the owner and the manufacturer, any portion or any combination of the tests itemized in 5.1.1 or 5.1.2 may form the basis of acceptance.
- 5.2 Age for Acceptance—Pipe shall be considered ready for acceptance when they conform to the requirements as indicated by the specified tests.

6. Materials

- 6.1 Reinforced Concrete—The reinforced concrete shall consist of cementitious materials, mineral aggregates, admixtures, if used, and water, in which steel has been embedded in such a manner that the steel and concrete act together.
 - 6.2 Cementitious Materials:
- 6.2.1 *Cement*—Cement shall conform to the requirements for portland cement of Specification C150/C150M, or shall be portland blast-furnace slag cement, portland-limestone cement, or portland-pozzolan cement conforming to the requirements

or thicker walls in accordance with the provisions of 7.3.

^B Concrete strength for designs with reinforcement tabulated. For modified or special designs, see 7.3.



- of Specification C595/C595M, except that the pozzolan constituent in the Type IP portland pozzolan cement shall be fly ash.
- 6.2.2 *Slag Cement*—Slag cement shall conform to the requirements of Grade 100 or 120 of Specification C989/C989M.
- 6.2.3 *Fly Ash*—Fly ash shall conform to the requirements of Class F or Class C of Specification C618.
- 6.2.4 Allowable Combinations of Cementitious Materials— The combination of cementitious materials used in the concrete shall be one of the following:
 - 6.2.4.1 Portland cement only,
 - 6.2.4.2 Portland blast-furnace slag cement only,
 - 6.2.4.3 Portland-pozzolan cement only,
 - 6.2.4.4 Portland-limestone cement only,
- 6.2.4.5 A combination of portland cement or portland-limestone cement and slag cement,
- 6.2.4.6 A combination of portland cement or portland-limestone cement and fly ash,
- 6.2.4.7 A combination of portland cement or portlandlimestone cement, slag cement, and fly ash, or
- 6.2.4.8 A combination of portland-pozzolan cement and fly ash.
- 6.3 *Aggregates*—Aggregates shall conform to the requirements of Specification C33/C33M except that the requirement for gradation shall not apply.
- 6.4 *Admixtures*—The following admixtures and blends are allowable:
- 6.4.1 Air-entraining admixture conforming to Specification C260/C260M;

- 6.4.2 Chemical admixture conforming to Specification C494/C494M;
- 6.4.3 Chemical admixture for use in producing flowing concrete conforming to Specification C1017/C1017M; and
 - 6.4.4 Chemical admixture or blend approved by the owner.
- 6.5 Steel Reinforcement—Reinforcement shall consist of wire or welded wire conforming to Specification A1064/A1064M, or of bars conforming to Specification A36/A36M, Specification A615/A615M Grade 280 or 420, or Specification A706/A706M Grade 420. For helically wound cages only, weld shear tests are not required.
- 6.6 *Fibers*—Synthetic fibers and nonsynthetic fibers shall be allowed to be used, at the manufacturer's option, in concrete pipe as a nonstructural manufacturing material. Synthetic fibers (Type II and Type III) and nonsynthetic fiber (Type 1) designed and manufactured specifically for use in concrete and conforming to the requirements of Specification C1116/C1116M shall be accepted.
- 6.7 *Water*—Water used in the production of concrete shall be potable or non-potable water that meets the requirements of Specification C1602/C1602M.

7. Design

7.1 Size and Shape—The standard sizes of elliptical pipe shall be as listed in Table 1 and Table 2. The internal shape for each size pipe shall be defined by the internal dimensions shown in Fig. 5, subject to permissible variations.

Quadrant 2 90 deg Vertical Top Midpoint | 8 Aso Aso Asi Aso Asi Quadrant 1 Quadrant 2 90 deg Quadrant 1


Note 1—The total reinforcement area (A'si) of the inner cage plus the quadrant mat in Quadrants 1 and 2 shall not be less than that specified for the inner cage in Table 1.

Note 2—The total reinforcement area (Aso) of the outer cage plus the quadrant mat in Quadrants 3 and 4 shall not be less than that specified for the outer cage in Table 1.

Note 3—The reinforcement area (Asi) of the inner cage in Quadrants 3 and 4 shall be not less than 25 % of that specified for the inner cage in Table

Note 4—The reinforcement area (A'so) of the outer cage in Quadrants 1 and 2 shall be not less than 25 % of that specified for the outer cage in Table 1.


FIG. 1 Quadrant Reinforcement, Horizontal Elliptical Pipe



Note 1—The total reinforcement area of the inner cage plus the middle cage shall not be less than that specified for the inner cage in Table 1.

Note 2—The total reinforcement area of the outer cage plus the middle cage shall not be less than that specified for the outer cage in Table 1.

FIG. 2 Horizontal Elliptical Pipe



Note 1—The total reinforcement area (Asi) of the inner cage plus the quadrant mat in Quadrants 1 and 2 shall not be less than that specified for the inner cage in Table 2.

Note 2—The total reinforcement area (Aso) of the outer cage plus the quadrant mat in Quadrants 3 and 4 shall not be less than that specified for the outer cage in Table 2.

Note 3—The reinforcement area (A'si) of the inner cage in Quadrants 3 and 4 shall be not less than 25 % of that specified for the inner cage in Table


Note 4—The reinforcement area (A'so) of the outer cage in Quadrants 1 and 2 shall be not less than 25 % of that specified for the outer cage in Table 2.

FIG. 3 Quadrant Reinforcement, Vertical Elliptical Pipe

- 7.2 Design Tables—The wall thickness, compressive strength of concrete, and the area of circumferential reinforcement shall be as prescribed in Table 1 and Table 2, subject to the provisions of 7.3, 11.4, and Section 12.
- 7.2.1 Footnotes to the tables herein are intended to be amplications of the tabulated requirements and are to be considered applicable and binding as if they were contained in the body of the specification.
 - 7.3 Modified and Special Designs:

- 7.3.1 If permitted by the owner, the manufacturer may request approval by the owner of modified designs which differ from the designs in this section; or special designs for sizes and loads beyond those shown in Table 1 and Table 2; or special designs for pipe sizes that do not have steel reinforcement areas shown in Table 1 and Table 2.
- 7.3.2 Such modified and special designs shall be based on rational or empirical evaluations of the ultimate strength and cracking behavior of pipe and shall fully describe to the owner






Note 1—The total reinforcement area of the inner cage plus the middle cage shall not be less than that specified for the inner cage in Table 2.

Note 2—The total reinforcement area of the outer cage plus the middle cage shall not be less than that specified for the outer cage in Table 2.

FIG. 4 Vertical Elliptical Pipe



Approximate Full Flow Equivalent Water Area, Rise, mm Span, mm A, mm B, mm R_1 , mm R_2 , mm θ degrees† Round Size, m² 0.170 22.6 0.305 22.6 0.383 22.6 0.474 22.6 0.588 22.6 0.684 22.6 0.816 22.6 0.948 22.6 1.20 22.6 1.55 22.6 1.90 22.6 22.6 2.30 2.73 22.6 3.21 22.6 22.6 3.73 4.28 22.6 4.87 22.6 5.49 22.6 22.6 6.17 6.87 22.6 7.63 22.7 22.6 9 22 11.0 22.6

†Editorially corrected

Note 1—Rise, span, and radii are fixed; other dimensions and angles are calculated.

FIG. 5 Shape of Elliptical Pipe