



Designation: E832 – 81 (Reapproved 2019)

Standard Specification for Laboratory Filter Papers¹

This standard is issued under the fixed designation E832; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers two types of filter paper for use in chemical analysis and provides procedures for the complete evaluation of the filter papers.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D774/D774M Test Method for Bursting Strength of Paper (Withdrawn 2010)³

2.2 *TAPPI Standards:*⁴

T 413 Ash in Paper

T 429 Alpha-Cellulose in Paper

T 509 Hydrogen Ion Concentration (pH) of Paper Extracts—Cold Extraction Method

3. Types and Classes

3.1 The types and classes of filter paper are as follows:

3.1.1 *Type I*—To be used for qualitative analysis (low ash content):

3.1.1.1 *Class AA*, for very coarse and gelatinous precipitates, very fast flow rate.

3.1.1.2 *Class A*, for coarse and gelatinous precipitates, fast flow rate.

3.1.1.3 *Class B*, for medium-size precipitates, medium flow rate.

3.1.1.4 *Class C*, for fine precipitates, slow flow rate.

3.1.1.5 *Class D*, hardened to facilitate scraping, for fine precipitates, slow flow rate.

3.1.2 *Type II*—to be used for quantitative analysis (ashless papers):

3.1.2.1 *Class E*, for coarse and gelatinous precipitates, fast flow rate.

3.1.2.2 *Class F*, for medium-size precipitates, medium flow rate.

3.1.2.3 *Class G*, for fine precipitates, slow flow rate.

4. Manufacture

4.1 The papers shall be made from such materials and by such methods as to ensure compliance with the requirements of Section 10, and shall be clean and free of imperfections that would affect their performance.

4.2 The papers shall be converted into circles, sheets, or any required sizes.

5. General Requirements

5.1 All classes of filter paper shall comply with the requirements given in **Table 1** and **Table 2** and Section 11.

5.2 The ash content of the Type II circles shall not exceed 0.01 %.

5.3 Class D filter papers shall have a surface hard enough to permit scraping collected precipitates off the sheet.

6. Sampling

6.1 If testing is required, the sample of each class shall be representative of the shipment, and specimens shall be taken at random from at least 3 % of the total packages.

7. Retests

7.1 If the results of the tests indicate noncompliance with the requirements of **Table 1** and **Table 2**, or other factors

¹ This specification is under the jurisdiction of ASTM Committee E41 on Laboratory Apparatus and is the direct responsibility of Subcommittee E41.01 on Laboratory Ware and Supplies.

Current edition approved July 1, 2019. Published August 2019. Originally approved in 1950. Last previous edition approved in 2013 as E832 – 81(2013). DOI: 10.1520/E0832-81R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Technical Association of the Pulp and Paper Industry (TAPPI), 15 Technology Parkway South, Norcross, GA 30092, http://www.tappi.org.

TABLE 1 General Requirements

Property	Requirement
alpha-cellulose content, min, %	95
pH value	5.0 to 8.0

TABLE 2 Wet Bursting Strength

Class	Water Flow Rate and Retention of Precipitates		
	Wet Bursting Strength min, aug points	Maximum Water Flow Rate, aug, s	Retention of Precipitates—Filtrate Clear from:
AA	3.0	10	ferric hydroxide
A	3.0	20	ferric hydroxide
B	3.5	40	lead sulfate
C	4.0	150	barium sulfate
D	45.0	300	barium sulfate
E	3.0	20	ferric hydroxide
F	3.5	40	lead sulfate
G	4.0	150	barium sulfate

described within this specification, take another representative sample of the shipment, selecting the specimens from different packages than those from which the first sample was taken.

7.2 Then test the second sample for compliance with this specification.

7.3 If the results of the retests indicate noncompliance with this specification, immediately consult the manufacturer for assistance in rectifying the problem.

8. Packaging and Marking

8.1 Flat circles of filter paper shall be packaged in units of 100 circles of the same diameter. Prefolded or fluted circles shall be packaged according to trade custom.

8.2 Each unit or package shall be marked with the manufacturer's name, size of circles, or catalog and lot number.

9. Test Methods

9.1 The most important tests to be performed are:

9.1.1 *pH Value*—Determine in accordance with TAPPI Method T 509.

9.1.2 *Alpha-Cellulose*—Determine in accordance with TAPPI Method T 429. This test may or may not be used for lot to lot determination.

9.1.3 *Ash Content*—Determine in accordance with Section 10.1 or TAPPI Method T 413, applicable for Type II papers.

9.1.4 Retention of precipitates, simple method to determine retention ability of filter paper as determined in accordance with 10.2.

9.1.5 *Water Flow Rate*—Determine the flow rates of filter paper in accordance with 10.3 or the Herzberg method (measurement of time for the filtration of 100 mL of prefiltered distilled water with a filter surface of 10 cm² at a constant pressure of 50 mm water column).

9.1.6 *Wet Bursting Strength*—Determine in accordance with 10.4.

10. Test Methods

10.1 *Ash Content:*

10.1.1 *Apparatus:*

10.1.1.1 *Crucibles*, 20-mL platinum, with tightly fitting covers. One for each sample.

10.1.1.2 *Heat Source*—An electric muffle furnace with an operating temperature of approximately 925 °C is recommended, but a gas burner yielding a similar temperature is sufficient.

10.1.1.3 *Test Specimens*, having a mass of at least 6 g, representative of the sample obtained as prescribed in Section 6, and cut in the shape of whole circles of the same diameter or small strips measured for area.

10.1.2 *Procedure:*

10.1.2.1 Heat the crucibles with their respective covers to approximately 925 °C. Cool in a desiccator and weigh to the nearest 0.1 mg. Add the specimen into crucible.

10.1.2.2 Heat the covered crucible plus test specimen gradually until smoking ceases, remove cover, then continue heating until the maximum temperature of 925 °C is reached and maintain for 2 h. Replace the cover and cool the covered crucible in a desiccator until temperature equilibrium with the surrounding air is reached. Weigh the crucible and contents to the nearest 0.1 mg. Ignition is considered to be complete when the weight of the covered crucible and ash does not change by more than 0.2 mg after reheating at 925 °C for 30 min.

10.1.2.3 *Blank*—Carry a tare crucible with cover through all operations in exactly the same manner as the crucibles containing specimens, as a check on possible loss of mass of the crucibles themselves.

10.1.2.4 Test at least two specimens per sample.

10.1.3 *Calculation and Report*—Calculate and report the ash, corrected for the results of the blank test, to two significant figures. Determine the weight percentage of the paper dried at 105 °C.

10.1.4 *Precision*—Duplicate determinations shall agree as follows:

Ash, %	Rounded to Nearest	Reproducibility, %
0.025	0.001	0.003
0.025 to 0.01	0.005	0.01
0.1	0.01	0.02

10.2 *Retention of Precipitates:*

10.2.1 *Apparatus:*

10.2.1.1 *Glass Funnels*, 60°, having stems about 6 in. long.

10.2.2 *Reagents:*

10.2.2.1 *Alcohol (95 %)*—Ethanol or formula No. 30.

10.2.2.2 *Ammonium Hydroxide*—Add one part, by volume, of cp ammonium hydroxide (NH₄ OH) to one part by volume of distilled water.

10.2.2.3 *Barium Chloride Solution (50 g/L)*—Dissolve 58.5 g of cp barium chloride (BaCl₂ · 2H₂ O) in distilled water and dilute to 1 L.

10.2.2.4 *Ferric Chloride Solution*—Dissolve 10 parts by weight of cp ferric chloride (FeCl₃ · 6H₂ O) in 100 mL of distilled water.

10.2.2.5 *Hydrochloric Acid* (sp gr 1.19).

10.2.2.6 *Lead Acetate*, cp anhydrous.

10.2.2.7 *Potassium Sulfate* (K₂ SO₄) cp.

10.2.2.8 *Sulfuric Acid* (6 N).

10.2.3 *Procedure:*