



Designation: ~~D6119~~—~~12~~ D6119 – 19

Standard Practice for Creating Surface Appearance Changes in Pile Yarn Floor Covering from Foot Traffic¹

This standard is issued under the fixed designation D6119; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the trafficking of pile yarn floor coverings in a laboratory in order to effect a change in surface appearance as a result of exposure to foot traffic under controlled conditions. A separate test method, [D7330](#), covers the assessment of surface appearance change using the [CRI-Carpet and Rug Institute Reference Scales](#).²

1.2 This practice is applicable to most changes in surface appearance observed in all types of carpet that are intended for residential or commercial use. It eliminates change in appearance associated with soiling by focusing on appearance change due to matting, flattening, or change in pile fiber configuration. Although “pile reversal” or “watermarking” is occasionally visible, this practice is not a reliable method for producing this phenomenon.

1.3 This practice may be used by mutual agreement between the purchaser and supplier to set purchasing specifications.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Section 7.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

[D123 Terminology Relating to Textiles](#)

[D1776 Practice for Conditioning and Testing Textiles](#)

[D5684 Terminology Relating to Pile Floor Coverings](#)

[D7330 Test Method for Assessment of Surface Appearance Change in Pile Floor Coverings Using Standard Reference Scales](#)

2.2 *TM-101 CRI Technical Bulletin:*

[Assessment of Carpet Surface Appearance Change Using CRI Reference Scales](#)³

3. Terminology

3.1 For definitions of terms relating to Pile Floor Coverings, ~~D13.21~~, refer to Terminology [D5684](#).

3.1.1 The following terms are relevant to this standard: carpet, change in surface appearance, crush, finished, finished pile yarn floor covering, floor covering, foot traffic units, loss of tuft definition, matting, pile, pile reversal, pile yarn floor covering, textile floor covering, tufted fabric.

3.2 For all other terminology related to textiles, refer to Terminology [D123](#).

¹ This practice is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of Subcommittee [D13.21](#) on Pile Floor Coverings. Current edition approved Feb. 1, 2012/July 1, 2019. Published March 2012/August 2019. Originally approved in 1997. Last previous edition approved in 2005/2012 as [D6119-05-12](#). DOI: [10.1520/D6119-12](#). [10.1520/D6119-19](#).

² Available from CRI, P.O. Box 2048, Dalton, GA 30722, [www.carpet-rug.org](#).

³ For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Practice

4.1 ~~Specimens~~ Test specimens are exposed to a specified number of foot traffics under controlled conditions.

5. Significance and Use

5.1 By exposure to sufficient foot traffic, this practice can be applied to any pile yarn floor covering which undergoes changes in surface appearance.

5.1.1 This practice does not simulate surface appearance changes due to soiling, pivoting, or rolling traffic, or traffic on stairs.

6. Apparatus

6.1 *Area for Foot Traffic*—A room that meets the following conditions:

6.1.1 The floor must be level, rigid, and free of high and low areas. Tile, concrete, or wood are satisfactory. This area should be kept free of pedestrian traffic other than the designated walkers.

6.1.2 The length of the test area shall be adequate for the test specimens plus the carpet walk-off areas at both ends of each row of test specimens. These areas are necessary to align the walkers to avoid twisting motion while stepping on the test specimens, and shall be a minimum of 2 yards (2 m) long.

6.1.3 The width of the test area shall be adequate to layout a pattern with an odd number of lanes of test specimens that require the walkers to automatically reverse their direction with each pass through the course. See Fig. 1 for typical traffic pattern.

6.1.4 *Physical Barriers*, such as pylons, are suggested to ensure straight-line entry and exit of the test area.

6.1.5 *Suitable Walk-Off Mats*, used to eliminate tracking of contaminants.

6.2 *Physical Barriers*, such as pylons, are suggested to ensure straight-line entry and exit of the test area.

6.3 *Suitable Walk-Off Mats*, used to eliminate tracking of contaminants.

6.4 *Double-Faced, Pressure Sensitive Tape*, or other means which will hold the specimens in place and yet permit easy removal.

6.5 *Traffic Counting Device*—An accurate means of counting foot traffic units. Photoelectric or hand held manual counting devices are satisfactory. Install photoelectric counters at a sufficient height to prevent multiple counting from arm or leg motion. Impact counters which generate multiple signals for an individual foot step are not recommended.

6.6 *Vacuum Cleaner*—~~Dual motor, top-loading.~~ An upright vacuum cleaner with a rotating brush approved by the Carpet and Rug Institute (CRI) Seal of Approval Program.

6.7 *Walker Personnel*—No minimum number is required. The number shall be small enough to prevent walkers from interfering with the progress of each other through the test area. Walking or athletic shoes must be worn by all walkers.

7. Hazards

7.1 The carpet specimens shall be secured to the floor to avoid a slipping or tripping hazard. Inspect the specimens periodically and secure loose specimens immediately.

8. Test Specimens

8.1 Test at least one test specimen from the machine direction and one from the cross machine direction. Retain an original (unexposed) specimen for grading visual comparisons.

8.1.1 In cases where there is a choice of color, select the lighter color specimen as this facilitates rating.

8.2 Cut each individual test specimen 9 in. by 22 in. (230 mm by 560 mm). The long dimension is always the width of the designated walker path. The specified width of the test specimen is necessary to assure uniform traffic density from one site to another. The test specimen length can be varied with no affect on test results.

8.3 *Marking Specimen*—To orient the carpet specimen with respect to machine direction, place a distinguishing mark such as an arrow on the back of the carpet. Place any other required identification on the back of each specimen before installation in the test area.

9. Conditioning

9.1 This practice ~~does not require conditioning, as directed in Practice can D1776.~~ Specimens need not be conditioned in the standard atmosphere (70°F, 65 % RH) for testing textiles. be conducted in common ambient room conditions.

10. Procedure

10.1 Choose a traffic level high enough to produce a noticeable change in surface appearance. 20 000 foot traffic units is recommended for household applications.

10.2 Place the test specimens adjacent to one another with the 22 in. (560 mm) dimension perpendicular to the traffic flow.

10.2.1 Group carpet test specimens to minimize thickness variation from one test specimen to another.