



Designation: **A27/A27M—17** **A27/A27M – 19**

Standard Specification for Steel Castings, Carbon, for General Application¹

This standard is issued under the fixed designation A27/A27M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers carbon steel castings for general applications that require up to 70 ksi (485 MPa) minimum tensile strength.

NOTE 1—The grades covered by this specification represent materials that are suitable for assembly with other steel castings or wrought steel parts by fusion welding. It is not intended to imply that all these grades possess the same degree of weldability or that the same welding techniques can be used on all castings. It is the responsibility of the purchaser to establish for himself a suitable welding technique.

1.2 Several grades and two classes of steel castings are covered, as indicated below. The grade and class desired shall be specified by the purchaser.

1.2.1 *Grade N-1*—Chemical analysis only.

1.2.2 *Grade N-2*—Heat treated but not mechanically tested.

1.2.3 *Grade U-60-30* [415-205]—Mechanically tested but not heat treated.

1.2.4 *Grades 60-30* [415-205][415-205], *-65-35* [450-240][450-240], *-70-36* [485-250][485-250],; and *70-40* [485-275]—Heat treated and mechanically tested.

1.2.5 Class 1 and Class 2 steel castings shall be specified in accordance with 9.2.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A781/A781M](#) Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use

[A957/A957M](#) Specification for Investment Castings, Steel and Alloy, Common Requirements, for General Industrial Use

3. General Conditions for Delivery

3.1 Except for steel investment castings, material furnished to this specification shall conform to the requirements of Specification [A781/A781M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification [A781/A781M](#) constitutes nonconformance with the specification. In case of a conflict between the requirements of this specification and Specification [A781/A781M](#), this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification [A957/A957M](#), including any supplementary requirements that are indicated in the purchase order. Failure to comply with the common

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved May 1, 2017/Sept. 1, 2019. Published May 2017/September 2019. Originally approved in 1901. Last previous edition approved in 2016/2017 as [A27/A27M – 13](#) (2016):[A27/A27M – 17](#). DOI: 10.1520/A0027_A0027M-17.10.1520/A0027_A0027M-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

requirements of Specification **A957/A957M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A957/A957M**, Specification **A957/A957M** shall prevail.

4. Ordering Information

- 4.1 Orders for material under this specification should include the following information in proper sequence.
- 4.1.1 Quantity,
 - 4.1.2 Specification, grade (1.2), and class (9.2),
 - 4.1.3 Description of the casting by pattern number or drawing,
 - 4.1.4 Options in the specification, and
 - 4.1.5 Supplementary requirements desired, including standards of acceptance.

5. Heat Treatment

5.1 All castings of Grades N-2, 60-30 [415-205], 65-35 [450-240], 70-36 [485-250], and 70-40 [485-275] shall be heat treated by full-annealing, normalizing, normalizing and tempering, or quenching and tempering. Unless otherwise specified in the inquiry, contract, or order, the castings may be heat treated by any one or combination of these heat treatments at the option of the manufacturer.

5.1.1 Heat treatment shall be performed after castings have been allowed to cool from the pouring temperature to below the transformation range.

5.2 Furnace temperatures for heat treating shall be regulated by the use of pyrometers.

6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 1**. Product analysis tolerances shall conform to the Product Analysis Tolerances shown in Specification **A781/A781M** or Specification **A957/A957M**. When residual element chemical content is of interest to the purchaser, S54 may be considered.

7. Tensile Properties

7.1 Except for Grades N-1 and N-2, one tension test shall be performed on each heat and the mechanical properties shall conform to the requirements specified in **Table 2**.

7.2 Test coupons may be cut from the heat-treated (if required) castings at the producer's option.

8. Retests

8.1 If any specimen is machined improperly or if flaws are revealed by machining or during testing, the specimen may be discarded and another substituted from the same heat.

8.2 At the manufacturer's option, castings may be reheat treated and retested. When castings are reheat treated, they may not be re-austenitized more than three times without the approval of the purchaser. Testing after reheat treatment shall consist of the full number of specimens taken from locations complying with the specification or order.

9. Rework and Retreatment

9.1 All welds shall be inspected to the same quality standards as were used to inspect the casting.

9.2 If postweldpost-weld heat treatment is required, Class 1 must be specified along with the grade, and the welds to be heat treated must be defined. If postweldpost-weld heat treatment is not required, Class 2 must be specified along with the grade.

10. Keywords

10.1 castings; general application; steel

TABLE 1 Chemical Requirements

Grade (UNS No.) ^A	Composition, %				
	Carbon, ^B max	Manganese, ^B max	Silicon, max	Sulfur, max	Phosphorus, max
Grade N-1 (J02500)	0.25	0.75	0.80	0.035	0.035
Grade N-2 (J03500)	0.35	0.60	0.80	0.035	0.035
Grade U-60-30 [415-205] (J02500)	0.25	0.75	0.80	0.035	0.035
Grade 60-30 [415-205] (J03000)	0.30	0.60	0.80	0.035	0.035
Grade 65-35 [450-240] (J03001)	0.30	0.70	0.80	0.035	0.035
Grade 70-36 [485-250] (J03501)	0.35	0.70	0.80	0.035	0.035
Grade 70-40 [485-275] (J02501)	0.25	1.20	0.80	0.035	0.035

^A Specify Class 1 or Class 2 in addition to grade designation (see 9.2).

^B For each reduction of 0.01 % carbon below the maximum specified, an increase of 0.04 % manganese above the maximum specified will be permitted to a maximum of 1.40 % for Grade 70-40 [485-275] and 1.00 % for the other grades.