



Designation: D6237 – 19

Standard Guide for Painting Inspectors (Concrete and Masonry Substrates)¹

This standard is issued under the fixed designation D6237; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is intended as an information aid to painting inspectors in carrying out the task efficiently. It includes the key elements of surface preparation, coatings application, and final approval for both field and shop work. The items should be selected that are pertinent to a specific project.

NOTE 1—For additional helpful information, refer to the following documents:

*Manual of Concrete Practice ACI 515R American Concrete Institute*²
*Manual of Coating Work for Light Water Nuclear Power Plant Primary Containment and Other Safety Related Facilities*³

C811 Practice for Surface Preparation of Concrete for Application of Chemical-Resistant Resin Monolithic Surfacing⁴

Steel Structures Painting Manual Vol. 1 - Good Painting Practices⁵
Steel Structures Painting Manual Vol. 2 - Systems and Specifications⁵
Manufacturers Specifications and Instructions (made available to the inspector for reference to special requirements for proper application)

Safety Data Sheets (needed to ensure that personnel take necessary precautions in handling hazardous materials). Available from Materials manufacturer.

1.2 Certain industries or owners may require certified inspection personnel. See Guide D4537 for establishing procedures to certify inspectors for coating work in nuclear facilities. SSPC offers a training and certification program for concrete coating inspection.⁵

1.3 In certain cases the inspector may be required to assess the condition of the concrete substrate. SSPC has published an illustrated guide for performing a concrete condition assessment.⁵

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

¹ This guide is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.46 on Industrial Protective Coatings.

Current edition approved Sept. 1, 2019. Published September 2019. Originally approved in 1998. Last previous edition approved in 2015 as D6237 – 09 (2015). DOI: 10.1520/D6237-19.

² Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

³ ASTM, 1979.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ Available from SSPC: The Society for Protective Coatings, 800 Trumbull Avenue, Pittsburgh, PA 15205, <http://www.sspc.org>.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.6 This guide is arranged in the following order:

	Section
Referenced Documents	2
ASTM Standards	2.1
OSHA Standards	2.2
ICRI Standards	2.3
SSPC Standards	2.4
Significance and Use	3
Preparation for Inspection	4
Surface Preparation Methods and Requirements	5
Surface Preparation	5.1
Factors Affecting Coating Performance	5.2
Surface Condition	5.2.1
Cleanliness	5.2.2
Moisture	5.2.3
Surface Preparation Procedures	5.3
Dry Surface Cleaning	5.3.1
Water and Steam Cleaning	5.3.2
Mechanical Tool Cleaning	5.3.3
Hand Tool Cleaning	5.3.3.1
Power Tool Cleaning	5.3.3.2
Scarifying Machines	5.3.3.3
Pre- and Post-Surface Preparation	5.3.3.4
Finished Surface	5.3.3.5
Blast Cleaning	5.3.4
Water Blast Cleaning	5.3.5
Acid Etching	5.3.6
Precautions in Preparing Unpainted and Previously Painted Surfaces	5.4
Inspection of Surfaces Prior to Field Painting	5.5
New Construction	5.5.1
Maintenance Repainting	5.5.2
Cracks and Voids	6
Cracks	6.1
Cracks in Concrete	6.1.1
Joints in Concrete	6.1.2
Voids	6.2
Recoat Intervals	6.3
Coating Storage and Handling	7
Storage of Coating and Thinner	7.1
Mixing of Coatings	7.2
Thinning	7.3
Thinning of Coating	7.3.1
Heating of Coating	7.4
Ambient Condition Considerations	8
Drying	8.1
Low Temperature	8.2
High Temperature	8.3
Moisture	8.4
Wind	8.5
Coating Application	9

Residual Contaminants	9.1
Quality Assurance	9.2
Film Defects	9.2.1
Brush Application	9.3
Spray Application	9.4
Roller Application	9.5
Miscellaneous Methods	9.6
Rate of Application	9.7
Additional Considerations	10
Ventilation	10.1
Painting Schedule	10.2
Film Integrity	10.3
Recoat Time	10.4
Coating System Failure	10.5
Inspection Equipment	11
General	11.1
Adhesion of Existing Coating	11.1.1
Portable Pull-Off Adhesion	11.1.2
Field Inspection Equipment	11.2
Drying and Curing Times	11.2.1
Thermometers	11.2.1.1
Psychrometric Charts	11.2.1.2
Wet-Film Thickness Gages	11.2.2
Interchemical Gage	11.2.2.1
Notched Gage	11.2.2.2
Dry-Film Thickness Gages	11.2.3
Destructive Thickness Gage	11.2.3.1
Nondestructive Film Thickness Gages	11.2.3.2
Discontinuity (Holiday) Tester	11.3
Inspection Checklist	Appendix X1

1.7 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:⁴

- C805** Test Method for Rebound Number of Hardened Concrete
- C811** Practice for Surface Preparation of Concrete for Application of Chemical-Resistant Resin Monolithic Surfacing (Withdrawn 2012)⁶
- D1212** Test Methods for Measurement of Wet Film Thickness of Organic Coatings
- D3359** Test Methods for Rating Adhesion by Tape Test
- D4138** Practices for Measurement of Dry Film Thickness of Protective Coating Systems by Destructive, Cross-Sectioning Means
- D4258** Practice for Surface Cleaning Concrete for Coating
- D4259** Practice for Preparation of Concrete by Abrasion Prior to Coating Application
- D4260** Practice for Liquid and Gelled Acid Etching of Concrete
- D4262** Test Method for pH of Chemically Cleaned or Etched Concrete Surfaces
- D4263** Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method
- D4285** Test Method for Indicating Oil or Water in Compressed Air
- D4414** Practice for Measurement of Wet Film Thickness by Notch Gages

- D4537** Guide for Establishing Procedures to Qualify and Certify Personnel Performing Coating and Lining Work Inspection in Nuclear Facilities
- D4787** Practice for Continuity Verification of Liquid or Sheet Linings Applied to Concrete Substrates
- D5064** Practice for Conducting a Patch Test to Assess Coating Compatibility
- D6132** Test Method for Nondestructive Measurement of Dry Film Thickness of Applied Organic Coatings Using an Ultrasonic Coating Thickness Gage
- D6677** Test Method for Evaluating Adhesion by Knife
- D7234** Test Method for Pull-Off Adhesion Strength of Coatings on Concrete Using Portable Pull-Off Adhesion Testers
- D7682** Test Method for Replication and Measurement of Concrete Surface Profiles Using Replica Putty
- E337** Test Method for Measuring Humidity with a Psychrometer (the Measurement of Wet- and Dry-Bulb Temperatures)
- F1869** Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride
- F2170** Test Method for Determining Relative Humidity in Concrete Floor Slabs Using in situ Probes

2.2 Occupational Safety and Health Administration (OSHA) Standard:

- 29 CFR 1926.59** Hazard Communication⁷
- 2.3 International Concrete Repair Institute (ICRI): Guideline No. 03732** Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays⁸

2.4 SSPC Standards:⁵

- SSPC-AB 1** Mineral and Slag Abrasives
- SSPC-Guide 6** Guide for Containing Debris Generated During Paint Removal Operations
- SSPC-Guide 7** Guide for the Disposal of Lead-Contaminated Surface Preparation Debris
- SSPC Guide 23** Field Methods for the Determination of Moisture in Concrete and Masonry Walls and Ceilings, EIFS, and Stucco
- SSPC-PA 7** Application of Coating to Concrete
- SSPC-PA 9** Measurement of Dry Coating Thickness Using Ultrasonic Gages
- SSPC-SP13/NACE No. 6** Surface Preparation of Concrete

3. Significance and Use

3.1 This guide is intended as a reference for those concerned with the inspection of thin- or thick-film coating application to concrete and masonry substrates. It does not cover the application of cement-type coatings. The requirements for inspection should be addressed in all protective coating and lining work specifications. This guide may be used by specification

⁶ The last approved version of this historical standard is referenced on www.astm.org.

⁷ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

⁸ Available from International Concrete Repair Institute, 3166 S. River Rd., Suite 132, Des Plaines, IL 60018, <http://www.icri.org>.

writers when selecting and establishing the inspection requirements for coating and lining specifications. A sample checklist for use by inspectors is included as Appendix X1.1.

4. Preparation for Inspection

4.1 The guide describes the duties of the inspector and discusses inspection methods, both visual and instrumental, that can be used to determine that the specification requirements have been met by the painting contractor.

4.2 Before painting is started, the project engineer should provide the inspector with information from the official plans and specifications as to surface preparation requirements, coating type, thinner to be used, mixing ratios to be used, recommended application thickness, recommended primer, tie coat, topcoat, time between coats, method of application, ambient condition restrictions, and any special precautions to be followed. These details should be recorded in an inspector's record book to eliminate any misunderstanding between the inspector and the contractor.

4.3 The inspector should obtain copies of Safety Data Sheets (SDS) for all products that will be used on the project, review any hazard communications program in accordance with 29 CFR 1926.59 that will apply to the project, and review other safety information related to the work that will be performed by the contractor. The inspector should examine these materials and be supplied with appropriate protective equipment and devices.

4.4 The Product Data Sheets (PDS) for the coating products to be used, including thinners where applicable, shall be provided with the procured product. Note that the coating specification may allow only specific pre-qualified coatings to be used.

5. Surface Preparation Methods and Requirements

5.1 *Surface Preparation* is one of the most important factors affecting the performance of coatings. The specifier determines the appropriate degree of surface preparation according to the expected service life and type of coating specified. Information on selection of surface preparation methods can be found in SSPC-SP13/NACE No. 6 and ICRI Guideline No. 03732.

5.2 *Factors Affecting Coating Performance*—There are a number of factors that must be considered to ensure a proper painting project.

5.2.1 *Surface Condition*—Concrete and masonry have unique properties associated with them due to their physical nature and method of formation. New concrete may be very smooth and hard if hard trowel finished or have cavities and holes at or just below the surface if poured. As with surface preparation of other substrates, contaminants must be removed and the surface suitably roughened. All protrusions should be removed by suitable hand or power tool technique prior to cleaning. Visible holes should be filled with a patching compound compatible with the coating to be applied.

5.2.2 *Cleanliness*—Many materials, if not removed from the surface, will affect the life of the coating. These include form release agents, surface hardeners, laitance, efflorescence,

grease, soil, fungus, mold, and mildew that make it difficult to attain proper adhesion.

5.2.3 *Moisture*—There should be no free standing water on the surface although a damp surface may be acceptable for certain types of coatings. Moisture is required to cure concrete, but after the specified cure time has passed, the inspector should check for excessive moisture below the surface as determined by Test Method D4263 or by use of a moisture meter. Many coating types will not adhere over entrapped moisture. Concrete slabs to which a floor coating will be applied are more commonly checked for moisture vapor transmission rate using the calcium chloride method as described in Test Method F1869, or in situ probes as described in Test Method F2170.

5.3 *Surface Preparation Procedures*—Safety precautions are not addressed separately for each of the following surface preparation methods. Each has its own safety-related hazards, and U.S. Occupational Health and Safety Administration regulations should be followed. Safety Data Sheets (SDS) for the solvents and cleaning compounds provided by the manufacturer should also be consulted for proper worker protection.

5.3.1 *Dry Surface Cleaning*—Broom, vacuum cleaners or a compressed air stream, or both, are used to remove surface dust and other loosely adherent solid contaminants in accordance with paragraphs 6.1 to 6.3 of Practice D4258. Compressed air should be free of water and oil. Test compressed air supply in accordance with Test Method D4285. Visually examine the surface for the presence of dust, debris and loosely adherent concrete.

5.3.2 *Water and Steam Cleaning*—These procedures are intended to remove dust, dirt, and water-soluble surface contaminants. Clean, potable water is used with sufficient pressure to remove dust, dirt, and loose material. Hand scrubbing with a stiff-bristled brush may be necessary. Visually examine the prepared surface for debris, dirt, oil, grease, loosely adherent concrete, and other contaminants. Moisture content may be determined after the surface has dried in accordance with Test Method D4263 or by use of a moisture meter.

5.3.2.1 Detergents or nonorganic solvent emulsifying agents are used with water and steam cleaning to remove oil and grease contaminants. Heavy oil grease deposits should be removed by scraping prior to cleaning. Residues of the cleaning agent should be removed by flushing the surface with clean potable water before the surface dries. Removal of the cleaning agent may be verified by measuring the surface pH in accordance with Test Method D4262.

5.3.2.2 Practice D4258, paragraphs 6.4 to 6.6 present the procedures and test methods for water and steam cleaning both with and without detergents or emulsifying agents.

5.3.3 *Mechanical Tool Cleaning*—Mechanical tool cleaning is used to remove fins and projections, laitance, glaze, efflorescence, and concrete curing compounds. It results in a sound concrete surface that is suitably roughened. Mechanical tool cleaning is presented in Practice D4259, paragraphs 6.1 to 6.5. Various techniques may be required by the specifier depending on the nature of the job.

5.3.3.1 *Hand Tool Cleaning* is one method used for the removal of loose or otherwise unsound concrete, by hand

chipping or scraping using wire, fiber or bristle brushes, hand scrapers or chisels, and chipping hammers.

(a) Wire brushes should be rigid enough to clean the surface thoroughly and shaped to penetrate all corners and joints. Brushes should be kept free of all materials that may clog the wires of the brush.

(b) Hand scrapers should be made of tool steel, tempered and ground to a sharp edge and should be of the proper size and shape to enable cleaning to be done as specified.

5.3.3.2 *Power Tool Cleaning* is a method used for the removal of loose or otherwise defective concrete and protrusions by power wire brushes, power impact tools, power grinders, power sanders or by a combination of these methods. All equipment should be suitable for the configuration of the work to be cleaned and maintained free of material that clogs the wire or disks making them ineffective. All impact tools should be kept sharp.

5.3.3.3 *Scarifying Machines* for concrete surfaces are available that either cut or chip away a thin layer. Aggregate loosened by mechanical impacting should be removed.

5.3.3.4 *Pre- and Post-Surface Preparation*—Mechanical tool cleaning requires that grease, oil and other penetrating contaminants be removed prior to cleaning and after surface preparation as described in 5.3.2.1.

5.3.3.5 *Finished Surface*—The surface is visually inspected for dirt, dust, grease, oil, and loose contaminants. The surface should have a roughened textured appearance and aggregate may be exposed. A roughness standard may be established by mutual agreement.

5.3.4 *Blast Cleaning* is used to remove foreign materials from concrete in accordance with Practice D4259 to provide a roughened surface. Blast cleaning is described in Practice D4259. Dry or wet abrasive blasting may be used or specified.

5.3.4.1 All visible oil, grease, and other contaminants should be removed prior to blast cleaning as described in 5.3.2.1. The compressed air used for blast cleaning should be free of condensed water or oil. Compressed air supply can be tested in accordance with Test Method D4285.

5.3.4.2 Blast-cleaning operations should be performed so that no damage is done to the completed portion of the work. Blast cleaning is often performed from the top to bottom of the structure and should only be carried on downwind from any recently painted areas.

5.3.4.3 Blast cleaned surfaces should be examined for any traces of oil, grease; where present, the contaminants should be removed by cleaning according to 5.3.2.1. Surfaces that have been dry blasted should be brushed with clean brushes, blown with compressed air free of oil and moisture, or vacuum cleaned to eliminate any traces of blast products, dust or dirt from the surface. This also serves to remove abrasive from pockets and corners.

5.3.4.4 The finished surface should have a roughened texture based on a roughness standard established by mutual agreement. The resulting surface texture can be assessed according to Test Method D7682, Method A or B, or using the ICRI Concrete Surface Profilers (CSPs) referenced in ICRI

Guideline No. 03732. Alternatively the surface profile can be measured using a depth micrometer that will measure up to 250 mils.

5.3.5 *Water Jetting*—A high pressure water cleaning/jetting is described in Practice D4259, Section 7. It should be noted that water introduced into the concrete will lengthen the drying time needed. The surface should have a roughened textured appearance.

5.3.6 *Acid Etching*—This method uses acids such as muriatic (hydrochloric), citric, phosphoric or sulfamic to remove foreign materials and weak surface laitance, and to roughen the surface. Acid etching is described in Practice D4260. It is only performed on horizontal surfaces.

5.3.6.1 Fins and protrusions, oil, grease, concrete curing compounds, form release agents, and concrete hardeners should be removed prior to acid etching by one or more of the techniques in 5.3.1 – 5.3.5. The surface is pre-wetted prior to application of the acid and free-standing water removed.

5.3.6.2 Bubbling should be uniformly evident after the etching solution is applied. The concentration of the etching solution may have to be increased if bubbling is not evident. Curing compounds, sealers, oil, grease, and hardeners inhibit acid etching. Areas where bubbling does not occur should be mechanically cleaned to remove these contaminants and the acid reapplied.

5.3.6.3 The surfaces should be flushed with clean potable water. Repeated flushing and scrubbing with a stiff-bristled brush may be needed to remove acid residues and perhaps neutralization. Test the surface pH in accordance with Test Method D4262 for removal of the etching solution.

5.3.6.4 The acid-etched surface should be uniformly roughened similar in appearance to a medium or coarse grade sandpaper.

5.3.6.5 It may necessary to test for moisture content in accordance with Test Method D4263 prior to applying the coating.

5.4 *Precautions in Preparing Unpainted and Previously Painted Surfaces*—Cleaning should proceed by sections, bays, or other readily identifiable parts of the work. The cleaning of each section, bay, or part of the work should be entirely completed, inspected, and accepted before any coating is applied. The system of alternately cleaning and painting short sections by one craftsman is not good practice.

5.4.1 If traffic or any other source produces an objectionable amount of dust, it is customary to control the dust by using tarpaulins, etc., for a sufficient distance around the structure and take any other precaution necessary to prevent dust and dirt from coming into contact with the cleaned or freshly painted surfaces. It may be necessary at times to use some of the specified methods for cleaning surfaces of newly applied coating between the various coats.

5.4.2 Some areas to be painted or repainted may be exposed to chemical fumes and should be washed with water before painting. Washing may also be necessary between coats of paint. If there is reason to suspect the presence of chemicals, the surfaces should be tested before applying subsequent paints.

5.4.3 Current regulations require containment and collection of surface preparation debris for disposal. When the existing coating contains regulated heavy metals such as lead or chromium, or other regulated compounds such as organotin, special precautions and handling of debris may be necessary. Inspection of containment and disposal requirements, especially site storage requirements, may be part of a coating inspector's activities. SSPC-Guide 6 and SSPC-Guide 7 present information useful to the inspector and sections of these guides may be referenced in the specification.

5.5 *Inspection of Surfaces Prior to Field Painting*—It should be emphasized that the first coat should be applied to the cleaned surfaces before any soiling or deterioration can occur. The cleaned surface should be inspected to ensure all visible contaminants have been removed. The substrate should be suitably roughened if mechanical tool cleaning, blast cleaning, water blast cleaning, or acid etching is used. Excessive roughness and exposed aggregate are just as deleterious as too smooth a finish.

5.5.1 *New Construction*—The strength of the concrete at or near the surface may affect the adhesion of the coating system. A pull-off adhesion tester as described in Test Method **D7234** may be used. Alternatively, the soundness of the concrete surface can be assessed in accordance with Test Method **C805** using a rebound hammer.

5.5.2 *Maintenance Repainting*—In most cases, maintenance painting will consist of spot-cleaning and priming of small isolated areas of deterioration followed by application of one overall new finish coat to all surfaces of the structure. The inspector of maintenance painting should be alert for several conditions not encountered in the painting of new work.

5.5.2.1 Sound coating not intended to be removed should not be damaged by cleaning operations on adjacent areas. This is particularly important with spot blast cleaning.

5.5.2.2 The junctions between sound coating and spot-cleaned areas should present a smooth, feathered appearance. The application of coating to be spot-cleaned areas should overlap the old, adjacent coating by 50 mm (2 in.) to ensure full coverage of the cleaned areas. Before the overall finish coat is applied, the inspector must verify that oil, grime, dust, and other contaminants are cleaned from the old coating surfaces.

5.5.2.3 Adhesion of the newly applied coat to the old coating should be carefully checked. Practice **D5064** presents the procedure for evaluating adhesion of maintenance coatings.

5.5.2.4 Under the direction of the engineer, the inspector may explore beneath the surface of the existing or new coating film for loosening of the old film, and where the inspector discovers such conditions, require that the surface be cleaned and repainted.

5.5.2.5 The effect of any newly applied coating on the old underlying coating should be noted. Any coating that shows curling, lifting, or wrinkling should be reported to the engineer immediately since it may have to be removed and the area repainted. If the defects are general, rather than existing in a few isolated areas, use of a different type of coating may be necessary.

6. Cracks and Voids

6.1 *Cracks* can be present in concrete or at joints in concrete and masonry. The specification should address how cracks will be prepared. Usually, this requires caulks, sealants, or fillers to be used before the coating is applied. Note that cracks may be static or dynamic. It is recommended that cracks be monitored over a 24-h period to determine their characteristics before repair.

6.1.1 *Cracks in Concrete* that are visible on the surface may require filling or sealing prior to coating. Either the specification or product data sheet for the crack filler/sealer will indicate the maximum width of crack for which the sealer can be used. A ruler or feeler gage can be used to measure crack width. Larger cracks usually require other materials or treatments, including routing out the crack. Manufacturer's instructions should be obtained and followed.

6.1.2 *Joints in Concrete and Masonry* that allow moisture or other elements to penetrate may also require caulking, sealing, or filling. Joints may also require sealing to provide a continuous surface for cosmetic reasons. Caulks, putties, and fillers are used. The inspector should ensure that all joints have been properly prepared, and that loose material has been removed. The caulk, putty, or filler should be applied in accordance with the manufacturer's instructions, including ambient condition restrictions. Expansion and control joints are designed to move. Coatings applied to these joints may crack when the joints move. The specifications should address the painting of expansion joints.

6.2 *Voids* or "bug holes" may be present in the surface or opened up by surface preparation. Voids should be filled prior to application of the coating. Note that voids may be static or dynamic. It is recommended that voids be monitored over a 24-h period to determine their characteristics before repair. In some cases, surface fillers are applied over the entire surface to seal pores and fill in voids to create a smooth surface. Limitations may exist on how deep a void can be filled, requiring multiple applications of the filler. The product data sheet for the filler should be consulted.

6.3 *Recoat Intervals* apply to crack sealers and void fillers as they do to coatings. The inspector should ensure the material cures for the minimum time before the coating is applied and the maximum recoat time, if applicable, is not exceeded.

7. Coating Storage and Handling

7.1 *Storage of Coating and Thinner*—All coatings and thinners should be stored in areas or structures that are well-ventilated and not subject to excessive heat, open flames, electrical discharge, or direct sunlight. Storage should conform to applicable regulations and the manufacturer's written instructions. Materials susceptible to damage at low temperatures should be stored to prevent freezing, such as in heated areas. Too high a storage temperature reduces the shelf life of the coating. If a coating is stocked for a considerable length of time (several months), it is desirable to invert the containers at monthly intervals. This will prevent hard settling and thus make mixing quicker and easier when the coating is used.

7.1.1 Coating containers should remain unopened until needed and the oldest should be used first. The manufacturer's

written instructions should be followed regarding shelf life. Coatings that have livered, gelled, or otherwise deteriorated during storage should not be used. If a material is in question, do not use it until it has been tested by the manufacturer or independent laboratory and found to be satisfactory.

7.1.2 Where a skin has formed in the container, the skin should be cut loose from the sides of the container, removed, and discarded. If the skins are thick enough to have a practical effect on the composition, the remaining coating should not be used until it has been tested and found to be satisfactory.

7.2 *Mixing of Coatings*—All coatings should be thoroughly and completely mixed in the containers in which they were supplied. When it is not possible to use the supplied containers other clean containers may be used. Where there is noticeable settling and mixing is done either by power stirrers or by hand, most of the vehicle should be poured off into a clean container. The pigment is then lifted from the bottom of the container with a clean broad, flat paddle, lumps broken up, and the pigment thoroughly mixed with the vehicle present. The poured-off vehicle should be returned slowly to the original container with simultaneous stirring. It is also useful at this point to mix or pour repeatedly from one container to another (boxing) until the composition is uniform. The bottom of the original container should be inspected for the unmixed pigment. Two component coatings should be mixed by agitation only, and not by boxing. After the individual components are homogenous, they are intermixed with agitation in the order stated in the manufacturer's instructions, that is, add Part B to Part A.

7.2.1 Some coatings may require straining after mixing to ensure homogeneity and to remove skins and foreign matter. The strainers should be of a type to remove only skins, etc., but not to remove pigment. For example, a 297 μm (50-mesh) strainer is normally satisfactory for most coatings unless some specific size is required in the specification. Containers should be covered when not in use, to reduce volatile losses and skinning.

7.2.2 Coatings should be agitated enough during application to ensure homogeneity. Some materials may even require constant agitation during use.

7.2.3 Coating materials that cure by chemical reaction may require an induction time to allow the components to partially react prior to thinning or application.

7.2.4 The components of plural component coatings should be thoroughly mixed as described in 7.2, and then pre-heated to the temperature recommended by the coating manufacturer. The two components are subsequently pumped in the required volume ratio by plural component equipment through heated or insulated hoses to specialized mixing equipment located immediately before the spray gun.

7.3 *Thinning*—Some specifications permit field thinning of coatings while others do not. This section describes some commonly accepted procedures when thinning is permitted.

7.3.1 *Thinning of Coating*—All additions of thinner should be made in the presence of the inspector and only amounts or types of thinner permitted by the specification or manufacturer, or both, should be added. Thinning is carried out by pouring about half of the thoroughly mixed coating into an empty, clean

container. The required thinner is then added and the two portions are remixed to obtain a homogenous mixture.

7.3.1.1 To estimate the wet-film thickness of the thinned coating required to obtain the specified dried-film thickness, the percent volume of the nonvolatile (solids) in the original coating must be known. This figure is readily obtained from the manufacturer's product data sheet. With this information the calculation may be made as follows:

$$W = \frac{D(1.0+T)}{S} \quad (1)$$

where:

W = wet-film thickness,

D = desired dry-film thickness,

S = percent by volume (expressed as a fraction) of coating solids, and

T = percent by volume (expressed as a fraction) of thinner added.

7.4 *Heating of Coating*—Coating as delivered in the manufacturer's containers and mixed thoroughly, are ready for use, unless the specification permits on-site thinning of high-viscosity material. When the temperature of the liquid coating is low (below 10°C (50°F)) the consistency (viscosity) may increase to the point that application is difficult. Where thinning is not permitted, the coating may be heated. Should the contractor wish to reduce the viscosity by heating to make application easier, the containers may be warmed in hot water, on steam radiators by storing in a warm room, or by other acceptable indirect heating processes. In-line heaters are also available for application equipment. Direct application of flame to the containers is forbidden by fire regulations. It should be noted, however, that heating of the coating alone will not compensate for ambient or surface temperatures, or both, that are below the minimum specified for that material. For products to be applied by plural component spray this section does not apply. See 7.2.4.

8. Ambient Condition Considerations

8.1 *Drying*—It is well known that most coatings will not dry properly at low temperatures and/or high relative humidity, nor will they perform well if applied over wet surfaces. Temperature limitations presented in the specification or manufacturer's product data sheet are mandatory.

8.2 *Low Temperature*—Many specifications indicate temperature limits between which painting may be undertaken. The typical minimum temperature (air, material and surface) is usually 5°C (40°F) but may be as low as -18°C (0°F) for "cold-curing" one or two component systems, or 10°C (50°F) for conventional two component systems. The requirements may state further that painting should not be undertaken when the temperature is dropping and within 3°C (5°F) of the lower limit. However, some authorities believe that some coatings may be applied at (or below) 0°C (32°F) without adverse effects. Within the limitations of the composition of the coating, this may be satisfactory depending upon the type of coating and providing the surface is dry. Painting over ice or frost will result in early adhesion failure of the coating.