

Edition 3.0 2023-02

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Fixed capacitors for use in electronic equipment –

Part 23: Sectional specification – Fixed metallized polyethylene naphthalate film dielectric surface mount DC capacitors

Condensateurs fixes utilisés dans les équipements électroniques – Partie 23: Spécification intermédiaire – Condensateurs fixes pour montage en surface pour courant continu à diélectrique en film de polynaphtalate d'éthylène métallisé





## THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2023 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat Tel.: +41 22 919 02 11

3, rue de Varembé info@iec.ch CH-1211 Geneva 20 www.iec.ch

Switzerland

#### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

#### **About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

#### IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

#### IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

#### IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

#### Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

#### A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Recherche de publications IEC -

#### webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

#### IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

#### Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

#### Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.



Edition 3.0 2023-02

## INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Fixed capacitors for use in electronic equipment –

Part 23: Sectional specification – Fixed metallized polyethylene naphthalate film dielectric surface mount DC capacitors

Condensateurs fixes utilisés dans les équipements électroniques – Partie 23: Spécification intermédiaire – Condensateurs fixes pour montage en surface pour courant continu à diélectrique en film de polynaphtalate d'éthylène métallisé

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 31.060.10 ISBN 978-2-8322-6341-9

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

### CONTENTS

Ε(	JKEWORL	)	5		
1	Scope				
2	Normative references				
3	Terms a	and definitions	8		
4		ed ratings and characteristics			
		referred climatic categories			
		referred values of ratings			
	4.2.1	Nominal capacitance $(C_{\mathbf{N}})$			
	4.2.2	Tolerance on nominal capacitance			
	4.2.3	Rated voltage ( $U_{R}$ )			
	4.2.4	Category voltage ( $U_{\mathbf{C}}$ )			
_	4.2.5	Rated temperature			
5		d measurement procedures			
		eneral			
		ounting			
	5.2.1	Initial inspections			
	5.2.2	Mounting method			
	5.2.3	Final inspections after mounting			
	5.3 Vi 5.3.1	sual examination and check of dimensions			
	5.3.1 5.3.2	Visual examination and check of dimensions			
	5.3.3	Requirements			
		ectrical tests			
	5.4.1	Voltage proof			
	5.4.2	Capacitance			
	5.4.3	Tangent of loss angle (tan $\delta$ )			
	5.4.4	Insulation resistance			
	5.5 SI	near test	13		
	5.5.1	General	13		
	5.5.2	Final inspections	13		
	5.6 St	ubstrate bending test	14		
	5.6.1	General	14		
	5.6.2	Initial inspections	14		
	5.6.3	Final inspections and requirements	14		
	5.7 R	esistance to soldering heat	14		
	5.7.1	General	14		
	5.7.2	Initial inspections			
	5.7.3	Test conditions			
	5.7.4	Recovery			
	5.7.5	Final inspections and requirements			
		olderability			
	5.8.1	General			
	5.8.2	Test conditions			
	5.8.3	Final inspections and requirements			
		apid change of temperature			
	5.9.1	General	15		

	5.9.2	2 Initial inspections	15
	5.9.3	B Test conditions	15
	5.9.4	Final inspections and requirements	15
	5.10	Climatic sequence	15
	5.10.	.1 General	15
	5.10.	.2 Initial inspections	15
	5.10.	.3 Dry heat	15
	5.10.	.4 Damp heat, cyclic, test Db, first cycle	16
	5.10.	.5 Cold	16
	5.10.	.6 Damp heat, cyclic, test Db, remaining cycles	16
	5.10.	.7 Recovery	16
	5.10.	.8 Final inspections and requirements	16
	5.11	Damp heat, steady state	16
	5.11.	.1 General	16
	5.11.	.2 Initial inspections	16
	5.11.	.3 Test conditions	16
	5.11.	.4 Recovery	16
	5.11.	.5 Final inspections and requirements	16
	5.12	Endurance	17
	5.12.	.1 General	17
	5.12.	.2 Initial inspections	17
	5.12.		
	5.12.	.4 Final inspections and requirements	17
	5.13	Charge and discharge	
	5.13.	.1 General <u>IEC 60384-23.2023</u>	17
	5.13.	.2 <sub>ind</sub> Initial inspections	18
	5.13.	.3 Test conditions	18
	5.13.	.4 Recovery	18
	5.13.	'	
	5.14	Component solvent resistance (if required)	18
	5.14.		
	5.14.	.2 Final inspections and requirements	18
	5.15	Solvent resistance of marking (if applicable)	18
	5.15.		
	5.15.	.2 Final inspections and requirements	18
6	Marki	king	18
	6.1	General	18
	6.2	Information for marking	19
	6.3	Marking on capacitors	19
	6.4	Marking on packaging	19
7	Inforr	mation to be given in a detail specification	19
	7.1	General	19
	7.2	Outline drawing and dimensions	19
	7.3	Mounting	20
	7.4	Ratings and characteristics	
	7.4.1	General	20
	7.4.2	Nominal capacitance range	20
	7.4.3	·	
	7.4.4	Soldering	20

7.5 Marking	20
8 Quality assessment procedures	20
8.1 Primary stage of manufacture	20
8.2 Structurally similar components	20
8.3 Certified test records of released lots	21
8.4 Qualification approval procedures	
8.4.1 General	
8.4.2 Qualification approval on the basis of the fixed sample size proce	
Annex A (normative) Quality conformance inspection	29
A.1 Formation of inspection lots	29
A.1.1 Groups A and B inspection	29
A.1.2 Group C inspection	
A.2 Test schedule	
A.3 Delayed delivery	
A.4 Assessment levels	
Annex X (informative) Cross-references to the previous edition of this document	
Bibliography	37
Table 4. Business Profit of the control of the cont	•
Table 1 – Percentage limit of the rated voltage at AC voltage frequency	
Table 2 – Test voltages	
Table 3 – Tangent of loss angle limits	
Table 4 – Requirements regarding insulation resistance	13
Table 5 – Correction factor dependent on temperature	13
Table 6 - Endurance test conditions for Grade 1 and Grade 2 capacitors	
Table 7 – Endurance test conditions for Grade 3 capacitors	<sup>14538b/iec-</sup> 17
Table 8 – Test and sampling plan for qualification approval Assessment level EZ	
Table 9 – Test schedule for qualification approval	23
Table A.1 – Lot-by-lot inspection	30
Table A.2 – Periodic inspection	31
Table X.1 – Cross-reference	36

#### INTERNATIONAL ELECTROTECHNICAL COMMISSION

#### FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT -

# Part 23: Sectional specification – Fixed metallized polyethylene naphthalate film dielectric surface mount DC capacitors

#### **FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60384-23 has been prepared by IEC technical committee 40: Capacitors and resistors for electronic equipment. It is an International Standard.

This third edition cancels and replaces the second edition published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) this edition includes the following significant technical changes with respect to the previous edition: revision of all parts of the document based on the ISO/IEC Directives, Part 2:2021, and harmonization with other similar kinds of documents:
- b) the document structure has been organized to follow new sectional specification structure decided in TC 40:
- c) revised tables and Clause 5 so as to prevent duplications and contradictions;

- d) in Subclause 5.2 (Mounting), the Subclauses 5.2.1, 5.2.2 and 5.2.3 have been added;
- e) in Subclause 5.5 (Shear test), the Subclauses 5.5.1 and 5.5.2 have been added;
- f) in Subclause 5.14 (Component solvent resistance), the Subclauses 5.14.1 and 5.14.2 have been added. In Table 8 and Table A.2, test 5.14 has been moved before 5.7.5 (Final inspections and requirements) in Group 1A and in Subgroup C1;
- g) In Subclause 5.15 (Solvent resistance of marking), the Subclauses 5.15.1 and 5.15.2 have been added:
- h) tangent of loss angle measurement has been added to the resistance to soldering heat test;
- i) lot-by-lot and periodical inspection tables including requirements have been moved to Annex A;
- j) revised Inspection Level (IL) of A1 subgroup.

The text of this International Standard is based on the following documents:

Draft	Report on voting
40/2983/FDIS	40/3019/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

The list of all parts of the IEC 60384 series, under the general title *Fixed capacitors for use in electronic equipment*, can be found on the IEC web site.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at <a href="https://www.iec.ch/members\_experts/refdocs">www.iec.ch/members\_experts/refdocs</a>. The main document types developed by IEC are described in greater detail at <a href="https://www.iec.ch/publications">www.iec.ch/publications</a>.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

#### FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT -

# Part 23: Sectional specification – Fixed metallized polyethylene naphthalate film dielectric surface mount DC capacitors

#### 1 Scope

This part of IEC 60384 is applicable to fixed surface mount capacitors for direct current, with metallized electrodes and polyethylene naphthalate dielectric for use in electronic equipment. These capacitors have metallized connecting pads or soldering strips and are intended to be mounted directly onto printed boards or onto substrates for hybrid circuits. These capacitors can have "self-healing properties" depending on conditions of use. They are primarily intended for applications where the AC component is small with respect to the rated voltage.

This part of IEC 60384 specifies preferred ratings and characteristics, selects from IEC 60384-1:2021 the appropriate quality assessment procedures, tests and measuring methods and gives general performance requirements for this type of capacitor. Test severities and requirements specified in detail specifications referring to this sectional specification are of an equal or higher performance level. Lower performance levels are not permitted.

Capacitors for electromagnetic interference suppression are not included, but are covered by IEC 60384-14.

#### 2 Normative references

IEC 60384-23:2023

https://standards.iteh.ai/catalog/standards/sist/8b26e96a-c24e-496f-8ee0-6ccdd2d4538b/iec-

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60062, Marking codes for resistors and capacitors

IEC 60063, Preferred number series for resistors and capacitors

IEC 60068-1:2013, Environmental testing – Part 1: General and guidance

IEC 60384-1:2021, Fixed capacitors for use in electronic equipment – Part 1: Generic specification

IEC 61193-2:2007, Quality assessment systems – Part 2: Selection and use of sampling plans for inspection of electronic components and packages

ISO 3, Preferred numbers – Series of preferred numbers

#### Terms and definitions

For the purposes of this document, the terms and definitions of IEC 60384-1:2021,and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at https://www.electropedia.org/
- ISO Online browsing platform: available at https://www.iso.org/obp

#### 3.1

#### grade 1 capacitors

capacitors for long-life applications with stringent requirements for the electrical parameters

#### 3.2

#### grade 2 capacitors

<general purpose> capacitors for general applications for which the stringent requirements for grade 1 capacitors are not necessary

#### 3.3

#### grade 3 capacitors

<low temperature, miniature type> miniature type capacitors having a rated temperature of 85°C and for which less stringent requirements than for grade 2 capacitors are acceptable

#### Preferred ratings and characteristics

### Preferred climatic categories [EC 60384-23:2023

The values given in detail specifications should be selected from the following.

The surface mount capacitors covered by this document are classified into climatic categories according to the general rules given in IEC 60068-1:2013, Annex A.

The lower and upper category temperature and the duration of the damp heat, steady-state test shall be chosen from the following:

-55 °C, -40 °C and -25 °C. Lower category temperature:

Upper category temperature: +85 °C (only grade 3), +100 °C, +125 °C and +155 °C.

Duration of the damp heat, steady state test: 21 days and 56 days.

At continuous operation at 155 °C beyond the endurance test time, accelerated ageing shall be carried out (see detail specification).

The severities for the cold and dry heat tests are the lower and upper category temperatures, respectively.

#### Preferred values of ratings 4.2

#### 4.2.1 Nominal capacitance $(C_N)$

Preferred values of nominal capacitance shall be taken from the E6 series of IEC 60063:

1,0-1,5-2,2-3,3-4,7 and 6,8 and their decimal multiples (×  $10^n$ , n = integer).

If other values are required, they should be chosen from the E12 series.

#### 4.2.2 Tolerance on nominal capacitance

The preferred tolerances on the nominal capacitance are  $\pm 5$  %,  $\pm 10$  % and  $\pm 20$  %.

#### 4.2.3 Rated voltage $(U_R)$

The preferred values of rated voltage shall be taken from R10 series of ISO 3 are:

1.0 - 1.6 - 2.5 - 4.0 - 5.0 - 6.3 and their decimal multiples (×  $10^{n}$ , n: integer).

The sum of the DC voltage and the peak AC voltage applied to the capacitor shall not exceed the rated voltage.

The value of the peak AC voltage shall not exceed the percentages of the rated voltage at the frequencies stated in Table 1 and should not be greater than 280 V, unless otherwise specified in the detail specification.

Table 1 - Percentage limit of the rated voltage at AC voltage frequency

AC voltage frequency	Percentage limit of the rated voltage		
iTeh SHZ AND A	2D PRF%/IFW		
50	20		
100 tandard	siteh a 15		
1 000	3		
10 000 IEC 6038	L-23-2023 1		

https://standards.iteh.ai/catalog/standards/sist/8h26e96a-c24e-496f-8ee0-6ccdd2d4538b/iec

#### 4.2.4 Category voltage $(U_{\rm C})$

The category voltage for Grade 1 and Grade 2 capacitors is:

- for upper category temperature 125 °C: 0,8  $U_{\rm R}$ ;
- for upper category temperature 155 °C: 0,5  $U_{\rm R}$ .

The category voltage for Grade 3 capacitors is:

- for upper category temperature 100 °C: 0,8  $U_{\rm R}$ ;
- for upper category temperature 125 °C: 0,5  $U_{\rm R}$ .

#### 4.2.5 Rated temperature

Grade 1 and Grade 2 capacitors

The standard value of rated temperature is 100 °C.

Grade 3 capacitors

The standard value of rated temperature is 85 °C.

#### 5 Test and measurement procedures

#### 5.1 General

This Clause 5 supplements the information given in the relevant clauses of IEC 60384-1:2021.

#### 5.2 Mounting

#### 5.2.1 Initial inspections

The capacitance shall be measured in accordance with 5.4.2.

The tangent of loss angle shall be measured in accordance with 5.4.3.

#### 5.2.2 Mounting method

See IEC 60384-1:2021, 5.5.

#### 5.2.3 Final inspections after mounting

After recovery, the capacitors shall be visually examined and measured and shall meet the requirements given in Table 9.

The measurement values are used as initial inspection values in subgroups 3.1, 3.2, 3.3 and 3.4 in Table 8 and in subgroups C3.1, C3.2, C3.3 and C3.4 in Table A.2.

#### 5.3 Visual examination and check of dimensions

#### 5.3.1 General

See IEC 60384-1:2021, 7.1 with the details of 5.3.2 and 5.3.3. 961-8ee0-6ccdd2d4538b/iec-

#### 5.3.2 Visual examination and check of dimensions

Visual examination shall be carried out with equipment with approximately 10× magnification and lighting appropriate to the specimen under test and the quality level required.

The operator should have available facilities for incident or transmitted illumination as well as an appropriate measuring facility.

#### 5.3.3 Requirements

The capacitors shall be examined to verify that the materials, design, construction, physical dimensions and workmanship are in accordance with the applicable requirements given in the detail specification.

#### 5.4 Electrical tests

#### 5.4.1 Voltage proof

#### 5.4.1.1 General

See IEC 60384-1:2021, 6.2 with the details of 5.4.1.2, 5.4.1.3 and 5.4.1.4.

#### 5.4.1.2 Test circuit

Delete the capacitor C<sub>1</sub>.

The product of  $R_1$  and the nominal capacitance of the capacitor under test  $(C_X)$  shall be smaller than or equal to 1 s and greater than 0,01 s.

 $R_1$  includes the internal resistance of the power supply.

 $R_2$  shall limit the discharge current to a value equal to or less than 1 A.

#### 5.4.1.3 Test conditions

The voltages given in Table 2 shall be applied between terminals, the measuring points 1a) of IEC 60384-1:2021, Table 3, for a duration of 1 min for qualification approval testing and for a duration of 1 s for the lot-by-lot quality conformance testing.

Table 2 – Test voltages

Measuring point	Test voltage
	Grade 1: 1,6 $U_{R}$
1a)	Grade 2: 1,4 $U_{R}$
	Grade 3: 1,4 $U_{R}$

## 5.4.1.4 Requirements TANDARD PREVIEW

There shall be no breakdown or flashover during the test.

NOTE The occurrence of self-healing breakdowns during the application of the test voltages is allowed.

#### 5.4.2 Capacitance

s iteh ai/catalog/standards/sist/8b26e96a-c24e-496f-8ee0-6ccdd2d4538b/iec-

#### **5.4.2.1** General

See IEC 60384-1:2021, 6.3 with the details of 5.4.2.2 and 5.4.2.3.

#### 5.4.2.2 Measuring conditions

The capacitance shall be measured at, or corrected to, a frequency of 1 kHz. For nominal capacitance values > 10  $\mu$ F, 50 Hz to 120 Hz may be used.

The applied peak voltage at 1 kHz shall not exceed 3 % of the rated voltage, and the applied peak voltage at 50 Hz to 120 Hz shall not exceed 20 % of the rated voltage with a maximum of 100 V (70 V RMS).

#### 5.4.2.3 Requirements

The capacitance shall be within the specified tolerance.

#### 5.4.3 Tangent of loss angle (tan $\delta$ )

#### 5.4.3.1 **General**

See IEC 60384-1:2021, 6.4 with the details of 5.4.3.2, 5.4.3.3, 5.4.3.4 and 5.4.3.5.

#### 5.4.3.2 Measuring conditions for measurements at 1 kHz

The test conditions are as follows:

Frequency: 1 kHz;

Peak voltage: ≤ 3 % of the rated voltage;

- Inaccuracy:  $\leq 10 \times 10^{-4}$  (absolute value).

#### 5.4.3.3 Requirement for measurements at 1 kHz

Tan  $\delta$  shall not exceed the applicable values shown in Table 3.

Table 3 – Tangent of loss angle limits

Nominal capacitance	Tan $\delta$ (absolute value)				
μF	Grade 1 capacitors	Grade 2 capacitors	Grade 3 capacitors		
≤ 1	0,006	0,010	0,010		
> 1	0,007	0,010	0,010		

#### 5.4.3.4 Measuring conditions for measurements at 10 kHz

For capacitors with  $C_N \le 1 \mu F$ ,  $\tan \delta$  shall be in addition measured when required in Table 9 for certain tests.

- Frequency: 10 kHz; and ards.iteh.ai)

Voltage: 1 V RMS;

Inaccuracy: ≤ 10 × 10<sup>-4</sup> (absolute value). no 2

## 5.4.3.5 Requirement for measurements at 10 kHz c24e-496f-8ee0-6ccdd2d4538b/iec-

Tangent of loss angle shall be as stated in the detail specification.

#### 5.4.4 Insulation resistance

#### 5.4.4.1 General

See IEC 60384-1:2021, 6.1 with the details of 5.4.4.2 and 5.4.4.3.

#### 5.4.4.2 Measuring conditions

Prior to the test, capacitors shall be carefully cleaned to remove any contamination. Cleanliness shall be maintained in the test chambers and during post-test measurements.

Before the measurement, the capacitors shall be fully discharged. The product of the resistance of the discharge circuit and the nominal capacitance of the capacitor under test shall be  $\geq 0.01$  s or any other value stated in the detail specification.

The measuring conditions shall be in accordance with IEC 60384-1:2021, 6.1.2. The measuring points shall be in accordance with IEC 60384-1:2021, Table 3.

The voltage shall be applied immediately at the correct value through the internal resistance of the voltage source.

The product of the internal resistance and the nominal capacitance of the capacitor shall be smaller than 1 s or any other value stated in the detail specification.

#### 5.4.4.3 Requirements

The insulation resistance shall meet the requirements of Table 4. However, in lot-by-lot quality conformance testing, the measurement may be interrupted at the time when the limits of Table 4 have been reached, which can be within 60 s.

Table 4 - Requirements regarding insulation resistance

Minimal $RC$ product $(R = \text{insulation resistance between the terminations})$ $(C = \text{nominal capacitance } C_N)$			Minimum insulation resistance between the terminations				
	s			ΜΩ			
	C <sub>N</sub> > 0,33 μF			C <sub>N</sub> ≤ 0,33 μF			
Rated voltage							
> 100 V		≤ 10	00 V	> 10	00 V	≤ 10	00 V
Grade:							
1	2,3	1	2,3	1	2,3	1	2,3
10 000	400	5 000	400	30 000	1 000	15 000	1 000

NOTE  $M\Omega$  is used instead of the correct unit  $G\Omega$  for the convenience of the user to calculate the time constant correctly, and from historical reasons.

When the test is carried out at a temperature other than 20 °C, the result shall, when necessary, be corrected to 20 °C by multiplying the result of the measurement by the appropriate correction factor. In case of doubt, the measurement at 20 °C is decisive. The correction factors given in Table 5 can be considered as average values for metallized polyethylene naphthalate film capacitors.

https://standards.iteh.ai/catalog/standards/sist/8b26e96a-c24e-496f-8ee0-6ccdd2d4538b/iec-

Table 5 - Correction factor dependent on temperature

Temperature	Correction factor
°C	
15	0,75
20	1,00
23	1,15
27	1,35
30	1,50
35	1,75

#### 5.5 Shear test

#### 5.5.1 General

See IEC 60384-1:2021, 7.7.

#### 5.5.2 Final inspections

The capacitors shall be visually examined and shall meet the requirements given in Table 9 or Table A.2.