



Designation: D3969 – 01 (Reapproved 2019)<sup>ε1</sup>

## Standard Test Method for Zirconium in Paint Driers by EDTA Method<sup>1</sup>

This standard is issued under the fixed designation D3969; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Footnote 4 title updated to current edition in October 2019.

### 1. Scope

1.1 This test method covers the titrimetric determination of zirconium in zirconium driers used in the coatings industry and utilizes the disodium salt of ethylenediaminetetraacetic acid dihydrate (EDTA).

1.2 This test method is limited to the determination of the zirconium content of a liquid zirconium drier that does not contain other drier elements. The test method is not applicable to drier blends and does not differentiate hafnium from zirconium.

1.3 All cations that can be titrated with EDTA in acid media interfere and must not be present in the sample.

1.4 This test method has been tested for concentrations of 6 and 12 % zirconium, but there is no reason to believe that it is not suitable for higher or lower zirconium concentrations, provided specimen size is adjusted proportionately.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Oct. 1, 2019. Published October 2019. Originally approved in 1980. Last previous edition approved in 2012 as D3969 – 01 (2012). DOI: 10.1520/D3969-01R19E01.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D600 Specification for Liquid Paint Driers

D1193 Specification for Reagent Water

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)<sup>3</sup>

E300 Practice for Sampling Industrial Chemicals

### 3. Summary of Test Method

3.1 The zirconium drier is digested with concentrated sulfuric acid and 30 % hydrogen peroxide to destroy all organic matter. The diluted solution is boiled with an excess of EDTA, the pH adjusted, and the excess titrated with bismuth nitrate using xylenol orange as the indicator.

### 4. Significance and Use

4.1 The amount of zirconium drier used in oxidizing-type coatings significantly affects their drying properties. This test method may be used to confirm the stated content of a pure liquid zirconium drier manufactured for use by the coatings industry.

### 5. Apparatus

5.1 *Centrifuge*, capable of developing 1000 to 2000 g.

### 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).