



Designation: B651 – 83 (Reapproved 2019)

# Standard Test Method for Measurement of Corrosion Sites in Nickel Plus Chromium or Copper Plus Nickel Plus Chromium Electroplated Surfaces with Double-Beam Interference Microscope<sup>1</sup>

This standard is issued under the fixed designation B651; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method provides a means for measuring the average dimensions and number of corrosion sites in an electroplated decorative nickel plus chromium or copper plus nickel plus chromium coating on steel after the coating has been subjected to corrosion tests. This test method is useful for comparing the relative corrosion resistances of different electroplating systems and for comparing the relative corrosivities of different corrosive environments. The numbers and sizes of corrosion sites are related to deterioration of appearance. Penetration of the electroplated coatings leads to appearance of basis metal corrosion products.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**B487 Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section**

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.05 on Decorative Coatings.

Current edition approved Oct. 1, 2019. Published October 2019. Originally approved in 1978. Last previous edition approved in 2015 as B651 – 83(2015). DOI: 10.1520/B0651-83R19.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Summary of Test Method

3.1 The depths and diameter of corrosion pits or the widths of corrosion crevices, and the number of pits per square millimetre or crevices per linear millimetre on a specimen surface, are determined using optical aids (magnifier, microscope, and interference microscope). The values are compared to dimensions and numbers of corrosion sites obtained from other specimens.

## 4. Significance and Use

4.1 Different electroplating systems can be corroded under the same conditions for the same length of time. Differences in the average values of the radius or half-width or of penetration into an underlying metal layer are significant measures of the relative corrosion resistance of the systems. Thus, if the pit radii are substantially higher on samples with a given electroplating system, when compared to other systems, a tendency for earlier failure of the former by formation of visible pits is indicated. If penetration into the semi-bright nickel layer is substantially higher, a tendency for earlier failure by corrosion of basis metal is evident.

## 5. Apparatus

5.1 *Double-Beam Interference Microscope* (lateral magnification about 100 $\times$ ), capable of producing, with white light, a visible group of interference fringes, and equipped with a calibrated fine focus and a graduated bifilar (movable cross hair) eyepiece.

5.2 *Magnifier or Microscope* (10 $\times$  to 20 $\times$ ), with light source.

5.3 *Rule*, graduated in millimetres, and a *scriber* for producing visible lines on the specimen surface.

5.4 *Microscope*, with a magnification capability of 500 $\times$ , equipped with a bifilar eyepiece, for making measurements on opaque surfaces.

5.5 Equipment for mounting and polishing of specimens for microscopical cross-sectional measurements.