



Designation: E2575 – 19

Standard Test Method for Determination of Oxygen in Copper and Copper Alloys by Inert Gas Fusion¹

This standard is issued under the fixed designation E2575; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of oxygen in copper and copper alloys from 0.00035 % to 0.090 %.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory

E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Inert Gas Fusion Techniques

E1601 Practice for Conducting an Interlaboratory Study to Evaluate the Performance of an Analytical Method

¹ This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.05 on Cu, Pb, Zn, Cd, Sn, Be, Precious Metals, their Alloys, and Related Metals.

Current edition approved June 15, 2019. Published August 2019. Originally approved in 2008. Last previous edition approved in 2008 as E2575–08, which was withdrawn January 2017 and reinstated in June 2019. DOI: 10.1520/E2575-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *IEEE/ASTM Standard:*²

IEEE/ASTM SI 10 American National Standard for Use of the International System of Units (SI): The Modern Metric System

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology E135.

4. Summary of Test Method

4.1 This test method is intended for use with commercially available inert gas fusion determinators.

4.2 The test specimen is fused in a graphite crucible under a flowing inert gas stream of argon (Ar), helium (He), or nitrogen (N₂) at a temperature sufficient to release oxygen. Oxygen from the specimen combines with carbon from the crucible to form carbon monoxide (CO). The detector output is converted to the mass fraction of oxygen in the specimen using a previously established calibration. Depending on the instrument design, CO is oxidized to carbon dioxide (CO₂) or left as CO and swept by the inert gas stream into an infrared detector.

4.3 In a typical instrument based on infrared detection the evolved gases are swept into an infrared cell through which infrared energy is transmitted. The CO in the gas stream absorbs some of the transmitted infrared energy and the decrease in the energy reaching the detector is processed and displayed directly as percent oxygen. Some instruments oxidize the CO to CO₂, which is subsequently measured by an infrared cell designed to measure CO₂.

5. Significance and Use

5.1 This test method is primarily intended as a referee test for compliance with compositional specifications. It is assumed that all who use this test method will be trained analysts, capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory.

6. Interferences

6.1 The elements usually present in copper and its alloys do not interfere.

7. Apparatus

7.1 *Instrument*—Fusion and measurement apparatus consisting of an electrode furnace, provision for scrubbing impurities from analytical gas stream, infrared measurement system, and auxiliary gas purification systems (see **Note 1**).

NOTE 1—Several models of commercial oxygen determinators are available and presently in use by industry. Each has its own unique design characteristics and operational requirements. Consult the instrument manufacturer's manual for operational details.

7.2 *Graphite Crucibles*—The crucibles must be made of high-purity graphite as recommended by the instrument manufacturer and be of the dimensions recommended by the instrument manufacturer.

7.3 *Tweezers*—, used to handle samples during the preparation process.

7.4 *Balance*—Measurement apparatus with capacity up to 10 g capable of weighing ± 0.1 mg accurately or as specified by the instrument manufacturer.

8. Reagents and Materials

8.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

8.2 *Graphite Powder/Carbon Black*—High-purity graphite powder or carbon black specified by the instrument manufacturer.

8.3 *Inert Gas*—Use the purity and type (Ar, He, or N₂) specified by the instrument manufacturer.

8.4 *Magnesium Perchlorate (Mg(ClO₄)₂)—Anhydrous*—Used as a moisture trap. Use purity specified by the instrument manufacturer.

8.5 *Rare Earth/Copper Oxide*—Reagent used in some instruments to oxidize CO to CO₂. Use purity specified by the instrument manufacturer.

8.6 *Sodium Hydroxide Impregnated Clay*—Used to absorb CO₂ in the inert gas stream. Use purity specified by the instrument manufacturer.

8.7 *Methanol*—Used in sample preparation, see Section 10.

8.8 *Copper Pickle Solution*—Prepare a fresh solution of equal parts of concentrated HNO₃, concentrated CH₃OOH, and concentrated H₃PO₄. Used in sample preparation, see Section 10.

8.9 *Hydrochloric Acid (HCl)*—Used in sample preparation, see Section 10.

9. Hazards

9.1 For hazards to be observed in the use of certain reagents in this test method refer to Practice E50.

9.2 Use care when handling hot crucibles and operating furnaces to avoid injury by either burn or electrical shock.

10. Sampling and Sample Preparation

10.1 Use only solid samples to minimize the potential for errors due to surface oxidation. Samples must be of the proper size to permit free introduction into the sample-loading device of the instrument. Sample mass range should be 0.5 g to 2.0 g. Refer to instrument manufacturer's recommendations.

10.2 Cut the sample to an appropriate size using a silicon carbide, water-cooled cut-off wheel or by other means that will avoid overheating. Avoid oxide cutting or abrading materials.

10.3 Etch sample with concentrated HCl at 20 °C for three minutes.

10.4 Etch sample in the copper pickle solution at 70 °C for one minute.

10.5 Rinse sample in three successive distilled water rinses.

10.6 Rinse sample in three successive methanol rinses.

10.7 Dry in a stream of hot air (hair dryer).

10.8 Do not touch sample with fingers during and following the final stages of cleaning. Store the prepared sample in a desiccator. If samples are not analyzed within four hours of preparation, repeat 10.3 – 10.7 prior to analysis.

10.9 Careful adherence to the sample preparation procedure described above is critical to obtaining accurate and unbiased results. The use of small and irregular shaped samples requires a diligent effort to ensure that all surface contamination has been removed.

11. Preparation of Apparatus

11.1 Assemble the apparatus as recommended by the manufacturer. Make the required power, gas, and water connections. Turn on the instrument and allow sufficient time to stabilize the system.

11.2 Change the chemical reagents and filters as required. Test the furnace and the analyzer to insure the absence of leaks. Make a minimum of two determinations using a sample as directed in Section 13 to condition the instrument before attempting to calibrate the system or to determine the value of the blank.

11.3 Calibrate the balance as recommended by the manufacturer using internal or external calibration traceable to the SI (see IEEE/ASTM SI 10).

12. Calibration

12.1 *Calibration Reference Materials* Use only copper or copper alloy reference materials. Select four reference materials containing approximately 0.0004 %, 0.01 %, 0.03 %, and 0.06 % oxygen and designate them as A, B, C, and D respectively.

³ "Reagent Chemicals, American Chemical Society Specifications," American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.