



Designation: **A1069/A1069M – 16 A1069/A1069M – 19**

## Standard Specification for Laser-Fused Laser and Laser Hybrid Welded Stainless Steel Bars, Plates, and Shapes<sup>1</sup>

This standard is issued under the fixed designation A1069/A1069M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This specification covers laser-fused laser and laser hybrid welded austenitic, ferritic, and duplex (ferritic-austenitic) stainless steel bars, plates, and shapes of structural quality for use in bolted or welded structural applications.

NOTE 1—The term laser fusion is also used to describe laser welding.

1.1.1 Supplementary requirements (S1, S2, S3) of an optional nature are provided. They shall apply only when specified by the purchaser.

1.2 Shapes covered in this specification include those classified in Article 3.1.2 of Specification A6/A6M, Specification A554 and those square and rectangular hollow sections, and additional shapes, including customized, that are made from two or more shapes or plates.

1.3 This specification establishes the minimum requirements for manufacturing of laser and laser hybrid welded stainless steel shapes.

1.4 This specification refers to Specifications A240/A240M, A276/A276M, A554, or A479/A479M for chemical requirements, but the mechanical test requirements are determined by the mechanical properties section of this standard.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.7 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling](#)

[A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications](#)

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A276/A276M Specification for Stainless Steel Bars and Shapes](#)

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[A380/A380M Practice for Cleaning, Descaling, and Passivation of Stainless Steel Parts, Equipment, and Systems](#)

[A479/A479M Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels](#)

[A480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved Sept. 1, 2016; Sept. 1, 2019. Published September 2016/October 2019. Originally approved in 2011. Last previous edition approved in 2014/2016 as ~~A1069/A1069M – 14~~; ~~A1069/A1069M – 16~~. DOI: ~~10.1520/A1069\_A1069M-16~~; ~~10.1520/A1069\_A1069M-19~~.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

[A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings](#)  
[A554 Specification for Welded Stainless Steel Mechanical Tubing](#)  
[A673/A673M Specification for Sampling Procedure for Impact Testing of Structural Steel](#)  
[A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment](#)  
[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)  
[A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels](#)  
[A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys](#)  
[A1084 Test Method for Detecting Detrimental Phases in Lean Duplex Austenitic/Ferritic Stainless Steels](#)  
[E190 Test Method for Guided Bend Test for Ductility of Welds](#)  
[E208 Test Method for Conducting Drop-Weight Test to Determine Nil-Ductility Transition Temperature of Ferritic Steels](#)  
[E290 Test Methods for Bend Testing of Material for Ductility](#)  
[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

#### 2.2 ISO Standards:

[ISO 13919-1 Welding and Laser-beam Welded Joints—guidance on Quality Levels for Imperfections—Part 1: Steel](#)  
[ISO 12932 Welding – Laser-arc hybrid welding of steels, nickel and nickel alloys – Quality levels for imperfections](#)  
[ISO 4063 Welding and allied processes - Nomenclature of processes and reference numbers](#)  
[ISO 15609-4 Specification and Qualification of Welding Procedures for Metallic Materials—Welding Procedure Specification](#)  
[ISO 15609-6 Specification and qualification of welding procedures for metallic materials -- Welding procedure specification -- Part 6: Laser-arc hybrid welding](#)  
[ISO 15614-11 Specification and Qualification of Welding Procedures for Metallic Materials—Welding Procedure Test—Part 11: Electron and Laser Beam Welding](#)

#### 2.3 U.S. Military Standards:

[MIL-STD-129 Marking for Shipment and Storage](#)

#### 2.4 Federal Standards:

[Federal Standard No. 123 Marking for Shipment \(Civil Agencies\)](#)

#### 2.5 AWS Standards:

[AWS A3.0M/A3.0 Standard Welding Terms and Definition, Including Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying](#)  
[AWS D1.6/D1.6M Structural Welding Code – Stainless Steel](#)  
[AWS C7.2M Recommended Practices for Laser Beam Welding, Cutting, and Allied Processes](#)  
[AWS C7.4/C7.4M Process Specification and Operator Qualification for Laser Beam Welding](#)  
[AWS C7.6/C7.6M Process Specification and Operator Qualification for Laser Hybrid Welding](#)

#### 2.6 ASME Standards:

[ASME SA-370](#)  
[ASME BPVC.IX-2019 ASME Boiler and Pressure Vessel Code, Section IX: Welding and Brazing Qualifications](#)

#### 2.7 SAE Standard:

[J1086 Practice for Numbering Metals and Alloys \(UNS\)](#)

### 3. Terminology

#### 3.1 Definitions:

3.1.1 Definitions of general terms pertaining to this specification shall be those of Terminology [A941](#), “Standard Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys.”

3.1.2 Definitions of terms pertaining to welding terminology shall be those of [AWS A3.0M /A3.0](#), “Standard Welding Terms and Definition, Including Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying.”

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *laser fusion, n*—a joining process that produces coalescence of material with the heat obtained from the application of a concentrated coherent light beam impinging on the surface of a weld joint.

3.2.2 *stainless steel starting materials, n*—stainless steels (in plate, sheet, strip, shape or bar form prior to joining by laser fusion) that are then further processed into the final product.

### 4. Ordering Information

4.1 ~~The purchaser has~~ It shall be the responsibility of the purchaser to specify appropriate requirements that are necessary to ~~adequately describe the product ordered under~~ for material ordered to this specification. Such requirements to be considered include, shall include but are not limited to, to the following:

4.1.1 Name of structural product (plate, shape, bar, or sheet ~~piling~~) product.

4.1.2 Shape designation and applicable dimensions including size, thickness, width, diameter, and length, if applicable.

4.1.3 Type of stainless steel or UNS designation as specified in Table 1 of Specification ~~UNS designation.~~ [A240/A240M](#).

NOTE 2—Stainless steel alloys are identified in the ASTM standards by Unified Numbering System (UNS) number in accordance with Practice E527 and SAE J1086.

- 4.1.4 Quantity (weight or number of pieces).
- 4.1.5 ASTM specification designation and edition year if other than the latest edition.
- 4.1.6 Condition of ~~fusion~~-welded product, whether as welded, or subsequently stress-relieved, or heat treated.
- 4.1.7 ~~Finish~~-Finish in accordance with Section 9.
- 4.2 The purchaser has the option to specify additional requirements, including but not limited to the following:
  - 4.2.1 Supplementary Requirements, if invoked.
    - 4.2.1.1 S1. Charpy V-notch Impact Test for Structural Shapes.
    - 4.2.1.2 S2. Drop-weight Test (for Material 0.625 in. [16 mm] and Over in Thickness).
    - 4.2.1.3 S3. Intergranular Corrosion Test.
  - 4.2.2 Preparation for special delivery.
  - 4.2.3 Special marking requirements.
  - 4.2.4 Other special requirements.

NOTE 3—A typical ordering description is as follows: 5000 lb (2300 kg), Angle, L4 × 4 × ½ in. (L100 × 100 × 13 mm), laser fused, or laser hybrid welded, 20 ft (6 m) in length, Type 304L, ASTM Specification AXXXX dated \_\_\_\_.

## 5. Materials and Manufacture

### 5.1 Condition:

5.1.1 ~~Stainless steel starting materials~~The stainless steel purchased to produce A1069/A1069M shapes shall be in accordance with the requirements of the following specifications.

5.1.1.1 ~~For plates, sheet and strip, stainless steel starting materials shall be in conformance to Specification A240/A240M.~~*Mechanical Properties:*

(1) If strength Grade 1 is specified, then the mechanical properties shall be in accordance with the appropriate specification, either Specification A240/A240M, A276/A276M, or Specification A479/A479M.

(2) If austenitic stainless steel strength Grade 2 is specified then the purchased material shall meet the minimum mechanical property requirements in Table 1.

(3) If UNS S32205 (2205) duplex stainless steel strength Grade 3 is specified then the purchased material shall meet those minimum mechanical property requirements in Table 1.

(4) If super duplex strength Grade 4 is specified, as defined in the footnote F of Table 1, then the purchased material shall meet the minimum mechanical property requirements in Table 1.

5.1.1.2 ~~For bars and shapes, stainless steel starting materials shall be in conformance to Specification A276.~~

5.1.1.2 For bars and shapes for use in boilers and other pressure vessels, stainless steel starting materials shall be in conformance to Specification A479/A479M.*General and Chemical Requirements:*

(1) Plate, sheet, and strip shall conform to the requirements of Specification A480/A480M and the chemical requirements of Specification A240/A240M.

**TABLE 1 Mechanical Test Requirements<sup>A,B,C,G</sup>**

Strength Grade	Tensile Strength, min		Yield Strength, min		Elongation in 2 in. or 50 mm, min, %
	ksi	MPa	ksi	MPa	
Austenitic (Chromium-Nickel) (Chromium-Manganese-Nickel)					
2 <sup>D</sup>	80	550	35	240	35
Duplex (Austenitic-Ferritic)					
3 <sup>E</sup>	95	655	65	450	25
4 <sup>F</sup>	116	795	80	550	15

<sup>A</sup> Yield strength shall be determined by the offset method at 0.2 % in accordance with Test Methods and Definitions A370. Unless otherwise specified.

<sup>B</sup> Bend tests are not required for any austenitic or duplex (austenitic-ferritic) stainless steels regardless of thickness.

<sup>C</sup> Brinell or Rockwell Hardness hardness requirements are determined by Specifications A240/A240M, A276/A276M, A554 or A479/A479M.

<sup>D</sup> This strength level applies to the following austenitics (UNS number (common name): UNS S30403 (304L), S30409 (304H), S31603 (316L), S31653 (316LN), and S31703 (317L). Order all other austenitics to strength Grade 1, ASTM A240/A240M mechanical properties.

<sup>E</sup> This strength level applies to S32205 (2205) up to 2.5 in. (64 mm) in thickness.

<sup>F</sup> This strength level can be achieved by the more highly alloyed, more corrosion resistant and higher strength super duplexes like S32750, and S32760 is limited to thicknesses of up to 2 inches (50 mm).

<sup>G</sup> All ferritic and duplex (austenitic-ferritic) stainless steels not listed in this table shall be ordered to strength grade 1 in accordance with 7.1.1.