



Designation: G20 – 10 (Reapproved 2019)

Standard Test Method for Chemical Resistance of Pipeline Coatings¹

This standard is issued under the fixed designation G20; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended for evaluating the resistance of pipe coating materials when exposed to various concentrations of reagents or suspected soil contaminants. The test serves as a guide to investigators wishing to compare the relative merits of pipe-coating materials in specific environments. The choice of reagents, concentrations, duration of immersion, temperature of test, and properties to be reported are necessarily arbitrary and should be chosen to reflect conditions known to exist along the pipeline right-of-way.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents](#)

[D883 Terminology Relating to Plastics](#)

[G8 Test Methods for Cathodic Disbonding of Pipeline Coatings](#)

[G12 Test Method for Nondestructive Measurement of Film](#)

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.48 on Durability of Pipeline Coating and Linings.

Current edition approved Oct. 1, 2019. Published October 2019. Originally approved in 1971. Last previous edition approved in 2015 as G20 – 10(2015). DOI: 10.1520/G0020-10R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Thickness of Pipeline Coatings on Steel](#) (Withdrawn 2013)³

[G17 Test Method for Penetration Resistance of Pipeline Coatings \(Blunt Rod\)](#)

3. Summary of Test Method

3.1 This test method consists of an immersion-type test in a closed container where coated pipe specimens are in long-term contact with both the liquid and vapor phase of the test reagent. Specimens exposed in this manner are inspected for visible signs of chemical attack. Subsequent tests for cathodic disbonding in accordance with Test Method G8, or penetration under load in accordance with Test Method G17, may be applied to determine if the specimens have undergone any loss of mechanical or bonding properties.

4. Significance and Use

4.1 The data obtained for short-term tests are of interest only in eliminating the most unsuitable materials or for indicating a probable order of resistance in any particular media.

4.2 Test conditions should take into account the manner and duration of immersion, the reagent, the temperature of the system, the area exposed above and below the liquid level, and other performance factors selected for the particular test.

5. Apparatus

5.1 *Thickness Gage*, capable of measuring the coating thickness in the manner prescribed by Test Method G12.

5.2 *Test Container*—A transparent closed container, sized to completely encase the pipe specimen and large enough to provide adequate exposure to both the liquid and vapor states of reagent.

NOTE 1—For example, a 2-L (2.0-qt) capacity, Mason-type jar with a 70-mm (2.75-in.) diameter neck has been found suitable for use with 2 in. pipe and is illustrated in Fig. 1.

5.2.1 To avoid pressure build-up within the test containers, the threaded cup shall be replaced with a solid-rubber stopper. A positive venting device, such as a water seal, shall be used when testing with volatile solvents at elevated temperatures.

³ The last approved version of this historical standard is referenced on www.astm.org.