



Designation: A1032 – 15 (Reapproved 2019)

Standard Test Method for Hydrogen Embrittlement Resistance for Steel Wire Hard-Drawn Used for Prestressed Concrete Pipe¹

This standard is issued under the fixed designation A1032; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes procedures to determine the hydrogen embrittlement (HE) resistance of hard-drawn steel wire used for prestressed concrete pipe.

1.2 HE resistance is reported as time-to-failure of specimens tested in a laboratory.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

A648 Specification for Steel Wire, Hard-Drawn for Prestressed Concrete Pipe

D1193 Specification for Reagent Water

3. Summary of Test Method

3.1 Characterization of HE resistance of hard-drawn steel wire is accomplished by determining the time-to-failure of a wire specimen under a maintained constant tensile force, while immersed in a heated solution of ammonium thiocyanate

¹ This test method is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 2004. Last previous edition approved in 2015 as A1032 – 15. DOI: 10.1520/A1032-15R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

(NH_4SCN). The tensile force, the solution temperature, and length of time in the test are continuously monitored.

4. Significance and Use

4.1 Hard-drawn steel wire as used in prestressed concrete pipe may be exposed to elemental hydrogen favorable to hydrogen induced embrittlement and cracking. Resistance to hydrogen embrittlement is necessary for prestressing wire to provide long-term performance to installed pipe.

4.2 The length of time that a stressed wire specimen resists failure while exposed to a heated solution of NH_4SCN , is an indication of the specimen's resistance to hydrogen embrittlement.

5. Apparatus

5.1 *Test Cell*—The test cell shall contain the test solution and the wire specimen and be constructed of material which is inert to NH_4SCN (as shown in Fig. 1). The test cell shall be cylindrical with an inside diameter sufficient to provide a minimum of 5 mL of solution per 100 mm² (2 in.³ per in.²) of wire specimen surface area in contact with the solution. The test cell length shall allow the exposure of a minimum test specimen length of 150 mm (6 in.) to the test solution. The test cell shall be so designed that the wire specimen passes through it and is sufficiently exposed outside the end of the cell as to allow application of a tensile force to the specimen.

5.2 *Chronometer*—A chronometer with a precision of at least ± 1 min. and capable of being stopped automatically on fracture of the specimen shall be used.

5.3 *Tensile Force Frame*—A closed stiff frame, in either horizontal or vertical orientation, shall be used to position the test cell such that a constant tensile force shall be applied to the test specimen and maintained. The tensile force shall be applied through use of a dead weight, or hydraulic loading system equipped with a force indicator.

6. Reagents and Materials

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where