



## Designation: D4066 – 13 (Reapproved 2019)

# Standard Classification System for Nylon Injection and Extrusion Materials (PA)<sup>1</sup>

This standard is issued under the fixed designation D4066; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## INTRODUCTION

This standard is maintained in order to support products that must utilize ASTM D4066 in the product definition. This is necessary because there are some differences between the material property test requirements of ASTM D4066 and ASTM D6779, Standard Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA). There are also differences between the two specifications in some of the Group/Class/Grade callouts. Designers of new products are urged to use ASTM D6779 rather than ASTM D4066.

### 1. Scope

1.1 This classification system covers nylon materials suitable for injection molding and extrusion. Some of these compositions are also suitable for compression molding and application from solution.

1.2 The properties included in this classification system are those required to identify the compositions covered. There may be other requirements necessary to identify particular characteristics important to specialized applications. These may be specified by using the suffixes as given in Section 5.

1.3 This classification system and subsequent line call-out (specification) are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastic field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this classification system.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 The following precautionary caveat pertains only to the test methods portion, Section 11, of this classification system. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety,*

*health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—This classification system is being revised to include international 4-mm specimens and test procedures as the standard for compliance. The 3.2-mm specimens; test methods; and Tables PA, A, and B are included in Appendix X3 as a reference for those wishing to use them. It is recommended that the material manufacturer be consulted on all call-outs against this classification system.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies

D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D257 Test Methods for DC Resistance or Conductance of Insulating Materials

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position

<sup>1</sup> This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 1982. Last previous edition approved in 2013 as D4066-13. DOI: 10.1520/D4066-13R19.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

- D789 Test Method for Determination of Relative Viscosity of Concentrated Polyamide (PA) Solutions  
 D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials  
 D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement  
 D883 Terminology Relating to Plastics  
 D1600 Terminology for Abbreviated Terms Relating to Plastics  
 D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry  
 D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials  
 D3892 Practice for Packaging/Packing of Plastics  
 D4000 Classification System for Specifying Plastic Materials  
 D5630 Test Method for Ash Content in Plastics  
 D6260 Test Method for Gravimetric Determination of Carbon Black in Nylon Materials (PA) (Withdrawn 2004)<sup>3</sup>  
 D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)  
 E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications  
 2.2 Military and Federal Specifications and Standards:<sup>4</sup>  
 L-P-410 Plastic, Polyamide (Nylon) Rigid: Rods, Tubes, Flats, Molded and Cast Parts  
 VV-I-530 Insulating Oil, Electrical (for Transformers, Switches, and Circuit Breakers)  
 2.3 ISO Standards:<sup>5</sup>  
 ISO 75-1:1993 Plastics—Determination of Temperature of Deflection Under Load—Part 1: General Test Methods  
 ISO 75-2:1993 Plastics—Determination of Temperature of Deflection Under Load—Part 2: Plastic and Ebonite  
 ISO 178:1993 Plastics—Determination of Flexural Properties  
 ISO 180:1993 Plastics—Determination of Izod Impact Strength  
 ISO/DIS 294-1:1995 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 1: General Principles, Multipurpose-Test Specimens (ISO Mould Type A) and Bars (ISO Mould Type B)  
 ISO 307 Determination of Viscosity Number of Polyamides In Dilute Solutions  
 ISO 527-1:1993 Plastics—Determination of Tensile Properties—Part 1: General Principles  
 ISO 527-2:1993 Plastics—Determination of Tensile Properties—Part 2: Testing Conditions  
 ISO 960:1969 Plastics—Determination of the Water Content in Polyamides

- ISO 1183:1987 Plastics—Methods for Determining the Density and Relative Density of Non-Cellular Plastics  
 ISO/DIS 1874-2:1995 Plastics—Polyamide (PA) Homopolymers for Moulding and Extrusion—Part 2: Preparation of Test Specimens and Determination of Properties  
 ISO 3146: Plastics—Determination of Melting Behaviour (Melting Temperature or Melting Range) of Semi-Crystalline Polymers  
 ISO 3167 Plastics, Multipurpose Test Specimens  
 ISO 3451-4:1994 Plastics—Determination of Ash—Part 4: Polyamides

### 3. Terminology

3.1 The terminology used in this classification system is in accordance with Terminologies D883 and D1600.

### 4. Classification

4.1 Nylon materials are classified into groups according to their composition. These groups are subdivided into classes and grades as shown in the Basic Property Table (Table PA).

NOTE 3—An example of this classification system for unreinforced nylon is given as follows: The designation PA0123 indicates the following:

PA = polyamide (nylon) as found in Terminology D1600,  
 01 (group) = 66 nylon,  
 2 (class) = heat stabilized, and  
 3 (grade) = with a minimum viscosity number of 210 and the requirements given in Table PA.

NOTE 4—An example of this classification system for reinforced nylon is given as follows: The designation PA012G35 indicates the following:

PA = polyamide (nylon) as found in Terminology D1600,  
 01 (group) = 66 nylon,  
 2 (class) = heat stabilized, and  
 G35 (grade) = nominal 35 % glass with the requirements given in Table PA.

4.1.1 Grades of reinforced or filled versions, or both, of the basic materials are identified by a single letter that indicates the reinforcement or filler used and two digits, in multiples of 5, that indicate the nominal quantity in percent by weight. Thus, a letter designation G for glass reinforced and 35 for percent or reinforcement, G35, specifies a material with a nominal glass level of 35 %. The reinforcement letter designations and associated tolerance levels are shown as follows:

Symbol	Material	Tolerance (Based on the Total Mass)
C	carbon- and graphite-fiber-reinforced	±2 %
G	glass-reinforced	±2 %
L	lubricants (such as PTFE, graphite, silicone, and molybdenum disulfide)	Depends upon material and process—to be specified.
M	mineral-reinforced	±2 %
R	combinations of reinforcements or fillers, or both	±3 %

NOTE 5—This part of the classification system uses percent of reinforcements or additives, or both, in the call-out of the modified basic material. The types and percentages of reinforcements and additives should be shown on the supplier's technical data sheet unless they are proprietary in nature. If necessary, additional control of these reinforcements and additives can be accomplished by use of the suffix part of the system (see Section 5).

NOTE 6—Materials containing reinforcements or fillers, or both, at

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

<sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

nominal levels not in multiples of 5 are included in the nearest PA grade designation. For example, a material with a nominal material level of 28 % is included with Grade M30.

NOTE 7—An example of this classification system for a 33 % glass-reinforced nylon is given as follows. The designation PA011G35 indicates the following:

PA = polyamide (nylon) as found in Terminology D1600,  
 01 (group) = 66 nylon,  
 1 (class) = general purpose, and  
 G35 (grade) = with requirements given in Table PA.

NOTE 8—Ash content of filled or reinforced materials may be determined using Test Method D5630.

**TABLE PA Requirements for Nylons Dry-as-Molded<sup>A,B</sup>**

Group	Description	Class	Description	Grade	Description <sup>C</sup>	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm <sup>3</sup>	Tensile Strength, <sup>D</sup> ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m <sup>2</sup>	Deflection Temperature at 1.82 MPa, <sup>E</sup> ISO 75-1 and ISO 75-2 min, °C
01	66 Nylon	1	General-purpose	1		135	1.13–1.15	70	2 300	3.3	60
				2		165	1.13–1.15	70	2 300	3.3	60
				3		210	1.13–1.15	70	2 300	3.3	60
				4		270	1.13–1.15	70	2 300	3.3	60
				5 recycled		115	1.13–1.15	70	2 300	3.3	60
				6 recycled		135	1.13–1.15	70	2 300	3.3	60
				0 other							
				G15	15 % glass	...	1.20–1.26	100	4 000	3.0	215
				G20	20 % glass	...	1.25–1.33	115	5 000	4.0	220
				G25	25 % glass	...	1.29–1.37	140	6 000	5.0	225
				G35	35 % glass	...	1.35–1.45	170	8 000	7.0	235
				G40	40 % glass	...	1.42–1.52	175	9 000	8.0	235
				G45	45 % glass	...	1.45–1.55	180	10 000	9.0	240
				M40	40 % mineral	...	1.45–1.55	80	5 000	2.0	150
		2	Heat-stabilized	1		135	1.13–1.15	70	2 300	3.0	60
				2		165	1.13–1.15	70	2 300	3.0	60
				3		210	1.13–1.15	70	2 300	3.0	60
				4		270	1.13–1.15	70	2 300	3.0	60
				5 recycled		115	1.13–1.15	70	2 300	3.0	60
				6 recycled		135	1.13–1.15	70	2 300	3.0	60
				0 other							
				G15	15 % glass	...	1.20–1.26	100	4 000	3.0	220
				G25	25 % glass	...	1.29–1.37	140	6 000	5.0	225
				G30	30 % glass	...	1.32–1.42	160	7 000	6.0	230
				G35	35 % glass	...	1.35–1.45	170	8 000	7.0	235
				G40	40 % glass	...	1.43–1.53	175	9 000	8.0	235
				G45	45 % glass	...	1.45–1.55	180	10 000	9.0	240
				M40	40 % mineral	...	1.45–1.55	80	5 000	2.0	150
				R20	20 % filler	...	1.23–1.31	70	3 200	1.5	...
				R40	40 % filler	...	1.43–1.53	100	5 500	2.5	200
		3	Nucleated	1		135	1.13–1.15	80	2 500	2.8	60
				2		165	1.13–1.15	80	2 500	2.8	60
				3		210	1.13–1.15	80	2 500	2.8	60
				4		270	1.13–1.15	80	2 500	2.8	60
				5 recycled		115	1.13–1.15	80	2 500	2.8	60
				6 recycled		135	1.13–1.15	80	2 500	2.8	60
				0 other							
		4	Nucleated, heat-stabilized	1							
				2							
				3							
				4							
				0 other							
		5	Impact-modified	1		...	1.06–1.12	52	1 700	9.0	50
				2 recycled		...	1.06–1.12	50	1 600	8.0	50
				0 other							
				G15	15 % glass	...	1.15–1.23	85	3 000	6.0	210
				G35	35 % glass	...	1.31–1.41	110	5 500	6.0	225
		6	Impact-modified, heat-stabilized	1		...	1.08–1.12	52	1 700	9.0	50
				2 recycled		...	1.08–1.12	50	1 600	8.0	50
				0 other							
				G15	15 % glass	...	1.15–1.23	85	3 000	6.0	210
				G35	35 % glass	...	1.31–1.41	110	5 500	6.0	225
				M40	40 % mineral	...	1.45–1.55	75	4 500	4.0	...
				R35	35 % filler	...	1.38–1.48	80	5 500	3.0	200
		7	Toughened	1		...	1.06–1.10	42	1 500	40	45
				2 recycled		...	1.05–1.11	40	1 300	35	45
				0 other							
				G15	15 % glass	...	1.15–1.23	70	2 800	9.0	180
				G35	35 % glass	...	1.28–1.38	110	5 500	11	220

**TABLE PA Requirements for Nylons Dry-as-Molded<sup>A,B</sup>**

Group	Description	Class	Description	Grade	Description <sup>C</sup>	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm <sup>3</sup>	Tensile Strength, <sup>D</sup> ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m <sup>2</sup>	Deflection Temperature at 1.82 MPa, <sup>E</sup> ISO 75-1 and ISO 75-2 min, °C
		8	Toughened, heat-stabilized	1		...	1.06–1.10	42	1 500	40	45
				2	recycled	...	1.05–1.11	40	1 300	35	45
				0	other						
				G15	15 % glass	...	1.15–1.23	70	2 800	9.0	180
				G35	35 % glass	...	1.28–1.38	110	5 500	11	220
				G45	45 % glass	...	1.39–1.49	130	8 000	10	230
				M35	35 % mineral	...	1.37–1.47	70	3 800	6.0	...
		9	Weather-stabilized <sup>F</sup>	1		135	1.13–1.17	80	2 400	2.5	60
				2	recycled	115	1.13–1.17	65	2 200	2.0	60
				0	other						
		0	Other	0	other						
02	6 Nylon	1	General-purpose	1		100	1.12–1.14	75	2 400	4	50
				2		135	1.12–1.14	70	2 200	3	50
				3		150	1.12–1.15	70	2 200	3	50
				4		200	1.12–1.15	70	2 200	3	50
				0	other						
				G15	15 % glass		1.20–1.28	110	4 200	4	170
				G25	25 % glass		1.28–1.36	135	5 000	6.5	180
				G30	30 % glass		1.32–1.40	150	7 000	7.5	180
				G35	35 % glass		1.38–1.44	155	7 500	8	180
				G00	other						
				M30	30 % mineral		1.30–1.40	70	3 200	2.4	50
				M40	40 % mineral		1.44–1.52	75	4 500	4	70
				M00	other						
				R40	40 % glass/mineral		1.42–1.50	100	6 000	3	180
				R00	other						
		2	Heat-Stabilized	1		100	1.12–1.14	75	2 400	4	50
				2		135	1.12–1.14	70	2 200	3	50
				3		150	1.12–1.15	70	2 200	3	50
				4		200	1.12–1.15	70	2 200	3	50
				7	recycled	135	1.12–1.14	70	2 000	3	50
				0	other						
				G5	5 % glass		1.16–1.22	85	2 500	2.5	110
				G15	15 % glass		1.20–1.28	110	4 200	4	180
				G25	25 % glass		1.28–1.36	135	5 000	6.5	190
				G30	30 % glass		1.32–1.40	150	7 000	7.5	190
				G35	35 % glass		1.36–1.44	155	7 500	8	190
				G45	45 % glass		1.46–1.54	175	10 000	10	190
				G50	50 % glass		1.52–1.60	175	10 000	10	190
				G65	65 % glass		1.70–1.78	175	13 000	10	200
				G00	other						
				M30	30 % mineral		1.30–1.40	70	3 200	2.4	50
				M35	35 % mineral		1.39–1.47	70	3 500	3	60
				M40	40 % mineral		1.44–1.52	75	4 500	4	70
				M00	other						
				R20	20 % glass/mineral		1.25–1.33	80	3 200	2.5	120
				R40	40 % glass/mineral		1.42–1.50	100	6 000	3	180
				R00	other						
		3	Nucleated	1		100	1.12–1.14	70	2 300	2.5	50
				2		135	1.12–1.14	70	2 300	2.5	50
				3		150	1.12–1.15	75	2 300	2.5	50
				4		200	1.12–1.15	80	2 300	2.5	50
				0	other						
		4	Nucleated and Heat-Stabilized	1		100	1.12–1.14	70	2 300	2.5	50
				2		135	1.12–1.14	70	2 300	2.5	50
				3		150	1.12–1.15	75	2 300	2.5	50
				4		200	1.12–1.15	80	2 300	2.5	50
				7	recycled	135	1.12–1.14	70	2 100	2.5	50
				0	other						
		5	Impact-Modified	1			1.05–1.12	45	1 700	30	45
				2			1.05–1.18	55	2 000	6	45
				3			1.05–1.18	40	1 000	6	35
				0	other						
				G15	15 % glass		1.15–1.24	75	3 300	9	130
				G30	30 % glass		1.30–1.40	135	6 500	15	180

**TABLE PA Requirements for Nylons Dry-as-Molded<sup>A,B</sup>**

Group	Description	Class	Description	Grade	Description <sup>C</sup>	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm <sup>3</sup>	Tensile Strength, <sup>D</sup> ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m <sup>2</sup>	Deflection Temperature at 1.82 MPa, <sup>E</sup> ISO 75-1 and ISO 75-2 min, °C
					G35 35 % glass G40 40 % glass G00 other	1.32–1.42 1.39–1.47	135 135	6 800 8 000	15 10	190 200	
6	Impact-Modified, Heat-Stabilized	1			1.05–1.12	45	1 700	30	45		
		2			1.05–1.18	55	2 000	6	45		
		3			1.05–1.18	40	1 000	6	35		
		4			1.05–1.18	25	1 000	30	30		
		0 other									
		G15 15 % glass G30 30 % glass G35 35 % glass G40 40 % glass G00 other			1.15–1.24 1.30–1.40 1.32–1.42 1.39–1.47	75 135 135 135	3 300 6 500 6 800 8 000	9 15 10 10	130 180 190 200		
		M35 35 % mineral M40 40 % mineral M00 other			1.35–1.45 1.37–1.47	65 65	3 200 3 200	3 3	50 50		
8	Flexurally-Modified, Heat-Stabilized	2	injection molding		1.05–1.16	55	2 375 max	10	45		
		3 extrusion			1.05–1.16	30	2 000 max	7	25		
		4 blends			1.05–1.10	35	1 700 max	4.5	35		
		0 other									
03 <sup>G</sup>	11 Nylon	0 Other									
	1	General purpose	1		221	1.03–1.06					
		2			234	1.03–1.06					
		3			252	1.03–1.06					
		4			291	1.03–1.06					
		5 hydrolysis-resistant				1.03–1.06					
		0 other									
2	Heat-stabilized	1			234	1.03–1.06					
		2			252	1.03–1.06	45				
		3			291	1.03–1.06					
		4 hydrolysis-resistant				1.03–1.06					
		0 other									
	Highly plasticized	1				1.03–1.06					
		2				1.03–1.06					
		3				1.03–1.06					
		4				1.03–1.06					
		0 other									
4	Highly plasticized, heat stabilized	1				1.03–1.06					
		2				1.03–1.06					
		3				1.03–1.06					
		4				1.03–1.06					
		0 other									
5	Moderately plasticized	1				1.03–1.06					
		2				1.03–1.06					
		3				1.03–1.06					
		4				1.03–1.06					
		5				1.03–1.06					
		0 other									
6	Moderately plasticized, heat-stabilized	1				1.03–1.06					
		2				1.03–1.06					
		3				1.03–1.06					
		4				1.03–1.06					
		5				1.03–1.06					
		0 other									
04	12 Nylon	0 Other									
	General purpose	1			100–210	1.00–1.06	30	800	2.5	35	
		2			100–210	1.00–1.06	35	1 000	2.5	35	
		3			211–270	1.00–1.06	35	1 000	2.5	35	
		4			271–340	1.00–1.06	35	1 000	2.5	35	
		0 other									
2	Heat-stabilized	1			100–150	1.00–1.06	35	800	2.5	35	
		2			151–210	1.00–1.06	35	800	2.5	35	
		3			211–280	1.00–1.06	35	1 000	2.5	35	
		0 other									

**TABLE PA Requirements for Nylons Dry-as-Molded<sup>A,B</sup>**

Group	Description	Class	Description	Grade	Description <sup>C</sup>	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm <sup>3</sup>	Tensile Strength, <sup>D</sup> ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m <sup>2</sup>	Deflection Temperature at 1.82 MPa, <sup>E</sup> ISO 75-1 and ISO 75-2 min, °C	
				G15	15 % glass	1.10–1.20	75	3 000	10	160		
				G25	25 % glass	1.10–1.25	90	3 000	15	160		
				G30	30 % glass	1.15–1.30	95	4 000	15	160		
				G40	40 % glass	1.30–1.45	100	4 500	15	160		
				R30	30 % filler	1.22–1.28	55	3 500	5.0	100		
		3	Nucleated	1		100–180	1.00–1.06	35	800	1.0	35	
				2		181–250	1.00–1.06	35	800	1.0	35	
				0 other								
		4	Plasticized	1		100–280	1.00–1.06	30	300–550	15	...	
				2		100–280	1.00–1.06	30	450–750	10	...	
				0 other								
		5	Plasticized, heat-stabilized	1		100–280	1.00–1.06	20	200–350	20	...	
				2		100–280	1.00–1.06	30	300–550	15	...	
				3		100–280	1.00–1.06	30	450–750	10	...	
				4		100–280	1.00–1.06	35	550–950	5.0	...	
				0 other								
		0	Other	0 other								
05	69 Nylon	1	General purpose	1		1.07–1.09						
				2		1.07–1.09						
				3		1.07–1.09						
				0 other								
		2	Heat-stabilized	1		1.07–1.09						
				2		1.07–1.09						
				3		1.07–1.09						
				0 other								
		0	Other	0 other								
06	612 Nylon	1	General purpose	1		100–139	1.05–1.07	50	1 800	2.0	45	
				2		140–199	1.05–1.07	50	1 800	2.5	45	
				3		200	1.05–1.07	50	1 800	3.0	45	
				0 other								
				G35	35 % glass	...	1.28–1.38	140	7 000	9.0	175	
				G45	45 % glass	...	1.38–1.48	150	8 500	11	180	
		2	Heat-stabilized	1		140	1.05–1.07	50	1 800	2.0	45	
				0 other								
				G30	30 % glass	...	1.25–1.33	120	5 500	5.0	170	
				G35	35 % glass	...	1.28–1.38	140	7 000	9.0	175	
		3	Weather-stabilized <sup>F</sup>	1		140	1.05–1.07	50	1 800	1.5	45	
				0 other								
		0	Other	0 other								
07	610 Nylon	1	General purpose	1		1.05–1.09						
				2		1.05–1.09						
				3		1.05–1.09						
				0 other								
		2	Heat-stabilized	1		1.05–1.09						
				2		1.05–1.09						
				0 other								
		0	Other	0 other								
08	Special	1	n-alkoxy-alkyl 6:6	1		1.09–1.12						
				0 other								
		0	Other	0 other								
09	46 Nylon	1	General-purpose	1								
				2								
				3								
				0 other								
		2	Heat-stabilized	1								
				2								
				3								
				0 other								
				G15	15 % glass	...	1.25–1.31	125	5 000	3.6	240	
				G30	30 % glass	...	1.38–1.42	175	8 000	7.5	280	
				G40	40 % glass	...	1.48–1.53	195	10 000	10.0	280	
				G50	50 % glass	...	1.58–1.63	210	12 000	12.0	280	
				R50	50 % filler	...	1.60–1.67	140	9 000	4.0	280	
		3	Flame-retardant, <sup>G</sup> heat-stabilized	1								
				2								
				0 other								
				G15	15 % glass	...	1.55–1.59	115	6 000	4.5	270	
				G30	30 % glass	...	1.63–1.69	155	10 000	7.5	280	
				G40	40 % glass	...	1.76–1.80	145	11 000	8.0	280	