Designation: F1563 - 01 (Reapproved 2019)

An American National Standard

Standard Specification for Tools to Squeeze-off Polyethylene (PE) Gas Pipe or Tubing¹

This standard is issued under the fixed designation F1563; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers the physical requirements for tools used to squeeze-off polyethylene (PE) pipe and tubing. It is limited to squeeze-off procedures set forth by the pipe manufacturer as referred to in Specification D2513 for gas pressure pipe systems.
- 1.2 Nothing in this specification shall be construed as recommending practices or systems at variances with governing codes and project specifications.
- 1.3 Where applicable in this specification, "pipe" shall mean "pipe and tubing," and "tool" shall mean "squeeze-off tool."
- 1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.5 The following safety hazards caveat pertains only to the test methods portions, Section 5 and Appendix X1 of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.
- 1.6 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards*:² D638 Test Method for Tensile Properties of Plastics

- D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D2513 Specification for Polyethylene (PE) Gas Pressure Pipe, Tubing, and Fittings
- F412 Terminology Relating to Plastic Piping Systems
- F1041 Guide for Squeeze-Off of Polyolefin Gas Pressure Pipe and Tubing

3. Terminology

- 3.1 *General*—Definitions are in accordance with Terminology F412, unless otherwise specified. Abbreviations are in accordance with Terminology D1600, unless otherwise specified.
 - 3.2 Definitions of Terms Specific to This Standard:
- 3.2.1 *squeeze-off*—a technique used to control the flow of gas through a pipe by the compressing action of a mechanical, hydraulic or pneumatic device. Squeeze-off may be used, as recommended by the tool or pipe manufacturer, to reduce the flow of gas to an acceptable rate. Under certain conditions complete stoppage of flow may be obtained.

4. Materials and Manufacture astm-fl 563-012019

4.1 Tools shall be manufactured from materials that have the structural properties to meet the requirements of this specification.

5. Other Requirements

- 5.1 Force Mechanism—The force mechanism (mechanical, hydraulic or pneumatic) shall provide a force of at least 1.25 times the force required to squeeze-off the most rigid pipe size within the squeeze parameters recommended by the manufacturer of the tool. The most rigid pipe is a function of pipe diameter, wall thickness, pipe material and temperature. The tool manufacturer determines which pipe products his tool is suitable for. Power tools such as impact wrenches or pneumatic motored torque multipliers shall not be used.
- 5.2 *Tool Strength*—A tool shall not be structurally damaged or functionally affected when tested as follows:
- 5.2.1 Measure the load (P) required to squeeze-off the most rigid pipe (largest size, thickest wall, highest density, lowest temperature) within the range of the tool.

 $^{^{\}rm 1}$ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.60 on Gas.

Current edition approved Aug. 1, 2019. Published November 2019. Originally approved in 1993. Last previous edition approved in 2011 as F1563-01(2011). DOI: 10.1520/F1563-01R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.