



Designation: ~~A987/A987M – 09 (Reapproved 2014)~~ A987/A987M – 19

Standard Practice for Measuring Shape Characteristics of Tin Mill Products¹

This standard is issued under the fixed designation A987/A987M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 Shape is a significant quality characteristic for tin mill products. Plate-shape is affected by mill process factors plus the temper, thickness, and width of the material supplied. It is the purpose of this practice to define accurately the different plate shape characteristics and to describe the practice(s) most commonly used to measure particular characteristics.

1.2 Quantitative limits are not addressed and should be established on an individual producer and user basis, where appropriate.

1.3 *Units*—The values stated in either ~~in-pound or SI units or inch-pound units~~ are to be regarded as ~~standard~~. ~~Within the text, the SI units are shown in brackets, separately as standard.~~ The values stated in each system ~~must~~ are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other. ~~Combining~~ other, and values from the two systems ~~may result in nonconformance with this specification shall not be combined.~~

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and ~~health~~ environmental practices and to determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A599/A599M](#) Specification for Tin Mill Products, Electrolytic Tin-Coated, Cold-Rolled Sheet

[A623](#) Specification for Tin Mill Products, General Requirements

[A623M](#) Specification for Tin Mill Products, General Requirements [Metric]

[A624/A624M](#) Specification for Tin Mill Products, Electrolytic Tin Plate, Single Reduced

[A625/A625M](#) Specification for Tin Mill Products, Black Plate, Single-Reduced - 5c54e685ccbb/astm-a987-a987m-19

[A626/A626M](#) Specification for Tin Mill Products, Electrolytic Tin Plate, Double Reduced

[A650/A650M](#) Specification for Tin Mill Products, Black Plate, Double Reduced

[A657/A657M](#) Specification for Tin Mill Products, Black Plate Electrolytic Chromium-Coated, Single and Double Reduced

3. Classification

3.1 The substrate shall conform to all the requirements of the appropriate specifications as follows: Specifications [A623](#), [A623M](#), [A599/A599M](#), [A624/A624M](#), [A625/A625M](#), [A626/A626M](#), [A650/A650M](#), and [A657/A657M](#).

4. Significance and Use

4.1 The definitions and procedures for measuring shape characteristics of tin mill products are provided so that purchasers and suppliers have common measuring procedures and definitions of shape characteristics. These procedures provide definitions and measuring techniques of shape characteristics. The intention of these definitions and measuring practices is not to provide a dimensional specification for shape characteristics, but rather common procedure(s) for quantifying shape anomalies.

¹ This practice is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.20](#) on Tin Mill Products.

Current edition approved Oct. 1, 2014 Nov. 1, 2019. Published November 2014 November 2019. Originally approved in 1998. Last previous edition approved in 2009 2014 as ~~A987 – 09~~ [A987/A987M – 09\(2014\)](#). DOI: ~~10.1520/A0987 – A0987M-09R14~~ [10.1520/A0987_A0987M-19](#).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

5. Interferences

5.1 Measurement of shape often has been subjective, at best. Successful measurement of various shape anomalies on quantitative terms requires recognition of several factors that can interfere with accurate measurements.

5.1.1 Flat surfaces are required. Measurement of several anomalies require laying of the sample on a flat surface. A machined flat surface is recommended. Laying a sample on a floor may introduce error due to areas on a floor that are not flat.

5.1.2 Several anomalies are measured by hanging the sheet. Hanging by holding the sample with a hand can introduce error from pressures exerted by fingers. A mechanical single device clamp to help hold these samples is recommended.

5.1.3 Stepblock gauges or tapered gauges should be checked regularly with a calibrated hand micrometer. Wear or dirt build up could affect accuracy.

5.1.4 Computer-based shape measuring instruments must be clean, and the sensors must be in good condition. The sheet sample must be damage free.

6. Apparatus

6.1 Appropriate tools to measure shape anomalies are described along with drawings (attached) as required.

6.1.1 *Flat Surfaces*—Accurate measurements of shape anomalies require a flat surface, machined flat preferred.

6.1.2 *Machined Stepblock Gauge*—See Fig. 1, typically, steps are in $\frac{1}{16}$ -in. increments.

6.1.3 *Tapered Gauge*—See Fig. 2.

6.1.4 *Standard Ruler or Tape Measure*.

6.1.5 *Hand Micrometer*.

6.1.6 *Shape Test Jig*—Fig. 3, or other shape test jigs of appropriate design.

6.1.7 *Light-Weight Straight-Edge*.

6.1.8 *Computer-based Shape Measuring Instruments* are designed for flatness measurements on samples of cold rolled sheet products or tin mill products.

6.1.9 *Push Block*—Wooden block with approximate dimensions of 1.5 in. thick x 3.5 in. wide x 6 in. long; preferably felt covered.

7. Procedure

Definitions and Measuring Practices of Shape Anomalies

7.1 *Wavy Edge* (See Fig. 4):

7.1.1 *Definition*—A series of rolling direction edge deviations from a recognized flat surface. When a sample is placed on a recognized flat table, wavy edges will appear as undulations along the edge, having the height (*A*) and a measurable cycle (*B*). This defect can be quantified using the “*T*” unit (see Section 8) or steepness calculations.

7.1.2 *Measuring Practices*:


7.1.2.1 A sample of approximately 3 ft [0.9 m] in length by coil width is placed on a flat table. Measure the height (*A*) at the peak point of each wave from the recognized flat surface with a tapered gauge or a stepblock gauge. Also measure the cycle length (*B*) from peak to peak of each wave with a ruler or tape measure.

7.1.2.2 Measure using a computer-based shape measuring instrument or other instrument of appropriate design.

7.2 *Ridge Buckle, Quarter Buckle, Center Buckle* (see Fig. 5):

7.2.1 *Definition*—These buckles are continuous deviations from a recognized flat surface occurring usually in narrow width areas parallel to the rolling direction other than at the sheet edges.

7.2.2 *Measuring Practices*:



NOTE 1—This is a stepblock gauge for all thicknesses and sizes of cut sheets.


NOTE 2—Dimensions given are approximate overall dimensions.

FIG. 1 Shape Stepblock Gauge



NOTE 1—This is a tapered gauge for all thicknesses and sizes of cut sheets.

FIG. 2 Shape Tapered Gauge



NOTE 1—To measure line bow (up or down) requires the use of a shape test jig.

FIG. 3 Shape Test Jig




FIG. 4 Wavy Edge

7.2.2.1 A sheet sample of approximately 3 ft [0.9 m] by coil width is placed on a flat table. Push material diagonally along the sample using a push block to within 4 in. [10 cm] of the selected corner and measure the vertical uplift using a tapered gauge, a stepblock gauge, or a stepblock gauge-standard ruler.

7.2.2.2 Shear through the center line of the shape anomaly and measure as an edge wave using a tapered gauge or a stepblock gauge.

7.2.2.3 Measure using a computer-based shape measuring instrument or other instrument of appropriate design.

7.3 Full Center (see Fig. 6):

7.3.1 Definition—Any overall deviation of a sheet from a recognized flat surface occurring over a major portion of the sheet width parallel to the rolling direction other than at the sheet edges.

7.3.2 Measuring Practices:

7.3.2.1 A sheet sample of approximately 3 ft [0.9 m] by coil width is placed on a flat table. Push material diagonally along the sample until the maximum lift occurs at the using a push block to within 4 in. [10 cm] of the selected corner and measure the vertical uplift using a tapered gauge or gauge, a stepblock gauge, or a standard ruler.




FIG. 5 Ridge Buckle, Quarter Buckle, Center Buckle




FIG. 6 Full Center

7.3.2.2 Shear through the center line of the shape anomaly and measure as an edge wave using a tapered gauge or a stepblock gauge.

7.3.2.3 Measure using a computer-based shape measuring instrument or other instrument of appropriate design.

7.4 Edge Lift (see Fig. 7):

7.4.1 Definition—Any deviation of one sheet edge other than a wavy edge. This edge lift is parallel to the rolling direction and rises when placed on a recognized flat surface.

7.4.2 Measuring Practice—A sheet sample of approximately 3 ft [0.9 m] by coil width is placed on a flat table. Push material diagonally along the sheet until the maximum lift occurs at the selected edge and measure the vertical distance (A) with a tapered gauge, a stepblock gauge, or a standard ruler.

7.5 Coil Set and Reverse Coil Set (see Fig. 8):

7.5.1 Definition—A bow condition or deviation in the sheet as measured from a recognized flat surface. The deviation runs parallel with the rolling direction and takes the shape of a coil. Reverse coil set reverses the shape of a coil. The degree of coil set usually is determined in a vertical, free-hanging position when held against a straight-edge. Use of the shape test jig (Fig. 3) is highly recommended for this measurement.




FIG. 7 Edge Lift