



Standard Specification for Titanium and Titanium Alloy Welded Pipe¹

This standard is issued under the fixed designation B862; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the requirements for 33 grades of titanium and titanium alloy welded pipe intended for general corrosion resisting and elevated temperature service as follows:

- 1.1.1 *Grade 1*—UNS R50250. Unalloyed titanium,
- 1.1.2 *Grade 2*—UNS R50400. Unalloyed titanium,
 - 1.1.2.1 *Grade 2H*—UNS R50400. Unalloyed titanium (Grade 2 with 58 ksi (400 MPa) minimum UTS),
- 1.1.3 *Grade 3*—UNS R50550. Unalloyed titanium,
- 1.1.4 *Grade 5*—UNS R56400. Titanium alloy (6 % aluminum, 4 % vanadium),
- 1.1.5 *Grade 7*—UNS R52400. Unalloyed titanium plus 0.12 to 0.25 % palladium,
 - 1.1.5.1 *Grade 7H*—UNS R52400. Unalloyed titanium plus 0.12 to 0.25 % palladium (Grade 7 with 58 ksi (400 MPa) minimum UTS),
- 1.1.6 *Grade 9*—UNS R56320. Titanium alloy (3 % aluminum, 2.5 % vanadium),
- 1.1.7 *Grade 11*—UNS R52250. Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.8 *Grade 12*—UNS R53400. Titanium alloy (0.3 % molybdenum, 0.8 % nickel),
- 1.1.9 *Grade 13*—UNS R53413. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.10 *Grade 14*—UNS R53414. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.11 *Grade 15*—UNS R53415. Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.12 *Grade 16*—UNS R52402. Unalloyed titanium plus 0.04 to 0.08 % palladium,
 - 1.1.12.1 *Grade 16H*—UNS R52402. Unalloyed titanium plus 0.04 to 0.08 % palladium (Grade 16 with 58 ksi (400 MPa) minimum UTS),
- 1.1.13 *Grade 17*—UNS R52252. Unalloyed titanium plus 0.04 to 0.08 % palladium,

- 1.1.14 *Grade 18*—UNS R56322. Titanium alloy (3 % aluminum, 2.5 % vanadium plus 0.04 to 0.08 % palladium),
- 1.1.15 *Grade 19*—UNS R58640. Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),
- 1.1.16 *Grade 20*—UNS R58645. Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 to 0.08 % palladium,
- 1.1.17 *Grade 21*—UNS R58210. Titanium alloy (15 % molybdenum, 3 % aluminum, 2.7 % niobium, 0.25 % silicon),
- 1.1.18 *Grade 23*—UNS R56407. Titanium alloy (6 % aluminum, 4 % vanadium, extra low interstitial, ELI),
- 1.1.19 *Grade 24*—UNS R56405. Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.04 to 0.08 % palladium,
- 1.1.20 *Grade 25*—UNS R56403. Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 to 0.8 % nickel and 0.04 to 0.08 % palladium,
- 1.1.21 *Grade 26*—UNS R52404. Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
 - 1.1.21.1 *Grade 26H*—UNS R52404. Unalloyed titanium plus 0.08 to 0.14 % ruthenium (Grade 26 with 58 ksi (400 MPa) minimum UTS),
- 1.1.22 *Grade 27*—UNS R52254. Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
- 1.1.23 *Grade 28*—UNS R56323. Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.08 to 0.14 % ruthenium,
- 1.1.24 *Grade 29*—UNS R56404. Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitial elements (ELI)) plus 0.08 to 0.14 % ruthenium,
- 1.1.25 *Grade 33*—UNS R53442. Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.26 *Grade 34*—UNS R53445. Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.27 *Grade 35*—UNS R56340. Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),
- 1.1.28 *Grade 37*—UNS R52815. Titanium alloy (1.5 % aluminum),
- 1.1.29 *Grade 38*—UNS R54250. Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron), and

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 1995. Last previous edition approved in 2014 as B862 – 14. DOI: 10.1520/B0862-19.

1.1.30 *Grade 39*—UNS R53390. Titanium alloy (0.25 % iron, 0.4 % silicon).

NOTE 1—H grade material is identical to the corresponding numeric grade (that is, Grade 2H = Grade 2) except for the higher guaranteed minimum UTS, and may always be certified as meeting the requirements of its corresponding numeric grade. Grades 2H, 7H, 16H, and 26H are intended primarily for pressure vessel use.

1.2 Pipe 8 in. NPS (nominal pipe size) and larger is most frequently custom made for an order. In such cases, the purchaser carefully should consider the applicability of this specification. Since the pipe is custom made, the purchaser may choose a wall thickness other than those in **Table 1** to meet specific operating conditions. The purchaser may also be better served to specify only the portions of this specification that are required to meet the operating conditions (for example, annealing, flattening test, chemistry, properties, etc.).

1.3 Optional supplementary requirements are provided for pipe where a greater degree of testing is desired. These supplementary requirements may be invoked by the purchaser, when desired, by specifying in the order.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#) <http://catalog/standards/sist/51572d08-55>
- [B600 Guide for Descaling and Cleaning Titanium and Titanium Alloy Surfaces](#)
- [E8 Test Methods for Tension Testing of Metallic Materials \[Metric\] E0008_E0008M](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- [E539 Test Method for Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry](#)
- [E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion](#)
- [E1417 Practice for Liquid Penetrant Testing](#)
- [E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method](#)
- [E1941 Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis](#)
- [E2371 Test Method for Analysis of Titanium and Titanium](#)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry \(Performance-Based Test Methodology\)](#)

[E2994 Test Method for Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry \(Performance-Based Method\)](#)

2.2 ANSI/ASME Standards:³

[B.1.20.1 Pipe Threads, General Purpose \(Inch\)](#)

[B 36.10 Carbon, Alloy and Stainless Steel Pipes](#)

[B 36.19M-1985 Stainless Steel Pipe](#)

[ASME Boiler and Pressure Vessel Code Section VIII](#)

2.3 AWS Standard:⁴

[AWS A5.16/A5.16M-2013 Specification for Titanium and Titanium Alloy Welding Electrodes and Rods](#)

3. Terminology

3.1 Definitions:

3.1.1 *lot, n*—a number of pieces of pipe of the same nominal size and wall thickness manufactured by the same process from a single heat of titanium or titanium alloy and heat treated by the same furnace parameters in the same furnace.

3.1.2 *welded pipe, n*—a hollow tubular product produced by forming flat-rolled product and seam welding to make a right circular cylinder.

4. Ordering Information

4.1 Orders for materials under this specification shall include the following information as required:

- 4.1.1 Quantity,
- 4.1.2 Grade number (Section 1 and **Table 2**),
- 4.1.3 Nominal pipe size and schedule (**Table 1**),
- 4.1.4 Diameter tolerance (see **9.2**),
- 4.1.5 Method of manufacture and finish (Sections 5 and 10),
- 4.1.6 Product analysis, if required (Sections 6 and 7; **Table 1** and **Table 3**),
- 4.1.7 Mechanical properties, (Sections 8, 11, 13, 14, and 15, and **Table 4**),
- 4.1.8 Packaging (Section 22),
- 4.1.9 Inspection and test reports (Sections 18, 19 and 20), and
- 4.1.10 Supplementary requirements.

5. Manufacture

5.1 Welded pipe shall be made from annealed flat-rolled products by a welding process that will yield a product meeting the requirements of this specification. Filler metal, if used, shall be produced to the latest revision of Specification AWS A5.16/A5.16M-2013 employing the ER Ti-X grade listed in **Table 5**, unless specified otherwise on the purchase order.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from American Welding Society (AWS), 550 NW LeJeune Rd., Miami, FL 33126, <http://www.aws.org>.

TABLE 1 Dimensions of Pipe

NOTE 1—Schedule sizes conform to ANSI/ASME B 36.19M-1985 (for “S” sizes) or B 36.10 (for non-S sizes).

NOTE 2—The decimal thickness listed for the respective pipe sizes represent their nominal wall thickness.

NPS Desig.	Outside Dia.		Nominal Wall Thickness															
	in	mm	Schedule 5S ^A		Schedule 5 ^A		Schedule 10S ^A		Schedule 10 ^A		Schedule 40S		Schedule 40		Schedule 80S		Schedule 80	
			in	mm	in	mm	in	mm	in	mm	in	mm	in	mm	in	mm	in	mm
1/6	0.405	10.29	x	x	x	x	0.049	1.24	0.049	1.24	0.068	1.73	0.068	1.73	0.095	2.41	0.095	2.41
1/4	0.540	13.72	x	x	x	x	0.065	1.65	0.065	1.65	0.088	2.24	0.088	2.24	0.119	3.02	0.119	3.02
3/8	0.675	17.15	x	x	x	x	0.065	1.65	0.065	1.65	0.091	2.31	0.091	2.31	0.126	3.20	0.126	3.20
1/2	0.840	21.34	0.065	1.65	0.065	1.65	0.083	2.11	0.083	2.11	0.109	2.77	0.109	2.77	0.147	3.73	0.147	3.73
3/4	1.050	26.67	0.065	1.65	0.065	1.65	0.083	2.11	0.083	2.11	0.113	2.87	0.113	2.87	0.154	3.91	0.154	3.91
1	1.315	33.40	0.065	1.65	0.065	1.65	0.109	2.77	0.109	2.77	0.133	3.38	0.133	3.38	0.179	4.55	0.179	4.55
1-1/4	1.660	42.16	0.065	1.65	0.109	2.77	0.109	2.77	0.109	2.77	0.140	3.56	0.140	3.56	0.191	4.85	0.191	4.85
1-1/2	1.900	48.26	0.065	1.65	0.109	2.77	0.109	2.77	0.109	2.77	0.145	3.68	0.145	3.68	0.200	5.08	0.200	5.08
2	2.375	60.32	0.065	1.65	0.109	2.77	0.109	2.77	0.109	2.77	0.154	3.91	0.154	3.91	0.218	5.54	0.218	5.54
2-1/2	2.875	73.02	0.083	2.11	0.120	3.05	0.120	3.05	0.120	3.05	0.203	5.16	0.203	5.16	0.276	7.01	0.276	7.01
3	3.500	88.90	0.083	2.11	0.120	3.05	0.120	3.05	0.120	3.05	0.216	5.49	0.216	5.49	0.300	7.62	0.300	7.62
3-1/2	4.000	101.60	0.083	2.11	0.120	3.05	0.120	3.05	0.120	3.05	0.226	5.74	0.226	5.74	0.318	8.08	0.318	8.08
4	4.500	114.30	0.083	2.11	0.120	3.05	0.120	3.05	0.120	3.05	0.237	6.02	0.237	6.02	0.337	8.56	0.337	8.56
5	5.563	141.30	0.109	2.77	0.134	3.40	0.134	3.40	0.134	3.40	0.258	6.55	0.258	6.55	0.375	9.53	0.375	9.53
6	6.625	168.27	0.109	2.77	0.134	3.40	0.134	3.40	0.134	3.40	0.280	7.11	0.280	7.11	0.432	10.97	0.432	10.97
8	8.625	219.07	0.109	2.77	0.148	3.76	0.148	3.76	0.148	3.76	0.322	8.18	0.322	8.18	0.500	12.70	0.500	12.70
10	10.75	273.05	0.134	3.40	0.165	4.19	0.165	4.19	0.165	4.19	0.365	9.27	0.365	9.27	0.500	12.70	0.500	12.70
12	12.75	323.85	0.156	3.96	0.180	4.57	0.180	4.57	0.180	4.57	0.375	9.53	0.406	10.31	0.500	12.70	0.688	17.48
14	14.00	355.60	0.156	3.96	0.188	4.78	0.188	4.78	0.250	6.35	x	x	0.438	11.13	x	x	0.750	19.05
16	16.00	406.40	0.165	4.19	0.188	4.78	0.188	4.78	0.250	6.35	x	x	0.500	12.70	x	x	0.844	21.44
18	18.00	457.20	0.165	4.19	0.188	4.78	0.188	4.78	0.250	6.35	x	x	0.562	14.27	x	x	0.938	23.83
20	20.00	508.00	0.188	4.78	0.188	4.78	0.218	5.54	0.250	6.35	x	x	0.594	15.09	x	x	1.031	26.19
22	22.00	558.80	0.188	4.78	0.188	4.78	0.218	5.54	0.250	6.35	x	x	x	x	x	x	1.125	28.58
24	24.00	609.60	0.218	5.54	0.250	6.35	0.250	6.35	0.250	6.35	x	x	0.688	17.48	x	x	1.219	30.96
26	26.00	660.40	x	x	x	x	0.312	7.92	0.312	7.92	x	x	x	x	x	x	x	x
28	28.00	711.20	x	x	x	x	0.312	7.92	0.312	7.92	x	x	x	x	x	x	x	x
30	30.00	762.00	0.250	6.35	0.312	7.92	0.312	7.92	0.312	7.92	x	x	x	x	x	x	x	x
32	32.00	812.80	x	x	x	x	0.312	7.92	0.312	7.92	x	x	0.688	17.48	x	x	x	x
34	34.00	863.60	x	x	x	x	0.312	7.92	0.312	7.92	x	x	0.688	17.48	x	x	x	x
36	36.00	914.40	x	x	x	x	0.312	7.92	0.312	7.92	x	x	0.750	19.05	x	x	x	x

^A Threading not permitted in accordance with ANSI B.1.20.1.

TABLE 2 Chemical Requirements

Composition, Weight Percent^{A,B,C,D,E}

Grade	UNS Number	Carbon, max.	Oxygen, range or max.	Nitrogen, max.	Hydrogen, max.	Iron, range or max.	Aluminum	Vanadium	Palladium	Ruthenium	Nickel	Molybdenum	Chromium	Cobalt	Zirconium	Niobium	Tin	Silicon	Other Elements, max. each	Other Elements, max. total	
1	R50250	0.08	0.18	0.03	0.015	0.20	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
2/2H	R50400	0.08	0.25	0.03	0.015	0.30	--	--	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
3	R50550	0.08	0.35	0.05	0.015	0.30	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--
5	R56400	0.08	0.20	0.05	0.015	0.40	5.5-6.75	3.5-4.5	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
7/7H	R52400	0.08	0.25	0.03	0.015	0.30	--	--	0.12-0.25	--	--	--	--	--	--	--	--	--	0.1	0.4	
9	R56320	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
11	R52250	0.08	0.18	0.03	0.015	0.20	--	--	0.12-0.25	--	--	--	--	--	--	--	--	--	0.1	0.4	
12	R53400	0.08	0.25	0.03	0.015	0.30	--	--	--	0.6-0.9	0.2-0.4	--	--	--	--	--	--	--	0.1	0.4	
13	R53413	0.08	0.10	0.03	0.015	0.20	--	--	--	0.04-0.06	0.4-0.6	--	--	--	--	--	--	--	0.1	0.4	
14	R53414	0.08	0.15	0.03	0.015	0.30	--	--	--	0.04-0.06	0.4-0.6	--	--	--	--	--	--	--	0.1	0.4	
15	R53415	0.08	0.25	0.05	0.015	0.30	--	--	--	0.04-0.06	0.4-0.6	--	--	--	--	--	--	--	0.1	0.4	
16/16H	R52402	0.08	0.25	0.03	0.015	0.30	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	0.1	0.4	
17	R52252	0.08	0.18	0.03	0.015	0.20	--	--	0.04-0.08	--	--	--	--	--	--	--	--	--	0.1	0.4	
18	R56322	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	0.08	--	--	--	--	--	--	--	--	--	0.1	0.4	
19	R58640	0.05	0.12	0.03	0.02	0.30	3.0-4.0	7.5-8.5	--	--	--	3.5-4.5	5.5-6.5	--	3.5-4.5	--	--	--	0.15	0.4	
20	R58645	0.05	0.12	0.03	0.02	0.30	3.0-4.0	7.5-8.5	0.04-0.08	--	--	3.5-4.5	5.5-6.5	--	3.5-4.5	--	--	--	0.15	0.4	
21	R58210	0.05	0.17	0.03	0.015	0.40	2.5-3.5	--	--	--	--	14.0-16.0	--	--	2.2-3.2	--	--	0.15-0.25	0.1	0.4	
23	R56407	0.08	0.13	0.03	0.0125	0.25	5.5-6.5	3.5-4.5	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
24	R56405	0.08	0.20	0.05	0.015	0.40	5.5-6.75	3.5-4.5	0.04-0.08	--	--	--	--	--	--	--	--	--	0.1	0.4	
25	R56403	0.08	0.20	0.05	0.015	0.40	6.75-5.5	3.5-4.5	0.04-0.08	--	0.3-0.8	--	--	--	--	--	--	--	0.1	0.4	
26/26H	R52404	0.08	0.25	0.03	0.015	0.30	--	--	--	0.08-0.14	--	--	--	--	--	--	--	--	0.1	0.4	
27	R52254	0.08	0.18	0.03	0.015	0.20	--	--	--	0.08-0.14	--	--	--	--	--	--	--	--	0.1	0.4	
28	R56323	0.08	0.15	0.03	0.015	0.25	2.5-3.5	2.0-3.0	--	--	--	--	--	--	--	--	--	--	0.1	0.4	
29	R56404	0.08	0.13	0.03	0.0125	0.25	5.5-6.5	3.5-4.5	--	0.08-0.14	--	--	--	--	--	--	--	--	0.1	0.4	
33	R53442	0.08	0.25	0.03	0.015	0.30	--	--	0.01-0.02	0.02-0.04	0.35-0.55	--	0.1-0.2	--	--	--	--	--	0.1	0.4	

TABLE 2 Continued

		Composition, Weight Percent ^{A,B,C,D,E}																		
Grade	UNS Number	Carbon, max.	Oxygen, range or max.	Nitrogen, max.	Hydrogen, max.	Iron, range or max.	Aluminum	Vanadium	Palladium	Ruthenium	Nickel	Molybdenum	Chromium	Cobalt	Zirconium	Niobium	Tin	Silicon	Other Elements, max. each	Other Elements, max. total
34	R53445	0.08	0.35	0.05	0.015	0.30	--	--	0.01-0.02	0.02-0.04	0.35-0.55	--	0.1-0.2	--	--	--	--	--	0.1	0.4
35	R56340	0.08	0.25	0.05	0.015	0.20-0.80	4.0-5.0	1.1-2.1	--	--	--	1.5-2.5	--	--	--	--	--	0.20-0.40	0.1	0.4
37	R52815	0.08	0.25	0.03	0.015	0.30	1.0-2.0	--	--	--	--	--	--	--	--	--	--	--	--	--
38	R54250	0.08	0.20-0.30	0.03	0.015	1.2-1.8	3.5-4.5	2.0-3.0	--	--	--	--	--	--	--	--	--	--	0.1	0.4
39	R53390	0.08	0.15	0.03	0.015	0.15-0.40	--	--	--	--	--	--	--	--	--	--	--	0.30-0.50	0.1	0.4

^A At minimum, the analysis of samples from the top and bottom of the ingot shall be completed and reported for all elements listed for the respective grade in this table.

^B Final product hydrogen shall be reported. Ingot hydrogen need not be reported. Lower hydrogen may be obtained by negotiation with the manufacturer.

^C Single values are maximum. The percentage of titanium is determined by difference.

^D Other elements need not be reported unless the concentration level is greater than 0.1 % each, or 0.4 % total. Other elements may not be added intentionally. Other elements may be present in titanium or titanium alloys in small quantities and are inherent to the manufacturing process. In titanium these elements typically include aluminum, vanadium, tin, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese, and tungsten.

^E The purchaser may, in the written purchase order, request analysis for specific elements not listed in this specification.

TABLE 3 Permissible Variations in Product Analysis

Element	Product Analysis Limits, Max or Range, %	Permissible Variation in Product Analysis
Aluminum	0.5 to 2.5	±0.20
Aluminum	2.5 to 6.75	±0.40
Carbon	0.10	+0.02
Chromium	0.1 to 0.2	±0.02
Chromium	5.5 to 6.5	±0.30
Hydrogen	0.02	+0.002
Iron	0.80	+0.15
Iron	1.2 to 1.8	±0.20
Molybdenum	0.2 to 0.4	±0.03
Molybdenum	1.5 to 4.5	±0.20
Molybdenum	14.0 to 16.0	±0.50
Nickel	0.3 to 0.9	±0.05
Niobium	2.2 to 3.2	±0.15
Nitrogen	0.05	+0.02
Oxygen	0.30	+0.03
Oxygen	0.31 to 0.40	+0.04
Palladium	0.01 to 0.02	±0.002
Palladium	0.04 to 0.08	±0.005
Palladium	0.12 to 0.25	±0.02
Ruthenium	0.02 to 0.04	±0.005
Ruthenium	0.04 to 0.06	±0.005
Ruthenium	0.08 to 0.14	±0.01
Silicon	0.06 to 0.50	±0.02
Vanadium	2.0 to 4.5	±0.15
Vanadium	7.5 to 8.5	±0.40
Zirconium	3.5 to 4.5	±0.20
Residuals ^A (each)	0.15	+0.02

^A A residual is an element in a metal or alloy in small quantities inherent to the manufacturing process but not added intentionally.

5.1.1 Welded pipe may be further reduced by cold working or hot working. Cold reduced pipe shall be annealed after cold working at a temperature of not less than 1000°F. Hot worked pipe finished above 1400°F (760°C) need not be further heat treated.

5.2 Pipe shall be furnished as follows unless otherwise specified:

5.2.1 Grades 1, 2, 2H, 7, 7H, 11, 13, 14, 16, 16H, 17, 26H, 33, 37, and 39 shall be furnished as welded or annealed.

5.2.2 Grades 3, 12, 15, and 34 shall be furnished as annealed.

5.2.3 Grade 5, Grade 23, Grade 24, Grade 25, or Grade 35 shall be furnished as annealed, or aged.

5.2.4 Grade 9, Grade 18, or Grade 38 shall be furnished as annealed.

5.2.5 Grade 19, Grade 20, or Grade 21 shall be furnished as solution treated, or solution treated and aged.

6. Chemical Composition

6.1 The grades of titanium and titanium alloy metal covered by this specification shall conform to the requirements of the chemical compositions shown in [Table 2](#).

6.1.1 The elements listed in [Table 2](#) are intentional alloy additions or elements that are inherent to the manufacture of titanium sponge, ingot, or mill product.

6.1.1.1 Elements other than those listed in [Table 2](#) are deemed to be capable of occurring in the grades listed in [Table 2](#) by and only by way of unregulated or unanalyzed scrap additions to the ingot melt. Therefore, product analysis for elements not listed in [Table 2](#) shall not be required unless specified and shall be considered to be in excess of the intent of this specification.

6.1.2 Elements intentionally added to the melt must be identified, analyzed, and reported in the chemical analysis.

6.2 When agreed upon by the producer and purchaser and requested by the purchaser in a written purchase order, chemical analysis shall be completed for specific residual elements not listed in this specification.

6.3 At least two samples for chemical analysis shall be tested to determine chemical composition. Samples shall be taken from the ingot or the opposite extremes of the product to be analyzed.

7. Product Analysis

7.1 When requested by the purchaser and stated in the purchase order, an analysis of chemical composition shall be made on the finished product.

7.2 The product analysis tolerances listed in [Table 3](#) do not broaden the specified analysis requirements but cover variations between different laboratories in the measurement of chemical content. The manufacturer shall not ship finished product outside of the limits specified in [Table 2](#) for the applicable grade.

8. Tensile Requirements

8.1 The tensile properties of the pipe, in the condition specified, shall conform to the room temperature requirements of [Table 4](#). Mechanical properties for other conditions may be established by written agreement between the manufacturer and the purchaser.

9. Permissible Variations in Dimensions

9.1 A system of standard pipe sizes approved by ANSI as American National Standard for Stainless Steel Pipe (ANSI/ASME B 36.19M-1985) reproduced as [Table 1](#) shall apply.

9.2 Permissible variations in dimensions at any point in the length of the pipe shall conform to the following:

9.2.1 Variations in outside diameter, unless otherwise specified, shall not exceed the limits prescribed in [Table 6](#). For diameters greater than 30 in., the diameter shall not exceed ± 0.5 % of the specified outside diameter. The tolerances on the outside diameter include ovality except as provided for in [9.2.2](#) and [9.2.3](#).

9.2.2 Thin-wall pipe usually develops significant ovality (out-of-roundness) during final annealing, straightening, or both. Thin-wall pipe are defined as having a wall thickness of 3 % or less of the outside diameter.

9.2.3 The diameter tolerances of [Table 6](#) are not sufficient to provide for additional ovality expected in thin-wall pipe and are applicable only to the mean of the extreme (maximum and minimum) outside diameter readings in any one cross section. However, for thin-wall pipe the difference in extreme outside diameter readings (ovality) in any one cross section shall not exceed 1.5 % of the specified outside diameter.

9.2.4 Straightness shall be determined by using a 10 ft (3 m) straight edge placed so that both ends of the straight edge are in contact with the pipe. The separation between the straight edge and the pipe shall not exceed 0.250 in. at any point.