



Designation: C400 – 19

Standard Test Methods for Quicklime and Hydrated Lime for Neutralization of Waste Acid¹

This standard is issued under the fixed designation C400; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the testing of quicklime and hydrated lime for use in the treatment of waste acid solutions and includes the characterization of the liming material and of the acid waste.

NOTE 1—When agreed upon by the manufacturer and the purchaser, this method may be used directly to evaluate the lime requirement for a plant waste acid and in the preparation of the lime slurry; the pH, the time, temperature, and other conditions of treatment may be adjusted to conform to plant practice. Otherwise the test shall be performed as described in this method.

NOTE 2—Under some conditions of test the lime requirement may vary substantially from that indicated by ultimate chemical analysis or by the use of a determination of available alkalinity by titration to a stoichiometric end point.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C50/C50M Practice for Sampling, Sample Preparation,](#)

[Packaging, and Marking of Lime and Limestone Products](#)
[C51 Terminology Relating to Lime and Limestone \(as used by the Industry\)](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

[E70 Test Method for pH of Aqueous Solutions With the Glass Electrode](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology [C51](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *neutralization coefficient*—the number of parts of lime required to neutralize one million parts by weight of sulfuric acid solution (1.5 %) to a pH of 4.4 in 30 min (see [Note 1](#)).

4. Significance and Use

4.1 Since all limes and waste acid solutions are different, this test method evaluates the relative quantity of a given lime needed for the neutralization of a specific quantity of acid.

4.2 Liming materials have a specific basicity factor or measure of alkalinity which can be used for comparing their relative neutralizing power. It avoids dependence on chemical analysis and is determined as grams of calcium oxide equivalents per kilogram of liming material.

4.3 Likewise, specific waste acids have an acid value that can be expressed as grams of hydrochloric acid equivalent per litre of acid waste. This value is related on a stoichiometric basis to lime neutralization requirements of a liquid acid waste.

5. Apparatus

5.1 *pH Measuring Apparatus*, conforming to the requirements of Section 5, Apparatus, and Section 6, Reagents and Materials, of Test Method [E70](#). A time-pH recording device or attachment is desirable but not required.

5.2 *Analytical Balance*, capable of reproducing results within 0.005 g.

5.3 *Stirrer*, motorized, capable of rotating at speeds from 120 to 600 r/min.

¹ These test methods are under the jurisdiction of ASTM Committee [C07](#) on Lime and Limestone and are the direct responsibility of Subcommittee [C07.05](#) on Chemical Tests.

Current edition approved Dec. 1, 2019. Published December 2019. Originally approved in 1957. Last previous edition approved in 2013 as C400 – 98 (2013) ^{ϵ 1}. DOI: 10.1520/C0400-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.