



Standard Test Method for Air Content of Hydraulic Cement Mortar¹

This standard is issued under the fixed designation C185; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of the air content of hydraulic cement mortar under the conditions hereinafter specified.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 Values in SI shall be obtained by measurement in SI units or by appropriate conversion, using the Rules for Conversion and Rounding in [IEEE/ASTM SI 10](#), of measurements made in other units.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 **Warning**—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

[C91/C91M](#) Specification for Masonry Cement

[C109/C109M](#) Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

[C150/C150M](#) Specification for Portland Cement

[C183/C183M](#) Practice for Sampling and the Amount of Testing of Hydraulic Cement

[C185](#) Test Method for Air Content of Hydraulic Cement Mortar

[C219](#) Terminology Relating to Hydraulic and Other Inorganic Cements

[C230/C230M](#) Specification for Flow Table for Use in Tests of Hydraulic Cement

[C305](#) Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

[C511](#) Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

[C595/C595M](#) Specification for Blended Hydraulic Cements

[C778](#) Specification for Standard Sand

[C1005](#) Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

[C1157/C1157M](#) Performance Specification for Hydraulic Cement

[C1328/C1328M](#) Specification for Plastic (Stucco) Cement

[C1329/C1329M](#) Specification for Mortar Cement

¹ This test method is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.21 on Air Entrainment. Current edition approved Sept. 1, 2015/Dec. 1, 2019. Published October 2015/December 2019. Originally approved in 1944. Last previous edition approved in 2015 as [C185 – 15](#)/[C185 – 15a](#). DOI: [10.1520/C0185-15A](#); [10.1520/C0185-19](#).

² Refer to the section on Safety Precautions, "Manual of Cement Testing," *Annual Book of ASTM Standards*, Vol 04.01.

³ For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

E438 Specification for Glasses in Laboratory Apparatus

E694 Specification for Laboratory Glass Volumetric Apparatus

IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI): The Modern Metric System

3. Terminology

3.1 *Definitions*—The terms in this test method are defined in Terminology [C219](#).

4. Summary of Test Method

4.1 Prepare a mortar with standard sand and the cement to be tested, using a water content sufficient to give a required flow. Compact the mortar into a measure of known volume and determine mass. Calculate the air content from the measured density of the mortar, the known densities of the constituents, and the mixture proportions.

5. Significance and Use

5.1 The purpose of this test method is to determine whether or not the hydraulic cement under test meets the air-entraining or non-air-entraining requirements of the applicable hydraulic cement specification for which the test is being made. The air content of concrete is influenced by many factors other than the potential of the cement for air entrainment.

6. Apparatus

6.1 *Flow Table, Flow Mold, and Caliper*, shall conform to Specification [C230/C230M](#).

6.2 *Measure*—A cylindrical measure having an inside diameter of 76 ± 2 mm and a depth (approximately 88 mm) adjusted by standardization with water to contain 400 ± 1 mL at $23.0 \pm 2.0^\circ\text{C}$. For the purposes of this test, the capacity of the measure in millilitres is the mass of the water content of the measure, in grams, divided by 0.9976, no correction in mass being made for the buoyant effect of air. The measure shall have a uniform wall thickness. The thickness of the wall and bottom shall not be less than 2.9 mm. The total mass of the empty measure shall not be more than 900 g. The measure shall be made of a metal not attacked by the cement mortar.

6.3 *Verification*—Verify the volume of the 400 mL measure by filling with distilled water at $23.0 \pm 2.0^\circ\text{C}$ to a point where the meniscus extends appreciably above the top of the measure, placing a clean piece of plate glass on the top of the measure, and allowing the excess water to be squeezed out. The absence of air bubbles as seen through the glass ensures that the measure is completely full. Care shall be taken that the excess water is wiped from the sides of the container before weighing. Perform the verification at least every 2 ½ years.

6.4 *Mixer, Bowl, and Paddle*, shall conform to the apparatus section of Practice [C305](#).

6.5 *Straightedge*—A steel straightedge not less than 200 mm long and not less than 1.5 mm nor more than 3.5 mm in thickness ([Note 1](#)).

NOTE 1—The trowel specified in Test Method [C109/C109M](#) and the straightedge specified in Test Method [C185](#) may be used for this purpose, providing they comply with the planeness indicated.

6.6 *Trowel*, having a steel blade 100 to 150 mm in length, with straight edges. The edges when placed on a plane surface shall not depart from straightness by more than 1 mm ([Note 1](#)).

6.7 *Weights and Weighing Devices*, shall conform to Specification [C1005](#). Evaluate the weighing device for precision and accuracy at a total load of 2 kg.

6.8 *Glass Graduates*—Glass graduates of 250 mL capacity, conforming to the requirements of Specifications [E438](#) and [E694](#).

6.9 *Tamper*, conforming to the requirements of Test Method [C109/C109M](#). The tamping face of the tamper shall be flat and at right angles to the length of the tamper.

6.10 *Tapping Stick*, a piece of hard wood having a diameter of approximately 16 mm and a length of approximately 152 mm.

6.11 *Spoon*—A metal restaurant-type serving spoon not less than 230 mm in length and with a bowl approximately 100 mm in length.

7. Temperature and Humidity

7.1 Maintain the temperature of the room and dry materials at $23.0 \pm 4.0^\circ\text{C}$. Maintain the temperature and the humidity of the mixing room and the temperature of the mixing water in accordance with Specification [C511](#) (Section Requirements for Cement Mixing Rooms).

~~6.2 Condition the mixing water and the measure, if it is being calibrated at $23 \pm 2^\circ\text{C}$.~~

~~6.3 Maintain the relative humidity of the laboratory at not less than 50 %.~~

8. Standard Sand

8.1 Use sand conforming to the requirements of Specification [C778](#) for 20–30 sand.