



Designation: ~~D3755~~—14 D3755 – 20

Standard Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials Under Direct-Voltage Stress¹

This standard is issued under the fixed designation D3755; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope—Scope*

1.1 This test method covers the determination of dielectric breakdown voltage and dielectric strength of solid electrical insulating materials under direct-voltage stress.

1.2 Since some materials require special treatment, reference shall also be made to ASTM specifications or to the test method directly applicable to the material to be tested. See Test Method [D149](#) for the determination of dielectric strength of electrical insulating materials at commercial power frequencies.

1.3 This test method is similar to IEC Publication 243-2. All procedures in this test method are included in IEC 243-2. Differences between this test method and IEC 243-2 are largely editorial.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific precaution statements are given in Section 7.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D149](#) Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies

[D176](#) Test Methods for Solid Filling and Treating Compounds Used for Electrical Insulation (Withdrawn 2013)³

[D877](#) Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using Disk Electrodes

[D1711](#) Terminology Relating to Electrical Insulation

[D2436](#) Specification for Forced-Convection Laboratory Ovens for Electrical Insulation (Withdrawn 1994)³

[D3487](#) Specification for Mineral Insulating Oil Used in Electrical Apparatus

2.2 *ANSI Standard:*⁴

[ANSI C68.1](#) Techniques for Dielectric Tests, IEEE Standard No. 4.

2.3 *IEC Standard:*

[IEC 243-2](#) Methods of test for electric strength of solid insulating materials—Part 2: Additional requirements for tests using direct voltage⁴

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee [D09](#) on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee [D09.12](#) on Electrical Tests.

Current edition approved ~~May 15, 2014~~ Jan. 1, 2020. Published ~~June 2014~~ January 2020. Originally approved in 1979. Last previous edition approved in ~~2004~~ 2014 as ~~D3755 – 97 (2004)D3755 – 14~~, which was withdrawn in January 2013 and reinstated in June 2014. DOI: 10.1520/D3755-14. DOI: 10.1520/D3755-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

*A Summary of Changes section appears at the end of this standard

3.1.1 *creepage distance, n*—shortest distance between two conductive parts (typically metal), measured along the surface of the dielectric insulator.

3.1.2 *dielectric breakdown voltage, n*—Refer to Terminology **D1711**.

3.1.3 *dielectric strength, n*—Refer to Terminology **D1711**.

3.1.4 *flashover, flashover (as related to electrical), n*—Refer to Terminology **D1711**: an electrical discharge between two electrodes which occurs around the surface of a solid dielectric in the surrounding medium.

4. Summary of Test Method

4.1 The specimen, held in a properly designed electrode system, is electrically stressed by the application of an increasing direct voltage until internal breakdown occurs. The test voltage is applied at a uniform rate of increase. The direct voltage is obtained from a high-voltage supply of adequate current capacity and regulation, reasonably ripple-free, with facilities for measuring and controlling the output voltage.

5. Significance and Use

5.1 This test method is intended for use as a control and acceptance test for direct-voltage applications. It can also be used in the partial evaluation of material for specific end uses and as a means for detecting changes in material due to specific deteriorating causes.

5.2 Experience indicates that the breakdown value obtained with direct voltage usually will be approximately 2 to 4 times the rms value of the 60-Hz alternating-voltage breakdown.

5.3 For a nonhomogeneous test specimen, the distribution of voltage stress within the specimen is determined by impedance (largely capacitive) with alternating voltage. With an increasing direct voltage, the voltage distribution will still be largely capacitive, although this depends partly on the rate of voltage increase. After steady application of direct voltage the voltage division across the test specimen is determined by resistance. The choice of direct or alternating voltage depends upon the purpose for which the breakdown test is to be used, and to some extent, on the intended application of the material.

5.4 A more complete discussion of the significance of dielectric breakdown tests is given in **Appendix X1** of this method and in **Appendix X1** of Test Method **D149**. Those appendix sections of Test Method **D149** that refer to alternating voltage are not applicable to the direct-voltage method.

6. Apparatus

6.1 *Basic Direct-Voltage Power Supplies*, or dielectric test sets of various voltage ratings, which can operate with one of the two output terminals grounded, are commonly available commercially. Such apparatus customarily includes the necessary voltage-control, voltage-measuring, and circuit-interrupting equipment. A provision for retaining the breakdown voltage reading after breakdown is desirable.

6.1.1 For a direct voltage derived from a rectified and filtered power frequency source, ripple on the output voltage shall be less than 1 %. The criterion is met if the time constant of the circuit is at least 0.4 s. The time constant is product of the filter capacitance plus the specimen capacitance in microfarads, and the specimen insulation resistance (in megaohms) corresponding to the parallel combination of the voltmeter circuit resistance and the specimen resistance.

6.2 *Voltage Control*, that will enable the test voltage to be increased at a linear rate. Preference shall be given to a variable-speed motor-driven voltage control over a manual control. The rate-of-rise of test voltage shall not vary more than ± 20 % from the specified rate at any point.

6.3 *Voltmeter*, to measure the voltage directly applied to the electrode system. The response of the voltmeter shall be such that its time lag shall not introduce an error greater than 1 % of full scale at any rate-of-rise used. The overall accuracy of the voltmeter and the voltage-measuring device used shall be such that the measurement error will not exceed ± 2 % of full scale and be in accordance with ANSI C68.1.

6.4 *Electrodes:*

6.4.1 For those cases when the insulating material is in the form of flat sheet or tape, or is of the nature of a semisolid (for example, grease potting material, and so forth) the electrodes shall be selected from those listed in Table 1 of Test Method **D149**. The electrode contact pressure shall be adequate to obtain good electrical contact.

6.4.2 Where excellent electrode contact is considered important, use paint or vaporized metal electrodes. Such electrodes shall also be used when specimen geometry prevents the use of rigid, solid metal electrodes. It is possible that the results obtained with painted or sprayed electrodes will not be comparable with those obtained using other types of electrodes.

6.5 *Test Chamber*—For tests under other than ambient conditions, the specimen must be placed in a suitable environmental chamber of adequate size. For tests at elevated temperatures, an oven that meets the requirements of Specification **D2436** will be convenient. The test chamber must be equipped with safety devices (Section 7).

6.6 *Ground Switch*—The power supply shall be equipped with a grounding switch that is gravity operated and designed to close in less than 0.5 s. The grounding switch shall connect the high-voltage output terminal of the power supply and ground terminal through a low resistance when the input supply power is removed or the test chamber door is opened.

7. Safety Precautions

7.1 **Warning**—Lethal voltages are a potential hazard during the performance of this test. It is essential that the test apparatus, and all associated equipment electrically connected to it, be properly designed and installed for safe operation. Solidly ground all electrically conductive parts that a person can contact during the test. Provide means for use at the completion of any test to ground any parts that were at high voltage during the test or have the potential for acquiring an induced charge during the test or retaining a charge even after disconnecting the voltage source. Thoroughly instruct all operators as to the correct procedures for performing tests safely. When making high-voltage tests, particularly in compressed gas or in oil, it is possible for the energy released at breakdown to be sufficient to result in fire, explosion, or rupture of the test chamber. Design test equipment, test chambers, and test specimens so as to minimize the possibility of such occurrences and to eliminate the possibility of personal injury. If the potential for fire exists, have fire suppression equipment available.

7.2 When a direct-voltage test has been applied to the test specimen, both the specimen and power supply can remain charged after the test voltage source has been de-energized. This will present a hazard to test personnel. Direct-voltage testing is more hazardous than testing with alternating voltage, where the charge on the specimen is rapidly dissipated in the low-impedance winding of the test transformer after the test is de-energized.

7.3 The test specimen and high-voltage output of the power supply must be enclosed in a grounded metallic screen. Access to the test enclosure must be dependent upon prior grounding of the power supply and test specimen through a low resistance as referred to in 6.6.

7.4 A manual grounding stick must be used to completely discharge the test specimen and power supply after the test and prior to handling them. The grounding stick shall be left in contact with the test specimen and high-voltage transformer terminals for as long as feasible.

7.5 **Warning**—Ozone is a physiologically hazardous gas at elevated concentrations. Levels of acceptable industrial exposure have been established by the American Conference of Government and Industrial Hygienists.⁵ Ozone has a distinctive odor that is initially discernible at low concentrations, but temporary loss of the sense of smell can occur. It is likely to be present wherever voltages exist that are sufficient to cause partial or complete discharges in air or other atmospheres containing oxygen. When the odor of ozone is persistently present or when ozone generating conditions continue, the concentration of ozone in the atmosphere shall be measured using commercially available monitoring devices. Appropriate means, such as installation of exhaust vents, shall be taken to maintain ozone concentrations in working areas within acceptable levels.

8. Criteria of Breakdown

8.1 Dielectric breakdown is generally accompanied by an increase in current in the test circuit that will activate a sensing element such as a circuit breaker, a fuse, or current-sensing circuit. If sensitivity of the element is well coordinated with the characteristics of the test equipment and the material under test, its operation will be a positive indication of breakdown.

8.2 Failure of a circuit breaker to operate is not be a positive criterion of the absence of breakdown. A breaker can fail to trip because it is set for too great a current or because of malfunction. On the other hand, if the tripping circuit is set for too low a current, currents due to leakage or partial discharge (corona) will cause it to trip before breakdown voltage is reached.

8.3 Observe the specimen during the test to ascertain that tripping of the breaker or current-sensing circuit is not caused by flashover. When flashover is a problem, it will be necessary to provide for more creepage distance around the electrodes, to decrease specimen thickness, or to immerse the specimen in a liquid dielectric (Section 13).

8.4 Observation of actual rupture or decomposition is positive evidence of specimen breakdown. In test position, however, these physical evidences of breakdown are not always apparent. If breakdown is in question it is common practice to repeat the test on the same specimen. Breakdown is confirmed when reapplication of test voltage results in a substantially lower breakdown voltage.

9. Test Specimens

9.1 For a description of test specimens of materials and their preparation, refer to the ASTM methods applicable to the materials to be tested.

9.2 Provide specimens that are representative of the material to be tested. Prepare enough specimens to permit making five tests. In the preparation of test specimens from solid materials, take care that the surfaces in contact with the electrodes are parallel and as plane and smooth as the material permits.

⁵ American Conference of Governmental Industrial Hygienists, Building D-7, 6500 Glenway Drive, Cincinnati, OH 45211.