

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Lightning protection system components (LPSC) –
Part 7: Requirements for earthing enhancing compounds**

**Composants des systèmes de protection contre la foudre (CSPF) –
Partie 7: Exigences pour les enrichisseurs de terre**

[IEC 62561-7:2024](https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024)

<https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024>





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2024 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications, symboles graphiques et le glossaire. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 500 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 25 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Lightning protection system components (LPSC) –
Part 7: Requirements for earthing enhancing compounds**

**Composants des systèmes de protection contre la foudre (CSPF) –
Partie 7: Exigences pour les enrichisseurs de terre**

[IEC 62561-7:2024](https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024)

<https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.020, 91.120.40

ISBN 978-2-8322-8276-2

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Requirements	8
4.1 General.....	8
4.2 Documentation and installation instructions	8
4.3 Material	8
4.4 Marking.....	8
5 Tests	9
5.1 General.....	9
5.2 Leaching test	9
5.2.1 General	9
5.2.2 Determination of leachable ions.....	10
5.2.3 Acceptance criteria	10
5.3 Sulphur determination.....	10
5.3.1 General	10
5.3.2 Acceptance criteria	10
5.4 Determination of resistivity.....	10
5.4.1 General	10
5.4.2 Testing apparatus.....	10
5.4.3 Test procedure	11
5.4.4 Acceptance criteria	12
5.5 pH measurement.....	12
5.5.1 General	12
5.5.2 Testing apparatus – Reagents	12
5.5.3 Material preparation.....	12
5.5.4 Test procedure	13
5.5.5 Acceptance criteria	13
5.6 Corrosion tests	13
5.6.1 General	13
5.6.2 Test apparatus	13
5.6.3 Test preparation	13
5.6.4 Test procedure	14
5.6.5 Acceptance criteria	14
5.7 Documentation and installation instructions	14
5.8 Marking.....	14
6 Structure and content of the test report.....	14
6.1 General.....	14
6.2 Report identification	15
6.3 Specimen description.....	15
6.4 Standards and references	15
6.5 Test procedure.....	15
6.6 Testing equipment description	16
6.7 Measuring instruments description.....	16

6.8	Results and parameters recorded	16
6.8.1	Measured, observed or derived results	16
6.8.2	Statement of pass or fail	16
Annex A (informative)	Corrosion load.....	17
Annex B (normative)	Applicability of previous tests	18
Bibliography	19
Figure 1	– Typical configurations for a four-electrode soil box.....	11
Figure A.1	– Corrosion load (free corrosion without concentration cell)	17
Table B.1	– Differences in the requirements for earthing enhancing compounds complying with IEC 62561-7:2011 or IEC 62561-7:2018.....	18

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62561-7:2024](https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024)

<https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

LIGHTNING PROTECTION SYSTEM COMPONENTS (LPSC) –

Part 7: Requirements for earthing enhancing compounds

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 62561-7 has been prepared by IEC technical committee 81: Lightning protection. It is an International Standard.

This third edition cancels and replaces the second edition published in 2018. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Figure A.1 has been replaced with a simpler one that clearly shows the high and low corrosion load limits of the earth enhancing compounds without the need for special knowledge;
- b) pH measurement has been introduced.

The text of this International Standard is based on the following documents:

Draft	Report on voting
81/755/FDIS	81/761/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 62561 series, published under the general title *Lightning protection system components (LPSC)*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62561-7:2024](#)

<https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024>

INTRODUCTION

This part of IEC 62561 deals with the requirements and tests for earthing enhancing compounds used as lightning protection system components (LPSC) designed and implemented in accordance with the IEC 62305 series.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62561-7:2024](#)

<https://standards.iteh.ai/catalog/standards/iec/77da246d-3a90-437f-a3b3-f95f968cf6a9/iec-62561-7-2024>

LIGHTNING PROTECTION SYSTEM COMPONENTS (LPSC) –

Part 7: Requirements for earthing enhancing compounds

1 Scope

This part of IEC 62561 specifies the requirements and tests for earthing enhancing compounds producing low resistance of an earth termination system.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4689-3, *Iron ores – Determination of sulfur content – Part 3: Combustion/infrared method*

EN 12457-2, *Characterisation of waste – Leaching – Compliance test for leaching of granular waste materials and sludges – Part 2: One stage batch test at a liquid to solid ratio of 10 l/kg for materials with particle size below 4 mm (without or with size reduction)*

CEN/TR 16192, *Waste – Guidance on analysis of eluates*

ASTM G57-20, *Standard Test Method for Measurement of Soil Resistivity Using the Wenner Four-Electrode Method*

ASTM G59-97, *Standard Test Method for Conducting Potentiodynamic Polarization Resistance Measurements*

ASTM G102-89, *Standard Practice for Calculation of Corrosion Rates and Related Information from Electrochemical Measurements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

earthing enhancing compound

EEC

low resistivity compound that is intended to lower the resistance to earth of an earth termination system when added between the buried earth electrode and the surrounding soil

3.2 leaching test

test during which the earthing enhancing compound is put into contact with a leachant and some constituents of the material are extracted

3.3 aggressive EEC

compound characterized by a pH value and resistivity within the range specified in Annex A

3.4 non-aggressive EEC

compound characterized by a pH value and resistivity within the range specified in Annex A

4 Requirements

4.1 General

Earthing enhancing compounds shall be so designed and constructed that in normal use their performance is reliable and without danger to persons and the surrounding environment.

The choice of a material depends on its ability to match the requirements of a particular application.

NOTE National regulations can apply.

4.2 Documentation and installation instructions

The manufacturer or supplier of the earthing enhancing compounds shall provide adequate information in his literature to ensure that the installer can select and install the materials in a suitable and safe manner, containing the following information:

- a) preparation instructions;
- b) installation instructions;
- c) resistivity value and the test method used;
- d) conformity statement to the present document (IEC 62561-7).

Compliance is checked in accordance with 5.7.

The manufacturer's literature shall contain information on how to maintain the characteristics of the earthing enhancing compound so it remains stable over time.

4.3 Material

The material of the earthing enhancing compound shall be chemically inert to subsoil. It shall not pollute the environment. It shall provide a stable environment in terms of physical and chemical properties.

Compliance is checked by the tests specified in 5.2, 5.3, 5.4, 5.5 and 5.6.

4.4 Marking

All products complying with this document shall have indelible markings containing at least the following information:

- a) manufacturer's or responsible vendor's name or its trademark;
- b) any identifying symbol;
- c) the type or the serial number of the batch of the earthing enhancing compound;

- d) the resistivity value;
- e) the pH value.

Where this proves to be impractical the marking in accordance with c), d) and e) may be given on the accompanying documentation.

The marking should be given on the packaging.

Compliance is checked in accordance with 5.8.

5 Tests

5.1 General

The tests in accordance with this document are type tests. These tests are of such a nature that, after they have been performed, it is not necessary to repeat them unless changes are made to the materials, design or type of manufacturing process, which can change the performance characteristics of the product.

Tests are carried out with the specimens prepared as in normal use according to the manufacturer's or supplier's instructions, unless otherwise specified.

All tests are carried out on new specimens.

Three samples are subjected to each individual test and the requirements are satisfied if all the criteria are met, unless otherwise specified.

The applicant, when submitting the material to be tested, can also submit an additional quantity which could be necessary should one test fail. The testing laboratory will then, without further request, repeat the test and will reject the samples only if a further failure occurs. If the additional sample is not submitted at the same time, the failure of one test will entail rejection.

For EECs already tested according to IEC 62561-7 the applicability of previous tests according to Annex B can be applied.

For new components complete type tests and samples according to Clause 5 are required.

5.2 Leaching test

5.2.1 General

The leaching test shall be performed in accordance with EN 12457-2 in order to determine the content of:

- Fe (iron);
- Cu (copper);
- Zn (zinc);
- Ni (nickel);
- Cd (cadmium);
- Co (cobalt);
- Pb (lead).

5.2.2 Determination of leachable ions

Determination of the concentrations of any or all of the metals listed in 5.2.1 shall be performed in accordance with CEN/TR 16192.

5.2.3 Acceptance criteria

The criteria are given by national or international regulations.

5.3 Sulphur determination

5.3.1 General

The test for the determination of sulphur shall be performed in accordance with ISO 4689-3:2017 that specifies a combustion and infrared method, using a high-frequency induction furnace, for the combustion of the sample and infrared technique for the determination of the sulphur content.

5.3.2 Acceptance criteria

The material is deemed to have passed the test if all the values measured according to 5.3.1 are less than 2 % in sulphur content. The recorded value of sulphur resulting from this test result shall be indicated in the product documentation.

5.4 Determination of resistivity

5.4.1 General

The four-electrode method shall be used to determine the resistivity of earthing enhancing compounds as described in ASTM G57-20. Representative samples of the materials shall be taken from a typical packaging as provided by the manufacturer and prepared in accordance with the manufacturer's instructions. Three samples of the earthing enhancement material shall be tested in a four-electrode soil box.

With the four-electrode method, a voltage is applied to the outer electrodes, which causes current to flow. The resulting voltage drop between the inner electrodes is measured using a voltmeter, and the resulting resistance is calculated. The resistance of the material can also be measured directly.

The resistance of each earthing enhancing compound sample shall be converted to the resistivity value using the following formula:

$$\rho = \frac{R \times A}{a} \quad (1)$$

where

ρ is the sample resistivity ($\Omega \cdot \text{m}$);

R is the resistance (Ω);

A is the cross-sectional area of the container perpendicular to the current flow (m^2);

a is the inner electrode spacing, measured from the inner edges of the electrodes (m).

5.4.2 Testing apparatus

The following apparatus are permitted to be used:

- a) Any reliable commercially available earth resistance meter having two current and two voltage terminals or a low frequency AC source, a high input impedance voltmeter and