



Designation: B971 – 10 (Reapproved 2020)^{ε1}

Standard Specification for Silver-Coated Braid and Ribbon Flat Copper Wire intended for use in Electronic Application¹

This standard is issued under the fixed designation B971; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial corrections were made to 6.4.1.2 and Explanatory Note 7 in January 2020.

1. Scope

1.1 This specification covers silver-coated copper braid and ribbon flat wire intended for electronic application (Explanatory Note 1).

1.2 Two classes of silver-coated braid and ribbon flat copper wire are covered as follows:

1.2.1 *Class A*—Annealed temper.

1.2.2 *Class H*—Hard-drawn.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3.1 *Exceptions*—The SI values for density, resistivity, and volume are to be regarded as standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:²

B1 Specification for Hard-Drawn Copper Wire

B3 Specification for Soft or Annealed Copper Wire

¹ This test method is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.04 on Conductors of Copper and Copper Alloys.

Current edition approved Jan. 1, 2020. Published January 2020. Originally approved in 2010. Last previous edition approved in 2014 as B971 – 10 (2014). DOI: 10.1520/B0971-10R20E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

B49 Specification for Copper Rod for Electrical Purposes
B193 Test Method for Resistivity of Electrical Conductor Materials

B258 Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors

2.2 *Other Standards*:³

NBS Handbook 100 Copper Wire Tables

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size,

3.1.2 Wire size-thickness and width in inches (see 5.4),

3.1.3 Class of wire (see 1.2),

3.1.4 Type of copper, if special (see 4.2),

3.1.5 Package size (see 10.1),

3.1.6 Special packaging marking, if required, and

3.1.7 Place of inspection (see 7.1).

4. Material

4.1 The material shall be silver-coated flat wire (Explanatory Note 1) of such quality and purity that the finished product shall meet the properties and characteristics prescribed in this specification.

4.2 *Copper-Base Metal*—The base metal shall be copper of such quality and purity that the finished product shall have properties and characteristics prescribed in this specification.

NOTE 1—Specifications B1, B3, or B49 define copper suitable for use.

5. General Requirements (See Section 8)

5.1 *Temper*—The silver-coated flat wire conductor shall be provided in either hard-drawn condition (Class H) or annealed condition (Class A) as agreed upon between the manufacturer and purchaser.

5.2 *Tensile and Elongation (Explanatory Note 2)*:

³ Available from National Technical Information Service (NTIS), 5285 Port Royal Rd., Springfield, VA 22161, http://www.ntis.gov.

5.2.1 *Class A*—The silver-coated copper flat wire in the annealed condition shall conform to the elongation requirements prescribed in [Table 1](#). See Explanatory [Note 3](#) for equivalent round diameter calculations based on given thickness and width dimensions for the flat wire. For flat wire whose nominal equivalent round diameter is more than 0.001 in. (0.025 mm) greater than a size listed in [Table 1](#), but less than that of the next larger size, the requirements of the next larger size shall apply. No requirements for tensile strength are specified.

5.2.2 *Class H*—The silver-coated copper flat wire in the hard-drawn condition shall conform to elongation requirements of 1 % minimum to 5 % maximum. The tensile strength shall be 55 000 psi (379 MPa) minimum.

5.3 *Resistivity (Explanatory Note 4)*—The electrical resistivity of the coated wire at a temperature of 20°C shall not exceed the values prescribed in [Table 2](#).

5.4 *Dimensions and Permissible Variations*—The flat wire sizes shall be expressed as the thickness and width of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.0025 mm). The silver-coated flat wire shall not vary from the specified thickness and width by more than the amounts specified in [Table 3](#) and [Table 4](#), respectively.

5.5 *Continuity of Coating*—The silver coating shall be continuous. The continuity of coating on the flat wire shall be determined on representative samples taken before braiding applications or insulating. The continuity of coating shall be determined by the hydrochloric acid-sodium polysulfide test in accordance with [6.4](#). Wire whose coating weight corresponds to a thickness less than 40 μ in. (0.00004 in.) shall not be subject to this test ([Explanatory Note 5](#)). The thickness of

TABLE 1 Tensile Properties^A

Equivalent Round Diameter, in.	Area at 20°C		Elongation in 10 in., min, %
	cmils	in. ²	
0.0641	4 110	0.00323	25
0.0571	3 260	0.00256	25
0.0508	2 580	0.00203	25
0.0453	2 050	0.00161	25
0.0403	1 620	0.00128	25
0.0359	1 290	0.00101	25
0.0320	1 020	0.000804	25
0.0285	812	0.000638	25
0.0253	640	0.000503	25
0.0226	511	0.000401	25
0.0201	404	0.00317	20
0.0179	320	0.000252	20
0.0159	253	0.000199	20
0.0142	202	0.000158	20
0.0126	159	0.000125	20
0.0113	128	0.000100	20
0.0100	100	0.0000785	20
0.0089	79.2	0.0000622	15
0.0080	64.0	0.0000503	15
0.0071	50.4	0.0000396	15
0.0063	39.7	0.0000312	15
0.0056	31.4	0.0000246	15
0.0050	25.0	0.0000196	15
0.0045	20.2	0.0000159	15
0.0040	16.0	0.0000126	15

^A See Explanatory [Note 3](#) for equivalent round calculation.

TABLE 2 Electrical Resistivity Requirements

Class of Wire	Ω-lb/mile ²
A	875.20
H	902.27

TABLE 3 Permissible Variations in Thickness

Nominal Thickness Range, Inch (mm)	Tolerance, Inch (mm)
0.0010 to 0.0014 (0.025 to 0.036)	+/- 0.0002 (0.005)
0.0015 to 0.0019 (0.038 to 0.048)	+/- 0.0003 (0.008)
0.0020 to 0.0049 (0.051 to 0.124)	+/- 0.0004 (0.010)
0.0050 to 0.0100 (0.127 to 0.254)	+/- 0.0005 (0.013)

TABLE 4 Permissible Variations in Width

Nominal Width Range, Inch (mm)	Tolerance, Inch (mm)
0.0100 to 0.0499 (0.254 to 1.27)	+/- 0.0013 (0.033)
0.0500 to 0.0699 (1.27 to 1.78)	+/- 0.0015 (0.038)
0.0700 to 0.0999 (1.78 to 2.54)	+/- 0.0020 (0.051)
0.1000 to 0.1249 (2.54 to 3.17)	+/- 0.0030 (0.076)
0.1250 to 0.1500 (3.18 to 3.81)	+/- 0.0040 (0.102)

coating shall be determined in accordance with Test Method A as prescribed in [Appendix X1](#).

5.6 *Joints*—Necessary joints in the wire and rods prior to final coating and drawing shall be made in accordance with the best commercial practice. There shall be no uncoated joints in the final product.

5.7 *Finish*—The coating shall consist of a smooth continuous layer, firmly adherent to the surface of the copper. The wire shall be free of all imperfections not consistent with the best commercial practice.

6. Test Methods

6.1 *Tensile Strength and Elongation (Explanatory Note 6):*

6.1.1 The tensile strength, expressed in pounds per square inch, shall be obtained by dividing the maximum load carried by the specimen during the tension test by the original cross-sectional area of the specimen. Tensile strength and elongation may be determined simultaneously on the same specimen.

6.1.2 The elongation shall be determined as the permanent increase in length, expressed in percent of the original length, due to the wire breaking in tension. The elongation of the flat wire may be determined by measurements made between the jaws of the tensile testing machine. The zero length shall be the distance between the jaws at the start of the tension test and be as near 10 in. (254 mm) as practicable. The final length shall be the distance between the jaws at the time of rupture. The

fracture shall be between the jaws of the testing machine and not closer than 1 in. (25.4 mm) to the jaw.

6.2 *Resistivity (Explanatory Note 4)*—The electrical resistivity of the material shall be determined in accordance with Test Method B193. The purchaser may accept certification that the wire was drawn from rod stock meeting the international standard for annealed copper instead of resistivity tests on the finished wire.

6.3 *Dimensional Measurements*—Dimensional measurements for width and thickness shall be made with a micrometer caliper equipped with a vernier graduated in 0.0001 in. (0.0025 mm). Measurements shall be made on at least three places on each unit selected for this test. Any measurement taken exceeding the dimensions and permissible variation requirements in 5.4 shall constitute failure to meet the dimensional conformance criterion.

6.4 *Continuity of Coating:*

6.4.1 *Specimens:*

6.4.1.1 *Length of Specimens*—Test specimens shall each have a length of about 6 in. (152 mm). They shall be tagged or marked to correspond with the coil, spool, or reel from which they were cut.

6.4.1.2 *Treatment of Specimens*—Thoroughly clean the specimens by immersion in a suitable organic solvent for at least 3 min; then remove and wipe dry with a clean, soft cloth (**Warning**—See Explanatory Note 7). Keep the specimens thus cleaned wrapped in a clean, dry cloth until tested. Do not handle that part of the specimen to be immersed in the test solution. Take care to avoid abrasion by the cut ends.

6.4.2 *Special Solutions:*

6.4.2.1 *Sodium Polysulfide Solution (sp gr 1.142)*—Make a concentrated solution by dissolving sodium sulfide crystals (cp) in distilled water until the solution is saturated at about 21°C, and adding sufficient flowers of sulfur (in excess of 250 g/L of solution) to provide complete saturation, as shown by the presence in the solution of an excess of sulfur after the solution has been allowed to stand for at least 24 h. Make the test solution by diluting a portion of the concentrated solution with distilled water to a specific gravity of 1.135 to 1.145 at 15.6°C. The sodium polysulfide test solution should have sufficient strength to blacken thoroughly a piece of clean uncoated copper wire in 5 s. A portion of the test solution used for testing samples shall not be considered to be exhausted until it fails to blacken a piece of clean copper as described (Explanatory Note 8):

6.4.2.2 *Hydrochloric Acid Solution (sp gr 1.088)*—Dilute commercial HCl (sp gr 1.12) with distilled water to a specific gravity of 1.088 measured at 15.6°C. A portion of the HCl solution having a volume of 180 mL shall be considered exhausted if it fails to remove within 15 s the discoloration of the silver due to the polysulfide immersion.

6.4.3 *Procedure:*

6.4.3.1 *Immersion in Polysulfide Solution*—Immerse a length of at least 4.5 in. (114 mm) from each of the clean specimens for 30 s in the sodium polysulfide solution, described in 6.4.2.1, maintained at a temperature between 15.6 and 21°C.

6.4.3.2 *Washing*—After the immersion, thoroughly wash the specimens in clean water and wipe dry with a clean, soft cloth.

6.4.3.3 *Immersion in Hydrochloric Acid*—After washing, immediately immerse the specimen 15 s in the HCl solution described in 6.4.2.2, thoroughly wash in clean water, and wipe dry with a clean, soft cloth.

6.4.3.4 *Examination of Specimens*—After immersion and washing examine the specimens to ascertain if copper exposed through openings in the silver coating has been blackened by action of the sodium polysulfide. Examine the specimen with the unaided eye (normal spectacles excepted) against a white background. The specimens shall be considered to have failed if, by such blackening exposed copper is revealed. No attention shall be paid to blackening within 0.5 in. (12.7 mm) of the cut end.

6.5 *Finish*—Surface-finish inspection shall be made with the unaided eye (normal spectacles excepted).

7. Inspection

7.1 *General (Explanatory Note 9)*—Unless otherwise specified in the contract or purchaser order, the manufacturer shall be responsible for the performance of all inspection and test requirements specified.

7.1.1 All inspections and tests shall be made at the place of manufacture unless otherwise especially agreed upon between the manufacturer and the purchaser at the time of purchase.

7.1.2 The manufacturer shall afford the inspector representing the purchaser all reasonable manufacturer's facilities to satisfy him that the material is being furnished in accordance with this specification.

7.1.3 Unless otherwise agreed upon between the purchaser and the manufacturer, conformance of the wire to the various requirements listed in Section 5 shall be determined on samples taken from each lot of wire presented for acceptance.

7.1.4 The manufacturer shall, if requested prior to inspection, certify that all wire in the lot was made under such conditions that the product as a whole conforms to the requirements of this specification as determined by regularly made and recorded tests.

7.2 *Definitions Applicable to Inspection:*

7.2.1 *lot*—any amount of wire of one type and size presented for acceptance at one time.

7.2.2 *Sample*—a quantity of production units (coils, reels, and so forth) selected at random from the lot for the purpose of determining conformance of the lot to the requirements of this specification.

7.2.3 *Specimen*—a length of wire removed for test purposes from any individual production unit of the sample.

7.3 *Sample Size (Explanatory Note 9)*—The number of production units in a sample shall be as follows:

7.3.1 A full (100 % inspection) will be completed at every set-up prior to running the order.

7.3.2 For elongation, resistivity, dimensional measurements, continuity of coating, and thickness of coating determinations, the sample shall consist of sequential production units from the lot.