This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.



Designation: C1542/C1542M - 19

Standard Test Method for Measuring Length of Concrete Cores¹

This standard is issued under the fixed designation C1542/C1542M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method is used to determine the length of a core drilled from concrete.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 The text of this standard refers to notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.5 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

- C42/C42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C174/C174M Test Method for Measuring Thickness of Concrete Elements Using Drilled Concrete Cores

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials C1604/C1604M Test Method for Obtaining and Testing

Drilled Cores of Shotcrete

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology C125.

4. Significance and Use

4.1 This test method provides two procedures for determining the length of a core obtained in accordance with either Test Method C42/C42M or Test Method C1604/C1604M. This length is used in conjunction with condition surveys, density and voids analysis, and other applications.

4.2 This procedure does not intend to include in the length measurement adhered particles not part of the concrete mixture.

4.3 Test Method C174/C174M also determines the length of concrete cores using a different measuring apparatus and procedure.

NOTE 1—Test Method C174/C174M uses an apparatus that establishes two parallel planes a known distance apart. The length of the core is determined by calculation using the known distance between the two parallel planes and the measured distance from the upper plane to the top of the core.

5. Apparatus

5.1 *Jaw Caliper*, measuring range; 0 to 300 mm [0 to 12 in.] or greater. Resolution or graduations; 0.01 mm [0.001 in.] or less. Accuracy; ± 0.03 mm [± 0.0015 in.] or better.

5.1.1 Offset points as part of caliper accessory kit to permit length measurements at points not on the core perimeter. Minimum depth of caliper jaws with offset points attached, 64 mm [2.5 in.].

5.2 *Ruler*, 300 mm [12 in.] or greater in length, graduated to 1 mm [$\frac{1}{16}$ or 0.05 in.] or less.

6. Test Specimens

6.1 Cores shall be obtained in accordance with Test Method C42/C42M or Test Method C1604/C1604M.

6.2 Cores shall be intact and be free of any coatings.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.61 on Testing for Strength.

Current edition approved Dec. 1, 2019. Published January 2020. Originally approved in 2002. Last previous edition approved in 2016 as C1542/C1542M – 16a. DOI: 10.1520/C1542_C1542M-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.