



Designation: D1422/D1422M – 13 (Reapproved 2020)

Standard Test Method for Twist in Single Spun Yarns by the Untwist-Retwist Method¹

This standard is issued under the fixed designation D1422/D1422M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method² describes the determination of twist in single spun yarns when only an approximation of the true twist is required.

NOTE 1—For a more accurate method see Test Method D1423.

1.2 This test method is applicable to spun single yarns in continuous lengths, and also to spun yarns reaveled from fabrics, provided specimens at least 200 mm [8 in.] long can be obtained.

1.3 This test method has been found satisfactory for use in determining the approximate twist content in single ring spun yarns of all types and fiber contents, but not in open-end spun yarns.

1.4 This specification shows the values in both inch-pound units and SI units. The “inch-pound” units is the technically correct name for the customary units used in the United States. The “SI” units is the technically corrected name for the system of metric units known as the International System of Units. The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.58 on Yarns and Fibers.

Current edition approved Feb. 1, 2020. Published February 2020. Originally approved in 1956. Last previous edition approved in 2013 as D1422 – 13. DOI: 10.1520/D1422_D1422M-13R20.

² This test method is commonly designated by the less precise term “Untwist-Twist Method.”

2. Referenced Documents

2.1 *ASTM Standards*:³

D123 Terminology Relating to Textiles

D1059 Test Method for Yarn Number Based on Short-Length Specimens

D1423 Test Method for Twist in Yarns by Direct-Counting

D2258 Practice for Sampling Yarn for Testing

D3888 Terminology for Yarn Spinning Systems

D4849 Terminology Related to Yarns and Fibers

3. Terminology

3.1 Refer to Terminology D4849 for definitions of the following terms used in this standard: direction of twist, single yarn, spun yarn, twist, twist factor, twist multiplier, and yarn.

3.2 Refer to Terminology D123 and Terminology D3888 for definitions of other terms used in this standard.

4. Summary of Test Method

4.1 A specimen is untwisted and then retwisted in the opposite direction until it contracts to its original length. It is assumed that the same amount of twist has been inserted as was originally present. Twist, as turns per unit length, is calculated as half the number of turns registered on the counter divided by the specimen length.

5. Significance and Use

5.1 This test method is used for acceptance testing in the trade for economic reasons even though it is less accurate than the direct method, Test Method D1423.

5.1.1 If there are differences or practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, the test samples should be used that are as homogeneous as possible, that are drawn from the material from which the disparate test results are obtained, and that are assigned randomly in equal numbers to each laboratory for testing. Other materials with established test values may be

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

used for this purpose. The test results from the two laboratories should be compared using a statistical test for unpaired data, at a probability level chosen prior to the testing series. If a bias is found, either its cause must be found and corrected, or future test results must be adjusted in consideration of the known bias.

5.2 The “setting” of twist in some fibers causes excessive contraction when the yarn is retwisted in the reverse direction. Therefore, the number of turns required to bring the specimen back to its original length may be less than the number of turns removed in untwisting. This effect may be partially offset by the use of higher pretensioning loads; but this increases the danger of stretching the yarn. Little information is available on the correct tensions to use for yarns made from different fibers or with different amounts of twist.

5.3 In addition to being less tedious, this test method requires fewer specimens than the direct-counting method and the results may be sufficiently accurate for certain purposes. This test method can be useful in those cases where the main objective is to measure variations from an average value. Another possible application is where a large amount of twist testing is required on yarns of similar type and twist. In this case preliminary tests comparing this method and the direct method could be used to determine the correct pretension.

5.4 Twist has important effects on the physical properties of yarn. Low-twist yarn is lofty and is usually preferred for knitting because of its softness, covering power, and warmth. Increasing the amount of twist causes an increase in yarn strength by increasing fiber cohesion, but as the twist angle increases beyond an optimum point, strength decreases due to a loss in effective fiber contribution. Maximum yarn strength is obtained by inserting a medium amount of twist to obtain an optimum balance between these two opposing forces. High twist produces yarns of high density (“hard” or “wiry”) and high elongation and may improve the abrasion and impact resistance of fabrics.

5.5 The optimum twist for either manufacturing efficiency or physical properties usually increases as staple length decreases.

5.6 The twist in a yarn before it is packaged may be different from that of the yarn after it has been withdrawn from the package because of changes in tension and the effect of the method of withdrawal. Withdraw the yarn from the package in the direction of normal use, either from the side or over-end. If the yarn is withdrawn over-end, a slight increase or decrease in twist will take place, depending upon the direction of the twist in the yarn, the direction of winding on the package, and the length of the turn (or wrap) on the package.

NOTE 2—The difference in twist between unwinding from the side and over-end is $1/\pi d$, where d is the diameter of the package.⁴ Thus, for a 25-mm [1-in.] diameter package, the difference would be about 13 tpm or about one third tpi.

5.7 When a yarn is taken from a more complex yarn structure or from a fabric, the resultant twist should be

considered only an approximation of the original value because of alterations that may have occurred as a result of the effects of unwinding, handling, and mechanical strains met in processing.

6. Apparatus

6.1 *Twist Tester*, consisting of a pair of clamps, one of which is rotatable in either direction and positively connected to a revolution counter. The tester may be hand- or power-driven. The position of one clamp (or both clamps) shall be adjustable to accommodate specimens having the length prescribed in 10.2. The tester shall be provided with a variable tensioning device so constructed that a specific force may be applied to the specimen at the beginning and end of the test and removed completely during the intervening untwisting and twisting operations.

6.2 Dissecting needle or stylus.

6.3 Metal ruler to verify gauge length (accurate to 2 mm [0.1 in.]).

7. Sampling

7.1 *Lot Sample*—Select one or more shipping units taken at random to represent an acceptance sampling lot and used as a source of laboratory samples.

7.2 *Laboratory Sample*—For packaged yarns, take a minimum of five packages for the laboratory sample unless otherwise agreed upon between purchaser and seller. For yarns from woven or knitted fabrics, the sample must be large enough to furnish specimens of the length and number specified in 7.3.3.

7.3 Selection of Specimens:

7.3.1 As nearly as possible take an equal number of specimens from each package or unit of the laboratory sample. Take the specimens from each package in a random manner to minimize the effect of cyclic variations introduced during manufacturing processes. When preparing specimens, conditioning them, or inserting them in the tester, take care to avoid any change in twist.

7.3.2 For packaged yarns, remove and discard the first 25 m [25 yd] of yarn. Using a minimum of tension, take specimens at random intervals greater than 1 m [1 yd] along the yarn. Withdraw the yarn from the package in the direction of normal use, either from the side or over-end, if known. If the direction is not known, withdraw the yarn from the side (Note 2). When more than five specimens are taken from an individual package, take groups of five or less at intervals of several yards. Do not cut the specimen free from the package or from the yarn to be discarded until after the yarn is secured in the clamps of the twist tester. When possible, take the specimen from near the center of the traverse and not at the traverse reversals.

7.3.3 For woven fabric, take warp specimens from separate ends, since each represents a separate package. Because the fabric may have been woven on any of a variety of looms which are random quilling, sequential quilling or shuttleless, take filling specimens at random through the whole laboratory

⁴ Woods, H. J., “The Kinematics of Twist, I, The Definition of Twist,” *Journal of Textile Science*, JTBA, vol 4, 1931, 33–36.