



Designation: D7559/D7559M – 09 (Reapproved 2020)

Standard Test Method for Determining Pressure Decay of Inflatable Restraint Cushions¹

This standard is issued under the fixed designation D7559/D7559M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended to determine the ability of an inflatable restraint cushion to retain air pressure at elevated pressures for a specified time interval.

1.2 Procedures and apparatus other than those stated in this test method may be used by agreement of purchaser and supplier, provided the specific deviations from the standard acknowledged in the report.

1.3 The results of this test method should not be used to predict the actual internal pressure decay of a cushion during a deployment.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D123 Terminology Relating to Textiles](#)

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and are the direct responsibility of Subcommittee D13.20 on Inflatable Restraints.

Current edition approved Feb. 1, 2020. Published February 2020. Originally approved as D7559/D7559M-09. Last previous edition approved in 2014 as D7559/D7559M-09(2014). DOI: 10.1520/D7559_D7559M-09R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

[D6799 Terminology Relating to Inflatable Restraints](#)

3. Terminology

3.1 For all terminology relating to D13.20, Inflatable restraints, refer to Terminology [D6799](#).

3.1.1 The following terms are relevant to this standard: deployment; inflatable restraint.

3.2 For all other terms related to textiles, see Terminology [D123](#).

4. Summary of Test Method

4.1 After inflation with air to a specific initial internal pressure, an inflatable restraint cushion is tested to for its ability to retain a specified residual pressure (allowing for some pressure loss) over a specified time period.

4.2 An inflatable restraint cushion is mounted onto a test stand that allows for the inflation of the cushion to a specified initial internal pressure. After the air supply is discontinued, instrumentation measures and records internal pressure drop over time.

4.3 Cushion internal pressure versus time data is recorded and compared to allowable limits agreed upon by the purchaser and supplier.

5. Significance and Use

5.1 This test method may be used for product development and design, production validation, manufacturing process control, lot acceptance, or for a combination thereof.

5.2 The rate of inflation in this method does not attempt to mimic that of an actual cushion deployment, nor is it intended to subject the cushion to the dynamic loads, stress, and temperatures during such an event. It is also recognized that the compressed air used for this tests may not leak through the cushion at the same rate as the gas or mixture of gasses typically used in cushion inflators. Rather this method is intended to give a relative indication of the pressure holding ability of the cushion.

5.3 The internal volume and internal design of cushions varies greatly. This test method is most useful when comparing

data from cushions of the same design and volume. This test method does not provide any data concerning the volume of gas leaking from the bag. At certain higher levels of the initial internal pressure, this test method will irreversibly damage the cushion and change its leakage properties for future testing or for commercial use. The damage to the bag is dependent on the design or shape of a specific bag and the type of coating applied. It is the responsibility of the supplier and/or purchaser to determine if the parameters under which a cushion is tested will be destructive and render the cushion unfit for future use.

5.4 Within the limits of variance expressed in Section 12, this test method is useful for design and production validation and may be suitable for incorporation in a cushion specification or for lot acceptance testing of commercial shipments.

6. Apparatus

6.1 *Air Supply Source*, capable of filling the cushion to the specified pressure, with a flow rate capable of maintaining the specified pressure at equilibrium. Typically the pressure used for testing the cushion will not exceed 200 kPa [29 psi], nor will the flow exceed 1500 L/min [53 CFM]. The air source should be equipped with an inline filter, shut off valve, and flow regulator. Care should be taken to trap out excess moisture or oil from the compressed air source.

6.2 *Shut Off Valve*, capable of being actuated either manually or remotely by an electrical signal.

6.3 *Mounting Fixture*, capable of allowing a sealed attachment of the cushion to the air supply source, the shut off valve, and instrumentation to monitor the pressure decay during the test. It should contain a pressure pickup tube. It shall be in an orientation that allows free expansion of the cushion geometry. It should have sufficient safety shielding and isolation for operator protection during the test. The clamping device that attaches the opening of the cushion to the filling tube fixture should be designed to properly fit the opening of the cushion, provide a secure mechanical attachment, and prevent gas leakage.

6.4 *Pickup Tube*, mounted coaxially inside filling tube of the mounting fixture. One end should extend inside the cushion at minimum of 25 mm [1 in.] beyond the clamping device. The other end should extend through the wall of the filling tube of the mounting fixture through a sealed joint, and be connected to a pressure transducer or gauge. The end that extends into the cushion should be oriented such that it allows free expansion of the cushion geometry.

6.5 *Pressure Transducer*, suitable for measuring pressures inside the cushion (via the pickup tube) from 0 to at least 200 kPa [0 to 29 psi] and maintained to an accuracy of a maximum of $\pm 2\%$.

6.6 *Pressure Gauge*, suitable for measuring pressures inside the cushion (via the pickup tube) from 0 to at least 200 kPa [0 to 29 psi] and maintained to an accuracy of a maximum of $\pm 2\%$.

6.7 *Data Acquisition System*, suitable for recording the output of the pressure transducer versus elapsed time. The input amplifier and the time interval at which the data is

recorded must have an accuracy of $\pm 1\%$. It is optional that this system can initiate the filling of the bag and the closure of the shut-off valve.

6.8 *Manual Timer (stopwatch)*, optional, suitable for manually observing elapsed time. This must have an accuracy of $\pm 1\%$.

6.9 Filter requirements, data sampling rate, transducer frequency response, and amplifier frequency response shall be such that the overall accuracy of the data acquisition system shall be within $\pm 1\%$. The significant figures of the recorded data of time and pressure, along with the timing increment should be agreed upon by the purchaser and supplier.

7. Sampling

7.1 The Cushion Pressure Decay Test at certain test parameters and pressures is a destructive test and therefore necessitates sampling procedures if used in conjunction with lot acceptance.

7.2 The determination of lot size and sampling plan shall be agreed to by purchaser and supplier.

7.3 One cushion assembly is a test specimen.

8. Equipment Calibration

8.1 For inflatable restraints, all test equipment used in accordance with this test method shall be certified for calibration annually using gages that are traceable to the National Institute of Science and Technology (NIST) or other national standards laboratory. The test parameters of the equipment shall be tested within the operating ranges covered in the cushion specification or equivalent document.

9. Conditioning

9.1 Conditioning of specimens and conducting of the testing in the standard atmosphere for testing textiles is desirable, but not required. It is recognized that conditions of the air from the compressed air source used to inflate the specimen will not be controlled, even though care should be taken to filter the air and trap out any excessive moisture or compressor oils.

9.2 Testing can be conducted in, or specimens conditioned in an environment other than that of the standard atmosphere for testing textiles, such as in hot or cold conditions. These conditions will be agreed upon between the purchaser and supplier, or as specified in any relevant customer or supplier specifications.

10. Procedure

10.1 Select and condition specimens in accordance with Sections 7 and 9.

10.2 Ensure that the shut off valve is closed and the pressure reading is at 0.

10.3 Mount the specimen onto the mounting fixture, ensuring that it is securely attached and sealed, and that the pickup tube does not interfere with the inflation of the cushion. If the cushion contains an internal gas guide or heat shield, it is