



Designation: **F949 – 15 (Reapproved 2019) F949 – 20**

Standard Specification for Poly(Vinyl Chloride) (PVC) Corrugated Sewer Pipe With a Smooth Interior and Fittings¹

This standard is issued under the fixed designation F949; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers requirements, test methods, and materials for 4 to 48 in. diameter poly(vinyl chloride) (PVC) corrugated pipe with a smooth interior. This profile wall pipe consists of an outer corrugated wall fused to a smooth inner wall providing pipe stiffness levels of 46 psi and ~~115 psi~~ 115 psi. Joints and fittings are included in this specification.

1.2 The requirements of this specification are intended to provide pipe and fittings suitable for underground use in nonpressure applications for sanitary sewers, storm sewers, and perforated and unperforated pipes for subdrainage.

NOTE 1—Industrial waste disposal lines should be installed only with the specific approval of the cognizant code authority, since chemicals not commonly found in drains and sewers and temperatures in excess of ~~140°F (60°C)~~ 140 °F (60 °C) may be encountered.

1.3 Pipe and fittings produced to this specification shall be installed in accordance with Practice **D2321**.

NOTE 2—For perforated pipe applications, the size of the embedment zone and permeability of the embedment material are important to the system's ability to provide the desired level of infiltration or exfiltration. The gradation of the embedment material must be compatible with the perforation slot size to avoid backfill migration into the pipe.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The following precautionary caveat pertains only to the test method portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D618 Practice for Conditioning Plastics for Testing

D1600 Terminology for Abbreviated Terms Relating to Plastics

D1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds

D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings

D2152 Test Method for Adequacy of Fusion of Extruded Poly(Vinyl Chloride) (PVC) Pipe and Molded Fittings by Acetone Immersion

D2321 Practice for Underground Installation of Thermoplastic Pipe for Sewers and Other Gravity-Flow Applications

D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading

D2444 Practice for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)

¹ This specification is under the jurisdiction of ASTM Committee **F17** on Plastic Piping Systems and is the direct responsibility of Subcommittee **F17.62** on Sewer. Current edition approved Aug. 1, 2019/Jan. 15, 2020. Published September 2019/February 2020. Originally approved in 1985. Last previous edition approved in 2015/2019 as **F949 – 15**/**F949 – 15(2019)**. DOI: ~~10.1520/F0949-15R19~~ 10.1520/F0949-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- D2564 Specification for Solvent Cements for Poly(Vinyl Chloride) (PVC) Plastic Piping Systems
- D2855 Practice for the Two-Step (Primer and Solvent Cement) Method of Joining Poly (Vinyl Chloride) (PVC) or Chlorinated Poly (Vinyl Chloride) (CPVC) Pipe and Piping Components with Tapered Sockets
- D3034 Specification for Type PSM Poly(Vinyl Chloride) (PVC) Sewer Pipe and Fittings
- D3212 Specification for Joints for Drain and Sewer Plastic Pipes Using Flexible Elastomeric Seals
- F412 Terminology Relating to Plastic Piping Systems
- F477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe
- F679 Specification for Poly(Vinyl Chloride) (PVC) Large-Diameter Plastic Gravity Sewer Pipe and Fittings
- F1057 Practice for Estimating the Quality of Extruded Poly (Vinyl Chloride) (PVC) Pipe by the Heat Reversion Technique
- 2.2 American Water Works Association (AWWA) Document:
AWWA Manual M45, Fiberglass Pipe Design³
- 2.3 Federal Standard:
Fed. Std. No. 123 Marking for Shipments (Civil Agencies)⁴
- 2.4 Military Standard:
MIL-STD-129 Marking for Shipment and Storage⁴

3. Terminology

3.1 Definitions are in accordance with Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise specified. The abbreviation for poly(vinyl chloride) plastic is PVC.

3.2 *parting line*—a slight mark or surface irregularity in the pipe or fitting surface as a result of a mold separation at that location.

4. Materials and Manufacture

4.1 *Material Specification*—The pipe shall be made of PVC compound having a minimum cell classification of 12454 in accordance with Specification D1784. The fittings shall be made of PVC compound having a cell classification of 12454, or 13343 as defined in Specification D1784. Compounds that have different cell classifications because one or more properties are superior to those of the specified compounds are also acceptable.

4.2 *Rework Material*—Clean rework material, generated from the manufacturer’s own pipe or fitting production, or both, may be used by the same manufacturer provided that the rework material meets the requirements of 4.1 and that the pipe and fittings produced meet the requirements of this specification.

4.3 *Pipe* shall be manufactured by simultaneous extrusion of the smooth and corrugated walls with the smooth inner wall fused to the outer corrugated wall.

4.4 *Fittings* shall be molded or fabricated.

4.5 *Joining Materials*:

4.5.1 *Gaskets*—Elastomeric seals (gaskets) shall be in accordance with the requirements of Specification F477.

4.5.2 *Lubricant*—The lubricant used for assembly shall be as recommended by the manufacturer and shall have no detrimental effect on the gasket or on the pipe and fittings.

4.5.3 *Solvent Cement*—The PVC cement shall comply with Specification D2564. The solvent cement shall be used only for bushings and saddle connections (see Fig. 1).

5. Requirements

5.1 *Workmanship*—The pipe and fittings shall be homogeneous throughout and free from visible cracks, holes, foreign inclusions, or other injurious defects. The pipe shall be as uniform as commercially practical in color, opacity, density, and other physical properties. Slots deliberately placed in pipe for perforations for subdrainage, etc., applications are acceptable.

5.2 *Dimensions and Tolerances*:

5.2.1 *Pipe*—Pipe dimensions shall meet the requirements given in Table 1 when measured in accordance with 7.3.

5.2.2 *Sockets*—All sockets (bells), dimensions on pipe, and fittings shall meet the requirements given in Table 2 when measured in accordance with 7.4. In the case of belled pipe, the thickness of wall in the bell shall be considered satisfactory if the pipe meets the minimum thicknesses listed in Table 1.

5.2.3 *Fittings*—Molded fitting dimensions shall meet the requirements of Table 3 when measured in accordance with 7.4. The wall thickness of molded fittings shall meet the requirements given in Table 4, when measured in accordance with 7.4. Fittings may also be fabricated from pipe, meeting the requirements of this specification or from pipe meeting the requirements of Specification D3034 or F679. In the case of a fabricated fitting with a formed bell, the thickness of the bell

³ Available from American Water Works Association (AWWA), 6666 W. Quincy Ave., Denver, CO 80235, <http://www.awwa.org>.

⁴ DLA Document Services Building 4/D 700 Robbins Avenue Philadelphia, PA 19111-5094 <http://quicksearch.dla.mil/>




FIG. 1 Molded Fitting Dimensions (see Table 3)

shall be considered satisfactory if it was formed from pipe meeting the requirements of the standard to which the pipe was produced. For reducing fittings or those with smaller inlets, the minimum wall thickness of each inlet shall be no less than the minimum wall thickness for that size pipe.


5.2.4 *Perforations*—Perforation slots shall be clearly cut and uniformly spaced along the length of pipe. Slots shall be centered in the corrugation valleys. Dimensions and spacing of the slots shall be as listed in Table 5. Other slot dimensions and spacing may be provided to meet the needs of the specifier. Alternatively, where the valley is large enough to accommodate a suitably sized round hole perforation without penetrating the void under the corrugation, round hole perforations of a size, pattern, and open area agreed upon by the specifier may be provided. All measurements shall be made in accordance with 7.9.

5.3 *Performance Requirements:*

5.3.1 *Pipe Stiffness*—Pipe stiffness shall be a minimum of 46 psi or 115 psi when tested in accordance with 7.5. Pipe stiffness shall be marked on pipe as per 11.2.3.

TABLE 1 Pipe Dimensions

NOTE 1—Other corrugation configurations, meeting the following dimensional requirements are permissible.



For Pipe Stiffness of 46 PSI

Nominal Size in.	Outside Diameter		Inside Diameter		Minimum Wall Thickness		
	Average, in. (mm)	Tolerance on Average, in. (mm)	Average, in. (mm)	Tolerance on Average, in. (mm)	Inner Wall, in. (mm)	Outer Wall, in. (mm)	At Valley, in. (mm)
4	4.300 (109.2)	±0.009 (±0.229)	3.950 (100.3)	±0.011 (±0.279)	0.022 (0.559)	0.018 (0.457)	0.028 (0.711)
6	6.420 (163.1)	±0.011 (±0.279)	5.909 (150.1)	±0.015 (±0.381)	0.025 (0.635)	0.022 (0.559)	0.032 (0.813)
8	8.600 (218.4)	±0.012 (±0.305)	7.881 (200.2)	±0.018 (±0.457)	0.035 (0.889)	0.030 (0.762)	0.045 (1.143)
10	10.786 (273.9)	±0.015 (±0.381)	9.846 (250.1)	±0.021 (±0.533)	0.045 (1.143)	0.036 (0.914)	0.055 (1.397)
12	12.795 (325.0)	±0.018 (±0.457)	11.715 (297.6)	±0.028 (±0.711)	0.058 (1.397)	0.049 (1.245)	0.072 (1.829)
15	15.658 (397.7)	±0.023 (±0.584)	14.338 (364.2)	±0.035 (±0.889)	0.077 (1.956)	0.055 (1.397)	0.092 (2.337)
18	19.152 (486.5)	±0.028 (±0.711)	17.552 (445.8)	±0.042 (±1.067)	0.084 (2.134)	0.067 (1.702)	0.103 (2.616)
21	22.630 (574.8)	±0.033 (±0.838)	20.705 (525.9)	±0.049 (±1.24)	0.095 (2.413)	0.073 (1.854)	0.110 (2.800)
24	25.580 (649.7)	±0.039 (±0.991)	23.469 (596.1)	±0.057 (±1.448)	0.110 (2.791)	0.085 (2.161)	0.123 (3.124)
27	28.860 (733.0)	±0.049 (±1.25)	26.440 (671.6)	±0.069 (±1.75)	0.120 (3.048)	0.091 (2.311)	0.137 (3.486)
30	32.150 (816.6)	±0.059 (±1.50)	29.469 (748.5)	±0.081 (±2.057)	0.130 (3.302)	0.105 (2.667)	0.147 (3.734)
36	38.740 (984.0)	±0.079 (±2.007)	35.475 (901.1)	±0.105 (±2.667)	0.150 (3.810)	0.125 (3.175)	0.171 (4.343)
42	45.800 (1163.3)	±0.093 (±2.36)	41.500 (1054.1)	±0.127 (±3.23)	0.160 (4.06)	0.135 (3.43)	0.188 (4.78)
48	52.800 (1341.1)	±0.108 (±2.74)	47.500 (1206.5)	±0.143 (±3.63)	0.165 (4.19)	0.140 (3.56)	0.195 (4.95)

For Pipe Stiffness of 115 PSI

Nominal Size	Outside Diameter		Inside Diameter		Minimum Wall Thickness		
	Average, in. (mm)	Tolerance on Average, in. (mm)	Average, in. (mm)	Tolerance on Average, in. (mm)	Inner Wall, in. (mm)	Outer Wall, in. (mm)	At Valley, in. (mm)
8	8.600 (218.4)	±0.012 (±0.305)	7.710 (195.8)	±0.018 (±0.457)	0.037 (0.940)	0.050 (1.270)	0.048 (1.219)
10	10.786 (273.9)	±0.015 (±0.381)	9.644 (245.0)	±0.021 (±0.533)	0.046 (1.295)	0.052 (1.320)	0.065 (1.651)
12	12.795 (325.0)	±0.018 (±0.457)	11.480 (291.6)	±0.028 (±0.711)	0.070 (1.778)	0.068 (1.727)	0.091 (2.311)
15	15.658 (397.7)	±0.023 (±0.584)	14.053 (356.97)	±0.035 (±0.889)	0.092 (2.337)	0.088 (2.235)	0.118 (2.997)

<https://standards.iteh.ai/catalog/standards/sist/5445217b-9d09-46b3-8dad-94be7e3eeff8e/astm-f949-20>

NOTE 3—This test is intended only for use as a quality control test and not as a simulated service test.

5.3.2 *Flattening*—There shall be no evidence of splitting, cracking, breaking, or separation of the two walls when the pipe is tested in accordance with 7.5 (see Note 4).

5.3.3 *Impact Strength*—Pipe shall have the minimum impact strengths listed in Table 6, when tested in accordance with 7.6. Failure of the test specimen shall be any crack, split, or shattering of either the waterway or corrugation wall. Separation of the ribs of the exterior corrugation from the waterway wall constitutes a failure.

NOTE 4—This test is intended only for use as a quality control test at time of manufacture, and not as a simulated service test.

5.3.4 *Extrusion Quality:*

5.3.4.1 *Acetone Immersion*—The pipe shall not flake, disintegrate, or exhibit separation of the two walls when tested in accordance with 7.7.1.

5.3.4.2 *Heat Reversion*—The pipe shall not exhibit any of the effects listed in the suggested interpretation of results of Practice F1057 when tested in accordance with 7.7.2.

5.3.5 *Bond*—The bond between the inner and outer walls (at the corrugation valley) shall not separate when tested in accordance with 7.10.


5.4 *Joint Tightness*—Gasketed pipe joints shall show no leakage when tested in accordance with 7.8.

NOTE 5—Testing for joint tightness is not intended to be a routine quality control test. The test is used to qualify pipe and fitting joints at a specified level of performance.

6. Sampling

6.1 *Sampling*—The selection of the sample or samples of pipe and fittings shall be as agreed upon between the purchaser and the seller. In the case of no prior agreement, any samples selected by the testing laboratory shall be deemed adequate.

TABLE 2 Bell (Socket) Dimensions for Gasketed Joints



Nominal Diameter	A ^A in. (mm)	B ^A in. (mm)	C in. (mm)
4	4.362 ± 0.025 (110.79 ± 0.64)	4.372 ± 0.025 (111.05 ± 0.64)	1.75 (44.5)
6	6.492 ± 0.030 (164.90 ± 0.76)	6.512 ± 0.030 (165.40 ± 0.76)	2.75 (69.9)
8	8.680 ± 0.035 (220.47 ± 0.89)	8.700 ± 0.035 (220.98 ± 0.84)	3.75 (95.3)
10	10.876 ± 0.045 (276.26 ± 1.14)	10.900 ± 0.045 (276.86 ± 1.14)	4.75 (120.7)
12	12.873 ± 0.055 (326.97 ± 1.40)	12.898 ± 0.055 (327.61 ± 1.40)	5.75 (146.1)
15	15.751 ± 0.065 (400.08 ± 1.65)	15.776 ± 0.065 (400.71 ± 1.65)	6.75 (171.5)
18	19.260 ± 0.075 (489.20 ± 1.91)	19.285 ± 0.075 (489.84 ± 1.91)	6.75 (171.5)
21	22.751 ± 0.080 (577.88 ± 2.032)	22.781 ± 0.080 (578.64 ± 2.032)	8.5 (215.9)
24	25.758 ± 0.085 (654.25 ± 2.159)	25.788 ± 0.085 (655.02 ± 2.159)	8.5 (215.9)
27	29.058 ± 0.090 (738.07 ± 2.286)	29.088 ± 0.090 (738.84 ± 2.286)	8.5 (215.9)
30	32.368 ± 0.095 (822.15 ± 2.413)	32.398 ± 0.095 (822.91 ± 2.413)	8.5 (215.9)
36	38.998 ± 0.105 (990.55 ± 2.667)	39.028 ± 0.105 (991.31 ± 2.667)	8.5 (215.9)
42	45.965 ± 0.130 (1167.51 ± 3.3)	45.995 ± 0.130 (1168.27 ± 3.3)	12.5 (317.5)
48	52.970 ± 0.130 (1345.44 ± 3.3)	53.000 ± 0.130 (1346.20 ± 3.3)	15.9 (403.9)

^A Some sockets, dependent on the method of the manufacturer, do not have taper on inside diameter of socket. Total bell inside diameter is equal to "A" dimension.

7. Test Methods

7.1 Conditioning:

7.1.1 Referee Testing—When conditioning is required for referee tests, condition the specimens in accordance with Procedure A of Practice D618 at 73.4 ± 3.6 °F (23 ± 2 °C) and 50 ± 10 % relative humidity for not less than 40 h prior to test. Conduct tests under the same conditions of temperature and humidity, unless otherwise specified.

7.1.2 Quality Control Tests—For quality control tests, condition the specimens for a minimum of 4 h in air or 1 h in water at 73.4 ± 3.6 °F (23 ± 2 °C). Test the specimens at 73.4 ± 3.6 °F (23 ± 2 °C) without regard to relative humidity.

7.2 Test Conditions—Conduct tests in the Standard Laboratory Atmosphere at 73.4 ± 3.6 °F (23 ± 2 °C) and 50 ± 5 % relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerance shall be ±1.8 °F (±1 °C) and ±2 % relative humidity.

7.3 Pipe Dimensions:

TABLE 3 Minimum Molded Fitting Dimensions (see Fig. 1)

NOTE 1—Fittings 10 in. and larger are typically fabricated. Contact the manufacturer for details on fittings. Bell dimensions meet the requirements of Table 2.

Fitting, in.	A in. (mm)	B in. (mm)	Fitting, in.	A in. (mm)	B in. (mm)	C in. (mm)
Couplings			Tees			
4	4.0 (102)		4 × 4 × 4	4.6 (117)	2.1 (53)	
6	6.0 (152)		6 × 6 × 4	6.7 (170)	3.1 (79)	
8	8.0 (203)		6 × 6 × 6	6.7 (170)	3.0 (7)	
10	10.0 (254)		8 × 8 × 4	8.5 (216)	5.0 (127)	
Saddle Tees			8 × 8 × 6	10.2 (259)	5.3 (135)	
6 × 4	8.0 (203)	3.3 (84)	8 × 8 × 8	9.0 (229)	4.1 (104)	
8 × 4	10.3 (262)	4.6 (117)	Wyes			
8 × 6	10.3 (262)	4.5 (114)	4 × 4 × 4	6.5 (165)	5.6 (142)	1.0 (25)
10 × 4	10.7 (272)	5.6 (137)	6 × 6 × 4	9.5 (241)	8.2 (208)	1.3 (33)
10 × 6	10.7 (272)	5.4 (137)	6 × 6 × 6	9.5 (241)	8.1 (206)	1.3 (33)
Saddle Wyes			8 × 8 × 4	11.5 (292)	7.5 (191)	0.7 (18)
6 × 4	9.0 (229)	6.5 (168)	8 × 8 × 6	13.3 (338)	8.0 (203)	1.7 (43)
8 × 4	14.5 (368)	10.3 (262)	8 × 8 × 8	17.0 (432)	8.3 (211)	3.5 (89)
8 × 6	14.5 (368)	10.2 (259)	Tee-Wye			
10 × 4	15.1 (384)	11.5 (292)	8 × 8 × 4	5.4 (137)	6.3 (160)	2.8 (71)
10 × 6	15.1 (384)	11.4 (290)	8 × 8 × 6	5.4 (137)	6.2 (157)	2.8 (71)
Spigot Caps			Bushing			
4	2.0 (51)		6 × 4	3.0 (76)	2.0 (51)	
6	3.0 (76)		8 × 6	4.0 (102)	3.0 (76)	
8	4.0 (102)		Adaptors			
10	5.0 (127)		4	2.0 (51)	2.0 (51)	
¼ Bend			6	3.0 (76)	2.5 (63)	
4	2.1 (53)	2.3 (58)				
6	3.1 (79)	2.4 (86)				
½ Bend						
4	1.1 (28)	1.1 (28)				
6	1.6 (41)	1.6 (41)				
8	2.2 (56)	2.2 (56)				
⅙ Bend						
4	0.5 (13)	0.5 (13)				
6	0.7 (18)	0.7 (18)				

TABLE 4 Molded Fittings

Nominal Diameter	Minimum Wall ^{A,B} Thickness, in.
4	0.120
6	0.180
8	0.240
10	0.300
12	0.360
15	0.437
18	0.499

^A The skirts on saddle fittings have a minimum wall thickness of 0.180 in.

^B The wall thickness is a minimum value except that a ±10 % variation resulting from core shift is allowable. In such a case, the average of two opposite wall thicknesses shall equal or exceed the value shown in the table.

7.3.1 *Pipe Diameters*—Measure the average outside diameter of the pipe in accordance with Test Method **D2122** using a circumferential wrap tape accurate to ±0.001 in. (±0.02 mm). The average inside diameter may be calculated from the average outside diameter and wall thickness measurements in accordance with Test Method **D2122**.

7.3.2 *Wall Thickness*—Measure the wall thicknesses in accordance with Test Method **D2122**. Each specimen will need to be cut lengthwise into at least eight segments in order to obtain a minimum of eight measurements in accordance with Test Method **D2122**. Do not measure on a mold line.

7.3.3 Measure the length of pipe with a steel tape with precision of at least ⅙-in. (1-mm) graduations in accordance with Test Method **D2122**.

7.4 Fitting Dimensions:

7.4.1 *Socket Diameters*—Measure the inside diameters of the sockets in accordance with Test Method **D2122**. Calculate the average inside diameters of the socket as the arithmetic mean of all of the diameters measured at each cross section.

7.4.2 *Socket Depth*—Measure the fittings socket depth using a good commercial quality scale calibrated in ⅙-in. (1-mm) increments in accordance with Test Method **D2122**.