



Designation: **C1728 – 17 C1728 – 20**

Standard Specification for Flexible Aerogel Insulation¹

This standard is issued under the fixed designation C1728; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the classification and performance of flexible aerogel thermal insulation. This will cover the range of continuous exposure operating temperatures from -321°F (-196°C) up to 1200°F (649°C).

1.2 For satisfactory performance, properly installed protective vapor retarders or barriers shall be used on below ambient temperature applications to reduce movement of moisture through or around the insulation to the colder surface. Failure to use a vapor retarder or barrier could lead to insulation and system non-performance.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

~~1.4 The following safety hazards caveat pertains only to the test methods described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*~~

1.4 The following safety hazards caveat pertains only to the test methods described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

C165 Test Method for Measuring Compressive Properties of Thermal Insulations

C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations [067bf16b98e/astm-c1728-20](#)

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation

C335 Test Method for Steady-State Heat Transfer Properties of Pipe Insulation

C356 Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat

C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation

C447 Practice for Estimating the Maximum Use Temperature of Thermal Insulations

C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C795 Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel

C1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions

C1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation

C1101/C1101M Test Methods for Classifying the Flexibility or Rigidity of Mineral Fiber Blanket and Board Insulation

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Feb. 1, 2017/Jan. 1, 2020. Published February 2017/March 2020. Originally approved in 2012. Last previous edition approved in 2013/2017 as C1728 – 13/C1728 – 17. DOI: 40.1520/C1728-17.10.1520/C1728-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus
C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings
C1617 Practice for Quantitative Accelerated Laboratory Evaluation of Extraction Solutions Containing Ions Leached from Thermal Insulation on Aqueous Corrosion of Metals
C1763 Test Method for Water Absorption by Immersion of Thermal Insulation Materials
E84 Test Method for Surface Burning Characteristics of Building Materials
E2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics

2.2 *Other Standards:*³

CAN/ULC-S102 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies

3. Terminology

3.1 *Definitions:* For definitions used in this specification, see Terminology A3.

3.1.1 *flexible aerogel insulation, n*—a flexible insulation containing a composite of aerogel, fibrous carrying media, or reinforcements, or a combination thereof.

3.1.1.1 *Discussion*—

Opacifiers are sometimes added as either fibers or powders.

3.2 *Abbreviations:*

3.2.1 *N/A*—Not applicable.

4. Classification

4.1 Flexible aerogel insulation shall be classified into three Types based on the maximum use temperature:

4.1.1 Type I — 257°F (125°C)

4.1.2 Type II — 390°F (200°C)

4.1.3 Type III — 1200°F (649°C)

4.2 Type I is subdivided as Grade 1 (tested in flat configuration) and Categories A or B by thermal conductivity.

4.3 Type II comprises a Grade 1 (tested in flat configuration) and Category A.

4.4 Type III is subdivided into two Grades 1 and 2 whereby Grade 1 is tested in a flat configuration using Test Method C177 and Grade 2 is tested only in a pipe configuration using Test Method C335.

5. Ordering Information

5.1 The Type, Grade, Category, dimensions, and thickness shall be specified by the purchaser. A product certification (if required) shall be specified in the purchase order.

6. Materials and Manufacture

6.1 *Composition*—Flexible aerogel insulation is a composite of an amorphous silica-based aerogel, a fibrous carrying media, or reinforcements, or a combination thereof, that allow the construct to be flexible.

6.1.1 A fibrous carrying media or reinforcement, or both, consists of the following: fibers, batts, strips, sheets, or some combination thereof.

6.1.1.1 This fibrous carrying media or reinforcement material, or both, is either organic, such as polyester, or inorganic, such as glass fibers. Additionally, some flexible aerogel insulation contains additives such as a water resistant treatment or opacifiers, or both.

7. Physical, Mechanical and Chemical Property Requirements

NOTE 1—Performance requirements for flexible aerogel insulation (Type I Grade 1 Category A, Type I Grade 1 Category B, Type II Grade 1 Category A, Type III Grade 1 Category A, and Type III Grade 2 Category A) are given in Table 1.

7.1 *Maximum Use Temperature*—When tested in accordance with Test Method C411 in a flat configuration and the hot surface performance of Practice C447 in a flat configuration at the insulation's maximum use temperature at a thickness of 80 mm or manufacturer's maximum recommended thickness, the flexible aerogel insulation shall not warp, flame, or glow during hot surface exposure. No evidence of melting or fiber degradation shall be evident upon post-test inspection.

³ Available from Underwriters Laboratories (UL), 2600 N.W. Lake Rd., Camas, WA 98607-8542, <http://www.ul.com>.

TABLE 1 Performance Requirements for Types I, II, and III Flexible Aerogel Insulation

Type	I	I	II	III	III
Grade	1	1	1	1	2
Category	A	B	A	A	A
Maximum use temperature, °F (°C)	257 (125)	257 (125)	390 (199)	1200 (649)	1200 (649)
Minimum use temperature, °F (°C)	-321 (-196)	-321 (-196)	-321 (-196)	75 (24)	75 (24)
Minimum / Maximum Composite Density, lbs/ft ³ (kg/m ³)	1.9 to 6.3 (30 to 100)	5.0 to 11.2 (80 to 180)	4.7 to 9.4 (75 to 150)	10.0 to 15.0 (160 to 240)	10.0 to 15.0 (160 to 240)
Apparent thermal conductivity, max, Btu•in/h•ft ² •°F (W/m•K) Mean Temperature, °F (°C)					
-200 (-129)	0.098 (0.014)	0.096 (0.014)	0.073 (0.011)	N/A	N/A
-100 (-73.3)	0.12 (0.017)	0.10 (0.015)	0.091 (0.013)	N/A	N/A
0 (-17.8)	0.14 (0.021)	0.11 (0.016)	0.11 (0.016)	N/A	N/A
75 (23.9)	0.17 (0.024)	0.12 (0.017)	0.13 (0.019)	0.14 (0.021)	0.16 (0.023)
100 (37.8)	0.17 (0.025)	0.12 (0.017)	0.14 (0.020)	0.15 (0.022)	0.17 (0.024)
200 (93.3)	0.21 (0.030)	0.13 (0.019)	0.18 (0.025)	0.16 (0.023)	0.18 (0.024)
300 (149)	NA	NA	0.22 (0.032)	0.18 (0.025)	0.21 (0.028)
400 (204)	NA	NA	NA	0.20 (0.029)	0.24 (0.033)
500 (260)	NA	NA	NA	0.22 (0.032)	0.28 (0.035)
600 (316)	NA	NA	NA	0.25 (0.036)	0.33 (0.040)
700 (371)	NA	NA	NA	0.30 (0.043)	0.39 (0.048)
Compressive resistance, min, @ 10% deformation, psi (kPa)	0.75 (5.2)	5 (34.5)	5 (34.5)	3 (20.7)	3 (20.7)
Surface burning characteristics: Flame spread index, max Smoke developed, max	Not Rated	25 50	Not Rated	5 10	5 10
Exothermic temperature rise, maximum, with no facings or jacketing of any type, run at maximum recommended thickness	NA	NA	NA	200°F (111°C)	200°F (111°C)
Water absorption, maximum % by weight					
Before conditioning at 600°F (316°C) for 24 h	150 %	8 %	8 %	8 %	8 %
After conditioning at 600°F (316°C) for 24 h				16 %	16 %

7.2 *Thickness and Density*—The thickness and density shall be determined and reported in accordance with Test Methods **C167** or **C303**.

7.3 *Apparent Thermal Conductivity*:

7.3.1 Determine the thermal conductivity as a function of temperature for the representative specimens with data obtained from a series of thermal tests utilizing Test Methods **C177**, **C518**, **C1114**, or **C335** as appropriate for the material under study. Specimen shall be tested unfaced and, for Type III, Grade 2 (pipe configuration per Test Method **C335**), test at a minimum of 4 layers. Each layer shall have a minimum thickness of 0.2 in (5 mm). The test report shall state the barometric pressure at the time of the tests. See **Note 2** below.

7.3.2 As specified in Practice **C1045**, the range of test conditions must include at least one test where the hot surface temperature is greater than, or equal to, the hot limit of the temperature range of desired data and at least one test where the cold temperature