



Designation: D1776/D1776M – 20

Standard Practice for Conditioning and Testing Textiles¹

This standard is issued under the fixed designation D1776/D1776M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers the conditioning and testing of textiles when conditioning is specified in a test method. Because prior exposure of textiles to high or low humidity may affect moisture pick-up equilibrium, a procedure also is given for preconditioning the material when required.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D123 Terminology Relating to Textiles
- D618 Practice for Conditioning Plastics for Testing
- D885 Test Methods for Tire Cords, Tire Cord Fabrics, and Industrial Filament Yarns Made from Manufactured Organic-Base Fibers
- D4920 Terminology Relating to Conditioning, Chemical,

and Thermal Properties

- D5867 Test Methods for Measurement of Physical Properties of Raw Cotton by Cotton Classification Instruments
- D7269 Test Methods for Tensile Testing of Aramid Yarns
- D7744 Test Methods for Tensile Testing of High Performance Polyethylene Tapes
- E337 Test Method for Measuring Humidity with a Psychrometer (the Measurement of Wet- and Dry-Bulb Temperatures)

2.2 ISO Standard:

- ISO 139 Textiles Standard Atmosphere for Conditioning and Testing³

3. Terminology

3.1 For terminology related to conditioning see Terminology D4920.

3.2 The following terms are relevant to this standard: accelerated conditioning, moisture content, moisture equilibrium, moisture equilibrium for preconditioning, moisture equilibrium for testing, precondition, standard atmosphere for preconditioning textiles, standard atmosphere for testing textiles, uncertainty of (in) measurement.

3.3 For definitions of other textile terms used in this standard see Terminology D123.

4. Summary of Practice

4.1 Samples or specimens requiring preconditioning are brought to relatively low moisture content in a specified atmosphere. Samples or specimens not requiring preconditioning are brought to moisture equilibrium (specific to fiber-content) according to the standard atmospheres for testing textiles as shown in Table 1.

4.2 Understanding of tolerance and uncertainty of measurement has evolved since the creation of the original version of this standard. Due to this new understanding, uncertainty of measurement has been taken into account in determining acceptable tolerances for the standard atmospheres for testing textiles as shown in Table 1.

¹ This practice is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.51 on Conditioning, Chemical and Thermal Properties.

Current edition approved Feb. 1, 2020. Published March 2020. Originally approved in 1960. Last previous edition approved in 2016 as D1776/D1776M-16. DOI: 10.1520/D1776_D1776M-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document summary page on the ASTM website.

³ Available from American National Standards Institute, 11 W. 42nd Street, 13th Floor, New York, NY 10036.

TABLE 1 Standard Atmospheres for Conditioning and Testing Textiles

Material	Preconditioning ^A Time (h), minimum	Temperature, °C [°F]	Relative Humidity %	Time (h), minimum	ASTM Standard
Textiles, general^B		21 ± 2 [70 ± 4]	65 ± 5		D1776/D1776M
Textiles, specific^C					
Cotton fiber classification and testing	4	21 ± 1 [70 ± 2]	65 ± 2		D1776/D1776M, D5867
Tire cords:					
Polyamide					
Option 2	Not applicable	24 ± 2 [75 ± 4]	55 ± 5	16	D885
Option 1	Not applicable	20 ± 2 [68 ± 4]	65 ± 5	16	D885
Polyester					
Option 2	Not applicable	24 ± 2 [75 ± 4]	55 ± 5		D885
Option 1	Not applicable	20 ± 2 [68 ± 4]	65 ± 5	16	D885
Rayon		20 ± 2 [68 ± 4]	65 ± 5	8	
Aramid ^D					
Option 1	3	20 ± 2 [68 ± 4]	65 ± 5	14	D7269
Option 2	3	24 ± 2 [75 ± 4]	55 ± 5	14	D7269
High Performance Polyethylene	Not applicable	20 ± 2 [68 ± 4]	65 ± 5	4	D7744
Glass fiber products:					D618
Plastic applications		23 ± 2 [73 ± 4]	50 ± 5		D1776/D1776M
Textile applications		21 ± 1 [70 ± 2]	65 ± 5		D1776/D1776M
Nonwovens		23 ± 2 [73 ± 4]	50 ± 5		D1776/D1776M
Plastics and electrical insulation		23 ± 2 [73 ± 4]	50 ± 5		D618

^A Preconditioning is an option and may be employed when samples are being brought to equilibrium moisture content from an extreme high or low moisture content.
^B Previous publications of this standard cited tolerances for general textiles without consideration of the uncertainty of measurement of the temperature and humidity controllers or the measurement devices used in textile laboratories. Changes in ISO 139 broadened tolerances to account for the uncertainty of measurement of controller and measurement devices have also been incorporated into the tolerances for the general textile category.
^C Specific textiles' conditioning tolerances and their associated standards do not account for the uncertainty of measurement of controllers or devices.
^D Report the standard atmosphere used.

(https://standards.iteh.ai)
 Document Preview

5. Significance and Use

5.1 The conditioning prescribed in this practice is designed to obtain reproducible results on textiles and textile products. Results of tests obtained on these materials under uncontrolled atmospheres may not be comparable with each other. In general, many of the physical properties of textiles and textile products are influenced by relative humidity and temperature in a manner that affects the results of the tests. To make reliable comparisons among different textile materials and products, and among different laboratories, it is necessary that standard atmospheres be utilized during conditioning and testing.

5.2 The documentation of standard atmospheres for preconditioning (if necessary), conditioning, testing settings and tolerances, including the determination of the uncertainty of measurement of temperature and relative humidity recording devices, may be necessary for laboratory accreditation. See [Appendix X1](#).

6. Apparatus

6.1 Conditioning Room or Chamber, consisting of:

6.1.1 Equipment for the generation of heated or cooled air, moisture, and air circulation with control devices to maintain standard atmospheres for testing textiles throughout a laboratory space, room or chamber within the tolerances given in [Table 1](#).

NOTE 1—Temperature and relative humidity recording devices used in a testing laboratory are separate ones from those cited in [6.1.1](#)

6.2 *Psychrometer, Ventilated by Aspiration*, or a similar measuring device, which is accurate to ±1°C [±2°F], for checking the recorded relative humidity, as directed in Test Method [E337](#).

6.3 *Preconditioning Cabinet, Room, or Space*, equipped for maintaining the standard atmosphere for preconditioning.

6.4 *Balance*, having a sensitivity of one part in 1000 of the mass of the specimen.

6.5 *Multiple Shelf Conditioning Rack*,^{4,5} for spreading out samples and specimens. See [Fig. 1](#).

7. Preparation of Test Apparatus and Calibration

7.1 Verify the uncertainty of measurement of the temperature and relative humidity devices being used to produce standard atmospheres and those recording temperature and relative humidity in laboratories as this factor should be

⁴ Drawings of the passive conditioning rack may be obtained from the American Association of Chemists and Colorists, P. O. Box 12215, Research Triangle Park, NC 27709-2215.

⁵ A suitable rapid conditioning system may be constructed in the laboratory. See “Earnest, D. W., *Advancements in USDA Cotton Classing Facilities, Proceedings 1996*, Beltwide Cotton Conferences, pp. 1651–1654,” and “Knowiton, J. I., and Alldredge, R. K., *A New Method for Accelerating Cotton Sample Conditioning in Cotton Classing Offices, Proceedings 1994*, Beltwide Cotton Conferences, pp. 582–584.” Suitable self-contained rapid conditioning units are available from at least two commercial sources.