This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: E3086 - 17 E3086 - 20

Standard Practice for Creating Appliques for Use in Testing of Nonplanar Soft Body Armor Designed for Females¹

This standard is issued under the fixed designation E3086; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice specifies a procedure for creating appliques (that is, build-up of clay) for use behind nonplanar, soft body armor test items and affixing the appliques to the clay block.

NOTE 1-This practice describes a single applique shape; additional shapes may be described in other standards.

1.2 The purpose of this practice is to specify critical parameters for creating appliques in order to improve consistency of the test setup between laboratories.

NOTE 2—In the past, testing of nonplanar soft armor has been done either with an unspecified buildup of clay behind the test item or with the test item pressed flat against the clay block.

1.3 This practice is applicable only to nonplanar soft body armor designed for females.

1.4 This practice is not applicable to hard armor test items.

1.5 This practice is primarily directed toward test laboratories but may be applicable to body armor manufacturers, researchers, and end users performing ballistic-resistance testing of body armor.

1.6 In this practice, "other standards and specifications" and "unless specified elsewhere" refer to documents (for example, military standards, purchase specifications) that require the use of this practice. Purchasers and other users are responsible for the "other standards and specifications" and for specifying any requirements that supersede those of this practice.

1.7 Units—The values stated in SI units are to be regarded as standard. Where appropriate, inch-pound units are included parenthetically for information purposes.

1.8 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety safety, health, and healthenvironmental practices and determine the applicability of regulatory limitations prior to use.

1.9 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

E3004 Specification for Preparation and Verification of Clay Blocks Used in Ballistic-Resistance Testing of Torso Body Armor E3005 Terminology for Body Armor

3. Terminology

3.1 For terms not defined in this practice, the following definitions of Terminology E3005 apply: <u>applique, applique pattern</u>, backface deformation, backing assembly, backing fixture, backing material, body armor, hard armor, <u>mold box</u>, nonplanar, soft armor, test item, and test threat.

3.2 Definitions of Terms Specific to This Standard:

¹ This practice is under the jurisdiction of ASTM Committee E54 on Homeland Security Applications and is the direct responsibility of Subcommittee E54.04 on Personal Protective Equipment (PPE).

Current edition approved Feb. 1, 2017 April 1, 2020. Published March 2017 April 2020. Originally approved in 2017. Last previous edition approved in 2017 as E3086 – 17. DOI: 10.1520/E3086-17.10.1520/E3086-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

E3086 - 20

3.2.1 applique, n-a three-dimensional item molded from backing material, that is shaped and sized for testing or conditioning a nonplanar test item.

3.2.1.1 Discussion-

Some appliques are designed for the purpose of filling the entire space behind a nonplanar test item; other appliques are designed to assess features of a nonplanar test item.

3.2.2 applique pattern, n-a replica of the final product (that is, applique) used for preparing the applique mold cavity.

3.2.3 mold box, n-a frame used in creation of the mold to contain and give shape to fluid material while it sets up.

4. Significance and Use

4.1 U.S. Department of Defense and U.S. Department of Justice standards for assessing the performance of ballistic-resistant torso body armor require the use of backing assemblies made with Roma Plastilina No. 1[®]. The creation of appliques behind nonplanar soft armor test items must be done in a consistent manner to reduce variability within and between laboratories.

4.2 This practice is applicable for certification testing or for research and development testing.

5. Equipment and Materials

5.1 The following equipment and materials are required for making appliques defined by this practice:

5.1.1 Clay—Unless specified elsewhere, the clay shall be ROMA Plastilina No. 1[®] modeling clay.

5.1.2 Backing Assembly—The backing assembly and clay used for building up behind nonplanar test items shall meet the requirements of Specification E3004.

5.1.3 Applique pattern.

5.1.4 Items for applique formation:

5.1.4.1 Mold box.

5.1.4.2 Mold-grade silicone rubber, Shore 15A hardness.

5.1.4.3 Release agent.

5.1.5 Draw knife or similar striking device.

5.1.6 Oven for heating clay.

5.1.7 Oven for storing appliques before use in testing. ent Preview

6. Procedure for Making Applique Molds

6.1 There are five possible sizes for appliques, and each applique size requires a separate mold.

6.2 Creating the mold requires a mold box, an applique pattern, and silicone. The size of the mold box and applique pattern are dependent on the size of the applique that is required.

6.3 Create an applique pattern whose top surface conforms to the equation below and whose base is formed by the x-y plane (where z = 0). In this shape, x, y, and z represent the length, width, and height respectively:³

$$z = \frac{513b(x-a)}{640a} \left(\left(\frac{x}{a}\right)^2 + \left(\frac{y}{b}\right)^2 \left(e^{0.005x}\right) - 1 \right)$$
(1)

6.4 Table 1 provides the values of a and b to be used in Eq 1 for the corresponding applique sizes. An example of a 3D printed applique pattern is shown in Fig. 1. DI E 1 Devenue teve feu Different Annlinue Cine

IABLE I	Parameters for	Different	Applique Sizes	
		,		

Applique Size Designation	<i>a</i> (mm)	<i>b</i> (mm)
A-1 (smallest)	69.189	53.222
A-2	76.740	59.031
A-3	84.291	64.839
A-4	91.842	70.648
A-5 (largest)	99.393	76.456

NOTE 3-Tolerances on the applique pattern, if required, will be specified in other standards or specifications.

6.5 Build a mold box based on the approximate inside dimensions provided in Table 2. The box shall be made from a rigid material, such as metal or wood.

NOTE 4-The mold box does not require a top or a bottom.

³ The equation provided here is a simplified version of the equation described, with its derivation, in the following paper: Stoe, D., Otterson, D., (2016) Research, Testing, and Standards for Body Armor Designed for Women Law Enforcement Officers, Personal Armour Systems Symposium, Amsterdam, Netherlands, September 20, 2016.