



Designation: B683 – 20

Standard Specification for Pure Palladium Electrical Contact Material¹

This standard is issued under the fixed designation B683; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers palladium in the form of rod, wire, strip, and sheet material for electrical contacts.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B476 Specification for General Requirements for Wrought Precious Metal Electrical Contact Materials

B542 Terminology Relating to Electrical Contacts and Their Use

B589 Specification for Refined Palladium

3. Terminology

3.1 Refer to Terminology **B542** for terms related to electrical contacts and their use.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved April 1, 2020. Published April 2020. Originally approved in 1980. Last previous edition approved in 2012 as B683 – 01 (2012). DOI: 10.1520/B0683-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. General Requirements

4.1 The provisions of Specification **B476** shall apply to all materials produced to this specification.

5. Ordering Information

5.1 Orders for this material under this specification shall include the following information:

5.1.1 Dimensions,

5.1.2 Chemical composition,

5.1.3 Mechanical property requirements,

5.1.4 Certification, and

5.1.5 Other requirements as agreed upon between the seller and the user.

6. Materials and Manufacture

6.1 Raw materials shall be of such quality and purity that the finished product will have the properties and characteristics prescribed in this specification.

6.2 The material shall be finished by such operations (cold working, annealing, turning, grinding, or pickling) as are required to produce the prescribed properties.

7. Chemical Composition

7.1 Material produced under this specification shall meet the requirements of chemical composition prescribed in **Table 1**.

NOTE 1—The chemical requirements for unfabricated palladium (refined material) are covered in Specification **B589**.

7.2 By agreement between the purchaser and the manufacturer, analysis may be required and limits established for elements or compounds not specified in the table of chemical composition.

8. Mechanical Property Requirements

8.1 The contract or order may specify ultimate tensile strength, elongation, microhardness (Knoop or Vickers), hardness (Rockwell or Rockwell Superficial), or a combination of these mechanical properties as temper criterion. If the contract or order does not specify a temper criterion, then the criterion for temper designation will be ultimate tensile strength and elongation.

*A Summary of Changes section appears at the end of this standard