



Designation: D3913 – 03 (Reapproved 2020)^{ε1}

Standard Test Method for Acidity in Basic Chromium Tanning Liquors¹

This standard is issued under the fixed designation D3913; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Editorial changes, including standardizing the use of Arabic versus Roman numerals to refer to Procedures 1 and 2, were made in April 2020.

1. Scope

1.1 This test method covers the determination of the titratable acidity of chromium tanning liquors. By *titratable acidity* is meant not only free acidity, which is rarely present, but also anions combined with weakly basic cations such as Chromium (III), which can be titrated with base at the phenolphthalein end point.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3898 Test Method for Chromic Oxide in Basic Chromium Tanning Liquors

3. Summary of Test Method

3.1 A sample of suitable size is taken by diluting and aliquoting, if necessary. The sample is then heated to boiling

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.06 on Chemical Analysis. This test method was developed in cooperation with the American Leather Chemists Assoc.

Current edition approved April 1, 2020. Published April 2020. Originally approved in 1991. Last previous edition approved in 2015 as D3913 – 03 (2015). DOI: 10.1520/D3913-03R20E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and titrated hot to the first appearance of a pink color, stable to boiling in the supernatant solution, as determined by viewing the settled solution against the rim of a porcelain dish, or against the light in a tall beaker or Erlenmeyer flask.



4. Significance and Use

4.1 The acidity of a chrome tanning liquor, as determined by this test method, is rarely employed as such. This result is normally combined with the results of a chromium analysis (see Test Method D3898) to determine a property of the liquor called basicity. This property, equal to the percentage by which anions in a normal chromic salt have been replaced by hydroxyl in the solution being analyzed, is closely related to the tanning behavior of the solution.

5. Interferences

5.1 Although for most purposes, the results of this analysis are intended to give a measure of the acid anions associated with chromium, it should be mentioned that any weak basic cation will behave similarly. Hence, aluminum, zirconium, ferric iron, and weak organic bases will all yield salts with acidity titratable by this test method. A discussion of the effect of these interferences has been published.³

5.2 If there are anions which form very stable complexes with chromium present in the solution, the titration:



where:

X = stable complexes,

will not go to completion at the phenolphthalein endpoint and the acidity reported will be low. Large excess of oxalate or complexing anions of lesser affinity used for masking effect will introduce this error.⁴ To obviate this, an entirely different method has been developed in which the hydroxyl groups are titrated and the chromium is completely complexed by oxalate.

³ Hartford, W. H., *JALCA*, Vol 56, 1961, p. 568.

⁴ Thorstensen, T. C., and Theis, E. R., *JALCA*, Vol 47, 1952, p. 583.