



Designation: B723 – 20

Standard Specification for Nickel-Chromium-Molybdenum-Cobalt-Tungsten-Iron-Silicon Alloy Welded Pipe¹

This standard is issued under the fixed designation B723; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers wrought alloy UNS N06333 in the form of welded pipe intended for heat-resisting applications and general corrosive service.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriated Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[B775 Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe](#)

[B718 Specification for Nickel-Chromium-Molybdenum-Cobalt-Tungsten-Iron-Silicon Alloy \(UNS N06333\) Plate, Sheet, and Strip](#)

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2020. Published May 2020. Originally approved in 1983. Last previous edition approved in 2014 as B723 – 00 (2014). DOI: 10.1520/B0723-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. General Requirement

3.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification [B775](#) unless otherwise provided herein.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

4.1.1 Alloy name or UNS number.

4.1.2 ASTM designation and year of issue.

4.1.3 Condition (temper) ([Table 1](#)).

4.1.4 *Dimensions:*

4.1.4.1 Nominal pipe size or outside diameter and schedule number or nominal wall thickness.

4.1.4.2 Length (specific or random).

4.1.5 Quantity (feet or metres, or number of pieces).

4.1.6 *Certification*—State if certification or a report of test results is required.

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished.

4.1.8 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

5. Material and Manufacture

5.1 The pipe shall be made from flat-rolled alloy conforming to Specification [B718](#), by an automatic welding process with no addition of filler metal.

5.2 Pipe shall be furnished annealed after welding, with oxide removed. When final heat treatment is performed in a protective atmosphere, descaling is not necessary.

6. Chemical Requirements

6.1 The material shall conform to the requirements as to chemical composition specified in [Table 1](#).

*A Summary of Changes section appears at the end of this standard