



Designation: **D6496/D6496M – 19** **D6496/D6496M – 20**

Standard Test Method for Determining Average Bonding Peel Strength Between Top and Bottom Layers of Needle-Punched Geosynthetic Clay Liners¹

This standard is issued under the fixed designation D6496/D6496M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the laboratory determination of the average bonding strength between the top and bottom layers of a sample of a geosynthetic clay liner (GCL).

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D76/D76M Specification for Tensile Testing Machines for Textiles](#)

[D123 Terminology Relating to Textiles](#)

[D4439 Terminology for Geosynthetics](#)

[D5889/D5889M Practice for Quality Control of Geosynthetic Clay Liners](#)

[D6072/D6072M Practice for Obtaining Samples of Geosynthetic Clay Liners](#)

<https://standards.iteh.ai/catalog/standards/sist/cb0d2470-e0ff-4268-a551-b6b9999c2f30/astm-d6496-d6496m-20>

3. Terminology

3.1 *Definitions:*

3.1.1 *geosynthetic clay liner, n*—a manufactured hydraulic barrier consisting of clay bonded to a layer or layers of geosynthetic material(s). **D4439**

3.2 For terminology of other terms used in this test method, refer to Terminologies [D123](#) and [D4439](#).

4. Summary of Test Method

4.1 The top and bottom layers of a geosynthetic clay liner are gripped individually in tensile grips and pulled at a constant rate of extension by a tensile testing machine until the top and bottom layers of the specimen separate. The average bonding peel strength of the test specimen can be calculated from machine scales, dials, recording charts, or an interface computer.

5. Significance and Use

5.1 The bonding strength test for the top and bottom layers of the geosynthetic clay liner is intended to be an index test. It is anticipated that the results of the test will be used to evaluate the quality of the bonding process.

¹ This test method is under the jurisdiction of ASTM Committee [D35](#) on Geosynthetics and is the direct responsibility of Subcommittee [D35.04](#) on Geosynthetic Clay Liners.

Current edition approved ~~May 1, 2019~~ May 1, 2020. Published ~~May 2019~~ May 2020. Originally approved in 1999. Last previous edition approved in ~~2018~~ 2019 as ~~D6496/D6496M – 18~~: D6496/D6496M – 19. DOI: ~~10.1520/D6496_D6496M-19~~: 10.1520/D6496_D6496M-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



6. Atmospheric Conditions

6.1 Atmospheric Conditions:

6.1.1 The atmospheric conditions of the laboratory determining average bonding peel strength between top and bottom layers of needle-punched geosynthetic clay liners shall be: relative humidity between 50 to 70 % and a temperature of 21 ± 2 °C [70 ± 4 °F].

7. Apparatus

7.1 *Tensile Testing Machine*—A constant rate of extension (CRE) type of testing machine described in Specification **D76/D76M** shall be used with a minimum precision measuring capability of 0.1 N/m [5.71×10^{-4} lbf/in.].

7.2 *Clamps*—The clamps shall be a minimum 25 by 100 mm [1 by 4 in.] and with appropriate clamping power to prevent slipping or crushing (damage).

7.3 *Die or Template*, 100 by 200 mm (± 1 mm) [4 by 8 in.].

7.4 *Miscellaneous*—Knives, razor, and the like, as required.

8. Test Specimen Sampling, Test Specimens, and Test Units

8.1 *Lot Sample*—For the lot sample, take rolls of GCLs as directed in an applicable material specification, Practice **D5889/D5889M**, or as agreed upon between the purchaser and the supplier.

8.2 *Laboratory Sample*—For the laboratory sample, sample shall be taken in accordance with Practice **D6072/D6072M**. The sample received at the testing laboratory should be in satisfactory condition and representative of the product manufactured or delivered to a site, or both.

8.3 *Test Specimens*—A minimum of five test specimens shall be taken in the machine direction from each swatch in the laboratory sample. Take specimens from the laboratory sample, with those for the measurement of the machine direction tensile properties from different positions across the GCL width. No specimens shall be taken within 10 cm [4 in.] of the selvage or edge of the GCL.

8.4 The size of the die or template for cutting specimens is 100 by 200 mm (minimum) [4 by 8 in.].

8.5 The loss of clay during the specimen cutting process should have no bearing on the results of the test.

7.4 A minimum of five test specimens should be cut from the laboratory sample such that they are representative of the entire roll width. All specimens should be parallel to the machine direction.

9. Conditioning

9.1 The test specimen shall be tested as received.

10. Procedure

10.1 *Obtain Specimens*—Using the die, or template and razor, and other necessary apparatus, carefully cut from the laboratory sample five test specimens. The five specimens should be randomly selected from locations on the sample, but should be distributed across the sample. All specimens should be cut parallel to the machine direction. Using a knife or razor, separate the top and bottom layer of the GCL for the first 50 ± 3 mm [2 ± 0.1 in.].

10.2 *Machine Setup Conditions*—Adjust the distance between the clamps at the start of the test to 50 ± 3 mm [2 ± 0.1 in.]. Set the CRE at 300 mm/min [12 in./min].

10.3 *Insertion of Specimen in Clamps*—Mount the specimen centrally in the clamps. The specimen must be visually observed above the clamp. The specimen length in the machine direction must be parallel to the direction of application of force.

10.4 *Measurement of Bonding Peel Strength*—Start the tensile testing machine. This is considered the start of the peel test and represents zero grip separation. Take readings of force and time starting from 50 mm [2 in.] of grip separation until 250 mm [10 in.] of grip separation. The average recorded peeling force of the GCL over 200 mm [8 in.] of grip separation is required and will signify a complete test of the specimen. (See Fig. 1.)

NOTE 1—If significant elongation of the geotextile continues after 50 mm [2 in.] additional grip peeling of the GCL, the recording interval should be adjusted. The recording interval should correspond to 200 mm [8 in.] of grip separation during the peeling of the GCL.

10.4.1 Readings of force and time shall be taken at a minimum rate of 20 readings per second.

10.4.2 If a specimen slips in the jaws, or if for any reason attributable to faulty operation the results fall significantly below the average for the set of specimens, discard the results and test another specimen. Continue until the required number of readings has been taken.




FIG. 1 Measurement of Bonding Peel Strength

11. Calculation

11.1 *Bonding Peel Strength*—Calculate the bond strength of individual specimens, that is, the average force to cause a specimen to separate expressed in N [lbf] of width, using the following equation:

$$\alpha_f = F_{\text{avg}} / W_S \quad (H)$$

$$\alpha_f = F_{\text{avg}} / W_S \quad (I)$$

where:

α_f = bonding peel strength, N/m [lbf/in.] of width,

F_{avg} = observed average force over a grip separation of 50 mm [2 in.] to 250 mm [10 in.], N [lbf], and

W_S = specified specimen width, m [in.].