



Designation: E1347 – 06 (Reapproved 2020)

Standard Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry¹

This standard is issued under the fixed designation E1347; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the instrumental measurement of specimens resulting in color coordinates and color difference values by using a tristimulus colorimeter, also known as a tristimulus filter colorimeter or a color-difference meter.

1.2 Provision is made in this test method for the measurement of color coordinates and color differences by reflected or transmitted light using either a hemispherical optical measuring system, such as an integrating sphere, or a bidirectional optical measuring system, such as annular, circumferential, or uniplanar 45:0 and 0:45 geometry.

1.3 Because of the limited absolute accuracy of tristimulus colorimeters, this test method specifies that, when color coordinates are required, the instrument be standardized by use of a standard having similar spectral (color) and geometric characteristics to those of the specimen. This standard is also known as a product standard. The use of a product standard of suitable stability is highly desirable.

1.4 Because tristimulus colorimeters do not provide any information about the reflectance or transmittance curves of the specimens, they cannot be used to gain any information about metamerism or paramerism.

1.5 Because of the inability of tristimulus (filter) colorimeters to detect metamerism or paramerism of specimens, this test method specifies that, when color differences are required, the two specimens must have similar spectral (color) and geometric characteristics. In this case, the instrument may be standardized for reflectance measurement by use of a white reflectance standard or, for transmittance measurement, with no specimen or standard at the specimen position.

1.6 This test method is generally suitable for any non-fluorescent, planar, object-color specimens of all gloss levels. Users must determine whether an instrument complying with

this method yields results that are useful to evaluate and characterize retroreflective specimens, or specimens having optical structures.

1.7 This test method does not apply to the use of a spectroradiometer, which is a spectrometer that provides colorimetric data, but not the underlying spectral data. Measurement by using a spectroradiometer is covered in Practice E1164 and methods on color measurement by spectrophotometry.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.9 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

E179 Guide for Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials

E284 Terminology of Appearance

E805 Practice for Identification of Instrumental Methods of Color or Color-Difference Measurement of Materials

E1164 Practice for Obtaining Spectrometric Data for Object-Color Evaluation

E1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements

¹ This test method is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.02 on Spectrophotometry and Colorimetry.

Current edition approved May 1, 2020. Published May 2020. Originally approved in 1990. Last previous edition approved in 2015 as E1347 – 06 (2015). DOI: 10.1520/E1347-06R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 Definitions:

3.1.1 The definitions contained in Guide E179 and Terminology E284 are applicable to this test method.

4. Summary of Test Method

4.1 This test method provides procedures for measuring object-color specimens in either transmission or reflection with a tristimulus colorimeter (hereafter referred to as a colorimeter) by use of the following geometric conditions and standardization procedures:

4.1.1 Color differences by reflected light of nonmetameric, nonparameric pairs of opaque or translucent specimens by use of either hemispherical geometry, with an integrating sphere, or bidirectional geometry, such as annular, circumferential, or uniplanar 45:0 or 0:45 geometry. The colorimeter may be standardized by use of a white reflectance standard.

4.1.2 Color differences by transmitted light of nonmetameric, nonparameric pairs of transparent or translucent specimens by use of hemispherical geometry. The colorimeter may be standardized by use of a white standard at the reflection port of the integrating sphere with no specimen in place. When translucent specimens are measured, they should be placed flush against the transmission port of the sphere, and the white standard should, for maximum accuracy, have the same reflectance and chemical composition as that of the lining of the integrating sphere.

4.1.3 Color coordinates by reflected light of opaque or translucent specimens by use of either bidirectional or hemispherical geometry. The colorimeter may be standardized by use of a standard having spectral (color) and geometric characteristics similar to those of the specimens. Such standards, often called *hitching-post* standards, are hereafter referred to as local standards.³

4.1.4 Color coordinates by transmitted light of transparent or translucent specimens by use of hemispherical geometry. The colorimeter may be standardized by use of a local standard.

4.1.5 This test method is not appropriate for fluorescent specimens.

4.1.6 For the measurement of the daytime color of retroreflective specimens, the 45:0 or 0:45 conditions are normally required. Some modern, high brightness, retroreflective sheeting has been shown to exhibit geometric artifacts if the cone angles are too narrow. In these cases, it may be more appropriate to use larger cone angles, with appropriate tolerances.

4.1.7 When the specimens exhibit directionality, and a colorimeter with uniplanar bidirectional geometry is used, information on directionality may be obtained by measuring the specimens at more than one rotation angle, typically at two angles 90° apart. When such information is not required, these measurements may be averaged, or a colorimeter with annular or circumferential bidirectional geometry may be used.

4.2 This test method includes two different procedures for standardizing the colorimeter. The first procedure utilizes a white standard of known reflectance factor; the second procedure utilizes a local standard.

4.2.1 When absolute values of color coordinates are to be determined, the use of a white standard is recommended only with colorimeters in which there is good conformance of the colorimeter readings to CIE tristimulus values, as determined by measurement of suitable verification standards (see Practice E1164). With instruments not meeting this requirement, the use of local standards is recommended, but only when the signal level (see Note 2) from the use of each colorimeter filter is adequately high.

NOTE 1—Of necessity, the above requirements are in part subjective, as the methods for verifying conformance to the requirements may not be available to the average user. Each user must decide whether the standardization procedure selected results in a loss of accuracy in the measurements that is negligibly small for the purpose for which data are obtained.

NOTE 2—The adequacy of the signal level can be determined by measuring the short-term repeatability without replacement, and ascertaining that the variation in the answer represents less than 30 % of the desired or allowable variation.

4.2.2 When color differences are to be measured, only relative measured values are required for the two members of the color-difference pair, and standardization by use of either a white standard or a local standard is satisfactory. In those cases where a computer program is being used to predict color tolerances, accuracy of the absolute values of the product standard color coordinates may become more important (see 4.2.1).

4.3 Procedures for selecting specimens suitable for precision measurement are included in this test method.

4.4 Most modern colorimeters compute the color coordinates of the specimen during the measurement. When this is the case, the user of this test method must designate the color system to be used in the computation (see Practice D2244).

5. Significance and Use

5.1 The most direct and accessible methods for obtaining the color differences and color coordinates of object colors are by instrumental measurement using colorimeters or spectrophotometers with either hemispherical or bidirectional optical measuring systems. This test method provides procedures for such measurement by use of a colorimeter with either a bidirectional or a hemispherical optical measuring system.

5.2 This test method is suitable for measurement of color differences of nonmetameric, nonparameric pairs of object-color specimens, or color coordinates of most such specimens. A further limitation to the use of colorimeters having hemispherical geometry is the existence of a chromatic integrating-sphere error that prevents accurate measurement of color coordinates when the colorimeter is standardized by use of a white standard.⁴

³ Hunter, R. S., "Photoelectric Tristimulus Colorimetry with Three Filters," *Journal, Optical Society of America*, Vol 32, 1942, pp. 509–558.

⁴ Hoffman, K., "Chromatic Integrating-Sphere Error in Tristimulus Colorimeters," *Journal of Color and Appearance*, Vol 1, No. 2, 1971, pp. 16–21.

5.3 For the measurement of retroreflective specimens by this test method, the use of bidirectional geometry is recommended (see Guide E179 and Practice E805).

NOTE 3—To ensure inter-instrument agreement in the measurement of retroreflective specimens, significantly tighter tolerances than those given in Practice E1164 in the section on Influx and Efflux Conditions for 45°:Normal (45:0) and Normal:45° (0:45) Reflectance Factor are required for the instrument angles of illumination and viewing. Information on the required tolerances is being developed.

5.4 A requirement for the use of a colorimeter to obtain accurate color coordinates is that the combination of source, filter, and detector characteristics to duplicate accurately the combined characteristics of a CIE standard illuminant and observer. When this requirement is not met, this test method requires the use of local standards for improving accuracy in the measurement of color coordinates (see also 4.2). For the measurement of small color differences between nonmetameric, nonparameric specimens, accuracy in absolute color coordinates is less important and standardization of the colorimeter by use of a white standard is satisfactory. However, accurate color-difference measurement requires that specimen pairs have similar spectral and geometric characteristics.

6. Apparatus

6.1 *Colorimeter*, designed for the measurement of object-color specimens. Use hemispherical geometry for reflection or transmission measurements or bidirectional geometry for reflection measurements.

6.2 *Standardization Plaques*, supplied by the manufacturer.

6.2.1 *White Reflecting Tile or Standard (Mandatory)*—(If the colorimeter has hemispherical geometry, a standard of hemispherical reflectance factor is required; if bidirectional geometry, a standard of bidirectional reflectance factor is required.)

6.2.2 *Local Standardization Plaques (Recommended)*, having spectral (color) and geometric characteristics similar to those of specimens to be measured, as required for the measurement of color coordinates.

6.2.3 *Light Trap (Hemispherical) or Polished Black Glass (Bidirectional) Standards (Recommended; mandatory if so indicated by the manufacturer)*, for setting or verifying the zero reading of the colorimeter.

6.3 *Verification Standards (Recommended)*, supplied by the manufacturer or obtained separately.

6.4 *Standard Backing Material(s) (Recommended)*, for backing translucent specimens during measurement.

7. Test Specimens

7.1 For highest precision, select specimens with the following properties:

7.1.1 High material uniformity and freedom from blemishes in the area to be measured, and

7.1.2 Opaque specimens that have at least one plane surface; translucent and transparent specimens that have two essentially plane and parallel surfaces and that have a standard thickness, when one is specified.

8. Standardization and Verification

8.1 *Standardization for the Measurement Color Differences of Specimen Pairs:*

8.1.1 Standardize the colorimeter by use of the white standard (mandatory) and the zero-reading standard (if required), following the manufacturer's instructions.

8.1.2 Verify the accuracy of the standardization and the instrument performance by measuring a series of verification standards (recommended).

8.2 *Standardization for Measurement of Color Coordinates:*

NOTE 4—If the verification tests of 8.2.2 are not to be carried out, omit 8.2.1 and 8.2.2 and proceed to 8.2.3.

8.2.1 Standardize the colorimeter by use of the white standard (mandatory) and the zero-reading standard (if required), following the manufacturer's instructions.

8.2.2 Verify the accuracy of the standardization and the instrument performance by measuring a series of verification standards (recommended).

8.2.3 Standardize the colorimeter by use of the appropriate local standard for the specimens to be measured (mandatory) and the zero-reading standard (if required), following the manufacturer's instructions.

9. Procedure

9.1 When required, select the color scales to be used in the computation of color coordinates or color differences.

9.2 Handle the specimen carefully; avoid touching the area to be measured. When necessary, clean the specimen by an agreed procedure.

9.3 When hemispherical geometry is used, make the following selections:

9.3.1 For the measurement of reflecting specimens, select inclusion or exclusion of the specular component of reflection as desired (see Guide E179 and Practice E805).

9.3.1.1 If the specimen is translucent, back it with a standard backing material during the measurement.

9.3.2 For the measurement of fully transparent specimens by transmission, place the specimen in the transmission compartment of the colorimeter.

9.3.2.1 If total luminous quantities are desired, place the specimen flush against the transmission measurement port of the integrating sphere.

9.3.2.2 If regular luminous quantities are desired, place the specimen as far away from the sphere port as possible.

9.3.3 For the measurement of translucent specimens, place the specimen in the transmission compartment, flush against the transmission measurement port of the integrating sphere. For maximum accuracy, the white standard at the reflection port should have the same reflectance and chemical composition as that of the lining of the integrating sphere.

9.4 When bidirectional geometry is used, make the following selections:

9.4.1 If the specimen exhibits directionality and the instrument has uniplanar geometry, measure the specimen at two