



Designation: C1435/C1435M – 20

Standard Practice for Molding Roller-Compacted Concrete in Cylinder Molds Using a Vibrating Hammer¹

This standard is issued under the fixed designation C1435/C1435M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice² covers molding cylindrical test specimens from concrete when the standard procedures of rodding and internal vibration, as described in Practice C31/C31M and Practice C1176/C1176M, are not practicable. This practice is applicable to freshly-mixed concrete, prepared in the laboratory and the field.

1.2 Freshly-mixed concrete is molded in cylindrical molds using an electric vibrating hammer equipped with a shaft and circular plate.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the inch-pound units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 The text of this practice references notes and footnotes, which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this practice.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of Committee C09 on Concrete and Concrete Aggregates and are the direct responsibility of Subcommittee C09.45 on Roller-Compacted Concrete.

Current edition approved April 1, 2020. Published May 2020. Originally approved in 1999. Last previous edition approved in 2014 as C1435/C1435M – 14. DOI: 10.1520/C1435_C1435M-20.

² Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C09-1045. Contact ASTM Customer Service at service@astm.org.

2. Referenced Documents

2.1 ASTM Standards:³

C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C172/C172M Practice for Sampling Freshly Mixed Concrete

C470/C470M Specification for Molds for Forming Concrete Test Cylinders Vertically

C496/C496M Test Method for Splitting Tensile Strength of Cylindrical Concrete Specimens

C1170/C1170M Test Method for Determining Consistency and Density of Roller-Compacted Concrete Using a Vibrating Table

C1176/C1176M Practice for Making Roller-Compacted Concrete in Cylinder Molds Using a Vibrating Table

2.2 ACI Documents:

ACI 207.5R Report on Roller-Compacted Concrete⁴

ACI 211.3 Practice for Selecting Proportions for No-Slump Concrete⁴

3. Summary of Practice

3.1 This practice describes molding cylindrical concrete test specimens using a vibrating hammer. Test specimens are molded vertically in cylindrical molds by compacting the stiff to very dry concrete mixture in four lifts using a vibrating hammer.

4. Significance and Use

4.1 This practice, intended for use in testing roller-compacted concrete, may be applicable to testing other types of cementitious material such as coarse-grained, soil-cement. This practice provides standardized requirements for molding stiff to very dry consistency concrete mixtures commonly used in roller compacted concrete construction. This practice is used

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ *ACI Manual of Concrete Practice, Part 1, Materials and General Properties of Concrete*, American Concrete Institute, Farmington Hills, MI.

*A Summary of Changes section appears at the end of this standard

instead of rodding or internal vibration, which cannot properly consolidate concrete of this consistency.

NOTE 1—Further description of roller compacted concrete consistency is given in ACI 207.5R and ACI 211.3. The consistency of concrete using a vibrating table may be determined in accordance with Test Methods **C1170/C1170M**.

4.2 This practice is used to mold cylindrical test specimens commonly used for testing compressive or tensile strength of concrete. Specimens tested for compressive strength and splitting tensile strength shall be in accordance with Test Methods **C39/C39M** and **C496/C496M**, respectively. Test specimens also may be used to determine density of fresh concrete.

NOTE 2—For some extremely dry mixtures; (those with a consistency greater than 45 s when tested in accordance with Test Methods **C1170/C1170M**)⁵ the density of specimens made in accordance with this practice may be greater than the in-place density of roller-compacted concrete due to the greater potential for voids at the bottom of the lifts in the field.

NOTE 3—The mass of the apparatus and amount of force applied by the operator may significantly affect the density of specimens made from these mixtures; thus, discretion is advised when interpreting test results on specimens made according to this practice.

5. Apparatus

5.1 Molds:

5.1.1 *Type A Reusable Mold*—A cylindrical mold conforming to the requirements of Specification **C470/C470M** for 150-mm [6-in.] diameter by 300-mm [12-in.] high reusable molds.

5.1.2 *Type B Single-Use Mold*—A single-use plastic, cylindrical mold 150-mm [6-in.] diameter and 300-mm [12-in.] in height. The mold specifications shall conform to Specification **C470/C470M** for single-use, plastic molds.

5.1.2.1 *Mold Sleeve*—A Type B cylindrical mold shall be inserted into a rigid cylindrical sleeve. The cylindrical sleeve shall be made of steel or other hard metal resistant to cement paste corrosion. The sleeve shall be capable of firmly holding the plastic mold upright without deformation of the mold. The sleeve shall be split and hinged on one side so that it can be opened to remove the plastic mold; adjustable clamps shall be provided on the other side for tightening the sleeve around the mold. A metal base plate with brackets shall be provided in which to insert the bottom portion of the sleeve to hold the sleeve during compaction. The sleeve shall have a minimum wall thickness of 3 mm [$\frac{1}{8}$ in.], and a minimum base plate thickness of 6 mm [$\frac{1}{4}$ in.]. The inside diameter of the mold sleeve shall be 3 ± 1 mm [$\frac{1}{8} \pm \frac{1}{16}$ in.] larger than the outside diameter of the Type B mold and have a height 13 ± 6 mm [$\frac{1}{2} \pm \frac{1}{4}$ in.] less than the height of the Type B mold.

5.2 *Vibrating Hammer*—A vibrating compaction hammer having a mass (without tamping plate and shaft) of 8.5 to 13.5 kg [19 to 30 lb]. It also shall have a minimum power input of 900 W and be capable of providing 2000 ± 200 impacts/min.

NOTE 4—The vibrating hammer used to compact the specimens, such as shown in Fig. 1, is of the type used typically for breaking up concrete and masonry. It provides oscillatory motion in the axial direction that makes the hammer an effective vibratory compactor.

⁵ Hansen, K. and Kahler, C., "RCC Tests, Testing, and Test Sections – Lessons Learned," *The Journal of Dam Safety*, Volume 2, Issue 1 (Winter 2004), p.14

5.3 *Tamping Plate*—A circular steel plate attached to a steel shaft, which is inserted into the vibrating hammer chuck. The plate diameter shall be 146 ± 3 mm [$5 \frac{3}{4} \pm \frac{1}{8}$ in.] and the mass of the plate and shaft assembly shall be 3 ± 1 kg [6.6 ± 2.2 lb] (See Fig. 2).

5.4 *Small Tools*—A square-ended shovel, a hand scoop, a tamping rod, and a stopwatch.

6. Sampling

6.1 Samples of freshly-mixed concrete shall be obtained in accordance with Practice **C172/C172M**.

6.2 Concrete samples shall have a maximum size aggregate of 50 mm [2 in.] or less. If the concrete has aggregate larger than 50 mm [2 in.] samples shall be obtained by wet sieving over a 50-mm [2-in.] sieve in accordance with Practice **C172/C172M**.

6.3 Concrete test specimens shall be molded within 45 min after the completion of mixing unless otherwise specified.

6.4 Technical Precautions:

6.4.1 When obtaining samples, ensure that the samples are representative of the bulk production.

6.4.2 Concrete with stiff to very dry consistency is highly susceptible to segregation during handling. To minimize segregation, use care in obtaining samples and during transporting, remixing, and preparation of the specimens.

7. Verification

7.1 Verify the frequency and mass of the vibrating hammer after any event, including repairs, that might affect its operation, after 300 h of service, or at least one time per year.

NOTE 5—Tachometers and stroboscopes have been found as suitable means to verify the frequency of the vibrating hammer.

8. Molding Specimens

8.1 Type A Molds:

8.1.1 Coat Type A molds with a suitable lubricant or bond breaker prior to casting the test specimens to facilitate removal from the mold.

8.2 Type B Molds:

8.2.1 Insert Type B mold into the mold sleeve and adjust the clamps to tighten the sleeve around the mold so that the mold is held firmly in the sleeve.

8.3 Type A and B Molds:

8.3.1 Hold the mold stationary either by clamping to a rigid, flat base or standing on the foot brackets and center the vibrating hammer so that the edges of the tamping plate do not touch the walls of the mold. Lower the vibrating hammer into the mold to check for proper clearance.

8.3.2 Place enough concrete in the mold so that the mold will be filled to one-fourth of its volume after consolidation, approximately 3.4 kg [7.5 lb]. Use a tamping rod to distribute the loose concrete as it is added. During filling, use square-ended shovels and scoops to obtain representative samples and handle the concrete in such a manner that larger sized coarse aggregates do not separate from the mortar.