



Designation: C1763 – 20

Standard Test Method for Water Absorption by Immersion of Thermal Insulation Materials¹

This standard is issued under the fixed designation C1763; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method determines the amount of water retained (excluding surface water) by flat or cylindrical specimens of thermal insulations after these materials have been fully immersed in liquid water for a prescribed time interval under isothermal conditions. This test method is intended to be used for the characterization of materials in the laboratory. It is not intended to simulate any particular environmental condition potentially encountered in building construction applications.

1.2 This test method does not address all the possible mechanisms of water intake and retention and related phenomena for thermal insulations. It relates only to those conditions outlined in 1.1. Determination of moisture accumulation in thermal insulations due to partial immersion, water vapor transmission, internal condensation, freeze-thaw cycling, or a combination of these effects requires different test procedures.

1.3 This test method does not address or attempt to quantify the drainage characteristics of materials.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Material And Specimen Characteristics that can Influence Results

2.1 The apparent water absorption measured by this test method is dependent on the surface to volume ratio of the sample and time of immersion. As such, comparisons between Procedures A, B, and, C cannot be made. Cracks in the specimens and rough surfaces can increase the apparent water absorption.

2.2 Some materials tend to collect water on surfaces or to trap water in corners and, if not removed, will give incorrect results.

2.3 Materials that change or react with water can have increased (or decreased) apparent water absorption and are not suitable for use with this method. 12.7.1 provides a method for ensuring the specimen has not been physically or chemically altered in a way that would invalidate the measurement. Use this method in cases of dispute.

3. Referenced Documents

3.1 ASTM Standards:²

- C168 Terminology Relating to Thermal Insulation
- C302 Test Method for Density and Dimensions of Preformed Pipe-Covering-Type Thermal Insulation
- C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation
- C870 Practice for Conditioning of Thermal Insulating Materials
- C1134 Test Method for Water Retention of Rigid Thermal Insulations Following Partial Immersion
- E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods
- E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33 on Insulation Finishes and Moisture.

Current edition approved May 1, 2020. Published May 2020. Originally approved in 2014. Last previous edition approved in 2019 as C1763 – 19^{e1}. DOI: 10.1520/C1763-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Terminology

4.1 *Definitions*—Terminology C168 applies to terms used in this test method.

5. Summary of Test Method

5.1 Test specimens are conditioned and then immersed in water for a prescribed amount of time. The amount of water absorbed is determined by the weight increase in the specimens.

6. Significance and Use

6.1 This test method provides a means of measuring the water absorption of flat or cylindrical specimens of thermal insulation materials under isothermal conditions as a result of direct immersion in liquid water. It is intended for quality control and product and material specifications.

6.2 The procedure to be used: A, B, or C as well as any exceptions shall be noted in material specifications citing this test method.

6.3 Repeatability has been established only for one type and size of material at one immersion duration.

NOTE 1—Specifications referring to this test method are encouraged to establish repeatability for specific materials, immersion duration, and dimensions for inclusion in this test method.

7. Apparatus

7.1 *Temperature measuring device*—Such as a thermometer, graduated in Celsius or Fahrenheit degrees with at least 1°C (2°F) sensitivity.

7.2 *Balance*, accurate to 0.1g.

7.3 *Immersion Pan*—A pan or vessel of width and length at least 50 mm (2 in.) larger than the dimensions of the specimen width and length, and of a depth at least 50 mm (2 in.) greater than the specimen thickness.

7.4 *Timing device*, such as stopwatch or timer capable of $\pm 1\%$ of the required immersion duration.

7.4.1 *Specimen Supports and Constraints*—Included in the construction of the immersion pan shall be a means for securing the specimens in a level position, that is, a noncorrosive support for the bottom surface of the specimens and a similar constraining device for the top surface for buoyant materials. The support and constraining devices shall not contact more than 15 % of the specimen surfaces. The space between the support and the bottom of the pan shall be not less than 5 mm (0.2 in.). The pressure exerted on the specimens by the constraining device for the top surface shall be limited to that required to counteract any buoyant force exerted by the specimens at the beginning of the test. Stainless steel is an acceptable support and weight material. An example of a suitable constraining device is a 6.4 mm. (0.25 in.) mesh rigid stainless steel screen.

8. Sampling, Test Specimens, and Test Units

8.1 Number of specimens, dimensions, and dimension tolerance of the test specimen or specimens shall be stated in the material specification to follow one of the following procedures:

8.2 *Procedure A:*

8.2.1 Test specimens shall be 152 ± 3 mm long, 89 ± 3 mm wide, and 51 ± 3 mm thick ($6 \pm \frac{1}{8}$ in. long, $3\frac{1}{2} \pm \frac{1}{8}$ in. wide, and $2 \pm \frac{1}{8}$ in. thick)

8.2.2 A minimum of two test specimens are required.

8.2.3 Immersion time shall be a minimum of 48 h.

8.2.4 The specimen shall be weighed immediately after the removal of surface water.

8.3 *Procedure B:*

8.3.1 *Flat Specimen:*

8.3.1.1 Test specimens shall be 305 ± 3 by 305 ± 3 mm (12 by 12 in.) with all four edges trimmed square and thickness representative of manufactured product.

8.3.1.2 One specimen from each of three boards shall be tested.

8.3.2 *Cylindrical Specimen:*

8.3.2.1 Cylindrical materials that are to be evaluated are limited to one-piece pipe sections.

8.3.2.2 Test specimen shall be 305 ± 3 mm (12 in.) long.

8.3.2.3 The diameter and wall thickness of the specimen are to be as manufactured without modification.

8.3.2.4 One specimen from each of three pipe segments shall be tested.

8.3.3 Immersion time shall be 2 h.

8.3.4 The specimen shall be drained by placing on end for 10 min.

NOTE 2—Procedure B is typically used for elastomeric and polyolefin foams in flat or cylindrical configuration, cellulosic fiber insulating board, and polyisocyanurate thermal insulation board.

8.4 *Procedure C:*

8.4.1 Test specimens shall be 305 ± 3 by 305 ± 3 mm by 25 mm thick. (12 by 12 in. by 1 in. thick.)

8.4.2 Three specimens shall be tested.

8.4.3 Immersion time shall be 24 h.

8.4.4 The specimen shall be shaken vigorously then weighed immediately after the removal of surface water.

NOTE 3—Procedure A is typically used for perlite block insulation.

NOTE 4—Procedure B is typically used for cellulosic fiber insulating board and polyisocyanurate thermal insulation board.

NOTE 5—Procedure C is typically used for polystyrene thermal insulation board.

9. Preparation of Apparatus

9.1 Fill the immersion pan with distilled, deionized water sufficient to maintain a 25 mm (1 in.) head of water over the sample surface at all times during the test.

9.2 Allow the water to reach a steady temperature of $23 \pm 1^\circ\text{C}$ ($73 \pm 2^\circ\text{F}$).

10. Calibration and Standardization

10.1 All measuring equipment shall have calibration certificates that are current at the time of use of the equipment.

11. Conditioning

11.1 Pre-condition per Test Method C870. Additional conditioning, such as heat-soaking, shall be performed as required by the material specification.

12. Procedure

12.1 Measure flat test specimen dimensions and calculate density per Test Method **C303**.

12.2 Measure cylindrical test specimen dimensions and calculate density per Test Method **C302**.

12.3 Weigh each specimen to the nearest 0.1 g. This weight is the pre-immersion weight, W_1 .

12.4 The selection of Procedure A, B, or C, including their proscribed sample size and duration of immersion, shall be stated in the material or product specification.

12.5 Submerge each specimen horizontally in the pan under 25 ± 2 mm (1 ± 0.1 in.) of distilled, deionized water. Specimens shall be placed on the sample supports described in **7.4.1**. For buoyant materials, the specimen constraints described in **7.4.1** shall be used. If necessary, add distilled, deionized water at $23 \pm 1^\circ\text{C}$ ($73 \pm 2^\circ\text{F}$) to ensure that the specimens are immersed to the required depth.

12.6 During the test, the immersion pan shall remain in an environment with a temperature of $23 \pm 2^\circ\text{C}$ ($73 \pm 4^\circ\text{F}$).

12.7 Remove the specimens from the water, drain as required in procedure B or C, then remove any excess surface water by light blotting with a paper towel not to exceed 2 s per surface. For a cylindrical specimen, after blotting the outside of the specimen, roll up a paper towel and pull it through the inside of the specimen. Non-rigid materials shall be supported for draining in a rack such as described in Test Method **C1134**, Fig. 2 and 3, with solid contact between the rack and specimen less than 15% in surface area. After draining and removal of surface water, immediately weigh each specimen to the nearest 0.1 g. This weight is the weight after immersion, W_2 .

12.7.1 Some insulation materials are either friable or reactive with water or both as described in **2.3**. In cases of dispute, the following procedure shall be performed. After water absorption testing, the specimens shall be dried in a drying oven at $50 \pm 2^\circ\text{C}$ ($120 \pm 5^\circ\text{F}$). The specimens shall be conditioned until constant mass is achieved. Constant mass is reached when consecutive weighings of the test specimens, taken at a minimum of 2 h apart, result in a weight change of not more than 0.2 %. The final specimen weight must not differ from the initial specimen weight by more than 5%. The purpose of this final requirement is to ensure the specimen has not undergone physical changes (such as breakage) or chemical changes that would invalidate the measurement.

13. Calculation or Interpretation of Results

13.1 Definitions of Symbols:

t	= specimen height, cm (in.)
l	= specimen length, cm (in.)
w	= specimen width, cm (in.)
V	= specimen volume, cm^3 (in. ³)
W_1	= pre-immersion weight of the specimen, g.
W_2	= specimen weight after immersion, draining & blotting, g.
ρ	= density of water in g/cm^3 (g/in^3)

13.2 Calculate the percent water absorbed by weight as:

$$100 \times (W_2 - W_1) / W_1 \quad (1)$$

13.3 Specimen Volume:

13.3.1 Calculate the volume for flat specimen according to Test Method **C303**.

13.3.2 Calculate the volume for cylindrical specimen according to Test Method **C302**.

13.4 Calculate the percent water absorbed by volume by multiplying the water absorption as:

$$\begin{aligned} (\text{Percent by Volume}) &= (\text{Percent by Weight}) \\ &\times (\text{Material Density}) / (\text{Water Density}) \quad (2) \end{aligned}$$

13.4.1 For the level of accuracy desired, the density of water shall be taken as $1 \text{ g}/\text{cm}^3$ ($62.4 \text{ lb}/\text{ft}^3$).

14. Report

14.1 Report the following information:

14.1.1 Procedure used: A, B, or C.

14.1.2 Description and nominal dimensions of the material tested.

14.1.3 Individual specimen weight, before immersion.

14.1.4 Duration of immersion.

14.1.5 Preconditioning and conditioning, if any.

14.1.6 Draining time, if any.

14.1.7 Individual specimen water absorption amount in grams.

14.1.8 Individual specimen percent water absorption by weight as described in **13.2**.

14.1.9 Individual specimen percent water absorption by volume as described in **13.4**, or as required by the material specification.

15. Precision and Bias³

15.1 The precision of this test method is based on two interlaboratory studies of Test Method C1763 conducted in 2015 and 2018. Each of ten laboratories tested three different insulating materials. Every “test result” represents an individual determination, and all participants reported triplicate test results. Practice **E691** was followed for the design and analysis of the data.

15.1.1 *Repeatability (r)*—The difference between repetitive results obtained by the same operator in a given laboratory applying the same test method with the same apparatus under constant operating conditions on identical test material within short intervals of time would in the long run, in the normal and correct operation of the test method, exceed the following values only in one case in 20.

15.1.1.1 Repeatability can be interpreted as maximum difference between two results, obtained under repeatability conditions, that is accepted as plausible due to random causes under normal and correct operation of the test method.

15.1.1.2 Repeatability limits are listed in **Tables 1-3**.

15.1.2 *Reproducibility (R)*—The difference between two single and independent results obtained by different operators applying the same test method in different laboratories using

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C16-1051. Contact ASTM Customer Service at service@astm.org.