



IEEE

IEC/IEEE 62582-3

Edition 2.0 2024-07
REDLINE VERSION

INTERNATIONAL STANDARD



**Nuclear power plants – Instrumentation and control important to safety –
Electrical equipment condition monitoring methods –
Part 3: Elongation at break**

Document Preview

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2024 IEC, Geneva, Switzerland
Copyright © 2024 IEEE

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing being secured. Requests for permission to reproduce should be addressed to either IEC at the address below or IEC's member National Committee in the country of the requester or from IEEE.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

Institute of Electrical and Electronics Engineers, Inc.
3 Park Avenue
New York, NY 10016-5997
United States of America
stds.ipr@ieee.org
www.ieee.org

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About the IEEE

IEEE is the world's largest professional association dedicated to advancing technological innovation and excellence for the benefit of humanity. IEEE and its members inspire a global community through its highly cited publications, conferences, technology standards, and professional and educational activities.

About IEC/IEEE publications

The technical content of IEC/IEEE publications is kept under constant review by the IEC and IEEE. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

<https://standards.itec.org/standards/iec-62582-3-2024>



IEEE

IEC/IEEE 62582-3

Edition 2.0 2024-07
REDLINE VERSION

INTERNATIONAL STANDARD



**Nuclear power plants – Instrumentation and control important to safety –
Electrical equipment condition monitoring methods –
Part 3: Elongation at break**

Document Preview

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 27.120.20

ISBN 978-2-8322-9486-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	2
1 Scope and object	10
2 Normative references	10
3 Terms and definitions	10
4 General description	11
5 Applicability and reproducibility	11
6 Measurement procedure	12
6.1 Stabilisation of the polymeric materials	12
6.2 Sampling.....	12
6.2.1 General	12
6.2.2 Sample requirements.....	12
6.3 Specimen preparation	13
6.3.1 General	13
6.3.2 Dumb-bell specimens	13
6.3.3 Tubular specimens	13
6.3.4 O-ring specimens	13
6.4 Instrumentation.....	14
6.4.1 Tensile test machine.....	14
6.4.2 Calibration.....	14
6.4.3 Use of extensometers.....	14
6.5 Tensile elongation measurement method.....	14
6.5.1 Conditioning	14
6.5.2 Dimensions of test specimens	14
6.5.3 Clamping.....	15
6.5.4 Testing speed.....	15
6.5.5 Recording data	15
6.5.6 Calculation of results	16
6.6 Measurement report.....	17
Annex A (informative) Shape and dimensions of test specimens	18
A.1 Preparation of dumb-bell specimens	18
A.2 Tubular specimens.....	18
A.3 O-ring specimens.....	20
Annex B (informative) Preparation of test specimens from cable samples	21
B.1 General.....	21
B.2 Preparation of specimens from large diameter cables	21
B.3 Preparation of specimens from small diameter cables	21
B.4 Preparation of test specimens from bonded material	22
Annex C (informative) Typical load versus elongation curves	23
Annex D (normative) Dies for cutting dumb-bell specimens.....	25
Annex E (informative) Example of a measurement report from tensile elongation measurements	26
Bibliography.....	27
Figure A.1 – Shape of dumb-bell specimens	18

Figure A.2 – Fitting end tabs to tubular specimens.....	19
Figure A.3 – Fitting soft inserts to tubular specimens	20
Figure A.4 – Mounting of O-ring specimens in the test machine	20
Figure C.1 – Typical load-elongation curves	23
Figure C.2 – Typical load-time curve with a slipping specimen	24
Figure D.1 – Suitable cutters for dumb-bell specimens.....	25
Table 1 – Testing speeds for elongation measurements.....	15
Table A.1 – Recommended dimensions for dumb-bell specimens	18

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**NUCLEAR POWER PLANTS –
INSTRUMENTATION AND CONTROL IMPORTANT TO SAFETY –
ELECTRICAL EQUIPMENT CONDITION MONITORING METHODS –****Part 3: Elongation at break**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC document(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation.

IEEE Standards documents are developed within IEEE Societies and Standards Coordinating Committees of the IEEE Standards Association (IEEE SA) Standards Board. IEEE develops its standards through a consensus development process, approved by the American National Standards Institute, which brings together volunteers representing varied viewpoints and interests to achieve the final product. Volunteers are not necessarily members of IEEE and serve without compensation. While IEEE administers the process and establishes rules to promote fairness in the consensus development process, IEEE does not independently evaluate, test, or verify the accuracy of any of the information contained in its standards. Use of IEEE Standards documents is wholly voluntary. *IEEE documents are made available for use subject to important notices and legal disclaimers (see <https://standards.ieee.org/ipr/disclaimers.html> for more information).*

IEC collaborates closely with IEEE in accordance with conditions determined by agreement between the two organizations. This Dual Logo International Standard was jointly developed by the IEC and IEEE under the terms of that agreement.

- 2) The formal decisions of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees. The formal decisions of IEEE on technical matters, once consensus within IEEE Societies and Standards Coordinating Committees has been reached, is determined by a balanced ballot of materially interested parties who indicate interest in reviewing the proposed standard. Final approval of the IEEE standards document is given by the IEEE Standards Association (IEEE SA) Standards Board.
- 3) IEC/IEEE Publications have the form of recommendations for international use and are accepted by IEC National Committees/IEEE Societies in that sense. While all reasonable efforts are made to ensure that the technical content of IEC/IEEE Publications is accurate, IEC or IEEE cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications (including IEC/IEEE Publications) transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC/IEEE Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC and IEEE do not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC and IEEE are not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or IEEE or their directors, employees, servants or agents including individual experts and members of technical committees and IEC National Committees, or volunteers of IEEE Societies and the Standards Coordinating Committees of the IEEE Standards Association (IEEE SA) Standards Board, for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC/IEEE Publication or any other IEC or IEEE Publications.
- 8) Attention is drawn to the normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.

- 9) Attention is drawn to the possibility that implementation of this IEC/IEEE Publication may require use of material covered by patent rights. By publication of this standard, no position is taken with respect to the existence or validity of any patent rights in connection therewith. IEC or IEEE shall not be held responsible for identifying Essential Patent Claims for which a license may be required, for conducting inquiries into the legal validity or scope of Patent Claims or determining whether any licensing terms or conditions provided in connection with submission of a Letter of Assurance, if any, or in any licensing agreements are reasonable or non-discriminatory. Users of this standard are expressly advised that determination of the validity of any patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC/IEEE 62582-3:2012. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

IEC/IEEE 62582-3 was prepared by subcommittee 45A: Instrumentation and control of nuclear facilities, of IEC technical committee 45: Nuclear instrumentation, in cooperation with the Nuclear Power Engineering Committee of the Power & Energy Society of the IEEE¹, under the IEC/IEEE Dual Logo Agreement between IEC and IEEE. It is an International Standard.

This document is published as an IEC/IEEE Dual Logo standard.

This second edition cancels and replaces the first edition published in 2012. This edition constitutes a technical revision.

This edition includes the following technical changes with respect to the previous edition:

- a) Updated best practices relating to condition monitoring using the tensile elongation method.
- b) Updated bibliography, references and context.

The text of this International Standard is based on the following IEC documents:

Draft	Report on voting
45A/1524/FDIS	45A/1538/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with the rules given in the ISO/IEC Directives, Part 2, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications/.

A list of all parts of the IEC/IEEE 62582 series, under the general title *Nuclear power plants – Instrumentation and control important to safety – Electrical equipment condition monitoring methods*, can be found on the IEC website.

¹ A list of IEEE participants can be found at the following URL: http://standards.ieee.org/downloads/62582-3/62582-3-2012/62582-3-2012_wg-participants.pdf.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>

INTRODUCTION

a) Technical background, main issues and organisation of the standard

This part of this IEC/IEEE standard specifically focuses on elongation at break methods for condition monitoring for the management of ageing of electrical equipment installed in nuclear power plants. The method is primarily suited to samples taken from equipment that are based on ~~thermoplastic or elastomeric polymers~~ polymeric materials.

This part of IEC/IEEE 62582 is the third part of the IEC/IEEE 62582 series. It contains detailed descriptions of condition monitoring based on elongation at break measurements.

The IEC/IEEE 62582 series is issued with a joint logo which makes it applicable to management of ageing of electrical equipment qualified to IEEE as well as IEC Standards.

~~Historically, IEEE Std 323-2003 introduced the concept and role that conditionbased qualification could be used in equipment qualification as an adjunct to qualified life. In equipment qualification, the condition of the equipment for which acceptable performance was demonstrated is the qualified condition. The qualified condition is the condition of equipment, prior to the start of a design basis event, for which the equipment was demonstrated to meet the design requirements for the specified service conditions.~~

IEC/IEEE 60780-323 defined term condition-based qualification which is an adjunct to type testing. The qualified condition is established by condition indicator(s) prior to the start of accident conditions for which the equipment was demonstrated to meet the design requirements for the specified service conditions. IEC/IEEE 60780-323 defined condition indicator.

Significant research has been performed on condition monitoring techniques and the use of these techniques in equipment qualification as noted in NUREG/CR-6704, vol.2 (BNL-NUREG-52610), JNES-SS-0903, 2009 and IAEA-TECDOC-1825:2017.

It is intended that this IEC/IEEE standard be used by test laboratories, operators of nuclear power plants, systems evaluators and licensors.

b) Situation of the current standard in the structure of the IEC SC 45A standard series

Part 3 of IEC/IEEE 62582 is the third level IEC SC 45A document tackling the specific issue of application and performance of elongation at break measurements in management of ageing of electrical instrument and control equipment in nuclear power plants.

Part 3 of IEC/IEEE 62582 is to be read in association with Part 1 of IEC/IEEE 62582, which provides requirements for application of methods for condition monitoring of electrical equipment important to safety of nuclear power plants.

For more details on the structure of the IEC SC 45A standard series, see item d) of this introduction.

c) Recommendations and limitations regarding the application of this standard

It is important to note that this document establishes no additional functional requirements for safety systems.

d) Description of the structure of the IEC SC 45A standard series and relationships with other IEC documents and other bodies documents (IAEA, ISO)

~~The top-level document of the IEC SC 45A standard series is IEC 61513. It provides general requirements for I&C systems and equipment that are used to perform functions important to safety in NPPs. IEC 61513 structures the IEC SC 45A standard series.~~

~~IEC 61513 refers directly to other IEC SC 45A standards for general topics related to categorization of functions and classification of systems, qualification, separation of systems, defence against common cause failure, software aspects of computer-based systems, hardware aspects of computer-based systems, and control room design. The standards referenced directly at this second level should be considered together with IEC 61513 as a consistent document set.~~

The IEC SC 45A standard series comprises a hierarchy of four levels. The top-level documents of the IEC SC 45A standard series are IEC 61513 and IEC 63046.

IEC 61513 provides general requirements for instrumentation and control (I&C) systems and equipment that are used to perform functions important to safety in nuclear power plants (NPPs). IEC 63046 provides general requirements for electrical power systems of NPPs; it covers power supply systems including the supply systems of the I&C systems.

IEC 61513 and IEC 63046 are to be considered in conjunction and at the same level. IEC 61513 and IEC 63046 structure the IEC SC 45A standard series and shape a complete framework establishing general requirements for instrumentation, control and electrical power systems for nuclear power plants.

IEC 61513 and IEC 63046 refer directly to other IEC SC 45A standards for general requirements for specific topics, such as categorization of functions and classification of systems, qualification, separation, defence against common cause failure, control room design, electromagnetic compatibility, human factors engineering, cybersecurity, software and hardware aspects for programmable digital systems, coordination of safety and security requirements and management of ageing. The standards referenced directly at this second level should be considered together with IEC 61513 and IEC 63046 as a consistent document set.

At a third level, IEC SC 45A standards not directly referenced by IEC 61513 or by IEC 63046 are standards related to specific requirements for specific equipment, technical methods, or **specific** activities. Usually these documents, which make reference to second-level documents for general **topics** requirements, can be used on their own.

A fourth level extending the IEC SC 45 standard series, corresponds to the Technical Reports which are not normative.

The IEC SC 45A standards series consistently implements and details the safety and security principles and basic aspects provided in the relevant IAEA safety standards and in the relevant documents of the IAEA nuclear security series (NSS). In particular this includes the IAEA requirements SSR-2/1, establishing safety requirements related to the design of nuclear power plants (NPPs), the IAEA safety guide SSG-30 dealing with the safety classification of structures, systems and components in NPPs, the IAEA safety guide SSG-39 dealing with the design of instrumentation and control systems for NPPs, the IAEA safety guide SSG-34 dealing with the design of electrical power systems for NPPs, the IAEA safety guide SSG-51 dealing with human factors engineering in the design of NPPs and the implementing guide NSS42-G for computer security at nuclear facilities. The safety and security terminology and definitions used by the SC 45A standards are consistent with those used by the IAEA.

IEC 61513 and IEC 63046 have adopted a presentation format similar to the basic safety publication IEC 61508 with an overall **safety** life-cycle framework and a system life-cycle framework. Regarding nuclear safety, IEC 61513 and IEC 63046 provide the interpretation of the general requirements of IEC 61508-1, IEC 61508-2 and IEC 61508-4, for the nuclear

application sector, ~~regarding nuclear safety~~. In this framework, IEC 60880, IEC 62138 and IEC 62566 correspond to IEC 61508-3 for the nuclear application sector. ~~IEC 61513 refers to ISO as well as to IAEA GS-R-3 and IAEA GS-G-3.1 for topics related to quality assurance (QA).~~

~~The IEC SC 45A standards series consistently implements and details the principles and basic safety aspects provided in the IAEA code on the safety of NPPs and in the IAEA safety series, in particular the Requirements NS-R-1, establishing safety requirements related to the design of Nuclear Power Plants, and the Safety Guide NS-G-1.3 dealing with instrumentation and control systems important to safety in Nuclear Power Plants. The terminology and definitions used by SC 45A standards are consistent with those used by the IAEA.~~

IEC 61513 and IEC 63046 refer to ISO 9001 as well as to IAEA GSR part 2 and IAEA GS-G-3.1 and IAEA GS-G-3.5 for topics related to quality assurance (QA).

At level 2, regarding nuclear security, IEC 62645 is the entry document for the IEC/SC 45A security standards. It builds upon the valid high level principles and main concepts of the generic security standards, in particular ISO/IEC 27001 and ISO/IEC 27002; it adapts them and completes them to fit the nuclear context and coordinates with the IEC 62443 series. At level 2, IEC 60964 is the entry document for the IEC/SC 45A control rooms standards, IEC 63351 is the entry document for the human factors engineering standards and IEC 62342 is the entry document for the ageing management standards.

NOTE 1 It is assumed that for the design of I&C systems in NPPs that implement conventional safety functions (e.g. to address worker safety, asset protection, chemical hazards, process energy hazards) international or national standards would be applied, ~~that are based on the requirements of a standard such as IEC 61508.~~

NOTE 2 IEC TR 64000 provides a more comprehensive description of the overall structure of the IEC SC 45A standards series and of its relationship with other standards bodies and standards.

Document Preview

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>

NUCLEAR POWER PLANTS – INSTRUMENTATION AND CONTROL IMPORTANT TO SAFETY – ELECTRICAL EQUIPMENT CONDITION MONITORING METHODS –

Part 3: Elongation at break

1 ~~Scope and object~~

This part of IEC/IEEE 62582 contains methods for condition monitoring of organic and polymeric materials in instrumentation and control systems using tensile elongation techniques in the detail necessary to produce accurate and reproducible measurements. This document includes the requirements for selection of samples, the measurement system and conditions, and the reporting of the measurement results.

The different parts of IEC/IEEE 62582 are measurement standards, primarily for use in the management of ageing in initial qualification and after installation. IEC/IEEE 62582-1 includes requirements for the application of the other parts of IEC/IEEE 62582 and some elements which are common to all methods. Information on the role of condition monitoring in qualification of equipment important to safety is found in ~~IEEE Std 323~~ IEC/IEEE 60780-323.

This document is ~~intended for application~~ applicable to non-energised equipment.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

[IEC/IEEE 62582-3:2024](https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024)

<https://standards.iteh.ai/catalog/standards/iec/6165e438-868e-4728-8a5b-82bb0b976b7f/iec-ieee-62582-3-2024>

For the purposes of this document, the following terms and definitions apply.

ISO, IEC and IEEE maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEEE Standards Dictionary Online: available at <http://dictionary.ieee.org>

3.1 elongation

E

tensile strain, expressed as a percentage of the test length, produced in the piece by a tensile stress

[SOURCE: ISO 37:~~2011~~2017, 3.2]

3.2 elongation at break

E_b

tensile strain in the test length at the breaking point

[SOURCE: ISO 37:~~2011~~2017, 3.5]

3.3

nominal elongation at break

tensile strain, expressed as a percentage of the specimen length between the grips, produced in the specimen at the breaking point

3.4

gauge length

L_0

initial distance between the gauge marks on the central part of the test specimen. It is expressed in millimetres (mm)

Note 1 to entry: See figures of the test specimens in the relevant part of ISO 527.

[SOURCE: ISO 527-1:20122019, 3.1]

3.5

test speed of testing

rate of separation of the ~~grips of the testing machine during the test~~ gripping jaws

Note 1 to entry: It is expressed in millimetres per minute (mm/min).

[SOURCE: ISO 527-1:20122019, 3.5]

4 General description

This document provides requirements for the condition monitoring of organic and polymeric materials using tensile elongation techniques whereby a test specimen is extended along its longitudinal axis at constant speed until the specimen ~~fractures~~ breaks. During the test, the load sustained on the specimen and its elongation are measured. For this standard, elongation at break is the measured parameter.

NOTE Elongation at break rather than tensile strength is used because for some ~~polymers~~ polymeric materials, particularly thermoplastics, the strength ~~may~~ can remain consistently equal to the yield strength after ageing even when the elongation has decreased to < 50 % absolute.

5 Applicability and reproducibility

The tensile elongation method described in this document is related to the long chain molecular structure of the polymer. As degradation proceeds, changes in the molecular structure occur as a result of cross-linking, chain scission, oxidation and other degradation mechanisms. These changes usually decrease the elongation at break.

The tensile elongation method described in this document is primarily suited to samples taken from equipment that are based on ~~thermoplastic or elastomeric polymers~~ polymeric materials. The method is generally not suitable for fibre reinforced ~~polymers~~ polymeric materials or resins such as epoxides.

The tensile elongation method described in this document cannot be used in the field in the nuclear power plant but uses samples taken from the plant, which are then measured in the laboratory. Each tensile elongation measurement in the laboratory can take between 5 min and 10 min to complete.

NOTE Round robin tests using a method close to the current standard have shown a typical laboratory variation in results of measurements of elongation at break on identical specimens of 8 % to 10 %.

The mechanical properties of some polymeric materials ~~may~~ can be affected by the moisture content. Most organic and polymeric materials currently used in the containment are not significantly hygroscopic. However, if hygroscopic materials are used, the influence of the moisture content of the material on elongation at break ~~may~~ should need to be considered, particularly after artificial thermal ageing as a consequence of long-term exposure to high temperature in an oven.

Degradation of some polymeric materials in radiation environments cannot be correlated to elongation at break.

6 Measurement procedure

6.1 Stabilisation of the polymeric materials

An appropriate time period shall be allowed for the polymeric materials in recently manufactured equipment to stabilise before any condition monitoring or accelerated ageing programmes are carried out. The time period over which the polymeric materials stabilise is normally dependent on the processing additives and polymer composition. If manufacturers' stabilisation time data are not available, a period of 6 months should be allowed before commencing ageing to allow initial values from unaged samples to become stable.

6.2 Sampling

6.2.1 General

Measurements of tensile elongation provide information on the status of the equipment only at the specific location which has been sampled. Knowledge of the environmental conditions in representative areas during plant operation is a prerequisite for selecting sample locations for condition monitoring. It is important that these locations represent as wide a range of ageing conditions as possible with special consideration given to locations where ageing conditions could be severe, e.g. hotspots. The location of the sampling and available information about the environmental time history at the sample location selected shall be documented.

Sampling procedures shall comply with local instructions, taking into account safety of personnel and equipment. Handling of equipment during removal of samples from the plant should be minimised, e.g. cables should not be bent more than is necessary to remove the sample.

Measurements of elongation at break are formulation dependent and ~~may~~ can be sensitive to manufacturing variations, such as porosity. Any changes in formulation ~~need to~~ shall be evaluated.

6.2.2 Sample requirements

When preparing samples from whole cables that have been aged in the laboratory or in a deposit, samples shall be taken from sections of the cable at least 100 mm from the ends, unless such ends have been sealed during ageing.

In order to obtain reasonable confidence, a minimum of 5 test specimens is required for elongation measurements to be made on one specific sample. However, it is recognised that in some cases, e.g. in samples taken from hot-spots, there ~~may~~ can be insufficient material available for this minimum to be satisfied.

The specimens ~~may~~ can be prepared from equipment taken from the sampling location or, alternatively, be prepared in advance and placed in the sample locations.

Care shall be taken to avoid unsuitable conditions in storage during the time period between sampling and measurements. It is recommended that samples be stored in the dark at temperatures not exceeding 25 °C and at humidity conditions within 45 % and 75 %.