



Designation: C1520 – 20

Standard Guide for Paintability of Latex Sealants¹

This standard is issued under the fixed designation C1520; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide describes the practical considerations that may be used to determine the compatibility of a paint or coating to be applied over a latex sealant or caulk. It evaluates the appearance and not the performance characteristics of the coated or painted joint.

1.2 The committee with jurisdiction over this standard is not aware of any comparable standards published by other organizations.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C717 Terminology of Building Seals and Sealants

D1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials

D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

E284 Terminology of Appearance

¹ This guide is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.10 on Specifications, Guides and Practices.

Current edition approved May 1, 2020. Published June 2020. Originally approved in 2002. Last previous edition approved in 2015 as C1520-02(2015) ^{ϵ 1}. DOI: 10.1520/C1520-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions*—Refer to Terminology C717 for definitions of the following term(s) used in this guide: compatibility, cure, joint, latex sealant. Refer to Terminology E284 for definitions of the following term(s) used in this guide: gloss.

3.2 *color change*—a change in either the observed (see Practice D1729) or measured color (see Practice D2244) of a substance.

3.3 *cracking*—a failure resulting in a discontinuous film (of paint) or bead (of sealant).

4. Summary of Practice

4.1 This guide reviews many of the issues concerning the compatibility of latex sealants with paint. While the focus of this guide is on latex sealants, the paint or coating may be of any composition.

5. Significance and Use

5.1 The intent of this guide is to provide the reader with information concerning possible reasons for paint failures where the paint is used over a latex sealant.

CONSIDERATIONS

6. Temperature

6.1 Since standard testing is usually performed at “room temperature,” about 23°C, this would be considered the ideal temperature for application and curing. As the temperature deviates from this ideal, the “science” of drying changes in that lower temperature results in slower drying and higher temperature results in faster drying.

7. Percent Relative Humidity

7.1 In waterborne sealants, the humidity directly affects the retained water in the material. Standard testing is typically performed at 50 % RH, which allows for an acceptable water evaporation rate. Temperature and humidity variations in climatic regions, and fluctuations occurring during the application and cure, will affect the cure and sealant performance.

8. Type of Paint

8.1 The type of paint applied to the sealant has an effect on how well the paint may accommodate dimensional changes,

adhere to the sealant, or dry during the curing of the sealant. Paints made from more flexible resins (low T_g) with low pigment volume content (PVC) ($PVC \ll CPVC$) will withstand the most dimensional change, while paints made with a hard resin (high T_g) with a high PVC will be less tolerant of dimensional changes. Broadly speaking, high gloss, interior paints represent the former, while interior flat paints represent the latter.

9. Type of Sealant

9.1 The sealant will have an effect on the adhesion of the paint film, the degree of change in geometry of the paint film, and changes in paint color and gloss; however, these changes are difficult to quantify by the type and quality of the sealant.

10. Cure Time

10.1 The degree of sealant cure may affect when the paint can be applied, the compatibility of the applied paint with the sealant, and the dry time of the applied paint. An uncured sealant may react with the paint ingredients. Cracking of the paint film may occur when the paint is applied before curing of the sealant bead is complete due to subsequent shrinkage of the underlying sealant. Additionally, migration of sealant components to the sealant bead surface may affect the paint adhesion.

11. Sealant Geometry/Tooling

11.1 Use of a sealant backing material may decrease sealant cracking and thereby decrease paint failure.

12. Method of Paint Application

12.1 The manner in which the paint is applied, (roller, brush or sprayer) may affect the thickness of the paint application. Some rollers and brushes, especially low-cost applicators, may lose bristles or leave brush strokes or surface irregularities in the paint film, which may promote premature failures.

13. Substrate Effects

13.1 The porosity, composition and cleanliness of the substrate affect the cure of both sealant and paint. A more porous

substrate will wick water or solvent and shorten the paint curing period. A substrate to which is difficult to adhere, or a substrate that consists of material containing low molecular weight oils, plasticizers, etc., will affect film formation and wetting, and may induce gloss and color change.

14. Type of Construction

14.1 The structure's design and type of construction may affect the substrates and quantity of movement to which the sealant and paint may be subjected.

15. Lot to Lot Variation

15.1 Several factors contribute to both sealant and paint lot variations. When a change of material lots occurs, it may be prudent to test the sealant/paint compatibility.

OBSERVATIONS

16. Cracking

16.1 This may be simple cracking of the paint film or may manifest itself as a crack in the sealant. The degree and amount of cracking between the sealant and the paint will affect the acceptability of this condition. Severe cracking of the sealant may exceed the crack bridging ability of the paint film.

17. Color Change

17.1 This may be caused by the migration of material from either the sealant or substrate into the paint, thereby changing the appearance of the paint. Color change may result from the paint being more susceptible to dirt pick-up, especially in areas where airborne dirt is prevalent.

18. Gloss

18.1 Plasticizer migration may cause the paint to develop a higher gloss over time.

19. Keywords

19.1 cracking; latex sealant; paint

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/