



Designation: **D5457—19c D5457 – 20**

Standard Specification for Computing Reference Resistance of Wood-Based Materials and Structural Connections for Load and Resistance Factor Design¹

This standard is issued under the fixed designation D5457; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

INTRODUCTION

Load and resistance factor design (LRFD) is a structural design method that uses concepts from reliability theory and incorporates them into a procedure usable by the design community. The basic design equation requires establishing a reference resistance based on several material property parameters. A standard method for calculating the required material property input data is critical so that all wood-based structural materials can be treated equitably. This specification provides the procedures that are required for the generation of reference resistance for LRFD.

1. Scope

1.1 This specification covers procedures for computing the reference resistance of wood-based materials and structural connections for use in load and resistance factor design (LRFD). The format conversion procedure is outlined in Section 4. The test-based derivation procedure is outlined in **Annex A1**. The reference resistance derived from this specification applies to the design of structures addressed by the load combinations in ASCE 7-16.

1.2 A commentary to this specification is provided in **Appendix X1**.

1.3 *Units*—The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D9 Terminology Relating to Wood and Wood-Based Products

D143 Test Methods for Small Clear Specimens of Timber

D198 Test Methods of Static Tests of Lumber in Structural Sizes

D1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials

D1761 Test Methods for Mechanical Fasteners in Wood

D1990 Practice for Establishing Allowable Properties for Visually-Graded Dimension Lumber from In-Grade Tests of Full-Size Specimens

D2718 Test Methods for Structural Panels in Planar Shear (Rolling Shear)

D2719 Test Methods for Wood Structural Panels in Shear Through-the-Thickness

D2915 Practice for Sampling and Data-Analysis for Structural Wood and Wood-Based Products

D3043 Test Methods for Structural Panels in Flexure

¹ This specification is under the jurisdiction of ASTM Committee **D07** on Wood and is the direct responsibility of Subcommittee **D07.02** on Lumber and Engineered Wood Products.

Current edition approved July 1, 2019/April 1, 2020. Published August 2019/June 2020. Originally approved in 1993. Last previous edition approved in 2019 as **D5457—19/D5457 – 19c**. DOI: [10.1520/D5457-19C](https://doi.org/10.1520/D5457-19C); [10.1520/D5457-20](https://doi.org/10.1520/D5457-20).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D3500 Test Methods for Structural Panels in Tension](#)
[D3501 Test Methods for Wood-Based Structural Panels in Compression](#)
[D3737 Practice for Establishing Allowable Properties for Structural Glued Laminated Timber \(Glulam\)](#)
[D4761 Test Methods for Mechanical Properties of Lumber and Wood-Based Structural Materials](#)
[D5055 Specification for Establishing and Monitoring Structural Capacities of Prefabricated Wood I-Joists](#)
[D5456 Specification for Evaluation of Structural Composite Lumber Products](#)
[E105 Practice for Probability Sampling of Materials](#)
 2.2 *ASCE Standard*.³
[ASCE 7-16 Minimum Design Loads and Associated Criteria for Buildings and Other Structures](#)

3. Terminology

3.1 Definitions:

3.1.1 For general definitions of terms related to wood, refer to Terminology [D9](#).

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *ASD reference design value, F_x* —the design value at reference conditions used in allowable stress design (ASD) prior to application of the load duration factor (C_D).

3.2.2 *coefficient of variation, CV_w* —the standard deviation divided by the mean of a 2-parameter Weibull distribution.

3.2.2.1 Discussion—

Coefficient of variation, CV_w , can be calculated three ways: the traditional method of moments; method of maximum likelihood; and method of least squares. The method of moments calculates the mean and standard deviation directly from the data of a complete data set. The methods of maximum likelihood and least squares calculate the Weibull parameters from complete or incomplete data sets. An incomplete data set includes suspended data (for example, data from proof loading.) Mean and standard deviation (and CV_w) are then calculated from the Weibull parameters.

3.2.3 *data confidence factor, Ω* —a factor that is used to adjust member reference resistance for sample variability and sample size.

3.2.4 *distribution percentile, R_p* —the value of the distribution associated with proportion, p , of the cumulative distribution function.

3.2.5 *factored resistance*—the product of the resistance factor (ϕ) and the reference or nominal resistance (R_n).

3.2.6 *format conversion factor, K_F* —a factor applied to convert resistance from the allowable stress design (ASD) format to the LRFD format, equal to the ratio R_n / F_x .

3.2.7 *lower tail*—a portion of an ordered data set consisting of all test specimens with the lowest property values (for example, lowest strengths).

3.2.8 *nominal resistance*—a term equivalent to the reference resistance used in reliability analysis and LRFD standards.

3.2.9 *reference conditions*—the design basis for which all applicable adjustment factors are equal to unity, except for the load duration factor in ASD or the time effect factor in LRFD.

3.2.10 *reference resistance, R_n* —the design value at reference conditions used in LRFD to represent member resistance prior to application of the resistance factor (ϕ) and the time effect factor (λ).

3.2.10.1 Discussion—

The reference value represents member resistance at 10-minute load duration.

3.2.11 *reliability normalization factor, K_R* —a factor used to establish the reference resistance (R_n) to achieve a target reliability index for a specific set of conditions.

3.2.12 *resistance factor, ϕ* —a factor applied to the resistance side of the LRFD equation.

4. Reference Resistance for LRFD

4.1 Reference resistance for LRFD shall be determined using one of the following procedures:

4.1.1 Format conversion per Section [4.2](#); or

4.1.2 Test-based derivation per [Annex A1](#).

4.2 Format Conversion Procedure:

³ Available from The American Society of Civil Engineers (ASCE), 1801 Alexander Bell Dr., Reston, VA 20191.

4.2.1 Resistance values for LRFD are permitted to be based on format conversion from code-recognized allowable stress design (ASD). It shall not be claimed that reference resistance values generated in this manner achieve a stated reliability index. Resistance factors for determining LRFD factored resistance, ϕR_n , are given in **Table 1**.

NOTE 1—Examples of standards that are used to generate code-recognized ASD values include Test Methods **D143**, **D198**, **D1037**, **D1761**, **D2718**, **D2719**, **D3043**, **D3500**, **D3501**, and **D4761**; Practices **D1990** and **D3737**; and Specifications **D5055** and **D5456**.

4.2.2 For standardization purposes, format conversion reference resistance values shall be based on the arithmetic conversion for a specific design case that results from the calibration of basic ASD and LRFD equations. Here, the calibration means providing an identical required section modulus, cross-sectional area, allowable load capacity, and so forth. The specific design case was chosen such that changes in design capacity over the range of expected load cases and load ratios were minimized.

4.2.3 Values of the format conversion factor, K_F , are given in **Table 2**.

4.2.4 The format conversion reference resistance is computed by multiplying the ASD resistance by K_F . For members and connections, the ASD resistance is based on a normal (10-year) load duration. For shear walls and diaphragms, the ASD resistance is based on a 10-minute load duration.

4.2.5 For lateral buckling (stability), compression perpendicular to grain, and rolling shear that is not subject to load duration or time effect adjustments, the value of K_F is based on the assumption that neither the ASD nor LRFD resistance values are modified by duration of load or time effect adjustments.

4.2.6 *Format Conversion Example*—An ASD bolt design value for a single shear connection, F_x , is 800 lbf (3.56 kN) (based on normal 10-year load duration). From **Table 2**, the format conversion factor, K_F , is 3.32. The corresponding LRFD bolt reference resistance value is as follows:

$$R_n = (K_F) \times F_x = (3.32) \times 800 = 2658 \text{ lbf (11.82 kN)} \quad (1)$$

$$R_n = (K_F)(F_x) = (3.32)(800) = 2658 \text{ lbf (11.82 kN)} \quad (1)$$

4.2.7 *Format Conversion Example for Shear Walls and Diaphragms*—An ASD shear wall design value, value for seismic design, F_x , is 395 lb/ft (5.76 kN/m) (based on a 10-minute load duration). From **Table 2**, the format conversion factor, K_F , is 2.8. The corresponding LRFD shear wall reference resistance value is as follows:

$$R_n = (K_F) \times F_x = 2.8 \times 395 = 1106 \text{ lb/ft (16.14 kN/m)} \quad (2)$$

$$R_n = (K_F)(F_x) = (2.8)(395) = 1106 \text{ lb/ft (16.14 kN/m)} \quad (2)$$

Similarly, if this shear wall was being designed to resist wind loads, $K_F = 2.0$ (from **Table 2** for wind), $F_x = 553$ lb/ft (8.06 kN/m), and $R_n = 1106$ lb/ft (16.14 kN/m).

5. Keywords

5.1 format conversion; load and resistance factor design (LRFD); reference resistance; structural connections; test-based derivation; wood-based materials

TABLE 1 Specified LRFD Resistance Factors, ϕ_s

Application	Property	ϕ_s
Members	compression ^A	0.90
	bending, lateral buckling (stability)	0.85
	tension parallel	0.80
	shear, radial tension	0.75
	all	0.65
Connections	all	0.65
	Shear Walls, diaphragms	
	shear (wind)	0.80
	shear (seismic)	0.50

^A Compression parallel-to-grain, compression perpendicular-to-grain, and bearing.

TABLE 2 Format Conversion Factor, K_F

Property	K_F
Compression Parallel to Grain	2.40
Bending	2.54
Tension Parallel to Grain	2.70
Shear	2.88 ^A
Radial Tension	2.88
Connections	3.32
Lateral Buckling (Stability)	1.76
Compression Perpendicular to Grain	1.67
Shear Wall and Diaphragm Shear (wind)	2.00 ^B
Shear Wall and Diaphragm Shear (seismic)	2.80 ^B

^A The value of the format conversion factor is 2.00 where shear is not subject to load duration or time effect adjustments (e.g., rolling shear in cross-laminated timber).

^B The format conversion factor for shear wall and diaphragm shear is only intended to be applied to the design capacity of shear wall or diaphragm assemblies, not to the design of individual members or subcomponents of these assemblies.

ANNEX

(Mandatory Information)

A1. TEST-BASED DERIVATION OF REFERENCE RESISTANCE FOR LRFD

A1.1 Parameters required for the derivation of reference resistance are presented in this Annex. These parameters include the distribution percentile, R_p , coefficient of variation, CV_w , data confidence factor, Ω , and reliability normalization factor, K_R . An example derivation of reference resistance is provided in **X1.8.5**.

A1.2 Sampling:

A1.2.1 Samples selected for analysis and implementation with this specification shall be representative of the population about which inferences are to be made. Both manufacturing and material source variability shall be considered. The principles of Practice **E105** shall be maintained. Practice **D2915** provides methods for establishing a sampling plan. Special attention is directed to sampling procedures in which the variability is low and results can be influenced significantly by manufacturing variables. It is essential that the sampling plan addresses the relative magnitude of the sources of variability.

A1.2.1.1 Data generated from a quality control program shall be acceptable if the criteria of **A1.2.1** are maintained.

A1.2.1.2 *Multiple Data Sets*—When data from multiple data sets are compiled or grouped, the criteria used to group such data shall be in accordance with the provisions of **A1.2.1**. When such procedures are available in applicable product standards, they shall be used.

A1.2.2 Sample Size:

A1.2.2.1 For data sets in which all specimens are tested to failure, the minimum sample size shall be 30.

NOTE A1.1—The confidence with which population properties can be estimated decreases with decreasing sample size. For sample sizes less than 60, extreme care must be taken during sampling to ensure a representative sample.

A1.2.2.2 For lower tail data sets, a minimum of 60 failed observations is required for sample sizes of $n = 600$ or less. This represents at least the lower 10 % of the distribution. For sample sizes greater than 600, a minimum of the lowest 10 % of the distribution is required. For example, sample size, $n = 720$, $0.10 (720) = 72$ failed test specimens in the lower tail. Only parameter estimation procedures designed specifically for lower tail data sets shall be used (see **Appendix X2**).

A1.3 Testing:

TABLE A1.1 Data Confidence Factor, Ω on $R_{0.05}$, for Two-Parameter Weibull Distribution with 75 % Confidence^A

CV_w	Sample Size, n									
	30	40	50	60	100	200	500	1000	2000	5000
0.10	0.95	0.95	0.96	0.96	0.97	0.98	0.99	0.99	0.99	1.0
0.15	0.92	0.93	0.94	0.95	0.96	0.97	0.98	0.99	0.99	0.99
0.20	0.89	0.91	0.92	0.93	0.94	0.96	0.98	0.98	0.99	0.99
0.25	0.87	0.88	0.90	0.91	0.93	0.95	0.97	0.98	0.98	0.99
0.30	0.84	0.86	0.88	0.89	0.92	0.94	0.96	0.97	0.98	0.99
0.35	0.81	0.84	0.86	0.87	0.90	0.93	0.96	0.97	0.98	0.99
0.40	0.79	0.81	0.84	0.85	0.89	0.92	0.95	0.96	0.97	0.98
0.45	0.76	0.79	0.82	0.85	0.87	0.91	0.94	0.96	0.97	0.98
0.50	0.73	0.77	0.80	0.81	0.86	0.90	0.94	0.95	0.97	0.98

^A Interpolation is permitted. For CV_w values below 0.10, the values for 0.10 shall be used.

A1.3.1 Testing shall be conducted in accordance with appropriate standard testing procedures. The intent of the testing shall be to develop data that represent the capacity of the product under standard conditions.

A1.3.2 *Periodic Property Assessment*—Periodic testing is recommended to verify that the properties of production material remain representative of published properties.

A1.4 *Reference Resistance, R_n* —The following equation establishes reference resistance for LRFD:

$$R_n = (R_p) \times \Omega \times K_R \quad (A1.1)$$

$$R_n = (R_p)(\Omega)(K_R) \quad (A1.1)$$

where:

- R_p = distribution percentile estimate,
- Ω = data confidence factor, and
- K_R = reliability normalization factor.

A1.4.1 *Distribution Percentile Estimate, R_p* :

A1.4.2 **Eq A1.2** is intended to be used to calculate any percentile of a two-parameter Weibull distribution. The percentile of interest depends on the property being estimated.

$$R_p = \eta[-\ln(1 - p)]^{1/\alpha} \quad (A1.2)$$

where:

- η = Weibull scale parameter,
- p = percentile of interest expressed as a decimal (for example, 0.05), and
- α = Weibull shape parameter.

A1.4.3 The shape (α) and scale (η) parameters of the two-parameter Weibull distribution shall be established to define the distribution of the material resistance (**1**).⁴ Algorithms for common estimation procedures are provided in **Appendix X2**.

A1.4.4 *Coefficient of Variation, CV_w* —The coefficient of variation of the material is necessary when determining the data confidence factor, Ω , and the reliability normalization factor, K_R . The CV_w can be estimated from the shape parameter of the Weibull distribution as follows:

$$CV_w \cong \alpha^{-0.92} \quad (A1.3)$$

NOTE A1.2—The above approximation is within 1 % of the exact solution for CV_w values between 0.09 and 0.50. An exact relationship of CV_w and α is shown in **Appendix X3**.

⁴ The boldface numbers in parentheses refer to a list of references at the end of this standard.

TABLE A1.2 Fifth-Percentile-Based Reliability Normalization Factors, K_R ^A

$CV_w, \%$	K_R					
	Compression and Bearing	Bending	Tension Parallel	Shear (2.1 basis)	Shear (SCL, 3.15 basis)	Shear (I-Joist, 2.37 basis)
10	1.30	1.25	1.35	1.40	0.95	1.25
15	1.30	1.25	1.30	1.40	0.95	1.25
20	1.20	1.15	1.25	1.30	0.90	1.15
25	1.15	1.10	1.15	1.25	0.80	1.10
30	1.05	1.00	1.05	1.15	0.75	1.00

^AInterpolation is permitted. For CV_w values below 0.10, the values for 0.10 shall be used.

A1.5 Data Confidence Factor, Ω —The data confidence factor accounts for uncertainty associated with data sets (2). This factor, which is a function of coefficient of variation, sample size, and specified percentile, is applied as a multiplier on the distribution estimate. Table A1.1 provides data confidence factors appropriate for lower fifth-percentile estimates.

NOTE A1.3—When a distribution tolerance limit is developed on a basis consistent with Ω , the data confidence factor is taken as unity.

A1.6 Reliability Normalization Factor, K_R —The reliability normalization factor, K_R , which is a function of CV_w and is generated for specific target reliability indices, is used to adjust the distribution estimate (for example, $R_{0.05}$) to achieve a target reliability index. The reliability normalization factor is the ratio of the computed resistance factor, ϕ_c (X1.8.5), to the specified resistance factor, ϕ_s (Table 1), adjusted by a scaling factor, which is a function of CV_w and is generated for specific target reliability indices. The K_R values presented in Table A1.2 were computed at a live-to-dead load ratio of 3. Computations (FORTRAN code listings reflecting 1980's methodologies) for determining reliability indices are contained in Refs (3) and (4). Calculations to derive input parameters for reliability analyses are outlined in Ref (5).

A1.7 Presentation of Results:

A1.7.1 Report the sampling plan and testing in accordance with applicable standards. When lower tail data sets are used, report the sample size and data used in the calculations. Report the estimated shape and scale parameters along with the calculated coefficient of variation. When appropriate, also report the mean and standard deviation (derived from the calculated coefficient of variation). Include a plot showing the data points and fitted Weibull distribution. In addition to these basic parameters, also report the data confidence factor, Ω , calculated percentile estimate, R_p , reliability normalization factor, K_R , and reference resistance, R_n .

APPENDIXES

(Nonmandatory Information)

X1. COMMENTARY TO THE TEXT

X1.1 Commentary to the Introduction:

X1.1.1 Load and resistance factor design (LRFD) is a design format. LRFD is a subset of a broader design methodology known as reliability-based design (RBD). The distinction between the two design procedures is significant. RBD implies, and often calculates, quantities related to the reliability of a member under a given set of conditions. A higher reliability corresponds to a lower probability of failure. One practical concern that arises when one attempts to apply RBD to real structural applications is that the calculations must idealize both the loads and the structural system response to reduce it to a mathematically tractable problem. This idealization process reduces the final calculation to a theoretically interesting, but often inapplicable, number. LRFD was developed by selecting a few of the basic concepts of RBD and using them to develop a format that is similar in many ways to current (allowable stress) design. LRFD provides incremental improvements in the design process in this way. The improvements provided by LRFD include the following:

X1.1.1.1 Consideration of the variability of various types of loads when assessing safety factors.

X1.1.1.2 Consideration of the consequences of various potential failure modes in a structure.