



Designation: C650 – 20

Standard Test Method for Determination of Resistance to Chemical Substances¹

This standard is issued under the fixed designation C650; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a procedure for determining whether, and to what degree, ceramic tiles and glass tiles are affected by prolonged exposure to chemical substances that are commonly used in the household or for cleaning purposes as well as other more severe conditions.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 The units used for concentration in this standard are v/v, which refers to the volume of reagent/1 L of solution, and g/L, which refers to the weight of reagent, in g, to be dissolved in 1 L of water.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Summary of Test Method

2.1 This test method calls for one or more tests, each consisting of exposing flat pieces of tile to the action of a specific chemical substance for a definite period of time. After exposure, the surfaces of the tile are rinsed with water and inspected for effect.

3. Significance and Use

3.1 This test method is intended for testing tiles that are to be used for food counters, lavatories, and similar residential, medical, and commercial installations, where they may come

in contact with food, chemical, and waste substances and for tile in areas where they may be exposed to contact with strong cleaning agents.

4. Apparatus

4.1 *Glass Test Tubes or PVC Tubes*, plain-end flint glass test tubes or PVC tubes with a diameter of approximately 20 mm and a length sufficient to contain the required amount of test solution.

4.2 *Oven*, capable of maintaining a constant temperature of at least 110 °C.

4.3 *Pencil*, HB hardness grade.

4.4 *Cloths*, a supply of lintless, absorbent cloths or paper towels.

4.5 *Distilled or Deionized Water*, for preparation of the solutions.

4.6 *Light Source*, standard, that supplies a minimum of 300 lux illumination.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.² Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 The required dilutions for the preparation of each test solution is found in **Table 1** of this test method.

5.2.1 *Common Household and Cleaning Chemicals*:

5.2.1.1 Acetic acid, 3 % (v/v).

5.2.1.2 Acetic acid, 10 % (v/v).

5.2.1.3 Ammonium chloride, 100 g/L.

5.2.1.4 Citric acid solution, 30 g/L.

¹ This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved June 1, 2020. Published June 2020. Originally approved in 1970. Last previous edition approved in 2019 as C650 – 04 (2019). DOI: 10.1520/C0650-20.

² *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeial and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

TABLE 1 Preparation of Test Solutions

NOTE 1—When mixing solutions using solid reagents, the reagent should be dissolved in a small amount of water first, and then water should be added to the solution such that the final volume of the solution is 1000 mL. For example, when mixing the citric acid solution, 30 g/L, dissolve 30.2 g of 99.5 % citric acid in 250 mL of water. After the reagent is dissolved, continue adding water until the solution has a final volume of 1000 mL.

Test Solution	Reagent Source	Amount of Reagent Required for Test Solution (See Note 1)	Distilled Water Required for Test Solution
<u>Common Household and Cleaning Chemicals</u>			
acetic acid, 3 % (v/v)	99.7 % glacial acetic acid	30.1 mL	969.9 mL
acetic acid, 10 % (v/v)	99.7 % glacial acetic acid	100.3 mL	899.7 mL
ammonium chloride, 100 g/L	99.5 % ammonium chloride	100.5 g	1000 mL
citric acid solution, 30 g/L	99.5 % citric acid	30.2 g	1000 mL
citric acid solution, 100 g/L	99.5 % citric acid	100.5 g	1000 mL
lactic acid, 5 % (v/v)	85 % lactic acid	58.8 mL	941.2 mL
phosphoric acid, 3 % (v/v)	85 % phosphoric acid	35.3 mL	964.7 mL
phosphoric acid, 10 % (v/v)	85 % phosphoric acid	117.6 mL	882.4 mL
sulfamic acid, 30 g/L	99 % sulfamic acid	30.3 g	1000 mL
sulfamic acid, 100 g/L	99 % sulfamic acid	101 g	1000 mL
<u>Swimming Pool Chemicals</u>			
sodium hypochlorite solution, 20 mg/L	technical grade sodium hypochlorite with 13 % active chlorine	0.15 mL	999.85 mL
<u>Acids and Bases</u>			
hydrochloric acid solution, 3 % (v/v)	38 % hydrochloric acid	78.9 mL	921.1 mL
hydrochloric acid solution, 18 % (v/v)	38 % hydrochloric acid	473.7 mL	526.3 mL
potassium hydroxide, 30 g/L	90 % potassium hydroxide	33.33 g	1000 mL
potassium hydroxide, 100 g/L	90 % potassium hydroxide	111.1 g	1000 mL

5.2.1.5 Citric acid solution, 100 g/L.

5.2.1.6 Lactic acid, 5 % (v/v).

5.2.1.7 Phosphoric acid, 3 % (v/v).

5.2.1.8 Phosphoric acid, 10 % (v/v).

5.2.1.9 Sulfamic acid, 30 g/L.

5.2.1.10 Sulfamic acid, 100 g/L.

5.3 *Swimming Pool Chemicals*—Sodium hypochlorite solution, 20 mg/L, prepared from technical grade sodium hypochlorite with about 13 % of active chloride.

5.4 *Acids and Bases*:

5.4.1 Hydrochloric acid solution, 3 % (v/v).

5.4.2 Hydrochloric acid solution, 18 % (v/v).

5.4.3 Potassium hydroxide, 100 g/L.

5.4.4 Potassium hydroxide, 30 g/L.

5.5 This test method may be used for exposing tile to any chemical substance deemed appropriate for the expected service conditions and may specify any reasonable combination of time and temperature for the exposure period. Exposure substances, time, and temperatures should be selected, either to simulate service conditions or accelerate deterioration that is possible under expected service conditions, or bear some other meaningful relation to expected service conditions.

5.6 Hydrofluoric acid should not be used as a test substance because most ceramics are silicates and are quite readily attacked by this acid.

6. Samples

6.1 *Number of Test Specimens*—One defect-free test specimen that is representative of the entire surface for each test solution is to be used. Test specimens shall be representative of the sample, and where tiles have different colors of decorative effects, take care to include all distinctive parts and more test specimens as necessary to incorporate all surface features.

6.2 *Size of Specimens*—The original tile for testing may be cut to 50 by 50 mm squares for testing with each cut piece labeled according to the testing solution to be applied.

6.3 The sample surfaces may be cleaned with a solvent such as acetone before testing.

6.4 The test specimens can be glazed or unglazed tile. If the tiles are glazed, then apply the testing solutions to the glazed surface.

7. Procedure for Test Solution Application

7.1 *Application of the Test Solutions* :

7.1.1 The labeled test specimens are laid out on a table in a well-ventilated area. (**Warning**—Since this test method involves the use of concentrated acids and bases, take proper precautions for the handling of these chemicals, such as protective clothing and fume hoods.)

7.1.2 Using a glass test tube or PVC tube, place approximately 5 mL of the test solution in contact with the surface of the specimen. If the surface of the specimen is textured, using a non-reacting sealing agent such as plumber's putty or petroleum jelly around the outside of the tube may be necessary to prevent leaking.

7.1.3 Carefully place the assembly on the table and leave undisturbed for 24 h.

7.2 *Removal of the Test Solutions*:

7.2.1 After 24 h of contact between the test specimens and the test solution has expired, remove the tube from the specimen and dispose of the testing solution properly.

7.2.2 Thoroughly rinse the specimens under running water to remove any residual testing solution. If needed, clean the surface with a soft bristle brush to remove test solutions.

7.2.3 Dry the specimens by heating in an oven adjusted to a minimum of 110 °C and not exceeding 160 °C for a minimum